



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Products contained in this shipment may be subject to ITAR regulations.

Warning:

The export of these commodity(ies), technology, or software are subject either to the U.S. Commerce Department Export Administration Regulations (E.A.R.), or to the U.S. State Department International Traffic In Arms Regulations (I.T.A.R.). Diversion, the shipment to unauthorized locations or entities, or the disclosure of related technical data or software to unauthorized foreign nationals is contrary to U.S. law and is prohibited. If export is authorized to a specific country or end-users, compliance with the U.S. export laws is required prior to transfer, transshipment on a non-continuous voyage, or disposal in any other country, or to any other end-user of these commodities, either in their original form or after being incorporated into other end-items.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Radiation Lot Acceptance Testing (RLAT) of the RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp for Linear Technology

Customer: Linear Technology, PO# 62433L

RAD Job Number: 12-275

Part Type Tested: RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp.

Traceability Information: Fab Lot Number: W10739896.2, Wafer Number: 20, Assembly Lot number: 626933.1, Date Code: 1120A. See photograph of unit under test in Appendix A.

Quantity of Units: 12 units received, 5 units for biased irradiation, 5 units for unbiased irradiation and 2 units for control. Serial numbers 519, 520, 521, 522 and 524 were biased during irradiation, serial numbers 536, 537, 538, 539 and 542 were unbiased during irradiation and serial numbers 543 and 544 were used as control. See Appendix B for the radiation bias connection table.

Radiation and Electrical Test Increments: 50-300rad(Si)/s ionizing radiation with electrical test increments: pre-irradiation, 20krad(Si), 50krad(Si), 100krad(Si) and 200krad(Si).

Pre-Irradiation Burn-In: Burn-In performed by Linear Technology prior to receipt by RAD

Overtest and Post-Irradiation Anneal: No overtest. No anneal.

Radiation Test Standard: MIL-STD-750E TM1019 and/or MIL-STD-883H TM1019 Condition A.

Test Hardware and Software: LTS2020 Automated Tester, Entity ID TS04, Calibration Date: 4/28/2011, Calibration Due: 4/28/2012. LTS2101 Family Board, Entity ID FB10. LTS0600 Test Fixture, Entity ID TF03. RH1499 BGSS-061114 DUT Board. Test Program: RH1499X.SRC

Facility and Radiation Source: Aeroflex RAD's Longmire Laboratories, Colorado Springs, CO. Gamma rays provided by JLSA 81-24 Co60 source. Dosimetry performed by Air Ionization Chamber (AIC) traceable to NIST. Aeroflex RAD's dosimetry has been audited by DSCC and Aeroflex RAD has been awarded Laboratory Suitability for MIL-STD-750 and MIL-STD-883 TM 1019.

Irradiation and Test Temperature: Room temperature controlled to 24°C±6°C per MIL-STD-883 and MIL-STD-750.

RLAT Result: PASSED. The units-under-test passed the total ionizing dose test to the maximum tested dose level of 200krad(Si) with all parameters remaining within their datasheet specifications.

An ISO 9001:2008 and DSCC Certified Company



1.0. Overview and Background

It is well known that total dose ionizing radiation can cause parametric degradation and ultimately functional failure in electronic devices. The damage occurs via electron-hole pair production, transport and trapping in the dielectric and interface regions. In discrete devices the bulk of the damage is frequently manifested as a reduction in the gain and/or breakdown voltage of the device. The damage will usually anneal with time following the end of the radiation exposure. Due to this annealing, and to ensure a worst-case test condition MIL-STD-883 TM1019.8 calls out a dose rate of 50 to 300rad(Si)/s as Condition A and further specifies that the time from the end of an incremental radiation exposure and electrical testing shall be 1-hour or less and the total time from the end of one incremental irradiation to the beginning of the next incremental radiation step should be 2-hours or less. The work described in this report was performed to meet MIL-STD-883 TM1019.8 Condition A.

2.0. Radiation Test Apparatus

The total ionizing dose testing described in this final report was performed using the facilities at Aeroflex RAD's Longmire Laboratories in Colorado Springs, CO. The high dose rate total ionizing dose (TID) source is a JLSA 81-24 irradiator modified to provide a panoramic exposure. The Co-60 rods are held in the base of the irradiator heavily shielded by lead. During the radiation exposures the rod is raised by an electronic timer/controller and the exposure is performed in air. The dose rate for this irradiator in this configuration ranges from <1rad(Si)/s to a maximum of approximately 120rad(Si)/s, determined by the distance from the source. For high-dose rate experiments the bias boards are placed in a radial fashion equidistant from the raised Co-60 rods with the distance adjusted to provide the required dose rate. The irradiator calibration is maintained by Aeroflex RAD Longmire Laboratories using air ionization chamber (AIC) equipment calibrated with traceability to the National Institute of Standards and Technology (NIST). Figure 2.1 shows a photograph of the JLSA 81-24 Co-60 irradiator at Aeroflex RAD's Longmire Laboratory facility.

Aeroflex RAD is currently certified by the Defense Supply Center Columbus (DSCC) for Laboratory Suitability under MIL STD 750 and MIL-STD-883. Additional details regarding Aeroflex RAD dosimetry for TM1019 Condition A testing are available in Aeroflex RAD's report to DSCC entitled: "Dose Rate Mapping of the J.L. Shepherd and Associates Model 81 Irradiator Installed by Radiation Assured Devices".



Figure 2.1. Aeroflex RAD's high dose rate Co-60 irradiator. The dose rate is obtained by positioning the device-under-test at a fixed distance from the gamma cell. The dose rate for this irradiator varies from approximately 120rad(Si)/s close to the rods down to 1rad(Si)/s at a distance of approximately 2-feet.



3.0. Radiation Test Conditions

The RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp described in this final report were irradiated under two different bias conditions, one when biased with a split 15V supply, and one when unbiased with all pins tied to ground. See the TID Bias Table in Appendix B for the full bias circuits. In our opinion, this bias circuit satisfies the requirements of MIL-STD-883H TM1019.8 Section 3.9.3 Bias and Loading Conditions which states "The bias applied to the test devices shall be selected to produce the greatest radiation induced damage or the worst-case damage for the intended application, if known. While maximum voltage is often worst case some bipolar linear device parameters (e.g. input bias current or maximum output load current) exhibit more degradation with 0 V bias."

The devices were irradiated to a maximum total ionizing dose level of 200krad(Si) with incremental readings at 20krad(Si), 50krad(Si) and 100krad(Si). Electrical testing occurred within one hour following the end of each irradiation segment. For intermediate irradiations, the parts were tested and returned to total dose exposure within two hours from the end of the previous radiation increment.

The TID bias board was positioned in the Co-60 cell to provide the required minimum of 50rad(Si)/s and was located inside a lead-aluminum enclosure. The lead-aluminum enclosure is required under MIL-STD-883H TM1019.8 Section 3.4 that reads as follows: "Lead/Aluminum (Pb/Al) container. Test specimens shall be enclosed in a Pb/Al container to minimize dose enhancement effects caused by low-energy, scattered radiation. A minimum of 1.5 mm Pb, surrounding an inner shield of at least 0.7 mm Al, is required. This Pb/Al container produces an approximate charged particle equilibrium for Si and for TLDs such as CaF₂. The radiation field intensity shall be measured inside the Pb/Al container (1) initially, (2) when the source is changed, or (3) when the orientation or configuration of the source, container, or test-fixture is changed. This measurement shall be performed by placing a dosimeter (e.g., a TLD) in the device-irradiation container at the approximate test-device position. If it can be demonstrated that low energy scattered radiation is small enough that it will not cause dosimetry errors due to dose enhancement, the Pb/Al container may be omitted."

The final dose rate within the high dose rate lead-aluminum enclosure was determined using calibration calculations based on air ionization chamber (AIC) dosimetry performed just prior to beginning the total dose irradiations. The final dose rate for this work was 50.43rad(Si)/s with a precision of $\pm 5\%$.



4.0. Tested Parameters

During the total ionizing dose characterization testing the following electrical parameters were measured pre- and post-irradiation:

1. +Supply Current (A) @ $V_S = \pm 15V$
2. -Supply Current (A) @ $V_S = \pm 15V$
3. Input Offset Voltage1 1 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
4. Input Offset Voltage1 2 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
5. Input Offset Voltage1 3 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
6. Input Offset Voltage1 4 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
7. Input Offset Current1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
8. Input Offset Current1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
9. Input Offset Current1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
10. Input Offset Current1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
11. +Input Bias Current BIAS1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
12. +Input Bias Current BIAS1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
13. +Input Bias Current BIAS1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
14. +Input Bias Current BIAS1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
15. -Input Bias Current BIAS1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
16. -Input Bias Current BIAS1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
17. -Input Bias Current BIAS1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
18. -Input Bias Current BIAS1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
19. Input Offset Voltage2 1 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
20. Input Offset Voltage2 2 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
21. Input Offset Voltage2 3 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
22. Input Offset Voltage2 4 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
23. Input Offset Current2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
24. Input Offset Current2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
25. Input Offset Current2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
26. Input Offset Current2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
27. +Input Bias Current BIAS2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
28. +Input Bias Current BIAS2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
29. +Input Bias Current BIAS2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
30. +Input Bias Current BIAS2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
31. -Input Bias Current BIAS2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
32. -Input Bias Current BIAS2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
33. -Input Bias Current BIAS2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
34. -Input Bias Current BIAS2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
35. Input Offset Voltage3 1 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
36. Input Offset Voltage3 2 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
37. Input Offset Voltage3 3 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

38. Input Offset Voltage3 4 (V) @ VS=+/-15V, VCM=-15V
39. Input Offset Current3 1 (A) @ VS=+/-15V, VCM=-15V
40. Input Offset Current3 2 (A) @ VS=+/-15V, VCM=-15V
41. Input Offset Current3 3 (A) @ VS=+/-15V, VCM=-15V
42. Input Offset Current3 4 (A) @ VS=+/-15V, VCM=-15V
43. +Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V
44. +Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V
45. +Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V
46. +Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V
47. -Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V
48. -Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V
49. -Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V
50. -Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V
51. Output Voltage Swing High1 1 (V) @ VS=+/-15V IL=0mA
52. Output Voltage Swing High1 2 (V) @ VS=+/-15V IL=0mA
53. Output Voltage Swing High1 3 (V) @ VS=+/-15V IL=0mA
54. Output Voltage Swing High1 4 (V) @ VS=+/-15V IL=0mA
55. Output Voltage Swing High2 1 (V) @ VS=+/-15V IL=1mA
56. Output Voltage Swing High2 2 (V) @ VS=+/-15V IL=1mA
57. Output Voltage Swing High2 3 (V) @ VS=+/-15V IL=1mA
58. Output Voltage Swing High2 4 (V) @ VS=+/-15V IL=1mA
59. Output Voltage Swing High3 1 (V) @ VS=+/-15V IL=10mA
60. Output Voltage Swing High3 2 (V) @ VS=+/-15V IL=10mA
61. Output Voltage Swing High3 3 (V) @ VS=+/-15V IL=10mA
62. Output Voltage Swing High3 4 (V) @ VS=+/-15V IL=10mA
63. Output Voltage Swing Low1 1 (V) @ VS=+/-15V IL=0mA
64. Output Voltage Swing Low1 2 (V) @ VS=+/-15V IL=0mA
65. Output Voltage Swing Low1 3 (V) @ VS=+/-15V IL=0mA
66. Output Voltage Swing Low1 4 (V) @ VS=+/-15V IL=0mA
67. Output Voltage Swing Low2 1 (V) @ VS=+/-15V IL=1mA
68. Output Voltage Swing Low2 2 (V) @ VS=+/-15V IL=1mA
69. Output Voltage Swing Low2 3 (V) @ VS=+/-15V IL=1mA
70. Output Voltage Swing Low2 4 (V) @ VS=+/-15V IL=1mA
71. Output Voltage Swing Low3 1 (V) @ VS=+/-15V IL=10mA
72. Output Voltage Swing Low3 2 (V) @ VS=+/-15V IL=10mA
73. Output Voltage Swing Low3 3 (V) @ VS=+/-15V IL=10mA
74. Output Voltage Swing Low3 4 (V) @ VS=+/-15V IL=10mA
75. Large Signal Voltage Gain1 1 (V/mV) @ VO=+/-14.5V, RL=10kΩ
76. Large Signal Voltage Gain1 2 (V/mV) @ VO=+/-14.5V, RL=10kΩ
77. Large Signal Voltage Gain1 3 (V/mV) @ VO=+/-14.5V, RL=10kΩ
78. Large Signal Voltage Gain1 4 (V/mV) @ VO=+/-14.5V, RL=10kΩ
79. Large Signal Voltage Gain2 1 (V/mV) @ VO=+/-10V, RL=2kΩ

An ISO 9001:2008 and DSCC Certified Company



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

- 80. Large Signal Voltage Gain² 2 (V/mV) @ $V_O = \pm 10V$, $R_L = 2k\Omega$
- 81. Large Signal Voltage Gain² 3 (V/mV) @ $V_O = \pm 10V$, $R_L = 2k\Omega$
- 82. Large Signal Voltage Gain² 4 (V/mV) @ $V_O = \pm 10V$, $R_L = 2k\Omega$
- 83. Common Mode Rejection Ratio¹ 1 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 84. Common Mode Rejection Ratio¹ 2 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 85. Common Mode Rejection Ratio¹ 3 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 86. Common Mode Rejection Ratio¹ 4 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 87. CMRR Match¹ 1 to 4 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 88. CMRR Match¹ 2 to 3 (dB) @ $V_S = \pm 15V$, $V_{CM} = \pm 15V$
- 89. Power Supply Rejection Ratio¹ 1 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 90. Power Supply Rejection Ratio¹ 2 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 91. Power Supply Rejection Ratio¹ 3 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 92. Power Supply Rejection Ratio¹ 4 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 93. PSRR Match¹ 1 to 4 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 94. PSRR Match¹ 2 to 3 (dB) @ $V_S = \pm 2V$ to $\pm 16V$
- 95. +Short-Circuit Current¹ 1 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 96. +Short-Circuit Current¹ 2 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 97. +Short-Circuit Current¹ 3 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 98. +Short-Circuit Current¹ 4 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 99. -Short-Circuit Current¹ 1 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 100. -Short-Circuit Current¹ 2 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 101. -Short-Circuit Current¹ 3 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 102. -Short-Circuit Current¹ 4 (A) @ $V_S = \pm 15V$, $V_{OUT} = 0V$
- 103. +Supply Current (A) @ $V_S = +5V$
- 104. -Supply Current (A) @ $V_S = +5V$
- 105. Input Offset Voltage⁴ 1 (V) @ $V_S = +5V$, $V_{CM} = 0V$
- 106. Input Offset Voltage⁴ 2 (V) @ $V_S = +5V$, $V_{CM} = 0V$
- 107. Input Offset Voltage⁴ 3 (V) @ $V_S = +5V$, $V_{CM} = 0V$
- 108. Input Offset Voltage⁴ 4 (V) @ $V_S = +5V$, $V_{CM} = 0V$
- 109. Input Offset Current⁴ 1 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 110. Input Offset Current⁴ 2 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 111. Input Offset Current⁴ 3 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 112. Input Offset Current⁴ 4 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 113. +Input Bias Current BIAS⁴ 1 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 114. +Input Bias Current BIAS⁴ 2 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 115. +Input Bias Current BIAS⁴ 3 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 116. +Input Bias Current BIAS⁴ 4 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 117. -Input Bias Current BIAS⁴ 1 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 118. -Input Bias Current BIAS⁴ 2 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 119. -Input Bias Current BIAS⁴ 3 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 120. -Input Bias Current BIAS⁴ 4 (A) @ $V_S = +5V$, $V_{CM} = 0V$
- 121. Input Offset Voltage⁵ 1 (V) @ $V_S = +5V$, $V_{CM} = 5V$

An ISO 9001:2008 and DSCC Certified Company



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

- 122. Input Offset Voltage5 2 (V) @ VS=+5V, VCM=5V
- 123. Input Offset Voltage5 3 (V) @ VS=+5V, VCM=5V
- 124. Input Offset Voltage5 4 (V) @ VS=+5V, VCM=5V
- 125. Input Offset Current5 1 (A) @ VS=+5V, VCM=5V
- 126. Input Offset Current5 2 (A) @ VS=+5V, VCM=5V
- 127. Input Offset Current5 3 (A) @ VS=+5V, VCM=5V
- 128. Input Offset Current5 4 (A) @ VS=+5V, VCM=5V
- 129. +Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V
- 130. +Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V
- 131. +Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V
- 132. +Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V
- 133. -Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V
- 134. -Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V
- 135. -Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V
- 136. -Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V
- 137. Output Voltage Swing High4 1 (V) @ VS=+5V IL=0mA
- 138. Output Voltage Swing High4 2 (V) @ VS=+5V IL=0mA
- 139. Output Voltage Swing High4 3 (V) @ VS=+5V IL=0mA
- 140. Output Voltage Swing High4 4 (V) @ VS=+5V IL=0mA
- 141. Output Voltage Swing High5 1 (V) @ VS=+5V IL=1mA
- 142. Output Voltage Swing High5 2 (V) @ VS=+5V IL=1mA
- 143. Output Voltage Swing High5 3 (V) @ VS=+5V IL=1mA
- 144. Output Voltage Swing High5 4 (V) @ VS=+5V IL=1mA
- 145. Output Voltage Swing High6 1 (V) @ VS=+5V IL=2.5mA
- 146. Output Voltage Swing High6 2 (V) @ VS=+5V IL=2.5mA
- 147. Output Voltage Swing High6 3 (V) @ VS=+5V IL=2.5mA
- 148. Output Voltage Swing High6 4 (V) @ VS=+5V IL=2.5mA
- 149. Output Voltage Swing Low4 1 (V) @ VS=+5V IL=0mA
- 150. Output Voltage Swing Low4 2 (V) @ VS=+5V IL=0mA
- 151. Output Voltage Swing Low4 3 (V) @ VS=+5V IL=0mA
- 152. Output Voltage Swing Low4 4 (V) @ VS=+5V IL=0mA
- 153. Output Voltage Swing Low5 1 (V) @ VS=+5V IL=1mA
- 154. Output Voltage Swing Low5 2 (V) @ VS=+5V IL=1mA
- 155. Output Voltage Swing Low5 3 (V) @ VS=+5V IL=1mA
- 156. Output Voltage Swing Low5 4 (V) @ VS=+5V IL=1mA
- 157. Output Voltage Swing Low6 1 (V) @ VS=+5V IL=2.5mA
- 158. Output Voltage Swing Low6 2 (V) @ VS=+5V IL=2.5mA
- 159. Output Voltage Swing Low6 3 (V) @ VS=+5V IL=2.5mA
- 160. Output Voltage Swing Low6 4 (V) @ VS=+5V IL=2.5mA
- 161. Large Signal Voltage Gain3 1 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 162. Large Signal Voltage Gain3 2 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 163. Large Signal Voltage Gain3 3 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ

An ISO 9001:2008 and DSCC Certified Company



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

- 164. Large Signal Voltage Gain³ 4 (V/mV) @ $V_O=75\text{mV}$ to 4.8V, $R_L=10\text{k}\Omega$
- 165. Common Mode Rejection Ratio² 1 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 166. Common Mode Rejection Ratio² 2 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 167. Common Mode Rejection Ratio² 3 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 168. Common Mode Rejection Ratio² 4 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 169. CMRR Match² 1 to 4 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 170. CMRR Match² 2 to 3 (dB) @ $V_S=+5\text{V}$, $V_{CM}=0$ to +5V
- 171. Power Supply Rejection Ratio² 1 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 172. Power Supply Rejection Ratio² 2 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 173. Power Supply Rejection Ratio² 3 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 174. Power Supply Rejection Ratio² 4 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 175. PSRR Match² 1 to 4 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 176. PSRR Match² 2 to 3 (dB) @ $V_S=+4.5\text{V}$ to +12V
- 177. +Short-Circuit Current² 1 (A) @ $V_S=+5\text{V}$
- 178. +Short-Circuit Current² 2 (A) @ $V_S=+5\text{V}$
- 179. +Short-Circuit Current² 3 (A) @ $V_S=+5\text{V}$
- 180. +Short-Circuit Current² 4 (A) @ $V_S=+5\text{V}$
- 181. -Short-Circuit Current² 1 (A) @ $V_S=+5\text{V}$
- 182. -Short-Circuit Current² 2 (A) @ $V_S=+5\text{V}$
- 183. -Short-Circuit Current² 3 (A) @ $V_S=+5\text{V}$
- 184. -Short-Circuit Current² 4 (A) @ $V_S=+5\text{V}$

Appendix C details the measured parameters, test conditions, pre-irradiation specification and measurement resolution for each of the measurements.

The parametric data was obtained as "read and record" and all the raw data plus an attributes summary are contained in this report as well as in a separate Excel file. The attributes data contains the average, standard deviation and the average with the KTL values applied. The KTL value used in this work is 2.742 per MIL-HDBK-814 using one sided tolerance limits of 90/90 and a 5-piece sample size. The 90/90 KTL values were selected to match the statistical levels specified in the MIL-PRF-38535 sampling plan for the qualification of a radiation hardness assured (RHA) component. Note that the following criteria must be met for a device to pass the total ionizing dose test: following the radiation exposure each of the 5 pieces irradiated under electrical bias shall pass the specification value. The units irradiated without electrical bias and the KTL statistics are included in this report for reference only. If any of the 5 pieces irradiated under electrical bias exceed the device post radiation data sheet specification limits, then the lot could be logged as a failure.



5.0. Total Ionizing Dose Test Results

Based on this criterion the RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp (from the lot traceability information provided on the first page of this test report) PASSED the total ionizing dose test to the maximum tested dose level of 200krad(Si) with all parameters remaining within their datasheet specifications.

Figures 5.1 through 5.184 show plots of all the measured parameters versus total ionizing dose while Tables 5.1 - 5.184 show the corresponding raw data for each of these parameters. In the data plots the solid diamonds are the average of the measured data points for the sample irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the units irradiated with all pins tied to ground. The black lines (solid or dashed) are the average of the data points after application of the KTL statistics on the sample irradiated in the biased condition while the shaded lines (solid or dashed) are the average of the data points after application of the KTL statistics on the sample irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.

The control units, as expected, show no significant changes to any of the parameters. Therefore we can conclude that the electrical testing remained in control throughout the duration of the tests and the observed degradation was due to the radiation exposure. Appendix D lists the figures used in this section to facilitate the location of a particular parameter.




Figure 5.1. Plot of +Supply Current (A) @ VS=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.1. Raw data for +Supply Current (A) @ VS=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Supply Current (A) @ VS=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.56E-03	7.41E-03	7.48E-03	7.34E-03	7.36E-03
520	7.58E-03	7.49E-03	7.44E-03	7.43E-03	7.50E-03
521	7.76E-03	7.68E-03	7.63E-03	7.62E-03	7.62E-03
522	7.48E-03	7.37E-03	7.33E-03	7.31E-03	7.31E-03
524	7.64E-03	7.60E-03	7.51E-03	7.50E-03	7.55E-03
536	7.51E-03	7.48E-03	7.43E-03	7.41E-03	7.37E-03
537	7.46E-03	7.41E-03	7.37E-03	7.36E-03	7.32E-03
538	7.38E-03	7.33E-03	7.30E-03	7.29E-03	7.24E-03
539	7.50E-03	7.45E-03	7.42E-03	7.40E-03	7.36E-03
542	7.47E-03	7.43E-03	7.40E-03	7.37E-03	7.33E-03
543	7.30E-03	7.25E-03	7.25E-03	7.25E-03	7.26E-03
544	7.75E-03	7.74E-03	7.74E-03	7.75E-03	7.76E-03
Biased Statistics					
Average Biased	7.60E-03	7.51E-03	7.48E-03	7.44E-03	7.47E-03
Std Dev Biased	1.06E-04	1.29E-04	1.09E-04	1.27E-04	1.27E-04
Ps90%/90% (+KTL) Biased	7.89E-03	7.86E-03	7.77E-03	7.79E-03	7.82E-03
Ps90%/90% (-KTL) Biased	7.31E-03	7.15E-03	7.18E-03	7.09E-03	7.12E-03
Un-Biased Statistics					
Average Un-Biased	7.47E-03	7.42E-03	7.39E-03	7.37E-03	7.32E-03
Std Dev Un-Biased	5.17E-05	5.53E-05	5.05E-05	4.68E-05	5.32E-05
Ps90%/90% (+KTL) Un-Biased	7.61E-03	7.57E-03	7.52E-03	7.49E-03	7.47E-03
Ps90%/90% (-KTL) Un-Biased	7.32E-03	7.27E-03	7.25E-03	7.24E-03	7.18E-03
Specification MAX	1.00E-02	1.00E-02	1.00E-02	1.00E-02	1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.2. Plot of -Supply Current (A) @ VS=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.2. Raw data for -Supply Current (A) @ VS=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Supply Current (A) @ VS=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-7.58E-03	-7.43E-03	-7.50E-03	-7.36E-03	-7.38E-03
520	-7.60E-03	-7.51E-03	-7.46E-03	-7.45E-03	-7.52E-03
521	-7.78E-03	-7.70E-03	-7.65E-03	-7.64E-03	-7.64E-03
522	-7.50E-03	-7.39E-03	-7.35E-03	-7.33E-03	-7.33E-03
524	-7.67E-03	-7.62E-03	-7.53E-03	-7.52E-03	-7.57E-03
536	-7.53E-03	-7.50E-03	-7.45E-03	-7.43E-03	-7.39E-03
537	-7.49E-03	-7.44E-03	-7.39E-03	-7.39E-03	-7.34E-03
538	-7.40E-03	-7.35E-03	-7.33E-03	-7.31E-03	-7.25E-03
539	-7.52E-03	-7.47E-03	-7.44E-03	-7.42E-03	-7.38E-03
542	-7.49E-03	-7.45E-03	-7.42E-03	-7.39E-03	-7.34E-03
543	-7.32E-03	-7.27E-03	-7.27E-03	-7.27E-03	-7.28E-03
544	-7.77E-03	-7.76E-03	-7.76E-03	-7.77E-03	-7.78E-03
Biased Statistics					
Average Biased	-7.62E-03	-7.53E-03	-7.49E-03	-7.46E-03	-7.49E-03
Std Dev Biased	1.06E-04	1.29E-04	1.09E-04	1.27E-04	1.27E-04
Ps90%/90% (+KTL) Biased	-7.33E-03	-7.18E-03	-7.19E-03	-7.11E-03	-7.14E-03
Ps90%/90% (-KTL) Biased	-7.91E-03	-7.88E-03	-7.79E-03	-7.81E-03	-7.84E-03
Un-Biased Statistics					
Average Un-Biased	-7.49E-03	-7.44E-03	-7.41E-03	-7.39E-03	-7.34E-03
Std Dev Un-Biased	5.20E-05	5.54E-05	5.01E-05	4.66E-05	5.33E-05
Ps90%/90% (+KTL) Un-Biased	-7.34E-03	-7.29E-03	-7.27E-03	-7.26E-03	-7.19E-03
Ps90%/90% (-KTL) Un-Biased	-7.63E-03	-7.59E-03	-7.54E-03	-7.51E-03	-7.49E-03
Specification MIN	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.3. Plot of Input Offset Voltage1 1 (V) @ VS=+-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.3. Raw data for Input Offset Voltage1 1 (V) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage1 1 (V) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.10E-05	6.57E-06	1.87E-05	5.13E-06	7.66E-06
520	1.76E-04	1.44E-04	1.42E-04	1.35E-04	1.24E-04
521	-1.19E-04	-1.28E-04	-1.33E-04	-1.38E-04	-1.46E-04
522	-3.01E-04	-3.25E-04	-3.22E-04	-3.30E-04	-3.33E-04
524	-8.07E-05	-9.94E-05	-9.67E-05	-8.81E-05	-8.49E-05
536	6.98E-05	5.38E-05	4.41E-05	3.50E-05	1.08E-05
537	-1.32E-04	-1.45E-04	-1.54E-04	-1.63E-04	-1.85E-04
538	-1.72E-04	-1.68E-04	-1.79E-04	-1.99E-04	-2.18E-04
539	-3.56E-04	-3.55E-04	-3.66E-04	-3.74E-04	-3.98E-04
542	-3.82E-05	-5.43E-05	-6.77E-05	-7.56E-05	-9.85E-05
543	-3.69E-04	-3.69E-04	-3.70E-04	-3.70E-04	-3.69E-04
544	-2.36E-04	-2.35E-04	-2.35E-04	-2.35E-04	-2.35E-04
Biased Statistics					
Average Biased	-5.89E-05	-8.04E-05	-7.83E-05	-8.33E-05	-8.63E-05
Std Dev Biased	1.77E-04	1.74E-04	1.74E-04	1.73E-04	1.71E-04
Ps90%/90% (+KTL) Biased	4.28E-04	3.95E-04	3.98E-04	3.90E-04	3.83E-04
Ps90%/90% (-KTL) Biased	-5.45E-04	-5.56E-04	-5.54E-04	-5.57E-04	-5.56E-04
Un-Biased Statistics					
Average Un-Biased	-1.26E-04	-1.34E-04	-1.45E-04	-1.55E-04	-1.78E-04
Std Dev Un-Biased	1.59E-04	1.51E-04	1.51E-04	1.52E-04	1.52E-04
Ps90%/90% (+KTL) Un-Biased	3.10E-04	2.81E-04	2.70E-04	2.61E-04	2.38E-04
Ps90%/90% (-KTL) Un-Biased	-5.61E-04	-5.49E-04	-5.60E-04	-5.72E-04	-5.93E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.4. Plot of Input Offset Voltage1 2 (V) @ VS=+-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.4. Raw data for Input Offset Voltage1 2 (V) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage1 2 (V) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.36E-04	-2.78E-04	-2.68E-04	-2.74E-04	-2.79E-04
520	3.42E-05	2.44E-05	2.43E-05	2.22E-05	2.41E-05
521	-2.10E-04	-2.46E-04	-2.49E-04	-2.32E-04	-2.29E-04
522	-2.39E-04	-2.53E-04	-2.42E-04	-2.39E-04	-2.31E-04
524	5.79E-05	2.91E-05	1.70E-05	2.22E-05	2.40E-05
536	4.33E-05	2.67E-05	1.68E-05	1.12E-05	-1.02E-05
537	-4.84E-04	-5.08E-04	-5.16E-04	-5.30E-04	-5.43E-04
538	-1.33E-04	-1.42E-04	-1.39E-04	-1.37E-04	-1.55E-04
539	-1.93E-04	-2.02E-04	-2.08E-04	-2.22E-04	-2.34E-04
542	-3.13E-04	-3.34E-04	-3.40E-04	-3.49E-04	-3.63E-04
543	-2.01E-04	-2.05E-04	-2.06E-04	-2.06E-04	-2.05E-04
544	-1.04E-04	-1.04E-04	-1.03E-04	-1.03E-04	-1.01E-04
Biased Statistics					
Average Biased	-1.19E-04	-1.45E-04	-1.44E-04	-1.40E-04	-1.38E-04
Std Dev Biased	1.51E-04	1.57E-04	1.50E-04	1.49E-04	1.49E-04
Ps90%/90% (+KTL) Biased	2.95E-04	2.86E-04	2.68E-04	2.68E-04	2.72E-04
Ps90%/90% (-KTL) Biased	-5.32E-04	-5.75E-04	-5.55E-04	-5.48E-04	-5.48E-04
Un-Biased Statistics					
Average Un-Biased	-2.16E-04	-2.32E-04	-2.37E-04	-2.45E-04	-2.61E-04
Std Dev Un-Biased	1.98E-04	2.01E-04	2.02E-04	2.06E-04	2.03E-04
Ps90%/90% (+KTL) Un-Biased	3.26E-04	3.21E-04	3.17E-04	3.19E-04	2.95E-04
Ps90%/90% (-KTL) Un-Biased	-7.58E-04	-7.84E-04	-7.91E-04	-8.10E-04	-8.17E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.5. Plot of Input Offset Voltage1 3 (V) @ VS=+-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.5. Raw data for Input Offset Voltage1 3 (V) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage1 3 (V) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-5.49E-05	-4.93E-05	-4.44E-05	-4.64E-05	-4.22E-05
520	-8.10E-05	-1.13E-04	-1.20E-04	-1.25E-04	-1.28E-04
521	-1.47E-04	-1.74E-04	-1.73E-04	-1.75E-04	-1.74E-04
522	2.95E-06	-8.40E-06	-1.06E-05	-1.42E-05	-2.01E-05
524	-1.69E-04	-1.97E-04	-2.20E-04	-2.25E-04	-2.35E-04
536	-5.39E-04	-5.55E-04	-5.60E-04	-5.72E-04	-6.01E-04
537	-1.18E-04	-1.49E-04	-1.56E-04	-1.71E-04	-1.90E-04
538	-1.98E-04	-2.15E-04	-2.26E-04	-2.44E-04	-2.66E-04
539	-4.72E-05	-2.58E-05	-3.85E-05	-5.46E-05	-7.14E-05
542	-3.36E-05	-5.13E-05	-6.51E-05	-8.47E-05	-1.11E-04
543	-6.68E-05	-6.99E-05	-7.08E-05	-6.92E-05	-6.82E-05
544	-1.15E-04	-1.14E-04	-1.16E-04	-1.13E-04	-1.12E-04
Biased Statistics					
Average Biased	-8.98E-05	-1.08E-04	-1.13E-04	-1.17E-04	-1.20E-04
Std Dev Biased	6.97E-05	8.01E-05	8.69E-05	8.73E-05	8.98E-05
Ps90%/90% (+KTL) Biased	1.01E-04	1.11E-04	1.25E-04	1.22E-04	1.26E-04
Ps90%/90% (-KTL) Biased	-2.81E-04	-3.28E-04	-3.52E-04	-3.56E-04	-3.66E-04
Un-Biased Statistics					
Average Un-Biased	-1.87E-04	-1.99E-04	-2.09E-04	-2.25E-04	-2.48E-04
Std Dev Un-Biased	2.07E-04	2.13E-04	2.10E-04	2.08E-04	2.11E-04
Ps90%/90% (+KTL) Un-Biased	3.81E-04	3.85E-04	3.66E-04	3.44E-04	3.31E-04
Ps90%/90% (-KTL) Un-Biased	-7.55E-04	-7.83E-04	-7.84E-04	-7.95E-04	-8.27E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.6. Plot of Input Offset Voltage1 4 (V) @ VS=+-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.6. Raw data for Input Offset Voltage1 4 (V) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage1 4 (V) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-1.78E-04	-2.00E-04	-1.96E-04	-1.95E-04	-1.92E-04
520	-1.76E-04	-2.20E-04	-2.20E-04	-2.24E-04	-2.23E-04
521	-3.63E-05	-7.52E-05	-7.26E-05	-7.48E-05	-7.15E-05
522	-1.39E-04	-1.51E-04	-1.43E-04	-1.46E-04	-1.43E-04
524	1.18E-05	-1.12E-05	-1.55E-05	-3.20E-06	1.63E-06
536	-1.70E-04	-1.69E-04	-1.74E-04	-1.83E-04	-2.04E-04
537	-4.90E-05	-5.37E-05	-5.93E-05	-6.39E-05	-7.78E-05
538	8.46E-05	7.91E-05	7.48E-05	6.39E-05	4.69E-05
539	-1.88E-04	-1.91E-04	-2.00E-04	-2.12E-04	-2.34E-04
542	-1.01E-05	-2.80E-05	-4.00E-05	-4.96E-05	-5.61E-05
543	1.83E-04	1.77E-04	1.75E-04	1.76E-04	1.79E-04
544	-1.00E-04	-1.00E-04	-1.00E-04	-9.99E-05	-9.92E-05
Biased Statistics					
Average Biased	-1.04E-04	-1.31E-04	-1.29E-04	-1.29E-04	-1.25E-04
Std Dev Biased	8.64E-05	8.74E-05	8.52E-05	9.01E-05	9.12E-05
Ps90%/90% (+KTL) Biased	1.33E-04	1.08E-04	1.04E-04	1.19E-04	1.25E-04
Ps90%/90% (-KTL) Biased	-3.41E-04	-3.71E-04	-3.63E-04	-3.76E-04	-3.75E-04
Un-Biased Statistics					
Average Un-Biased	-6.63E-05	-7.27E-05	-7.98E-05	-8.89E-05	-1.05E-04
Std Dev Un-Biased	1.14E-04	1.11E-04	1.11E-04	1.11E-04	1.15E-04
Ps90%/90% (+KTL) Un-Biased	2.45E-04	2.30E-04	2.25E-04	2.16E-04	2.09E-04
Ps90%/90% (-KTL) Un-Biased	-3.78E-04	-3.76E-04	-3.84E-04	-3.94E-04	-4.19E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.7. Plot of Input Offset Current1 1 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.7. Raw data for Input Offset Current1 1 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current1 1 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.75E-09	4.14E-09	4.13E-09	5.26E-09	6.03E-09
520	1.55E-09	7.40E-10	8.90E-10	1.17E-09	-8.60E-10
521	-8.40E-10	-1.14E-09	-9.70E-10	-6.40E-10	-2.10E-10
522	-3.86E-09	-4.42E-09	-3.10E-09	-4.05E-09	-4.95E-09
524	-1.70E-10	-4.60E-10	-7.20E-10	-1.70E-10	-3.00E-10
536	2.35E-09	2.75E-09	3.13E-09	4.26E-09	4.94E-09
537	8.40E-10	7.40E-10	1.02E-09	1.09E-09	1.22E-09
538	-3.46E-09	-3.23E-09	-4.05E-09	-4.06E-09	-3.75E-09
539	-6.61E-09	-6.26E-09	-7.39E-09	-7.66E-09	-9.18E-09
542	-1.28E-09	-1.91E-09	-2.33E-09	-2.51E-09	-2.98E-09
543	-1.39E-09	-1.39E-09	-1.39E-09	-1.37E-09	-1.36E-09
544	-5.91E-09	-5.94E-09	-5.92E-09	-5.93E-09	-5.89E-09
Biased Statistics					
Average Biased	8.60E-11	-2.28E-10	4.60E-11	3.14E-10	-5.80E-11
Std Dev Biased	2.83E-09	3.10E-09	2.69E-09	3.37E-09	3.93E-09
Ps90%/90% (+KTL) Biased	7.85E-09	8.28E-09	7.42E-09	9.55E-09	1.07E-08
Ps90%/90% (-KTL) Biased	-7.68E-09	-8.73E-09	-7.33E-09	-8.92E-09	-1.08E-08
Un-Biased Statistics					
Average Un-Biased	-1.63E-09	-1.58E-09	-1.92E-09	-1.78E-09	-1.95E-09
Std Dev Un-Biased	3.54E-09	3.50E-09	4.15E-09	4.61E-09	5.34E-09
Ps90%/90% (+KTL) Un-Biased	8.08E-09	8.00E-09	9.45E-09	1.09E-08	1.27E-08
Ps90%/90% (-KTL) Un-Biased	-1.13E-08	-1.12E-08	-1.33E-08	-1.44E-08	-1.66E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.8. Plot of Input Offset Current1 2 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.8. Raw data for Input Offset Current1 2 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current1 2 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.10E-10	-1.50E-10	-5.10E-10	-6.50E-10	-4.60E-10
520	-2.87E-09	-3.20E-09	-3.55E-09	-3.48E-09	-4.11E-09
521	3.47E-09	2.88E-09	3.65E-09	2.87E-09	2.55E-09
522	-9.40E-10	-1.00E-09	-1.45E-09	-4.70E-10	-2.90E-10
524	-6.10E-10	-7.90E-10	-9.30E-10	-5.00E-10	3.10E-10
536	3.76E-09	3.78E-09	3.75E-09	4.96E-09	3.58E-09
537	-4.88E-09	-5.18E-09	-5.16E-09	-5.97E-09	-5.36E-09
538	-7.50E-10	-6.30E-10	-5.60E-10	-1.57E-09	-1.26E-09
539	1.74E-09	2.15E-09	1.72E-09	1.83E-09	1.51E-09
542	-6.13E-09	-5.97E-09	-5.82E-09	-5.13E-09	-5.92E-09
543	-2.37E-09	-2.36E-09	-2.38E-09	-2.34E-09	-2.33E-09
544	5.98E-09	6.04E-09	6.10E-09	6.04E-09	5.95E-09
Biased Statistics					
Average Biased	-8.80E-11	-4.52E-10	-5.58E-10	-4.46E-10	-4.00E-10
Std Dev Biased	2.33E-09	2.19E-09	2.63E-09	2.25E-09	2.40E-09
Ps90%/90% (+KTL) Biased	6.31E-09	5.55E-09	6.64E-09	5.72E-09	6.17E-09
Ps90%/90% (-KTL) Biased	-6.48E-09	-6.45E-09	-7.76E-09	-6.61E-09	-6.97E-09
Un-Biased Statistics					
Average Un-Biased	-1.25E-09	-1.17E-09	-1.21E-09	-1.18E-09	-1.49E-09
Std Dev Un-Biased	4.22E-09	4.33E-09	4.20E-09	4.62E-09	4.16E-09
Ps90%/90% (+KTL) Un-Biased	1.03E-08	1.07E-08	1.03E-08	1.15E-08	9.93E-09
Ps90%/90% (-KTL) Un-Biased	-1.28E-08	-1.30E-08	-1.27E-08	-1.39E-08	-1.29E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.9. Plot of Input Offset Current1 3 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.9. Raw data for Input Offset Current1 3 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current1 3 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.81E-09	2.75E-09	2.53E-09	3.03E-09	3.15E-09
520	-1.22E-09	-7.30E-10	-1.09E-09	-1.11E-09	-1.24E-09
521	-5.30E-10	5.00E-11	7.00E-11	-3.20E-10	3.00E-11
522	-3.00E-10	5.30E-10	0.00E+00	1.10E-09	2.86E-09
524	-4.66E-09	-4.85E-09	-4.99E-09	-5.84E-09	-6.07E-09
536	-2.69E-09	-2.59E-09	-3.27E-09	-2.16E-09	-2.44E-09
537	-2.80E-09	-2.82E-09	-2.59E-09	-2.80E-09	-1.85E-09
538	2.30E-10	2.90E-10	3.10E-10	4.50E-10	-1.00E-10
539	3.98E-09	4.75E-09	4.23E-09	4.18E-09	4.88E-09
542	-3.73E-09	-4.06E-09	-4.47E-09	-4.95E-09	-7.08E-09
543	-2.22E-09	-2.19E-09	-2.23E-09	-2.21E-09	-2.22E-09
544	-1.61E-09	-1.65E-09	-1.70E-09	-1.66E-09	-1.63E-09
Biased Statistics					
Average Biased	-9.80E-10	-4.50E-10	-6.96E-10	-6.28E-10	-2.54E-10
Std Dev Biased	2.35E-09	2.78E-09	2.74E-09	3.31E-09	3.75E-09
Ps90%/90% (+KTL) Biased	5.46E-09	7.17E-09	6.82E-09	8.45E-09	1.00E-08
Ps90%/90% (-KTL) Biased	-7.42E-09	-8.07E-09	-8.21E-09	-9.71E-09	-1.05E-08
Un-Biased Statistics					
Average Un-Biased	-1.00E-09	-8.86E-10	-1.16E-09	-1.06E-09	-1.32E-09
Std Dev Un-Biased	3.16E-09	3.53E-09	3.49E-09	3.50E-09	4.32E-09
Ps90%/90% (+KTL) Un-Biased	7.65E-09	8.80E-09	8.41E-09	8.55E-09	1.05E-08
Ps90%/90% (-KTL) Un-Biased	-9.66E-09	-1.06E-08	-1.07E-08	-1.07E-08	-1.32E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.10. Plot of Input Offset Current1 4 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.10. Raw data for Input Offset Current1 4 (A) @ VS= \pm 15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current1 4 (A) @ VS= \pm 15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.10E-10	3.00E-10	5.90E-10	0.00E+00	-3.40E-10
520	-1.45E-09	-1.37E-09	-1.23E-09	-1.86E-09	-1.92E-09
521	-5.07E-09	-5.50E-09	-4.82E-09	-5.13E-09	-4.40E-09
522	-1.68E-09	-1.73E-09	-1.49E-09	-1.43E-09	-1.02E-09
524	1.54E-09	2.36E-09	3.22E-09	4.91E-09	5.35E-09
536	-1.80E-09	-1.97E-09	-1.26E-09	-3.80E-10	2.10E-10
537	2.92E-09	3.04E-09	2.89E-09	3.77E-09	3.17E-09
538	5.70E-10	2.00E-10	-9.00E-11	6.50E-10	-1.92E-09
539	1.54E-09	2.26E-09	2.17E-09	3.04E-09	2.20E-09
542	5.22E-09	5.15E-09	5.66E-09	4.52E-09	6.54E-09
543	-4.41E-09	-4.47E-09	-4.51E-09	-4.49E-09	-4.48E-09
544	-4.73E-09	-4.71E-09	-4.67E-09	-4.69E-09	-4.57E-09
Biased Statistics					
Average Biased	-1.27E-09	-1.19E-09	-7.46E-10	-7.02E-10	-4.66E-10
Std Dev Biased	2.50E-09	2.90E-09	2.95E-09	3.66E-09	3.60E-09
Ps90%/90% (+KTL) Biased	5.59E-09	6.77E-09	7.35E-09	9.32E-09	9.40E-09
Ps90%/90% (-KTL) Biased	-8.13E-09	-9.15E-09	-8.85E-09	-1.07E-08	-1.03E-08
Un-Biased Statistics					
Average Un-Biased	1.69E-09	1.74E-09	1.87E-09	2.32E-09	2.04E-09
Std Dev Un-Biased	2.62E-09	2.73E-09	2.70E-09	2.09E-09	3.19E-09
Ps90%/90% (+KTL) Un-Biased	8.87E-09	9.21E-09	9.27E-09	8.06E-09	1.08E-08
Ps90%/90% (-KTL) Un-Biased	-5.49E-09	-5.74E-09	-5.53E-09	-3.42E-09	-6.69E-09
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.11. Plot of +Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.11. Raw data for +Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.40E-07	-2.53E-07	-2.58E-07	-2.75E-07	-2.94E-07
520	-2.50E-07	-2.62E-07	-2.74E-07	-2.86E-07	-3.10E-07
521	-2.52E-07	-2.64E-07	-2.77E-07	-2.89E-07	-3.11E-07
522	-2.53E-07	-2.66E-07	-2.76E-07	-2.89E-07	-3.11E-07
524	-2.36E-07	-2.48E-07	-2.60E-07	-2.74E-07	-2.97E-07
536	-2.27E-07	-2.38E-07	-2.53E-07	-2.71E-07	-3.02E-07
537	-2.39E-07	-2.51E-07	-2.65E-07	-2.83E-07	-3.13E-07
538	-2.28E-07	-2.40E-07	-2.54E-07	-2.72E-07	-3.03E-07
539	-2.30E-07	-2.41E-07	-2.56E-07	-2.75E-07	-3.05E-07
542	-2.49E-07	-2.60E-07	-2.75E-07	-2.94E-07	-3.26E-07
543	-2.45E-07	-2.47E-07	-2.47E-07	-2.47E-07	-2.47E-07
544	-2.73E-07	-2.75E-07	-2.75E-07	-2.74E-07	-2.73E-07
Biased Statistics					
Average Biased	-2.46E-07	-2.59E-07	-2.69E-07	-2.82E-07	-3.05E-07
Std Dev Biased	7.84E-09	7.64E-09	9.31E-09	7.44E-09	8.43E-09
Ps90%/90% (+KTL) Biased	-2.25E-07	-2.38E-07	-2.44E-07	-2.62E-07	-2.81E-07
Ps90%/90% (-KTL) Biased	-2.67E-07	-2.80E-07	-2.95E-07	-3.03E-07	-3.28E-07
Un-Biased Statistics					
Average Un-Biased	-2.35E-07	-2.46E-07	-2.61E-07	-2.79E-07	-3.10E-07
Std Dev Un-Biased	9.10E-09	9.37E-09	9.26E-09	9.66E-09	1.01E-08
Ps90%/90% (+KTL) Un-Biased	-2.10E-07	-2.20E-07	-2.35E-07	-2.53E-07	-2.82E-07
Ps90%/90% (-KTL) Un-Biased	-2.60E-07	-2.72E-07	-2.86E-07	-3.05E-07	-3.38E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.12. Plot of +Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.12. Raw data for +Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	-2.48E-07	-2.60E-07	-2.64E-07	-2.80E-07	-2.96E-07
	520	-2.43E-07	-2.53E-07	-2.64E-07	-2.74E-07	-2.94E-07
	521	-2.84E-07	-2.95E-07	-3.06E-07	-3.16E-07	-3.37E-07
	522	-2.46E-07	-2.57E-07	-2.67E-07	-2.76E-07	-2.95E-07
	524	-2.18E-07	-2.28E-07	-2.36E-07	-2.47E-07	-2.64E-07
	536	-2.30E-07	-2.39E-07	-2.52E-07	-2.68E-07	-2.94E-07
	537	-2.45E-07	-2.56E-07	-2.69E-07	-2.86E-07	-3.12E-07
	538	-2.27E-07	-2.37E-07	-2.48E-07	-2.64E-07	-2.89E-07
	539	-2.55E-07	-2.66E-07	-2.79E-07	-2.95E-07	-3.22E-07
	542	-2.52E-07	-2.62E-07	-2.75E-07	-2.92E-07	-3.21E-07
	543	-1.88E-07	-1.90E-07	-1.90E-07	-1.90E-07	-1.89E-07
	544	-2.47E-07	-2.48E-07	-2.48E-07	-2.48E-07	-2.46E-07
Biased Statistics						
Average Biased		-2.48E-07	-2.59E-07	-2.67E-07	-2.79E-07	-2.97E-07
Std Dev Biased		2.37E-08	2.38E-08	2.47E-08	2.49E-08	2.58E-08
Ps90%/90% (+KTL) Biased		-1.83E-07	-1.93E-07	-2.00E-07	-2.10E-07	-2.27E-07
Ps90%/90% (-KTL) Biased		-3.13E-07	-3.24E-07	-3.35E-07	-3.47E-07	-3.68E-07
Un-Biased Statistics						
Average Un-Biased		-2.42E-07	-2.52E-07	-2.65E-07	-2.81E-07	-3.08E-07
Std Dev Un-Biased		1.27E-08	1.32E-08	1.37E-08	1.41E-08	1.54E-08
Ps90%/90% (+KTL) Un-Biased		-2.07E-07	-2.16E-07	-2.27E-07	-2.43E-07	-2.65E-07
Ps90%/90% (-KTL) Un-Biased		-2.77E-07	-2.88E-07	-3.02E-07	-3.20E-07	-3.50E-07
Specification MIN		-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status		PASS	PASS	PASS	PASS	PASS
Specification MAX		7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.13. Plot of +Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.13. Raw data for +Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.45E-07	-2.59E-07	-2.63E-07	-2.80E-07	-2.98E-07
520	-2.29E-07	-2.40E-07	-2.52E-07	-2.65E-07	-2.86E-07
521	-2.87E-07	-2.99E-07	-3.11E-07	-3.23E-07	-3.50E-07
522	-2.45E-07	-2.56E-07	-2.67E-07	-2.77E-07	-2.97E-07
524	-2.22E-07	-2.34E-07	-2.44E-07	-2.56E-07	-2.78E-07
536	-2.31E-07	-2.42E-07	-2.57E-07	-2.75E-07	-3.05E-07
537	-2.45E-07	-2.57E-07	-2.72E-07	-2.91E-07	-3.23E-07
538	-2.31E-07	-2.42E-07	-2.55E-07	-2.72E-07	-3.00E-07
539	-2.52E-07	-2.63E-07	-2.78E-07	-2.96E-07	-3.25E-07
542	-2.49E-07	-2.61E-07	-2.76E-07	-2.96E-07	-3.28E-07
543	-1.88E-07	-1.90E-07	-1.90E-07	-1.90E-07	-1.90E-07
544	-2.47E-07	-2.47E-07	-2.47E-07	-2.47E-07	-2.46E-07
Biased Statistics					
Average Biased	-2.46E-07	-2.58E-07	-2.67E-07	-2.80E-07	-3.02E-07
Std Dev Biased	2.52E-08	2.53E-08	2.62E-08	2.59E-08	2.81E-08
Ps90%/90% (+KTL) Biased	-1.76E-07	-1.88E-07	-1.96E-07	-2.09E-07	-2.25E-07
Ps90%/90% (-KTL) Biased	-3.15E-07	-3.27E-07	-3.39E-07	-3.51E-07	-3.79E-07
Un-Biased Statistics					
Average Un-Biased	-2.42E-07	-2.53E-07	-2.68E-07	-2.86E-07	-3.16E-07
Std Dev Un-Biased	9.99E-09	1.04E-08	1.07E-08	1.16E-08	1.27E-08
Ps90%/90% (+KTL) Un-Biased	-2.14E-07	-2.24E-07	-2.38E-07	-2.54E-07	-2.81E-07
Ps90%/90% (-KTL) Un-Biased	-2.69E-07	-2.82E-07	-2.97E-07	-3.18E-07	-3.51E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.14. Plot of +Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.14. Raw data for +Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.41E-07	-2.54E-07	-2.58E-07	-2.74E-07	-2.92E-07
520	-2.52E-07	-2.62E-07	-2.72E-07	-2.83E-07	-3.02E-07
521	-2.53E-07	-2.63E-07	-2.74E-07	-2.84E-07	-3.03E-07
522	-2.52E-07	-2.64E-07	-2.74E-07	-2.85E-07	-3.04E-07
524	-2.41E-07	-2.52E-07	-2.61E-07	-2.73E-07	-2.93E-07
536	-2.27E-07	-2.37E-07	-2.49E-07	-2.64E-07	-2.90E-07
537	-2.36E-07	-2.46E-07	-2.58E-07	-2.72E-07	-2.99E-07
538	-2.25E-07	-2.35E-07	-2.47E-07	-2.63E-07	-2.89E-07
539	-2.26E-07	-2.35E-07	-2.47E-07	-2.62E-07	-2.87E-07
542	-2.48E-07	-2.58E-07	-2.72E-07	-2.89E-07	-3.16E-07
543	-2.47E-07	-2.50E-07	-2.50E-07	-2.50E-07	-2.49E-07
544	-2.76E-07	-2.77E-07	-2.77E-07	-2.76E-07	-2.75E-07
Biased Statistics					
Average Biased	-2.48E-07	-2.59E-07	-2.68E-07	-2.80E-07	-2.99E-07
Std Dev Biased	6.16E-09	5.68E-09	7.74E-09	5.89E-09	6.05E-09
Ps90%/90% (+KTL) Biased	-2.31E-07	-2.43E-07	-2.47E-07	-2.64E-07	-2.82E-07
Ps90%/90% (-KTL) Biased	-2.65E-07	-2.75E-07	-2.89E-07	-2.96E-07	-3.15E-07
Un-Biased Statistics					
Average Un-Biased	-2.32E-07	-2.42E-07	-2.55E-07	-2.70E-07	-2.96E-07
Std Dev Un-Biased	9.80E-09	1.01E-08	1.06E-08	1.13E-08	1.21E-08
Ps90%/90% (+KTL) Un-Biased	-2.05E-07	-2.15E-07	-2.25E-07	-2.39E-07	-2.63E-07
Ps90%/90% (-KTL) Un-Biased	-2.59E-07	-2.70E-07	-2.84E-07	-3.01E-07	-3.30E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.15. Plot of -Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.15. Raw data for -Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS1 1 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.43E-07	-2.57E-07	-2.62E-07	-2.79E-07	-3.00E-07
520	-2.51E-07	-2.62E-07	-2.75E-07	-2.87E-07	-3.09E-07
521	-2.51E-07	-2.62E-07	-2.75E-07	-2.88E-07	-3.10E-07
522	-2.48E-07	-2.61E-07	-2.73E-07	-2.84E-07	-3.06E-07
524	-2.35E-07	-2.47E-07	-2.59E-07	-2.74E-07	-2.96E-07
536	-2.29E-07	-2.40E-07	-2.55E-07	-2.74E-07	-3.06E-07
537	-2.39E-07	-2.51E-07	-2.65E-07	-2.83E-07	-3.13E-07
538	-2.24E-07	-2.36E-07	-2.49E-07	-2.68E-07	-2.98E-07
539	-2.23E-07	-2.34E-07	-2.48E-07	-2.67E-07	-2.95E-07
542	-2.47E-07	-2.58E-07	-2.72E-07	-2.91E-07	-3.22E-07
543	-2.43E-07	-2.46E-07	-2.45E-07	-2.45E-07	-2.45E-07
544	-2.67E-07	-2.68E-07	-2.68E-07	-2.67E-07	-2.66E-07
Biased Statistics					
Average Biased	-2.46E-07	-2.58E-07	-2.69E-07	-2.82E-07	-3.04E-07
Std Dev Biased	6.74E-09	6.45E-09	7.73E-09	5.87E-09	5.97E-09
Ps90%/90% (+KTL) Biased	-2.27E-07	-2.40E-07	-2.48E-07	-2.66E-07	-2.88E-07
Ps90%/90% (-KTL) Biased	-2.64E-07	-2.76E-07	-2.90E-07	-2.99E-07	-3.21E-07
Un-Biased Statistics					
Average Un-Biased	-2.33E-07	-2.44E-07	-2.58E-07	-2.77E-07	-3.07E-07
Std Dev Un-Biased	1.02E-08	1.02E-08	1.04E-08	1.03E-08	1.10E-08
Ps90%/90% (+KTL) Un-Biased	-2.04E-07	-2.16E-07	-2.30E-07	-2.48E-07	-2.76E-07
Ps90%/90% (-KTL) Un-Biased	-2.61E-07	-2.72E-07	-2.87E-07	-3.05E-07	-3.37E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.16. Plot of -Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.16. Raw data for -Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS1 2 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.48E-07	-2.60E-07	-2.64E-07	-2.79E-07	-2.96E-07
520	-2.40E-07	-2.50E-07	-2.60E-07	-2.71E-07	-2.90E-07
521	-2.87E-07	-2.97E-07	-3.09E-07	-3.18E-07	-3.38E-07
522	-2.45E-07	-2.56E-07	-2.65E-07	-2.75E-07	-2.94E-07
524	-2.17E-07	-2.27E-07	-2.35E-07	-2.46E-07	-2.64E-07
536	-2.33E-07	-2.42E-07	-2.56E-07	-2.72E-07	-2.97E-07
537	-2.40E-07	-2.50E-07	-2.63E-07	-2.79E-07	-3.06E-07
538	-2.26E-07	-2.36E-07	-2.47E-07	-2.62E-07	-2.86E-07
539	-2.56E-07	-2.67E-07	-2.80E-07	-2.97E-07	-3.23E-07
542	-2.45E-07	-2.56E-07	-2.69E-07	-2.86E-07	-3.14E-07
543	-1.86E-07	-1.87E-07	-1.87E-07	-1.87E-07	-1.87E-07
544	-2.52E-07	-2.53E-07	-2.53E-07	-2.53E-07	-2.52E-07
Biased Statistics					
Average Biased	-2.47E-07	-2.58E-07	-2.67E-07	-2.78E-07	-2.96E-07
Std Dev Biased	2.53E-08	2.51E-08	2.66E-08	2.61E-08	2.67E-08
Ps90%/90% (+KTL) Biased	-1.78E-07	-1.89E-07	-1.94E-07	-2.06E-07	-2.23E-07
Ps90%/90% (-KTL) Biased	-3.17E-07	-3.27E-07	-3.39E-07	-3.49E-07	-3.70E-07
Un-Biased Statistics					
Average Un-Biased	-2.40E-07	-2.50E-07	-2.63E-07	-2.79E-07	-3.05E-07
Std Dev Un-Biased	1.16E-08	1.21E-08	1.24E-08	1.31E-08	1.43E-08
Ps90%/90% (+KTL) Un-Biased	-2.08E-07	-2.17E-07	-2.29E-07	-2.43E-07	-2.66E-07
Ps90%/90% (-KTL) Un-Biased	-2.72E-07	-2.84E-07	-2.97E-07	-3.15E-07	-3.44E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.17. Plot of -Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.17. Raw data for -Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS1 3 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.47E-07	-2.61E-07	-2.66E-07	-2.82E-07	-3.01E-07
520	-2.27E-07	-2.39E-07	-2.51E-07	-2.63E-07	-2.84E-07
521	-2.86E-07	-2.98E-07	-3.11E-07	-3.22E-07	-3.49E-07
522	-2.44E-07	-2.56E-07	-2.66E-07	-2.78E-07	-3.00E-07
524	-2.17E-07	-2.29E-07	-2.38E-07	-2.51E-07	-2.72E-07
536	-2.28E-07	-2.38E-07	-2.53E-07	-2.72E-07	-3.01E-07
537	-2.42E-07	-2.54E-07	-2.69E-07	-2.88E-07	-3.20E-07
538	-2.31E-07	-2.42E-07	-2.55E-07	-2.72E-07	-3.00E-07
539	-2.55E-07	-2.67E-07	-2.81E-07	-2.99E-07	-3.29E-07
542	-2.45E-07	-2.56E-07	-2.72E-07	-2.90E-07	-3.21E-07
543	-1.86E-07	-1.88E-07	-1.88E-07	-1.88E-07	-1.88E-07
544	-2.45E-07	-2.45E-07	-2.45E-07	-2.45E-07	-2.44E-07
Biased Statistics					
Average Biased	-2.44E-07	-2.57E-07	-2.66E-07	-2.79E-07	-3.01E-07
Std Dev Biased	2.62E-08	2.64E-08	2.73E-08	2.70E-08	2.93E-08
Ps90%/90% (+KTL) Biased	-1.72E-07	-1.84E-07	-1.91E-07	-2.05E-07	-2.21E-07
Ps90%/90% (-KTL) Biased	-3.16E-07	-3.29E-07	-3.41E-07	-3.53E-07	-3.81E-07
Un-Biased Statistics					
Average Un-Biased	-2.40E-07	-2.51E-07	-2.66E-07	-2.84E-07	-3.14E-07
Std Dev Un-Biased	1.12E-08	1.15E-08	1.18E-08	1.19E-08	1.28E-08
Ps90%/90% (+KTL) Un-Biased	-2.09E-07	-2.20E-07	-2.34E-07	-2.52E-07	-2.79E-07
Ps90%/90% (-KTL) Un-Biased	-2.71E-07	-2.83E-07	-2.98E-07	-3.17E-07	-3.49E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.18. Plot of -Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.18. Raw data for -Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS1 4 (A) @ VS=+/-15V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.42E-07	-2.54E-07	-2.58E-07	-2.74E-07	-2.91E-07
520	-2.50E-07	-2.60E-07	-2.70E-07	-2.81E-07	-2.99E-07
521	-2.48E-07	-2.58E-07	-2.69E-07	-2.79E-07	-2.98E-07
522	-2.50E-07	-2.62E-07	-2.72E-07	-2.83E-07	-3.03E-07
524	-2.42E-07	-2.54E-07	-2.64E-07	-2.77E-07	-2.98E-07
536	-2.25E-07	-2.34E-07	-2.47E-07	-2.63E-07	-2.89E-07
537	-2.38E-07	-2.48E-07	-2.61E-07	-2.76E-07	-3.02E-07
538	-2.25E-07	-2.35E-07	-2.46E-07	-2.62E-07	-2.87E-07
539	-2.27E-07	-2.37E-07	-2.49E-07	-2.65E-07	-2.89E-07
542	-2.53E-07	-2.63E-07	-2.77E-07	-2.93E-07	-3.22E-07
543	-2.42E-07	-2.45E-07	-2.45E-07	-2.45E-07	-2.45E-07
544	-2.70E-07	-2.71E-07	-2.72E-07	-2.71E-07	-2.70E-07
Biased Statistics					
Average Biased	-2.46E-07	-2.57E-07	-2.67E-07	-2.79E-07	-2.98E-07
Std Dev Biased	4.10E-09	3.61E-09	5.59E-09	3.45E-09	4.24E-09
Ps90%/90% (+KTL) Biased	-2.35E-07	-2.48E-07	-2.51E-07	-2.69E-07	-2.86E-07
Ps90%/90% (-KTL) Biased	-2.58E-07	-2.67E-07	-2.82E-07	-2.88E-07	-3.09E-07
Un-Biased Statistics					
Average Un-Biased	-2.34E-07	-2.43E-07	-2.56E-07	-2.72E-07	-2.98E-07
Std Dev Un-Biased	1.21E-08	1.22E-08	1.29E-08	1.30E-08	1.46E-08
Ps90%/90% (+KTL) Un-Biased	-2.00E-07	-2.10E-07	-2.21E-07	-2.36E-07	-2.58E-07
Ps90%/90% (-KTL) Un-Biased	-2.67E-07	-2.77E-07	-2.91E-07	-3.08E-07	-3.38E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.19. Plot of Input Offset Voltage2 1 (V) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.19. Raw data for Input Offset Voltage2 1 (V) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage2 1 (V) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.04E-04	1.78E-04	1.89E-04	1.79E-04	1.85E-04
520	3.92E-04	3.60E-04	3.62E-04	3.58E-04	3.61E-04
521	1.41E-04	1.10E-04	1.09E-04	1.05E-04	1.05E-04
522	1.93E-04	1.76E-04	1.86E-04	1.86E-04	1.94E-04
524	2.76E-04	2.57E-04	2.55E-04	2.63E-04	2.76E-04
536	6.49E-05	4.80E-05	4.12E-05	3.17E-05	1.23E-05
537	1.95E-04	1.81E-04	1.75E-04	1.69E-04	1.47E-04
538	7.66E-05	7.32E-05	7.04E-05	6.04E-05	5.09E-05
539	5.84E-06	1.12E-05	6.82E-06	6.60E-07	-1.90E-05
542	2.27E-04	2.14E-04	2.06E-04	2.03E-04	1.94E-04
543	7.32E-05	7.18E-05	7.12E-05	7.13E-05	7.18E-05
544	2.32E-04	2.31E-04	2.31E-04	2.32E-04	2.33E-04
Biased Statistics					
Average Biased	2.41E-04	2.16E-04	2.20E-04	2.18E-04	2.24E-04
Std Dev Biased	9.73E-05	9.58E-05	9.48E-05	9.62E-05	9.75E-05
Ps90%/90% (+KTL) Biased	5.08E-04	4.79E-04	4.80E-04	4.82E-04	4.92E-04
Ps90%/90% (-KTL) Biased	-2.59E-05	-4.66E-05	-3.99E-05	-4.53E-05	-4.29E-05
Un-Biased Statistics					
Average Un-Biased	1.14E-04	1.05E-04	9.99E-05	9.29E-05	7.71E-05
Std Dev Un-Biased	9.33E-05	8.77E-05	8.65E-05	8.83E-05	9.04E-05
Ps90%/90% (+KTL) Un-Biased	3.70E-04	3.46E-04	3.37E-04	3.35E-04	3.25E-04
Ps90%/90% (-KTL) Un-Biased	-1.42E-04	-1.35E-04	-1.37E-04	-1.49E-04	-1.71E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.20. Plot of Input Offset Voltage2 2 (V) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.20. Raw data for Input Offset Voltage2 2 (V) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage2 2 (V) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.53E-05	-1.46E-05	-7.07E-06	-8.27E-06	-6.34E-06
520	1.85E-04	1.85E-04	1.87E-04	1.90E-04	1.99E-04
521	5.84E-06	-4.15E-05	-4.14E-05	-2.63E-05	-1.59E-05
522	3.35E-05	1.59E-05	2.94E-05	3.69E-05	5.15E-05
524	8.63E-05	3.58E-05	2.95E-05	4.51E-05	5.99E-05
536	6.55E-05	4.87E-05	4.27E-05	4.01E-05	2.20E-05
537	-3.62E-05	-4.55E-05	-5.48E-05	-5.84E-05	-7.19E-05
538	2.21E-04	2.12E-04	2.16E-04	2.20E-04	2.09E-04
539	1.88E-04	1.77E-04	1.75E-04	1.66E-04	1.60E-04
542	5.72E-05	3.98E-05	3.64E-05	2.70E-05	1.80E-05
543	-3.06E-04	-3.09E-04	-3.10E-04	-3.09E-04	-3.09E-04
544	1.01E-04	1.01E-04	1.02E-04	1.02E-04	1.03E-04
Biased Statistics					
Average Biased	6.53E-05	3.60E-05	3.95E-05	4.75E-05	5.76E-05
Std Dev Biased	7.41E-05	8.81E-05	8.76E-05	8.51E-05	8.58E-05
Ps90%/90% (+KTL) Biased	2.68E-04	2.78E-04	2.80E-04	2.81E-04	2.93E-04
Ps90%/90% (-KTL) Biased	-1.38E-04	-2.06E-04	-2.01E-04	-1.86E-04	-1.78E-04
Un-Biased Statistics					
Average Un-Biased	9.90E-05	8.63E-05	8.31E-05	7.91E-05	6.74E-05
Std Dev Un-Biased	1.05E-04	1.06E-04	1.11E-04	1.13E-04	1.15E-04
Ps90%/90% (+KTL) Un-Biased	3.86E-04	3.77E-04	3.87E-04	3.88E-04	3.82E-04
Ps90%/90% (-KTL) Un-Biased	-1.88E-04	-2.04E-04	-2.20E-04	-2.30E-04	-2.47E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.21. Plot of Input Offset Voltage2 3 (V) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.21. Raw data for Input Offset Voltage_{2 3} (V) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage _{2 3} (V) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	1.72E-04	2.18E-04	2.20E-04	2.13E-04	2.18E-04
520	3.41E-04	3.03E-04	3.00E-04	3.01E-04	3.07E-04
521	1.68E-04	1.41E-04	1.28E-04	1.44E-04	1.49E-04
522	1.58E-04	1.32E-04	1.37E-04	1.40E-04	1.42E-04
524	1.03E-05	-1.48E-05	-3.04E-05	-2.75E-05	-2.65E-05
536	-2.23E-04	-2.38E-04	-2.41E-04	-2.47E-04	-2.70E-04
537	1.38E-04	1.15E-04	1.14E-04	1.04E-04	9.39E-05
538	1.03E-04	8.84E-05	8.34E-05	7.43E-05	5.80E-05
539	1.58E-04	1.84E-04	1.75E-04	1.66E-04	1.53E-04
542	7.50E-05	5.62E-05	4.93E-05	3.86E-05	2.54E-05
543	1.71E-04	1.70E-04	1.70E-04	1.71E-04	1.72E-04
544	1.71E-04	1.71E-04	1.71E-04	1.72E-04	1.74E-04
Biased Statistics					
Average Biased	1.70E-04	1.56E-04	1.51E-04	1.54E-04	1.58E-04
Std Dev Biased	1.17E-04	1.18E-04	1.23E-04	1.21E-04	1.23E-04
Ps90%/90% (+KTL) Biased	4.90E-04	4.78E-04	4.89E-04	4.85E-04	4.94E-04
Ps90%/90% (-KTL) Biased	-1.51E-04	-1.67E-04	-1.87E-04	-1.77E-04	-1.78E-04
Un-Biased Statistics					
Average Un-Biased	5.04E-05	4.13E-05	3.62E-05	2.71E-05	1.20E-05
Std Dev Un-Biased	1.56E-04	1.63E-04	1.62E-04	1.60E-04	1.64E-04
Ps90%/90% (+KTL) Un-Biased	4.78E-04	4.88E-04	4.80E-04	4.67E-04	4.63E-04
Ps90%/90% (-KTL) Un-Biased	-3.77E-04	-4.06E-04	-4.08E-04	-4.12E-04	-4.39E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.22. Plot of Input Offset Voltage2 4 (V) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.22. Raw data for Input Offset Voltage2 4 (V) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage2 4 (V) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.15E-04	9.19E-05	9.39E-05	9.40E-05	1.00E-04
520	7.06E-05	3.55E-05	3.77E-05	3.76E-05	4.70E-05
521	1.98E-04	1.62E-04	1.65E-04	1.66E-04	1.76E-04
522	6.98E-05	6.21E-05	6.90E-05	7.14E-05	7.97E-05
524	2.73E-04	2.53E-04	2.47E-04	2.60E-04	2.74E-04
536	-6.01E-05	-5.59E-05	-5.80E-05	-6.44E-05	-7.60E-05
537	2.65E-04	2.62E-04	2.56E-04	2.49E-04	2.35E-04
538	2.55E-04	2.60E-04	2.59E-04	2.50E-04	2.41E-04
539	1.33E-05	1.27E-05	7.66E-06	-1.88E-06	-1.91E-05
542	5.69E-05	4.65E-05	3.69E-05	3.35E-05	2.26E-05
543	3.19E-04	3.14E-04	3.13E-04	3.14E-04	3.16E-04
544	1.68E-04	1.70E-04	1.70E-04	1.69E-04	1.70E-04
Biased Statistics					
Average Biased	1.45E-04	1.21E-04	1.22E-04	1.26E-04	1.35E-04
Std Dev Biased	8.84E-05	8.76E-05	8.39E-05	8.83E-05	9.08E-05
Ps90%/90% (+KTL) Biased	3.88E-04	3.61E-04	3.53E-04	3.68E-04	3.84E-04
Ps90%/90% (-KTL) Biased	-9.71E-05	-1.19E-04	-1.08E-04	-1.17E-04	-1.14E-04
Un-Biased Statistics					
Average Un-Biased	1.06E-04	1.05E-04	1.00E-04	9.33E-05	8.08E-05
Std Dev Un-Biased	1.47E-04	1.47E-04	1.47E-04	1.47E-04	1.48E-04
Ps90%/90% (+KTL) Un-Biased	5.09E-04	5.09E-04	5.04E-04	4.96E-04	4.86E-04
Ps90%/90% (-KTL) Un-Biased	-2.96E-04	-2.98E-04	-3.04E-04	-3.10E-04	-3.25E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.23. Plot of Input Offset Current2 1 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.23. Raw data for Input Offset Current2 1 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current2 1 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.12E-09	2.85E-09	2.02E-09	1.31E-09	1.86E-09
520	1.88E-09	1.60E-10	-5.40E-10	-2.23E-09	-2.37E-09
521	8.40E-10	-1.60E-10	2.20E-10	-5.00E-11	2.65E-09
522	6.38E-09	3.90E-09	4.03E-09	5.89E-09	5.90E-09
524	-1.19E-09	-1.52E-09	-3.94E-09	-5.81E-09	-5.00E-09
536	-5.70E-10	-1.29E-09	-8.40E-10	-1.81E-09	-1.46E-09
537	-8.30E-10	-4.30E-10	-1.10E-09	4.30E-10	-1.03E-09
538	5.88E-09	4.09E-09	5.27E-09	5.03E-09	5.40E-09
539	-5.30E-09	-1.72E-09	-3.08E-09	-4.69E-09	-7.19E-09
542	3.05E-09	3.01E-09	1.52E-09	1.41E-09	1.39E-09
543	-1.50E-10	-1.20E-10	-1.50E-10	-2.10E-10	-1.80E-10
544	4.00E-10	1.50E-10	2.50E-10	1.80E-10	2.00E-10
Biased Statistics					
Average Biased	2.61E-09	1.05E-09	3.58E-10	-1.78E-10	6.08E-10
Std Dev Biased	3.11E-09	2.25E-09	2.98E-09	4.33E-09	4.30E-09
Ps90%/90% (+KTL) Biased	1.11E-08	7.21E-09	8.53E-09	1.17E-08	1.24E-08
Ps90%/90% (-KTL) Biased	-5.91E-09	-5.12E-09	-7.82E-09	-1.20E-08	-1.12E-08
Un-Biased Statistics					
Average Un-Biased	4.46E-10	7.32E-10	3.54E-10	7.40E-11	-5.78E-10
Std Dev Un-Biased	4.24E-09	2.64E-09	3.20E-09	3.63E-09	4.59E-09
Ps90%/90% (+KTL) Un-Biased	1.21E-08	7.98E-09	9.12E-09	1.00E-08	1.20E-08
Ps90%/90% (-KTL) Un-Biased	-1.12E-08	-6.51E-09	-8.41E-09	-9.88E-09	-1.32E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.24. Plot of Input Offset Current2 2 (A) @ VS=+-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.24. Raw data for Input Offset Current2 2 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current2 2 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	8.68E-09	8.37E-09	7.43E-09	6.67E-09	7.71E-09
520	-1.67E-09	-1.84E-09	-2.90E-09	-3.73E-09	-4.08E-09
521	1.05E-08	1.89E-09	2.96E-09	5.43E-09	9.84E-09
522	3.65E-09	2.64E-09	4.00E-09	5.41E-09	4.96E-09
524	6.65E-09	-2.18E-09	-3.22E-09	-1.73E-09	2.20E-09
536	2.72E-09	2.21E-09	2.53E-09	3.03E-09	2.16E-09
537	6.96E-09	5.95E-09	5.35E-09	6.42E-09	4.03E-09
538	1.06E-08	1.18E-08	1.20E-08	1.39E-08	1.25E-08
539	1.19E-08	1.11E-08	1.10E-08	9.38E-09	1.29E-08
542	-5.10E-10	-1.58E-09	-1.57E-09	-1.96E-09	-3.47E-09
543	1.43E-09	1.16E-09	1.20E-09	1.16E-09	1.14E-09
544	8.86E-09	8.81E-09	8.82E-09	9.16E-09	9.01E-09
Biased Statistics					
Average Biased	5.57E-09	1.78E-09	1.65E-09	2.41E-09	4.13E-09
Std Dev Biased	4.78E-09	4.27E-09	4.61E-09	4.77E-09	5.41E-09
Ps90%/90% (+KTL) Biased	1.87E-08	1.35E-08	1.43E-08	1.55E-08	1.90E-08
Ps90%/90% (-KTL) Biased	-7.55E-09	-9.94E-09	-1.10E-08	-1.07E-08	-1.07E-08
Un-Biased Statistics					
Average Un-Biased	6.34E-09	5.90E-09	5.85E-09	6.15E-09	5.61E-09
Std Dev Un-Biased	5.24E-09	5.74E-09	5.71E-09	6.03E-09	7.01E-09
Ps90%/90% (+KTL) Un-Biased	2.07E-08	2.16E-08	2.15E-08	2.27E-08	2.48E-08
Ps90%/90% (-KTL) Un-Biased	-8.02E-09	-9.83E-09	-9.79E-09	-1.04E-08	-1.36E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.25. Plot of Input Offset Current2 3 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.25. Raw data for Input Offset Current_{2 3} (A) @ VS=±15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{2 3} (A) @ VS=±15V, VCM=15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	-8.80E-10	5.16E-09	5.17E-09	3.09E-09	4.37E-09
520	3.40E-10	-4.10E-10	-1.05E-09	-1.45E-09	4.20E-10
521	1.31E-08	1.27E-08	1.18E-08	1.12E-08	1.30E-08
522	-1.91E-09	-4.03E-09	-2.91E-09	1.58E-09	2.85E-09
524	-3.20E-10	-2.92E-09	-4.42E-09	-4.24E-09	-3.09E-09
536	-6.27E-09	-7.27E-09	-8.33E-09	-8.24E-09	-8.49E-09
537	-5.41E-09	-7.68E-09	-5.44E-09	-5.42E-09	-4.50E-09
538	1.34E-08	1.34E-08	1.44E-08	1.53E-08	1.66E-08
539	-2.98E-09	-3.92E-09	-5.31E-09	-3.58E-09	-2.95E-09
542	4.19E-09	-2.60E-10	-2.20E-10	6.30E-10	1.52E-09
543	-3.14E-09	-2.12E-09	-2.14E-09	-2.07E-09	-1.93E-09
544	-2.94E-09	-3.22E-09	-3.20E-09	-3.07E-09	-3.08E-09
Biased Statistics					
Average Biased	2.07E-09	2.10E-09	1.72E-09	2.04E-09	3.52E-09
Std Dev Biased	6.23E-09	6.91E-09	6.72E-09	5.85E-09	6.02E-09
Ps90%/90% (+KTL) Biased	1.91E-08	2.10E-08	2.02E-08	1.81E-08	2.00E-08
Ps90%/90% (-KTL) Biased	-1.50E-08	-1.68E-08	-1.67E-08	-1.40E-08	-1.30E-08
Un-Biased Statistics					
Average Un-Biased	5.92E-10	-1.14E-09	-9.80E-10	-2.56E-10	4.30E-10
Std Dev Un-Biased	8.27E-09	8.67E-09	9.08E-09	9.29E-09	9.71E-09
Ps90%/90% (+KTL) Un-Biased	2.33E-08	2.26E-08	2.39E-08	2.52E-08	2.70E-08
Ps90%/90% (-KTL) Un-Biased	-2.21E-08	-2.49E-08	-2.59E-08	-2.57E-08	-2.62E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.26. Plot of Input Offset Current2 4 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.26. Raw data for Input Offset Current_{2 4} (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{2 4} (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	6.07E-09	5.37E-09	2.34E-09	7.20E-10	2.24E-09
520	-5.86E-09	-7.05E-09	-7.78E-09	-8.38E-09	-6.08E-09
521	-1.40E-08	-1.35E-08	-1.53E-08	-1.69E-08	-1.60E-08
522	1.04E-08	1.01E-08	8.42E-09	1.01E-08	8.65E-09
524	2.77E-09	2.70E-09	-8.90E-10	-3.30E-09	-1.43E-09
536	9.30E-10	6.00E-11	-1.32E-09	-2.06E-09	-8.40E-10
537	-1.30E-09	-2.38E-09	-2.72E-09	-3.82E-09	-4.80E-09
538	-9.39E-09	-8.55E-09	-8.61E-09	-8.60E-09	-8.80E-09
539	6.22E-09	7.39E-09	7.27E-09	5.38E-09	7.97E-09
542	-1.30E-09	-1.23E-09	-2.07E-09	-1.58E-09	-2.65E-09
543	-7.00E-11	-2.50E-10	-1.80E-10	-2.10E-10	-2.10E-10
544	4.81E-09	5.00E-09	5.02E-09	4.90E-09	4.91E-09
Biased Statistics					
Average Biased	-1.34E-10	-4.82E-10	-2.65E-09	-3.55E-09	-2.53E-09
Std Dev Biased	9.77E-09	9.60E-09	9.18E-09	1.01E-08	9.27E-09
Ps90%/90% (+KTL) Biased	2.67E-08	2.58E-08	2.25E-08	2.40E-08	2.29E-08
Ps90%/90% (-KTL) Biased	-2.69E-08	-2.68E-08	-2.78E-08	-3.12E-08	-2.79E-08
Un-Biased Statistics					
Average Un-Biased	-9.68E-10	-9.42E-10	-1.49E-09	-2.14E-09	-1.82E-09
Std Dev Un-Biased	5.62E-09	5.71E-09	5.69E-09	5.04E-09	6.23E-09
Ps90%/90% (+KTL) Un-Biased	1.44E-08	1.47E-08	1.41E-08	1.17E-08	1.52E-08
Ps90%/90% (-KTL) Un-Biased	-1.64E-08	-1.66E-08	-1.71E-08	-1.59E-08	-1.89E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.27. Plot of +Input Bias Current BIAS2 1 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.27. Raw data for +Input Bias Current BIAS2 1 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS2 1 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.83E-07	3.19E-07	3.59E-07	4.11E-07	4.83E-07
520	3.09E-07	3.44E-07	3.90E-07	4.43E-07	5.19E-07
521	2.93E-07	3.40E-07	3.84E-07	4.36E-07	5.07E-07
522	2.91E-07	3.31E-07	3.73E-07	4.18E-07	4.98E-07
524	2.92E-07	3.26E-07	3.65E-07	4.20E-07	4.98E-07
536	2.81E-07	3.17E-07	3.62E-07	4.18E-07	4.99E-07
537	2.81E-07	3.16E-07	3.58E-07	4.11E-07	4.86E-07
538	2.72E-07	3.14E-07	3.57E-07	4.14E-07	4.87E-07
539	2.75E-07	3.15E-07	3.58E-07	4.12E-07	4.83E-07
542	2.94E-07	3.33E-07	3.80E-07	4.43E-07	5.20E-07
543	2.86E-07	2.88E-07	2.88E-07	2.88E-07	2.87E-07
544	3.15E-07	3.16E-07	3.16E-07	3.16E-07	3.15E-07
Biased Statistics					
Average Biased	2.94E-07	3.32E-07	3.74E-07	4.26E-07	5.01E-07
Std Dev Biased	9.15E-09	1.01E-08	1.26E-08	1.33E-08	1.34E-08
Ps90%/90% (+KTL) Biased	3.19E-07	3.60E-07	4.09E-07	4.62E-07	5.38E-07
Ps90%/90% (-KTL) Biased	2.68E-07	3.04E-07	3.39E-07	3.89E-07	4.65E-07
Un-Biased Statistics					
Average Un-Biased	2.80E-07	3.19E-07	3.63E-07	4.20E-07	4.95E-07
Std Dev Un-Biased	8.69E-09	7.92E-09	9.45E-09	1.35E-08	1.51E-08
Ps90%/90% (+KTL) Un-Biased	3.04E-07	3.41E-07	3.89E-07	4.57E-07	5.36E-07
Ps90%/90% (-KTL) Un-Biased	2.57E-07	2.97E-07	3.37E-07	3.83E-07	4.54E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.28. Plot of +Input Bias Current BIAS2 2 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.28. Raw data for +Input Bias Current BIAS2 2 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS2 2 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.01E-07	3.39E-07	3.81E-07	4.34E-07	5.05E-07
520	2.90E-07	3.27E-07	3.72E-07	4.22E-07	4.98E-07
521	3.24E-07	3.60E-07	4.09E-07	4.65E-07	5.39E-07
522	2.99E-07	3.36E-07	3.78E-07	4.24E-07	5.08E-07
524	2.76E-07	3.07E-07	3.43E-07	3.90E-07	4.60E-07
536	2.91E-07	3.29E-07	3.75E-07	4.33E-07	5.14E-07
537	2.94E-07	3.31E-07	3.76E-07	4.33E-07	5.08E-07
538	2.87E-07	3.25E-07	3.67E-07	4.21E-07	4.87E-07
539	3.15E-07	3.53E-07	4.05E-07	4.63E-07	5.37E-07
542	2.93E-07	3.31E-07	3.79E-07	4.39E-07	5.13E-07
543	2.46E-07	2.47E-07	2.47E-07	2.47E-07	2.46E-07
544	3.04E-07	3.05E-07	3.05E-07	3.04E-07	3.04E-07
Biased Statistics					
Average Biased	2.98E-07	3.34E-07	3.76E-07	4.27E-07	5.02E-07
Std Dev Biased	1.78E-08	1.92E-08	2.35E-08	2.68E-08	2.82E-08
Ps90%/90% (+KTL) Biased	3.47E-07	3.86E-07	4.41E-07	5.01E-07	5.79E-07
Ps90%/90% (-KTL) Biased	2.49E-07	2.81E-07	3.12E-07	3.54E-07	4.25E-07
Un-Biased Statistics					
Average Un-Biased	2.96E-07	3.34E-07	3.80E-07	4.38E-07	5.12E-07
Std Dev Un-Biased	1.12E-08	1.11E-08	1.46E-08	1.56E-08	1.76E-08
Ps90%/90% (+KTL) Un-Biased	3.27E-07	3.64E-07	4.20E-07	4.81E-07	5.60E-07
Ps90%/90% (-KTL) Un-Biased	2.65E-07	3.03E-07	3.40E-07	3.95E-07	4.64E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.29. Plot of +Input Bias Current BIAS2 3 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.29. Raw data for +Input Bias Current BIAS2 3 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS2 3 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.88E-07	3.30E-07	3.71E-07	4.24E-07	4.96E-07
520	2.77E-07	3.11E-07	3.53E-07	4.03E-07	4.75E-07
521	3.30E-07	3.65E-07	4.14E-07	4.74E-07	5.52E-07
522	2.91E-07	3.35E-07	3.77E-07	4.23E-07	5.08E-07
524	2.71E-07	3.08E-07	3.41E-07	3.94E-07	4.65E-07
536	2.81E-07	3.18E-07	3.63E-07	4.19E-07	4.99E-07
537	2.86E-07	3.28E-07	3.73E-07	4.29E-07	5.06E-07
538	2.96E-07	3.35E-07	3.80E-07	4.36E-07	5.08E-07
539	3.08E-07	3.40E-07	3.93E-07	4.51E-07	5.25E-07
542	2.87E-07	3.27E-07	3.72E-07	4.36E-07	5.12E-07
543	2.43E-07	2.44E-07	2.44E-07	2.44E-07	2.44E-07
544	2.89E-07	2.89E-07	2.89E-07	2.89E-07	2.88E-07
Biased Statistics					
Average Biased	2.91E-07	3.30E-07	3.71E-07	4.23E-07	4.99E-07
Std Dev Biased	2.33E-08	2.29E-08	2.79E-08	3.10E-08	3.40E-08
Ps90%/90% (+KTL) Biased	3.55E-07	3.93E-07	4.48E-07	5.08E-07	5.92E-07
Ps90%/90% (-KTL) Biased	2.28E-07	2.67E-07	2.95E-07	3.38E-07	4.06E-07
Un-Biased Statistics					
Average Un-Biased	2.92E-07	3.29E-07	3.76E-07	4.34E-07	5.10E-07
Std Dev Un-Biased	1.08E-08	8.50E-09	1.11E-08	1.18E-08	9.67E-09
Ps90%/90% (+KTL) Un-Biased	3.21E-07	3.53E-07	4.07E-07	4.66E-07	5.37E-07
Ps90%/90% (-KTL) Un-Biased	2.62E-07	3.06E-07	3.45E-07	4.02E-07	4.84E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.30. Plot of +Input Bias Current BIAS2 4 (A) @ VS=+/-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.30. Raw data for +Input Bias Current BIAS2 4 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS2 4 (A) @ VS=+/-15V, VCM=15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.85E-07	3.20E-07	3.58E-07	4.10E-07	4.82E-07
520	2.95E-07	3.31E-07	3.76E-07	4.27E-07	5.06E-07
521	2.93E-07	3.29E-07	3.71E-07	4.22E-07	4.93E-07
522	3.00E-07	3.38E-07	3.78E-07	4.22E-07	5.01E-07
524	3.05E-07	3.40E-07	3.78E-07	4.32E-07	5.08E-07
536	2.74E-07	3.14E-07	3.56E-07	4.13E-07	4.94E-07
537	2.78E-07	3.18E-07	3.59E-07	4.09E-07	4.82E-07
538	2.78E-07	3.17E-07	3.60E-07	4.16E-07	4.89E-07
539	2.81E-07	3.16E-07	3.61E-07	4.15E-07	4.84E-07
542	2.90E-07	3.28E-07	3.76E-07	4.32E-07	5.14E-07
543	2.90E-07	2.91E-07	2.91E-07	2.91E-07	2.91E-07
544	3.25E-07	3.26E-07	3.26E-07	3.26E-07	3.25E-07
Biased Statistics					
Average Biased	2.96E-07	3.32E-07	3.72E-07	4.23E-07	4.98E-07
Std Dev Biased	7.73E-09	8.01E-09	8.29E-09	8.24E-09	1.08E-08
Ps90%/90% (+KTL) Biased	3.17E-07	3.54E-07	3.95E-07	4.45E-07	5.27E-07
Ps90%/90% (-KTL) Biased	2.74E-07	3.10E-07	3.49E-07	4.00E-07	4.68E-07
Un-Biased Statistics					
Average Un-Biased	2.80E-07	3.19E-07	3.62E-07	4.17E-07	4.92E-07
Std Dev Un-Biased	6.12E-09	5.53E-09	7.74E-09	9.04E-09	1.28E-08
Ps90%/90% (+KTL) Un-Biased	2.97E-07	3.34E-07	3.84E-07	4.42E-07	5.27E-07
Ps90%/90% (-KTL) Un-Biased	2.63E-07	3.04E-07	3.41E-07	3.92E-07	4.57E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.31. Plot of -Input Bias Current BIAS2 1 (A) @ VS=+-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.31. Raw data for -Input Bias Current BIAS2 1 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS2 1 (A) @ VS=+/-15V, VCM=15V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	2.78E-07	3.16E-07	3.55E-07	4.06E-07	4.79E-07
	520	3.06E-07	3.42E-07	3.86E-07	4.42E-07	5.18E-07
	521	2.92E-07	3.39E-07	3.81E-07	4.34E-07	5.03E-07
	522	2.85E-07	3.26E-07	3.68E-07	4.11E-07	4.92E-07
	524	2.93E-07	3.27E-07	3.67E-07	4.25E-07	5.01E-07
	536	2.81E-07	3.18E-07	3.62E-07	4.18E-07	4.99E-07
	537	2.82E-07	3.17E-07	3.57E-07	4.10E-07	4.84E-07
	538	2.66E-07	3.10E-07	3.49E-07	4.07E-07	4.79E-07
	539	2.80E-07	3.16E-07	3.60E-07	4.15E-07	4.87E-07
	542	2.91E-07	3.29E-07	3.77E-07	4.37E-07	5.18E-07
	543	2.87E-07	2.88E-07	2.88E-07	2.88E-07	2.87E-07
	544	3.15E-07	3.15E-07	3.16E-07	3.15E-07	3.14E-07
Biased Statistics						
Average Biased		2.91E-07	3.30E-07	3.72E-07	4.24E-07	4.99E-07
Std Dev Biased		1.03E-08	1.04E-08	1.23E-08	1.50E-08	1.42E-08
Ps90%/90% (+KTL) Biased		3.19E-07	3.59E-07	4.05E-07	4.65E-07	5.37E-07
Ps90%/90% (-KTL) Biased		2.63E-07	3.02E-07	3.38E-07	3.82E-07	4.60E-07
Un-Biased Statistics						
Average Un-Biased		2.80E-07	3.18E-07	3.61E-07	4.18E-07	4.93E-07
Std Dev Un-Biased		9.18E-09	7.13E-09	1.03E-08	1.17E-08	1.56E-08
Ps90%/90% (+KTL) Un-Biased		3.05E-07	3.37E-07	3.89E-07	4.50E-07	5.36E-07
Ps90%/90% (-KTL) Un-Biased		2.55E-07	2.98E-07	3.33E-07	3.85E-07	4.50E-07
Specification MIN		-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status		PASS	PASS	PASS	PASS	PASS
Specification MAX		7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.32. Plot of -Input Bias Current BIAS2 2 (A) @ VS=+-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.32. Raw data for -Input Bias Current BIAS2 2 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS2 2 (A) @ VS=+/-15V, VCM=15V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	2.92E-07	3.30E-07	3.70E-07	4.25E-07	4.97E-07
	520	2.91E-07	3.29E-07	3.71E-07	4.25E-07	4.99E-07
	521	3.14E-07	3.54E-07	4.01E-07	4.54E-07	5.28E-07
	522	2.95E-07	3.33E-07	3.72E-07	4.16E-07	4.99E-07
	524	2.69E-07	3.09E-07	3.43E-07	3.90E-07	4.56E-07
	536	2.88E-07	3.26E-07	3.70E-07	4.27E-07	5.09E-07
	537	2.87E-07	3.25E-07	3.67E-07	4.24E-07	5.00E-07
	538	2.76E-07	3.13E-07	3.51E-07	4.03E-07	4.71E-07
	539	3.04E-07	3.38E-07	3.89E-07	4.48E-07	5.18E-07
	542	2.94E-07	3.32E-07	3.78E-07	4.39E-07	5.13E-07
	543	2.45E-07	2.46E-07	2.46E-07	2.46E-07	2.45E-07
	544	2.95E-07	2.95E-07	2.95E-07	2.95E-07	2.95E-07
Biased Statistics						
	Average Biased	2.92E-07	3.31E-07	3.71E-07	4.22E-07	4.96E-07
	Std Dev Biased	1.59E-08	1.60E-08	2.04E-08	2.30E-08	2.57E-08
	Ps90%/90% (+KTL) Biased	3.36E-07	3.75E-07	4.27E-07	4.85E-07	5.66E-07
	Ps90%/90% (-KTL) Biased	2.49E-07	2.87E-07	3.15E-07	3.59E-07	4.26E-07
Un-Biased Statistics						
	Average Un-Biased	2.90E-07	3.27E-07	3.71E-07	4.28E-07	5.02E-07
	Std Dev Un-Biased	1.00E-08	9.41E-09	1.38E-08	1.72E-08	1.85E-08
	Ps90%/90% (+KTL) Un-Biased	3.17E-07	3.53E-07	4.09E-07	4.75E-07	5.53E-07
	Ps90%/90% (-KTL) Un-Biased	2.62E-07	3.01E-07	3.33E-07	3.81E-07	4.51E-07
	Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
	Status	PASS	PASS	PASS	PASS	PASS
	Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.33. Plot of -Input Bias Current BIAS2 3 (A) @ VS=+-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.33. Raw data for -Input Bias Current BIAS2 3 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS2 3 (A) @ VS=+/-15V, VCM=15V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	2.89E-07	3.25E-07	3.64E-07	4.19E-07	4.89E-07
	520	2.77E-07	3.11E-07	3.50E-07	4.01E-07	4.74E-07
	521	3.17E-07	3.50E-07	4.02E-07	4.60E-07	5.35E-07
	522	2.92E-07	3.38E-07	3.76E-07	4.21E-07	5.02E-07
	524	2.71E-07	3.10E-07	3.45E-07	3.96E-07	4.68E-07
	536	2.87E-07	3.25E-07	3.68E-07	4.25E-07	5.06E-07
	537	2.91E-07	3.35E-07	3.78E-07	4.33E-07	5.08E-07
	538	2.83E-07	3.22E-07	3.64E-07	4.19E-07	4.86E-07
	539	3.11E-07	3.43E-07	3.94E-07	4.52E-07	5.26E-07
	542	2.83E-07	3.27E-07	3.72E-07	4.33E-07	5.09E-07
	543	2.46E-07	2.46E-07	2.46E-07	2.46E-07	2.45E-07
	544	2.91E-07	2.92E-07	2.92E-07	2.92E-07	2.91E-07
Biased Statistics						
Average Biased		2.89E-07	3.27E-07	3.67E-07	4.19E-07	4.93E-07
Std Dev Biased		1.79E-08	1.73E-08	2.28E-08	2.52E-08	2.68E-08
Ps90%/90% (+KTL) Biased		3.38E-07	3.74E-07	4.30E-07	4.88E-07	5.67E-07
Ps90%/90% (-KTL) Biased		2.40E-07	2.79E-07	3.05E-07	3.50E-07	4.20E-07
Un-Biased Statistics						
Average Un-Biased		2.91E-07	3.30E-07	3.75E-07	4.32E-07	5.07E-07
Std Dev Un-Biased		1.18E-08	8.49E-09	1.20E-08	1.23E-08	1.43E-08
Ps90%/90% (+KTL) Un-Biased		3.23E-07	3.53E-07	4.08E-07	4.66E-07	5.46E-07
Ps90%/90% (-KTL) Un-Biased		2.58E-07	3.07E-07	3.42E-07	3.98E-07	4.68E-07
Specification MIN		-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status		PASS	PASS	PASS	PASS	PASS
Specification MAX		7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.34. Plot of -Input Bias Current BIAS2 4 (A) @ VS=+-15V, VCM=15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.34. Raw data for -Input Bias Current BIAS2 4 (A) @ VS=+/-15V, VCM=15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS2 4 (A) @ VS=+/-15V, VCM=15V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	2.79E-07	3.15E-07	3.54E-07	4.06E-07	4.76E-07
	520	3.01E-07	3.37E-07	3.77E-07	4.33E-07	5.07E-07
	521	3.06E-07	3.35E-07	3.82E-07	4.36E-07	5.06E-07
	522	2.90E-07	3.28E-07	3.66E-07	4.12E-07	4.90E-07
	524	3.03E-07	3.37E-07	3.76E-07	4.32E-07	5.09E-07
	536	2.73E-07	3.14E-07	3.54E-07	4.13E-07	4.91E-07
	537	2.79E-07	3.19E-07	3.57E-07	4.09E-07	4.84E-07
	538	2.88E-07	3.25E-07	3.67E-07	4.22E-07	4.94E-07
	539	2.74E-07	3.09E-07	3.48E-07	4.04E-07	4.73E-07
	542	2.92E-07	3.29E-07	3.75E-07	4.34E-07	5.11E-07
	543	2.90E-07	2.91E-07	2.92E-07	2.91E-07	2.91E-07
	544	3.20E-07	3.21E-07	3.21E-07	3.20E-07	3.20E-07
Biased Statistics						
Average Biased		2.96E-07	3.30E-07	3.71E-07	4.24E-07	4.98E-07
Std Dev Biased		1.12E-08	9.65E-09	1.12E-08	1.38E-08	1.42E-08
Ps90%/90% (+KTL) Biased		3.26E-07	3.57E-07	4.02E-07	4.61E-07	5.37E-07
Ps90%/90% (-KTL) Biased		2.65E-07	3.04E-07	3.41E-07	3.86E-07	4.59E-07
Un-Biased Statistics						
Average Un-Biased		2.81E-07	3.19E-07	3.60E-07	4.17E-07	4.90E-07
Std Dev Un-Biased		8.25E-09	8.34E-09	1.05E-08	1.19E-08	1.41E-08
Ps90%/90% (+KTL) Un-Biased		3.04E-07	3.42E-07	3.89E-07	4.49E-07	5.29E-07
Ps90%/90% (-KTL) Un-Biased		2.58E-07	2.96E-07	3.31E-07	3.84E-07	4.52E-07
Specification MIN		-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status		PASS	PASS	PASS	PASS	PASS
Specification MAX		7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.35. Plot of Input Offset Voltage3 1 (V) @ VS=+-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.35. Raw data for Input Offset Voltage3 1 (V) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage3 1 (V) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.18E-05	-1.06E-05	5.40E-07	-1.07E-05	-1.11E-05
520	2.27E-04	1.96E-04	1.96E-04	1.87E-04	1.73E-04
521	-1.17E-04	-1.29E-04	-1.35E-04	-1.41E-04	-1.50E-04
522	-1.40E-04	-1.66E-04	-1.61E-04	-1.69E-04	-1.76E-04
524	-8.41E-05	-1.03E-04	-9.97E-05	-9.10E-05	-9.22E-05
536	-1.14E-04	-1.32E-04	-1.38E-04	-1.53E-04	-1.77E-04
537	-2.01E-04	-2.14E-04	-2.21E-04	-2.33E-04	-2.58E-04
538	-4.76E-05	-4.45E-05	-5.86E-05	-7.26E-05	-9.27E-05
539	-2.61E-04	-2.63E-04	-2.71E-04	-2.80E-04	-3.06E-04
542	5.67E-05	4.12E-05	2.95E-05	1.77E-05	4.20E-07
543	-3.15E-04	-3.17E-04	-3.18E-04	-3.17E-04	-3.17E-04
544	-2.04E-04	-2.04E-04	-2.05E-04	-2.04E-04	-2.04E-04
Biased Statistics					
Average Biased	-2.05E-05	-4.24E-05	-3.98E-05	-4.52E-05	-5.12E-05
Std Dev Biased	1.50E-04	1.45E-04	1.45E-04	1.43E-04	1.40E-04
Ps90%/90% (+KTL) Biased	3.91E-04	3.55E-04	3.58E-04	3.47E-04	3.33E-04
Ps90%/90% (-KTL) Biased	-4.32E-04	-4.40E-04	-4.38E-04	-4.37E-04	-4.36E-04
Un-Biased Statistics					
Average Un-Biased	-1.14E-04	-1.22E-04	-1.32E-04	-1.44E-04	-1.67E-04
Std Dev Un-Biased	1.25E-04	1.24E-04	1.21E-04	1.20E-04	1.24E-04
Ps90%/90% (+KTL) Un-Biased	2.30E-04	2.16E-04	2.00E-04	1.85E-04	1.73E-04
Ps90%/90% (-KTL) Un-Biased	-4.57E-04	-4.61E-04	-4.64E-04	-4.73E-04	-5.06E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.36. Plot of Input Offset Voltage3 2 (V) @ VS=+-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.36. Raw data for Input Offset Voltage3 2 (V) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage3 2 (V) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.59E-04	-3.00E-04	-2.91E-04	-2.95E-04	-3.02E-04
520	1.24E-04	1.15E-04	1.15E-04	1.13E-04	1.10E-04
521	-3.49E-04	-3.86E-04	-3.88E-04	-3.74E-04	-3.72E-04
522	-3.41E-04	-3.59E-04	-3.49E-04	-3.46E-04	-3.39E-04
524	1.29E-04	9.87E-05	8.75E-05	9.22E-05	9.28E-05
536	4.67E-05	2.83E-05	2.00E-05	1.04E-05	-1.23E-05
537	-3.81E-04	-4.08E-04	-4.17E-04	-4.27E-04	-4.42E-04
538	-1.41E-04	-1.51E-04	-1.49E-04	-1.46E-04	-1.64E-04
539	-1.75E-04	-1.83E-04	-1.91E-04	-2.03E-04	-2.16E-04
542	-2.48E-04	-2.71E-04	-2.76E-04	-2.85E-04	-3.00E-04
543	-9.06E-05	-9.59E-05	-9.70E-05	-9.60E-05	-9.60E-05
544	-6.15E-05	-6.04E-05	-6.18E-05	-6.02E-05	-5.95E-05
Biased Statistics					
Average Biased	-1.39E-04	-1.66E-04	-1.65E-04	-1.62E-04	-1.62E-04
Std Dev Biased	2.45E-04	2.51E-04	2.46E-04	2.43E-04	2.42E-04
Ps90%/90% (+KTL) Biased	5.33E-04	5.23E-04	5.08E-04	5.05E-04	5.01E-04
Ps90%/90% (-KTL) Biased	-8.12E-04	-8.55E-04	-8.39E-04	-8.29E-04	-8.25E-04
Un-Biased Statistics					
Average Un-Biased	-1.80E-04	-1.97E-04	-2.03E-04	-2.10E-04	-2.27E-04
Std Dev Un-Biased	1.57E-04	1.60E-04	1.61E-04	1.62E-04	1.59E-04
Ps90%/90% (+KTL) Un-Biased	2.50E-04	2.43E-04	2.40E-04	2.35E-04	2.10E-04
Ps90%/90% (-KTL) Un-Biased	-6.09E-04	-6.37E-04	-6.45E-04	-6.56E-04	-6.64E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.37. Plot of Input Offset Voltage3 3 (V) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.37. Raw data for Input Offset Voltage3 3 (V) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage3 3 (V) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-4.89E-05	-4.39E-05	-3.95E-05	-4.15E-05	-3.83E-05
520	-8.57E-05	-1.19E-04	-1.24E-04	-1.29E-04	-1.35E-04
521	-2.15E-04	-2.43E-04	-2.40E-04	-2.42E-04	-2.44E-04
522	1.85E-05	4.27E-06	4.04E-06	3.00E-07	-6.70E-06
524	1.74E-06	-2.78E-05	-5.00E-05	-5.54E-05	-6.82E-05
536	-5.25E-04	-5.41E-04	-5.47E-04	-5.54E-04	-5.86E-04
537	1.30E-05	-2.00E-05	-2.54E-05	-3.99E-05	-5.95E-05
538	-2.13E-04	-2.29E-04	-2.38E-04	-2.56E-04	-2.80E-04
539	-1.09E-04	-8.71E-05	-9.75E-05	-1.16E-04	-1.34E-04
542	9.84E-05	8.05E-05	6.86E-05	4.73E-05	2.34E-05
543	5.38E-05	4.89E-05	4.90E-05	4.97E-05	5.08E-05
544	-6.29E-05	-6.49E-05	-6.45E-05	-6.49E-05	-6.25E-05
Biased Statistics					
Average Biased	-6.59E-05	-8.58E-05	-8.99E-05	-9.35E-05	-9.84E-05
Std Dev Biased	9.32E-05	9.87E-05	9.58E-05	9.53E-05	9.40E-05
Ps90%/90% (+KTL) Biased	1.90E-04	1.85E-04	1.73E-04	1.68E-04	1.59E-04
Ps90%/90% (-KTL) Biased	-3.22E-04	-3.57E-04	-3.53E-04	-3.55E-04	-3.56E-04
Un-Biased Statistics					
Average Un-Biased	-1.47E-04	-1.59E-04	-1.68E-04	-1.84E-04	-2.07E-04
Std Dev Un-Biased	2.42E-04	2.41E-04	2.40E-04	2.35E-04	2.39E-04
Ps90%/90% (+KTL) Un-Biased	5.17E-04	5.02E-04	4.89E-04	4.61E-04	4.49E-04
Ps90%/90% (-KTL) Un-Biased	-8.11E-04	-8.20E-04	-8.24E-04	-8.28E-04	-8.64E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.38. Plot of Input Offset Voltage3 4 (V) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.38. Raw data for Input Offset Voltage_{3 4} (V) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage _{3 4} (V) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-1.38E-04	-1.61E-04	-1.55E-04	-1.55E-04	-1.57E-04
520	-2.34E-05	-7.02E-05	-6.85E-05	-7.53E-05	-7.47E-05
521	1.24E-04	8.50E-05	8.78E-05	8.51E-05	8.66E-05
522	-8.54E-05	-9.93E-05	-9.01E-05	-9.25E-05	-9.18E-05
524	1.04E-04	7.86E-05	7.74E-05	8.82E-05	9.01E-05
536	-1.15E-04	-1.15E-04	-1.19E-04	-1.28E-04	-1.47E-04
537	-1.70E-04	-1.73E-04	-1.78E-04	-1.85E-04	-2.00E-04
538	1.76E-04	1.69E-04	1.64E-04	1.54E-04	1.38E-04
539	-1.74E-04	-1.76E-04	-1.85E-04	-1.97E-04	-2.18E-04
542	-8.07E-05	-9.48E-05	-1.05E-04	-1.15E-04	-1.26E-04
543	4.14E-04	4.05E-04	4.03E-04	4.04E-04	4.08E-04
544	2.08E-05	1.99E-05	1.91E-05	2.01E-05	2.19E-05
Biased Statistics					
Average Biased	-3.67E-06	-3.33E-05	-2.96E-05	-3.00E-05	-2.94E-05
Std Dev Biased	1.15E-04	1.10E-04	1.07E-04	1.11E-04	1.12E-04
Ps90%/90% (+KTL) Biased	3.13E-04	2.69E-04	2.65E-04	2.73E-04	2.77E-04
Ps90%/90% (-KTL) Biased	-3.20E-04	-3.35E-04	-3.24E-04	-3.33E-04	-3.36E-04
Un-Biased Statistics					
Average Un-Biased	-7.27E-05	-7.81E-05	-8.48E-05	-9.40E-05	-1.11E-04
Std Dev Un-Biased	1.44E-04	1.43E-04	1.43E-04	1.43E-04	1.44E-04
Ps90%/90% (+KTL) Un-Biased	3.23E-04	3.13E-04	3.08E-04	2.99E-04	2.84E-04
Ps90%/90% (-KTL) Un-Biased	-4.68E-04	-4.69E-04	-4.78E-04	-4.87E-04	-5.05E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.39. Plot of Input Offset Current3 1 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.39. Raw data for Input Offset Current_{3 1} (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{3 1} (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	4.25E-09	4.59E-09	4.65E-09	5.61E-09	6.15E-09
520	2.13E-09	1.08E-09	1.46E-09	1.53E-09	-1.04E-09
521	-1.01E-09	-1.42E-09	-1.46E-09	-9.90E-10	-1.19E-09
522	-2.83E-09	-3.37E-09	-1.99E-09	-2.90E-09	-4.34E-09
524	-1.50E-10	-5.20E-10	-7.10E-10	-1.80E-10	-3.50E-10
536	8.90E-10	7.60E-10	1.64E-09	3.00E-09	2.85E-09
537	3.30E-10	1.50E-10	7.10E-10	1.30E-10	-1.70E-10
538	-2.92E-09	-2.82E-09	-3.68E-09	-3.09E-09	-3.64E-09
539	-6.85E-09	-6.84E-09	-7.82E-09	-7.69E-09	-1.00E-08
542	-6.90E-10	-1.24E-09	-1.66E-09	-1.87E-09	-3.18E-09
543	-1.12E-09	-1.09E-09	-1.09E-09	-1.08E-09	-1.07E-09
544	-6.80E-09	-6.86E-09	-6.86E-09	-6.85E-09	-6.83E-09
Biased Statistics					
Average Biased	4.78E-10	7.20E-11	3.90E-10	6.14E-10	-1.54E-10
Std Dev Biased	2.76E-09	2.99E-09	2.72E-09	3.22E-09	3.85E-09
Ps90%/90% (+KTL) Biased	8.05E-09	8.28E-09	7.85E-09	9.43E-09	1.04E-08
Ps90%/90% (-KTL) Biased	-7.09E-09	-8.14E-09	-7.07E-09	-8.20E-09	-1.07E-08
Un-Biased Statistics					
Average Un-Biased	-1.85E-09	-2.00E-09	-2.16E-09	-1.90E-09	-2.83E-09
Std Dev Un-Biased	3.15E-09	3.04E-09	3.78E-09	3.97E-09	4.79E-09
Ps90%/90% (+KTL) Un-Biased	6.80E-09	6.33E-09	8.21E-09	8.98E-09	1.03E-08
Ps90%/90% (-KTL) Un-Biased	-1.05E-08	-1.03E-08	-1.25E-08	-1.28E-08	-1.60E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.40. Plot of Input Offset Current3 2 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.40. Raw data for Input Offset Current_{3 2} (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{3 2} (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.90E-10	-3.40E-10	-7.80E-10	-1.00E-09	-1.04E-09
520	-2.14E-09	-2.45E-09	-2.79E-09	-2.55E-09	-3.64E-09
521	2.49E-09	1.66E-09	2.48E-09	1.68E-09	9.00E-10
522	-2.19E-09	-2.27E-09	-3.23E-09	-1.86E-09	-1.84E-09
524	-9.00E-11	2.00E-11	-2.80E-10	1.40E-10	1.02E-09
536	4.57E-09	4.89E-09	4.50E-09	5.42E-09	3.77E-09
537	-4.77E-09	-5.04E-09	-5.06E-09	-6.26E-09	-4.78E-09
538	-9.20E-10	-5.70E-10	-3.90E-10	-8.70E-10	-1.92E-09
539	2.24E-09	2.33E-09	2.05E-09	2.58E-09	2.55E-09
542	-6.33E-09	-6.20E-09	-6.17E-09	-5.13E-09	-5.87E-09
543	-2.03E-09	-2.01E-09	-2.03E-09	-2.02E-09	-2.00E-09
544	6.89E-09	6.97E-09	6.98E-09	6.98E-09	6.88E-09
Biased Statistics					
Average Biased	-3.08E-10	-6.76E-10	-9.20E-10	-7.18E-10	-9.20E-10
Std Dev Biased	1.95E-09	1.71E-09	2.28E-09	1.68E-09	1.96E-09
Ps90%/90% (+KTL) Biased	5.05E-09	4.02E-09	5.34E-09	3.88E-09	4.45E-09
Ps90%/90% (-KTL) Biased	-5.66E-09	-5.37E-09	-7.18E-09	-5.31E-09	-6.29E-09
Un-Biased Statistics					
Average Un-Biased	-1.04E-09	-9.18E-10	-1.01E-09	-8.52E-10	-1.25E-09
Std Dev Un-Biased	4.59E-09	4.72E-09	4.56E-09	4.97E-09	4.30E-09
Ps90%/90% (+KTL) Un-Biased	1.15E-08	1.20E-08	1.15E-08	1.28E-08	1.05E-08
Ps90%/90% (-KTL) Un-Biased	-1.36E-08	-1.39E-08	-1.35E-08	-1.45E-08	-1.30E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.41. Plot of Input Offset Current3 3 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.41. Raw data for Input Offset Current_{3 3} (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{3 3} (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	2.26E-09	3.24E-09	3.07E-09	3.43E-09	3.59E-09
520	-1.62E-09	-1.01E-09	-1.51E-09	-1.55E-09	-1.91E-09
521	-1.50E-09	-1.10E-09	-8.00E-10	-1.48E-09	-1.15E-09
522	-2.80E-10	6.60E-10	-1.50E-10	1.41E-09	3.43E-09
524	-4.12E-09	-3.71E-09	-4.41E-09	-5.29E-09	-5.24E-09
536	-3.04E-09	-3.34E-09	-4.11E-09	-2.60E-09	-3.40E-09
537	-1.95E-09	-2.01E-09	-1.36E-09	-1.47E-09	-4.50E-10
538	5.00E-11	1.60E-10	-1.10E-10	2.60E-10	4.60E-10
539	4.05E-09	4.37E-09	4.18E-09	4.18E-09	3.73E-09
542	-3.09E-09	-3.55E-09	-3.74E-09	-4.71E-09	-6.99E-09
543	-1.73E-09	-1.76E-09	-1.76E-09	-1.74E-09	-1.74E-09
544	-1.49E-09	-1.57E-09	-1.59E-09	-1.60E-09	-1.56E-09
Biased Statistics					
Average Biased	-1.05E-09	-3.84E-10	-7.60E-10	-6.96E-10	-2.56E-10
Std Dev Biased	2.32E-09	2.56E-09	2.69E-09	3.31E-09	3.77E-09
Ps90%/90% (+KTL) Biased	5.31E-09	6.63E-09	6.61E-09	8.39E-09	1.01E-08
Ps90%/90% (-KTL) Biased	-7.41E-09	-7.40E-09	-8.13E-09	-9.78E-09	-1.06E-08
Un-Biased Statistics					
Average Un-Biased	-7.96E-10	-8.74E-10	-1.03E-09	-8.68E-10	-1.33E-09
Std Dev Un-Biased	2.99E-09	3.28E-09	3.35E-09	3.35E-09	4.06E-09
Ps90%/90% (+KTL) Un-Biased	7.41E-09	8.13E-09	8.16E-09	8.32E-09	9.80E-09
Ps90%/90% (-KTL) Un-Biased	-9.00E-09	-9.87E-09	-1.02E-08	-1.01E-08	-1.25E-08
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.42. Plot of Input Offset Current3 4 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.42. Raw data for Input Offset Current_{3 4} (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{3 4} (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	8.10E-10	9.10E-10	1.15E-09	5.50E-10	-1.60E-10
520	0.00E+00	2.40E-10	3.40E-10	-4.80E-10	-5.70E-10
521	-4.34E-09	-4.89E-09	-3.92E-09	-4.24E-09	-3.45E-09
522	-1.36E-09	-1.36E-09	-1.17E-09	-1.23E-09	-1.04E-09
524	2.85E-09	3.36E-09	4.68E-09	6.59E-09	7.52E-09
536	-1.66E-09	-1.64E-09	-1.00E-09	1.80E-10	1.10E-09
537	2.17E-09	2.23E-09	2.07E-09	3.05E-09	1.80E-09
538	1.59E-09	1.01E-09	5.00E-10	1.63E-09	-3.40E-10
539	2.00E-09	2.51E-09	3.10E-09	3.13E-09	3.06E-09
542	5.25E-09	5.57E-09	5.50E-09	4.53E-09	7.09E-09
543	-3.03E-09	-3.07E-09	-3.07E-09	-3.11E-09	-3.08E-09
544	-4.16E-09	-4.23E-09	-4.18E-09	-4.22E-09	-4.10E-09
Biased Statistics					
Average Biased	-4.08E-10	-3.48E-10	2.16E-10	2.38E-10	4.60E-10
Std Dev Biased	2.68E-09	3.05E-09	3.16E-09	3.97E-09	4.15E-09
Ps90%/90% (+KTL) Biased	6.93E-09	8.03E-09	8.87E-09	1.11E-08	1.18E-08
Ps90%/90% (-KTL) Biased	-7.74E-09	-8.72E-09	-8.44E-09	-1.07E-08	-1.09E-08
Un-Biased Statistics					
Average Un-Biased	1.87E-09	1.94E-09	2.03E-09	2.50E-09	2.54E-09
Std Dev Un-Biased	2.45E-09	2.61E-09	2.49E-09	1.66E-09	2.82E-09
Ps90%/90% (+KTL) Un-Biased	8.60E-09	9.10E-09	8.85E-09	7.04E-09	1.03E-08
Ps90%/90% (-KTL) Un-Biased	-4.86E-09	-5.22E-09	-4.78E-09	-2.03E-09	-5.20E-09
Specification MIN	-7.00E-08	-1.00E-07	-1.00E-07	-1.00E-07	-1.00E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.00E-08	1.00E-07	1.00E-07	1.00E-07	1.00E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.43. Plot of +Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.43. Raw data for +Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.92E-07	-3.06E-07	-3.13E-07	-3.32E-07	-3.59E-07
520	-3.08E-07	-3.23E-07	-3.37E-07	-3.55E-07	-3.89E-07
521	-3.11E-07	-3.25E-07	-3.40E-07	-3.59E-07	-3.89E-07
522	-3.03E-07	-3.18E-07	-3.31E-07	-3.49E-07	-3.76E-07
524	-2.95E-07	-3.10E-07	-3.24E-07	-3.46E-07	-3.75E-07
536	-2.85E-07	-2.98E-07	-3.14E-07	-3.36E-07	-3.74E-07
537	-2.93E-07	-3.06E-07	-3.22E-07	-3.48E-07	-3.81E-07
538	-2.81E-07	-2.94E-07	-3.11E-07	-3.32E-07	-3.71E-07
539	-2.85E-07	-2.98E-07	-3.15E-07	-3.37E-07	-3.77E-07
542	-3.04E-07	-3.18E-07	-3.34E-07	-3.61E-07	-3.97E-07
543	-3.04E-07	-3.07E-07	-3.07E-07	-3.06E-07	-3.06E-07
544	-3.40E-07	-3.45E-07	-3.45E-07	-3.45E-07	-3.40E-07
Biased Statistics					
Average Biased	-3.02E-07	-3.16E-07	-3.29E-07	-3.48E-07	-3.77E-07
Std Dev Biased	8.28E-09	7.99E-09	1.06E-08	1.05E-08	1.23E-08
Ps90%/90% (+KTL) Biased	-2.79E-07	-2.95E-07	-3.00E-07	-3.19E-07	-3.44E-07
Ps90%/90% (-KTL) Biased	-3.24E-07	-3.38E-07	-3.58E-07	-3.77E-07	-4.11E-07
Un-Biased Statistics					
Average Un-Biased	-2.90E-07	-3.03E-07	-3.19E-07	-3.43E-07	-3.80E-07
Std Dev Un-Biased	9.19E-09	9.51E-09	9.33E-09	1.19E-08	9.91E-09
Ps90%/90% (+KTL) Un-Biased	-2.64E-07	-2.77E-07	-2.94E-07	-3.10E-07	-3.53E-07
Ps90%/90% (-KTL) Un-Biased	-3.15E-07	-3.29E-07	-3.45E-07	-3.76E-07	-4.07E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.44. Plot of +Input Bias Current BIAS3 2 (A) @ VS=+-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.44. Raw data for +Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.04E-07	-3.18E-07	-3.24E-07	-3.40E-07	-3.63E-07
520	-2.99E-07	-3.11E-07	-3.24E-07	-3.37E-07	-3.67E-07
521	-3.50E-07	-3.61E-07	-3.75E-07	-3.88E-07	-4.13E-07
522	-3.08E-07	-3.21E-07	-3.32E-07	-3.45E-07	-3.70E-07
524	-2.75E-07	-2.88E-07	-2.97E-07	-3.10E-07	-3.33E-07
536	-2.87E-07	-2.99E-07	-3.13E-07	-3.32E-07	-3.64E-07
537	-2.99E-07	-3.12E-07	-3.27E-07	-3.52E-07	-3.77E-07
538	-2.85E-07	-2.97E-07	-3.10E-07	-3.29E-07	-3.60E-07
539	-3.10E-07	-3.22E-07	-3.37E-07	-3.62E-07	-3.90E-07
542	-3.07E-07	-3.19E-07	-3.34E-07	-3.54E-07	-3.90E-07
543	-2.43E-07	-2.44E-07	-2.45E-07	-2.44E-07	-2.44E-07
544	-3.06E-07	-3.08E-07	-3.08E-07	-3.07E-07	-3.06E-07
Biased Statistics					
Average Biased	-3.07E-07	-3.20E-07	-3.30E-07	-3.44E-07	-3.69E-07
Std Dev Biased	2.68E-08	2.64E-08	2.84E-08	2.80E-08	2.87E-08
Ps90%/90% (+KTL) Biased	-2.33E-07	-2.47E-07	-2.53E-07	-2.67E-07	-2.91E-07
Ps90%/90% (-KTL) Biased	-3.81E-07	-3.92E-07	-4.08E-07	-4.21E-07	-4.48E-07
Un-Biased Statistics					
Average Un-Biased	-2.98E-07	-3.10E-07	-3.24E-07	-3.46E-07	-3.76E-07
Std Dev Un-Biased	1.14E-08	1.17E-08	1.20E-08	1.45E-08	1.40E-08
Ps90%/90% (+KTL) Un-Biased	-2.67E-07	-2.78E-07	-2.91E-07	-3.06E-07	-3.38E-07
Ps90%/90% (-KTL) Un-Biased	-3.29E-07	-3.42E-07	-3.57E-07	-3.85E-07	-4.15E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.45. Plot of +Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.45. Raw data for +Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.01E-07	-3.16E-07	-3.23E-07	-3.40E-07	-3.67E-07
520	-2.84E-07	-2.97E-07	-3.11E-07	-3.26E-07	-3.58E-07
521	-3.53E-07	-3.67E-07	-3.82E-07	-3.97E-07	-4.24E-07
522	-3.05E-07	-3.19E-07	-3.31E-07	-3.48E-07	-3.73E-07
524	-2.81E-07	-2.95E-07	-3.06E-07	-3.23E-07	-3.54E-07
536	-2.88E-07	-3.02E-07	-3.19E-07	-3.40E-07	-3.76E-07
537	-2.99E-07	-3.13E-07	-3.30E-07	-3.57E-07	-3.92E-07
538	-2.89E-07	-3.02E-07	-3.17E-07	-3.38E-07	-3.74E-07
539	-3.07E-07	-3.20E-07	-3.36E-07	-3.61E-07	-3.97E-07
542	-3.04E-07	-3.17E-07	-3.34E-07	-3.61E-07	-4.00E-07
543	-2.44E-07	-2.45E-07	-2.45E-07	-2.45E-07	-2.45E-07
544	-3.07E-07	-3.08E-07	-3.08E-07	-3.08E-07	-3.07E-07
Biased Statistics					
Average Biased	-3.05E-07	-3.19E-07	-3.31E-07	-3.47E-07	-3.75E-07
Std Dev Biased	2.91E-08	2.92E-08	3.04E-08	3.00E-08	2.83E-08
Ps90%/90% (+KTL) Biased	-2.25E-07	-2.39E-07	-2.47E-07	-2.65E-07	-2.97E-07
Ps90%/90% (-KTL) Biased	-3.84E-07	-3.99E-07	-4.14E-07	-4.29E-07	-4.52E-07
Un-Biased Statistics					
Average Un-Biased	-2.97E-07	-3.11E-07	-3.27E-07	-3.51E-07	-3.88E-07
Std Dev Un-Biased	8.42E-09	8.38E-09	8.77E-09	1.15E-08	1.19E-08
Ps90%/90% (+KTL) Un-Biased	-2.74E-07	-2.88E-07	-3.03E-07	-3.20E-07	-3.55E-07
Ps90%/90% (-KTL) Un-Biased	-3.21E-07	-3.34E-07	-3.51E-07	-3.83E-07	-4.20E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.46. Plot of +Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.46. Raw data for +Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.94E-07	-3.07E-07	-3.13E-07	-3.30E-07	-3.57E-07
520	-3.10E-07	-3.22E-07	-3.34E-07	-3.49E-07	-3.77E-07
521	-3.11E-07	-3.23E-07	-3.36E-07	-3.53E-07	-3.78E-07
522	-3.03E-07	-3.17E-07	-3.28E-07	-3.44E-07	-3.70E-07
524	-3.02E-07	-3.15E-07	-3.26E-07	-3.41E-07	-3.73E-07
536	-2.83E-07	-2.94E-07	-3.08E-07	-3.26E-07	-3.56E-07
537	-2.90E-07	-3.01E-07	-3.15E-07	-3.31E-07	-3.65E-07
538	-2.78E-07	-2.90E-07	-3.03E-07	-3.22E-07	-3.55E-07
539	-2.81E-07	-2.92E-07	-3.06E-07	-3.24E-07	-3.55E-07
542	-3.03E-07	-3.15E-07	-3.30E-07	-3.52E-07	-3.87E-07
543	-3.06E-07	-3.09E-07	-3.09E-07	-3.08E-07	-3.08E-07
544	-3.44E-07	-3.47E-07	-3.46E-07	-3.46E-07	-3.44E-07
Biased Statistics					
Average Biased	-3.04E-07	-3.17E-07	-3.27E-07	-3.43E-07	-3.71E-07
Std Dev Biased	7.13E-09	6.59E-09	9.15E-09	8.70E-09	8.53E-09
Ps90%/90% (+KTL) Biased	-2.85E-07	-2.99E-07	-3.02E-07	-3.20E-07	-3.47E-07
Ps90%/90% (-KTL) Biased	-3.24E-07	-3.35E-07	-3.52E-07	-3.67E-07	-3.94E-07
Un-Biased Statistics					
Average Un-Biased	-2.87E-07	-2.99E-07	-3.13E-07	-3.31E-07	-3.64E-07
Std Dev Un-Biased	1.02E-08	1.04E-08	1.09E-08	1.24E-08	1.36E-08
Ps90%/90% (+KTL) Un-Biased	-2.59E-07	-2.70E-07	-2.83E-07	-2.97E-07	-3.26E-07
Ps90%/90% (-KTL) Un-Biased	-3.15E-07	-3.27E-07	-3.42E-07	-3.65E-07	-4.01E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.47. Plot of -Input Bias Current BIAS3 1 (A) @ VS=+-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.47. Raw data for -Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS3 1 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.96E-07	-3.11E-07	-3.18E-07	-3.38E-07	-3.66E-07
520	-3.10E-07	-3.23E-07	-3.38E-07	-3.55E-07	-3.87E-07
521	-3.09E-07	-3.23E-07	-3.38E-07	-3.60E-07	-3.87E-07
522	-3.00E-07	-3.15E-07	-3.29E-07	-3.44E-07	-3.73E-07
524	-2.95E-07	-3.09E-07	-3.23E-07	-3.45E-07	-3.76E-07
536	-2.85E-07	-2.98E-07	-3.15E-07	-3.38E-07	-3.77E-07
537	-2.93E-07	-3.06E-07	-3.22E-07	-3.48E-07	-3.80E-07
538	-2.78E-07	-2.91E-07	-3.07E-07	-3.28E-07	-3.66E-07
539	-2.78E-07	-2.91E-07	-3.07E-07	-3.28E-07	-3.63E-07
542	-3.03E-07	-3.16E-07	-3.32E-07	-3.58E-07	-3.95E-07
543	-3.02E-07	-3.05E-07	-3.05E-07	-3.05E-07	-3.05E-07
544	-3.33E-07	-3.34E-07	-3.34E-07	-3.34E-07	-3.33E-07
Biased Statistics					
Average Biased	-3.02E-07	-3.16E-07	-3.29E-07	-3.48E-07	-3.78E-07
Std Dev Biased	7.32E-09	6.74E-09	8.84E-09	8.99E-09	9.08E-09
Ps90%/90% (+KTL) Biased	-2.82E-07	-2.98E-07	-3.05E-07	-3.24E-07	-3.53E-07
Ps90%/90% (-KTL) Biased	-3.22E-07	-3.35E-07	-3.54E-07	-3.73E-07	-4.03E-07
Un-Biased Statistics					
Average Un-Biased	-2.87E-07	-3.00E-07	-3.17E-07	-3.40E-07	-3.76E-07
Std Dev Un-Biased	1.08E-08	1.08E-08	1.08E-08	1.28E-08	1.27E-08
Ps90%/90% (+KTL) Un-Biased	-2.58E-07	-2.71E-07	-2.87E-07	-3.05E-07	-3.41E-07
Ps90%/90% (-KTL) Un-Biased	-3.17E-07	-3.30E-07	-3.46E-07	-3.75E-07	-4.11E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.48. Plot of -Input Bias Current BIAS3 2 (A) @ VS=+-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.48. Raw data for -Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS3 2 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.04E-07	-3.17E-07	-3.24E-07	-3.40E-07	-3.65E-07
520	-2.97E-07	-3.09E-07	-3.21E-07	-3.34E-07	-3.66E-07
521	-3.53E-07	-3.65E-07	-3.78E-07	-3.90E-07	-4.16E-07
522	-3.05E-07	-3.18E-07	-3.29E-07	-3.41E-07	-3.70E-07
524	-2.75E-07	-2.88E-07	-2.97E-07	-3.10E-07	-3.34E-07
536	-2.92E-07	-3.03E-07	-3.18E-07	-3.37E-07	-3.69E-07
537	-2.95E-07	-3.07E-07	-3.21E-07	-3.39E-07	-3.76E-07
538	-2.84E-07	-2.96E-07	-3.09E-07	-3.27E-07	-3.60E-07
539	-3.12E-07	-3.25E-07	-3.39E-07	-3.64E-07	-3.93E-07
542	-3.01E-07	-3.13E-07	-3.27E-07	-3.52E-07	-3.83E-07
543	-2.41E-07	-2.43E-07	-2.43E-07	-2.43E-07	-2.42E-07
544	-3.13E-07	-3.14E-07	-3.14E-07	-3.14E-07	-3.13E-07
Biased Statistics					
Average Biased	-3.07E-07	-3.19E-07	-3.30E-07	-3.43E-07	-3.70E-07
Std Dev Biased	2.85E-08	2.81E-08	2.96E-08	2.90E-08	2.93E-08
Ps90%/90% (+KTL) Biased	-2.29E-07	-2.42E-07	-2.49E-07	-2.64E-07	-2.90E-07
Ps90%/90% (-KTL) Biased	-3.85E-07	-3.97E-07	-4.11E-07	-4.23E-07	-4.51E-07
Un-Biased Statistics					
Average Un-Biased	-2.97E-07	-3.09E-07	-3.23E-07	-3.44E-07	-3.76E-07
Std Dev Un-Biased	1.05E-08	1.08E-08	1.11E-08	1.42E-08	1.25E-08
Ps90%/90% (+KTL) Un-Biased	-2.68E-07	-2.79E-07	-2.92E-07	-3.05E-07	-3.42E-07
Ps90%/90% (-KTL) Un-Biased	-3.26E-07	-3.38E-07	-3.53E-07	-3.83E-07	-4.11E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.49. Plot of -Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.49. Raw data for -Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS3 3 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.03E-07	-3.19E-07	-3.26E-07	-3.45E-07	-3.71E-07
520	-2.82E-07	-2.96E-07	-3.10E-07	-3.25E-07	-3.56E-07
521	-3.51E-07	-3.65E-07	-3.80E-07	-3.96E-07	-4.22E-07
522	-3.04E-07	-3.19E-07	-3.31E-07	-3.48E-07	-3.76E-07
524	-2.77E-07	-2.90E-07	-3.02E-07	-3.17E-07	-3.47E-07
536	-2.85E-07	-2.98E-07	-3.14E-07	-3.37E-07	-3.73E-07
537	-2.97E-07	-3.11E-07	-3.28E-07	-3.55E-07	-3.87E-07
538	-2.89E-07	-3.02E-07	-3.17E-07	-3.38E-07	-3.73E-07
539	-3.11E-07	-3.24E-07	-3.40E-07	-3.67E-07	-3.97E-07
542	-3.00E-07	-3.13E-07	-3.31E-07	-3.55E-07	-3.90E-07
543	-2.42E-07	-2.44E-07	-2.44E-07	-2.44E-07	-2.43E-07
544	-3.05E-07	-3.06E-07	-3.06E-07	-3.06E-07	-3.05E-07
Biased Statistics					
Average Biased	-3.03E-07	-3.18E-07	-3.30E-07	-3.46E-07	-3.75E-07
Std Dev Biased	2.93E-08	2.95E-08	3.03E-08	3.06E-08	2.91E-08
Ps90%/90% (+KTL) Biased	-2.23E-07	-2.37E-07	-2.47E-07	-2.62E-07	-2.95E-07
Ps90%/90% (-KTL) Biased	-3.83E-07	-3.99E-07	-4.13E-07	-4.30E-07	-4.54E-07
Un-Biased Statistics					
Average Un-Biased	-2.96E-07	-3.10E-07	-3.26E-07	-3.50E-07	-3.84E-07
Std Dev Un-Biased	1.01E-08	1.01E-08	1.04E-08	1.29E-08	1.07E-08
Ps90%/90% (+KTL) Un-Biased	-2.69E-07	-2.82E-07	-2.97E-07	-3.15E-07	-3.55E-07
Ps90%/90% (-KTL) Un-Biased	-3.24E-07	-3.37E-07	-3.55E-07	-3.86E-07	-4.14E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.50. Plot of -Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.50. Raw data for -Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS3 4 (A) @ VS=+/-15V, VCM=-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.94E-07	-3.08E-07	-3.14E-07	-3.31E-07	-3.58E-07
520	-3.10E-07	-3.22E-07	-3.34E-07	-3.51E-07	-3.78E-07
521	-3.07E-07	-3.18E-07	-3.32E-07	-3.50E-07	-3.76E-07
522	-3.02E-07	-3.16E-07	-3.27E-07	-3.41E-07	-3.72E-07
524	-3.05E-07	-3.18E-07	-3.31E-07	-3.53E-07	-3.81E-07
536	-2.81E-07	-2.92E-07	-3.07E-07	-3.26E-07	-3.59E-07
537	-2.92E-07	-3.03E-07	-3.17E-07	-3.34E-07	-3.69E-07
538	-2.79E-07	-2.91E-07	-3.04E-07	-3.23E-07	-3.56E-07
539	-2.83E-07	-2.94E-07	-3.09E-07	-3.27E-07	-3.59E-07
542	-3.09E-07	-3.20E-07	-3.36E-07	-3.58E-07	-3.94E-07
543	-3.02E-07	-3.05E-07	-3.06E-07	-3.05E-07	-3.05E-07
544	-3.36E-07	-3.38E-07	-3.38E-07	-3.37E-07	-3.36E-07
Biased Statistics					
Average Biased	-3.04E-07	-3.16E-07	-3.28E-07	-3.45E-07	-3.73E-07
Std Dev Biased	5.93E-09	5.38E-09	7.86E-09	9.14E-09	9.19E-09
Ps90%/90% (+KTL) Biased	-2.87E-07	-3.02E-07	-3.06E-07	-3.20E-07	-3.48E-07
Ps90%/90% (-KTL) Biased	-3.20E-07	-3.31E-07	-3.49E-07	-3.70E-07	-3.98E-07
Un-Biased Statistics					
Average Un-Biased	-2.89E-07	-3.00E-07	-3.14E-07	-3.34E-07	-3.67E-07
Std Dev Un-Biased	1.21E-08	1.23E-08	1.29E-08	1.44E-08	1.57E-08
Ps90%/90% (+KTL) Un-Biased	-2.56E-07	-2.66E-07	-2.79E-07	-2.94E-07	-3.24E-07
Ps90%/90% (-KTL) Un-Biased	-3.22E-07	-3.34E-07	-3.50E-07	-3.73E-07	-4.10E-07
Specification MIN	-7.15E-07	-8.15E-07	-8.65E-07	-9.15E-07	-9.65E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	7.15E-07	8.15E-07	8.65E-07	9.15E-07	9.65E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.51. Plot of Output Voltage Swing High1 1 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.51. Raw data for Output Voltage Swing High1 1 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High1 1 (V) @ VS=+/-15V IL=0mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	5.94E-03	5.78E-03	6.08E-03	6.11E-03	6.38E-03
	520	5.62E-03	5.70E-03	5.96E-03	6.11E-03	6.16E-03
	521	5.72E-03	5.88E-03	5.91E-03	6.16E-03	6.16E-03
	522	5.92E-03	5.97E-03	6.06E-03	6.33E-03	6.46E-03
	524	5.52E-03	5.72E-03	5.95E-03	5.97E-03	6.06E-03
	536	5.94E-03	6.10E-03	6.32E-03	6.38E-03	6.67E-03
	537	5.71E-03	6.00E-03	6.05E-03	6.28E-03	6.70E-03
	538	5.79E-03	5.85E-03	6.01E-03	6.24E-03	6.55E-03
	539	5.60E-03	5.72E-03	6.00E-03	6.31E-03	6.43E-03
	542	5.72E-03	5.70E-03	6.08E-03	6.24E-03	6.55E-03
	543	5.64E-03	5.80E-03	5.80E-03	5.71E-03	5.64E-03
	544	5.55E-03	5.60E-03	5.63E-03	5.69E-03	5.69E-03
Biased Statistics						
	Average Biased	5.74E-03	5.81E-03	5.99E-03	6.14E-03	6.24E-03
	Std Dev Biased	1.84E-04	1.14E-04	7.40E-05	1.30E-04	1.68E-04
	Ps90%/90% (+KTL) Biased	6.25E-03	6.12E-03	6.19E-03	6.49E-03	6.71E-03
	Ps90%/90% (-KTL) Biased	5.24E-03	5.50E-03	5.79E-03	5.78E-03	5.78E-03
Un-Biased Statistics						
	Average Un-Biased	5.75E-03	5.87E-03	6.09E-03	6.29E-03	6.58E-03
	Std Dev Un-Biased	1.25E-04	1.74E-04	1.31E-04	5.83E-05	1.08E-04
	Ps90%/90% (+KTL) Un-Biased	6.10E-03	6.35E-03	6.45E-03	6.45E-03	6.88E-03
	Ps90%/90% (-KTL) Un-Biased	5.41E-03	5.40E-03	5.73E-03	6.13E-03	6.28E-03
	Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.52. Plot of Output Voltage Swing High1 2 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.52. Raw data for Output Voltage Swing High1 2 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High1 2 (V) @ VS=+/-15V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.91E-03	6.02E-03	6.27E-03	6.23E-03	6.53E-03
520	5.69E-03	5.92E-03	6.05E-03	6.11E-03	6.36E-03
521	5.91E-03	5.92E-03	6.05E-03	6.19E-03	6.41E-03
522	5.84E-03	5.99E-03	6.05E-03	6.26E-03	6.57E-03
524	5.71E-03	5.80E-03	5.93E-03	6.09E-03	6.25E-03
536	6.21E-03	6.29E-03	6.55E-03	6.68E-03	7.00E-03
537	5.94E-03	5.97E-03	6.27E-03	6.33E-03	6.60E-03
538	5.72E-03	5.95E-03	5.93E-03	6.16E-03	6.45E-03
539	5.99E-03	6.02E-03	6.25E-03	6.43E-03	6.75E-03
542	5.84E-03	5.93E-03	6.08E-03	6.38E-03	6.68E-03
543	5.74E-03	5.67E-03	5.73E-03	5.69E-03	5.66E-03
544	5.91E-03	5.83E-03	6.00E-03	6.14E-03	6.14E-03
Biased Statistics					
Average Biased	5.81E-03	5.93E-03	6.07E-03	6.18E-03	6.42E-03
Std Dev Biased	1.06E-04	8.49E-05	1.23E-04	7.40E-05	1.30E-04
Ps90%/90% (+KTL) Biased	6.10E-03	6.16E-03	6.41E-03	6.38E-03	6.78E-03
Ps90%/90% (-KTL) Biased	5.52E-03	5.70E-03	5.73E-03	5.97E-03	6.07E-03
Un-Biased Statistics					
Average Un-Biased	5.94E-03	6.03E-03	6.22E-03	6.40E-03	6.70E-03
Std Dev Un-Biased	1.83E-04	1.48E-04	2.32E-04	1.88E-04	2.03E-04
Ps90%/90% (+KTL) Un-Biased	6.44E-03	6.44E-03	6.85E-03	6.91E-03	7.25E-03
Ps90%/90% (-KTL) Un-Biased	5.44E-03	5.63E-03	5.58E-03	5.88E-03	6.14E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.53. Plot of Output Voltage Swing High1 3 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.53. Raw data for Output Voltage Swing High1 3 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High1 3 (V) @ VS=+/-15V IL=0mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	6.08E-03	6.24E-03	6.32E-03	6.23E-03	6.53E-03
	520	6.11E-03	6.12E-03	6.17E-03	6.36E-03	6.46E-03
	521	5.92E-03	6.04E-03	6.25E-03	6.23E-03	6.50E-03
	522	5.72E-03	5.80E-03	5.95E-03	6.23E-03	6.26E-03
	524	5.74E-03	5.83E-03	5.88E-03	6.04E-03	6.28E-03
	536	6.24E-03	6.49E-03	6.55E-03	6.75E-03	6.99E-03
	537	5.99E-03	5.92E-03	6.23E-03	6.41E-03	6.92E-03
	538	5.86E-03	5.90E-03	6.08E-03	6.24E-03	6.50E-03
	539	6.06E-03	6.22E-03	6.40E-03	6.61E-03	6.92E-03
	542	5.98E-03	5.95E-03	6.32E-03	6.45E-03	6.58E-03
	543	5.64E-03	5.87E-03	5.73E-03	5.86E-03	5.89E-03
	544	5.69E-03	5.88E-03	5.86E-03	5.87E-03	6.03E-03
Biased Statistics						
	Average Biased	5.91E-03	6.01E-03	6.11E-03	6.22E-03	6.41E-03
	Std Dev Biased	1.83E-04	1.89E-04	1.91E-04	1.14E-04	1.27E-04
	Ps90%/90% (+KTL) Biased	6.42E-03	6.52E-03	6.64E-03	6.53E-03	6.75E-03
	Ps90%/90% (-KTL) Biased	5.41E-03	5.49E-03	5.59E-03	5.90E-03	6.06E-03
Un-Biased Statistics						
	Average Un-Biased	6.03E-03	6.10E-03	6.32E-03	6.49E-03	6.78E-03
	Std Dev Un-Biased	1.40E-04	2.56E-04	1.77E-04	1.95E-04	2.25E-04
	Ps90%/90% (+KTL) Un-Biased	6.41E-03	6.80E-03	6.80E-03	7.03E-03	7.40E-03
	Ps90%/90% (-KTL) Un-Biased	5.64E-03	5.40E-03	5.83E-03	5.96E-03	6.17E-03
	Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.54. Plot of Output Voltage Swing High1 4 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.54. Raw data for Output Voltage Swing High1 4 (V) @ VS=+-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High1 4 (V) @ VS=+-15V IL=0mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	6.09E-03	6.20E-03	6.28E-03	6.40E-03	6.65E-03
520	5.89E-03	5.93E-03	6.13E-03	6.28E-03	6.53E-03
521	5.81E-03	5.88E-03	6.03E-03	6.29E-03	6.41E-03
522	6.19E-03	6.22E-03	6.44E-03	6.60E-03	6.68E-03
524	6.28E-03	6.24E-03	6.62E-03	6.67E-03	6.89E-03
536	5.94E-03	6.02E-03	6.05E-03	6.33E-03	6.51E-03
537	5.99E-03	6.09E-03	6.15E-03	6.33E-03	6.68E-03
538	5.86E-03	5.97E-03	6.22E-03	6.23E-03	6.62E-03
539	5.94E-03	5.82E-03	6.10E-03	6.31E-03	6.70E-03
542	6.26E-03	6.17E-03	6.49E-03	6.55E-03	6.90E-03
543	5.74E-03	5.87E-03	5.83E-03	5.76E-03	5.74E-03
544	5.76E-03	5.83E-03	5.80E-03	5.87E-03	5.93E-03
Biased Statistics					
Average Biased	6.05E-03	6.09E-03	6.30E-03	6.45E-03	6.63E-03
Std Dev Biased	1.98E-04	1.74E-04	2.37E-04	1.79E-04	1.79E-04
Ps90%/90% (+KTL) Biased	6.60E-03	6.57E-03	6.95E-03	6.94E-03	7.12E-03
Ps90%/90% (-KTL) Biased	5.51E-03	5.62E-03	5.65E-03	5.96E-03	6.14E-03
Un-Biased Statistics					
Average Un-Biased	6.00E-03	6.01E-03	6.20E-03	6.35E-03	6.68E-03
Std Dev Un-Biased	1.54E-04	1.32E-04	1.73E-04	1.19E-04	1.43E-04
Ps90%/90% (+KTL) Un-Biased	6.42E-03	6.38E-03	6.68E-03	6.68E-03	7.07E-03
Ps90%/90% (-KTL) Un-Biased	5.58E-03	5.65E-03	5.73E-03	6.02E-03	6.29E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.55. Plot of Output Voltage Swing High2 1 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.55. Raw data for Output Voltage Swing High2 1 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High2 1 (V) @ VS=+/-15V IL=1mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	7.22E-02	7.32E-02	7.47E-02	7.50E-02	7.57E-02
	520	6.85E-02	6.99E-02	7.05E-02	7.11E-02	7.14E-02
	521	6.84E-02	6.99E-02	7.04E-02	7.10E-02	7.16E-02
	522	7.35E-02	7.47E-02	7.54E-02	7.60E-02	7.66E-02
	524	6.79E-02	6.80E-02	6.93E-02	7.00E-02	7.05E-02
	536	6.99E-02	7.02E-02	7.08E-02	7.13E-02	7.21E-02
	537	7.16E-02	7.18E-02	7.22E-02	7.28E-02	7.35E-02
	538	7.11E-02	7.13E-02	7.20E-02	7.25E-02	7.33E-02
	539	6.99E-02	7.02E-02	7.07E-02	7.13E-02	7.20E-02
	542	7.06E-02	7.08E-02	7.12E-02	7.19E-02	7.27E-02
	543	6.88E-02	6.83E-02	6.84E-02	6.83E-02	6.83E-02
	544	6.47E-02	6.46E-02	6.45E-02	6.47E-02	6.47E-02
Biased Statistics						
	Average Biased	7.01E-02	7.11E-02	7.21E-02	7.26E-02	7.32E-02
	Std Dev Biased	2.56E-03	2.74E-03	2.81E-03	2.69E-03	2.78E-03
	Ps90%/90% (+KTL) Biased	7.71E-02	7.87E-02	7.98E-02	8.00E-02	8.08E-02
	Ps90%/90% (-KTL) Biased	6.31E-02	6.36E-02	6.44E-02	6.52E-02	6.56E-02
Un-Biased Statistics						
	Average Un-Biased	7.06E-02	7.09E-02	7.14E-02	7.20E-02	7.27E-02
	Std Dev Un-Biased	7.31E-04	7.11E-04	6.86E-04	6.67E-04	6.74E-04
	Ps90%/90% (+KTL) Un-Biased	7.26E-02	7.28E-02	7.33E-02	7.38E-02	7.46E-02
	Ps90%/90% (-KTL) Un-Biased	6.86E-02	6.89E-02	6.95E-02	7.01E-02	7.09E-02
	Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.56. Plot of Output Voltage Swing High2 2 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.56. Raw data for Output Voltage Swing High2 2 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High2 2 (V) @ VS=+/-15V IL=1mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	7.14E-02	7.20E-02	7.38E-02	7.36E-02	7.44E-02
	520	6.94E-02	7.07E-02	7.14E-02	7.20E-02	7.26E-02
	521	6.77E-02	6.88E-02	6.94E-02	7.00E-02	7.06E-02
	522	6.78E-02	6.85E-02	6.94E-02	7.00E-02	7.07E-02
	524	6.72E-02	6.73E-02	6.90E-02	6.95E-02	7.01E-02
	536	6.96E-02	6.97E-02	7.01E-02	7.08E-02	7.17E-02
	537	7.06E-02	7.07E-02	7.15E-02	7.17E-02	7.27E-02
	538	6.78E-02	6.81E-02	6.88E-02	6.93E-02	6.99E-02
	539	7.09E-02	7.11E-02	7.18E-02	7.23E-02	7.31E-02
	542	7.04E-02	7.08E-02	7.12E-02	7.19E-02	7.26E-02
	543	6.93E-02	6.91E-02	6.91E-02	6.91E-02	6.92E-02
	544	6.71E-02	6.71E-02	6.70E-02	6.68E-02	6.70E-02
Biased Statistics						
	Average Biased	6.87E-02	6.94E-02	7.06E-02	7.10E-02	7.17E-02
	Std Dev Biased	1.71E-03	1.88E-03	2.02E-03	1.75E-03	1.79E-03
	Ps90%/90% (+KTL) Biased	7.34E-02	7.46E-02	7.61E-02	7.58E-02	7.66E-02
	Ps90%/90% (-KTL) Biased	6.40E-02	6.43E-02	6.50E-02	6.62E-02	6.68E-02
Un-Biased Statistics						
	Average Un-Biased	6.99E-02	7.01E-02	7.07E-02	7.12E-02	7.20E-02
	Std Dev Un-Biased	1.23E-03	1.25E-03	1.24E-03	1.19E-03	1.30E-03
	Ps90%/90% (+KTL) Un-Biased	7.33E-02	7.35E-02	7.41E-02	7.45E-02	7.55E-02
	Ps90%/90% (-KTL) Un-Biased	6.65E-02	6.66E-02	6.73E-02	6.79E-02	6.84E-02
	Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.57. Plot of Output Voltage Swing High2 3 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.57. Raw data for Output Voltage Swing High2 3 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High2 3 (V) @ VS=+/-15V IL=1mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	7.12E-02	7.21E-02	7.36E-02	7.36E-02	7.43E-02
	520	7.03E-02	7.15E-02	7.24E-02	7.29E-02	7.36E-02
	521	6.78E-02	6.87E-02	6.96E-02	7.02E-02	7.07E-02
	522	6.77E-02	6.85E-02	6.93E-02	7.00E-02	7.06E-02
	524	6.73E-02	6.74E-02	6.86E-02	6.96E-02	7.01E-02
	536	6.94E-02	6.98E-02	7.04E-02	7.09E-02	7.17E-02
	537	7.11E-02	7.13E-02	7.17E-02	7.25E-02	7.32E-02
	538	6.81E-02	6.79E-02	6.88E-02	6.92E-02	6.99E-02
	539	7.10E-02	7.13E-02	7.16E-02	7.22E-02	7.32E-02
	542	7.03E-02	7.06E-02	7.12E-02	7.19E-02	7.26E-02
	543	7.02E-02	6.96E-02	6.97E-02	6.96E-02	6.98E-02
	544	6.75E-02	6.75E-02	6.74E-02	6.75E-02	6.75E-02
Biased Statistics						
Average Biased		6.88E-02	6.96E-02	7.07E-02	7.13E-02	7.19E-02
Std Dev Biased		1.79E-03	2.05E-03	2.18E-03	1.86E-03	1.94E-03
Ps90%/90% (+KTL) Biased		7.38E-02	7.52E-02	7.67E-02	7.64E-02	7.72E-02
Ps90%/90% (-KTL) Biased		6.39E-02	6.40E-02	6.47E-02	6.62E-02	6.66E-02
Un-Biased Statistics						
Average Un-Biased		7.00E-02	7.02E-02	7.08E-02	7.13E-02	7.21E-02
Std Dev Un-Biased		1.28E-03	1.43E-03	1.20E-03	1.34E-03	1.37E-03
Ps90%/90% (+KTL) Un-Biased		7.35E-02	7.41E-02	7.40E-02	7.50E-02	7.59E-02
Ps90%/90% (-KTL) Un-Biased		6.65E-02	6.63E-02	6.75E-02	6.76E-02	6.84E-02
Specification MAX		1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.58. Plot of Output Voltage Swing High2 4 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.58. Raw data for Output Voltage Swing High2 4 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High2 4 (V) @ VS=+/-15V IL=1mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	7.30E-02	7.39E-02	7.56E-02	7.55E-02	7.61E-02
	520	6.89E-02	7.02E-02	7.08E-02	7.16E-02	7.21E-02
	521	6.85E-02	6.99E-02	7.04E-02	7.12E-02	7.17E-02
	522	7.35E-02	7.45E-02	7.56E-02	7.59E-02	7.68E-02
	524	6.76E-02	6.78E-02	6.90E-02	6.97E-02	7.02E-02
	536	7.01E-02	7.03E-02	7.11E-02	7.13E-02	7.22E-02
	537	7.10E-02	7.12E-02	7.18E-02	7.25E-02	7.32E-02
	538	7.13E-02	7.19E-02	7.23E-02	7.30E-02	7.38E-02
	539	7.01E-02	7.04E-02	7.11E-02	7.16E-02	7.24E-02
	542	7.04E-02	7.08E-02	7.12E-02	7.19E-02	7.26E-02
	543	6.83E-02	6.80E-02	6.81E-02	6.80E-02	6.82E-02
	544	6.46E-02	6.44E-02	6.45E-02	6.46E-02	6.47E-02
Biased Statistics						
	Average Biased	7.03E-02	7.12E-02	7.23E-02	7.28E-02	7.34E-02
	Std Dev Biased	2.75E-03	2.88E-03	3.09E-03	2.78E-03	2.87E-03
	Ps90%/90% (+KTL) Biased	7.78E-02	7.91E-02	8.07E-02	8.04E-02	8.13E-02
	Ps90%/90% (-KTL) Biased	6.28E-02	6.33E-02	6.38E-02	6.52E-02	6.55E-02
Un-Biased Statistics						
	Average Un-Biased	7.06E-02	7.09E-02	7.15E-02	7.20E-02	7.28E-02
	Std Dev Un-Biased	5.74E-04	6.49E-04	5.16E-04	6.80E-04	6.37E-04
	Ps90%/90% (+KTL) Un-Biased	7.22E-02	7.27E-02	7.29E-02	7.39E-02	7.46E-02
	Ps90%/90% (-KTL) Un-Biased	6.90E-02	6.91E-02	7.01E-02	7.02E-02	7.11E-02
	Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.59. Plot of Output Voltage Swing High3 1 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.59. Raw data for Output Voltage Swing High3 1 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High3 1 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.80E-01	3.81E-01	3.89E-01	3.89E-01	3.94E-01
520	3.61E-01	3.64E-01	3.66E-01	3.69E-01	3.73E-01
521	3.59E-01	3.62E-01	3.64E-01	3.68E-01	3.71E-01
522	3.84E-01	3.86E-01	3.91E-01	3.94E-01	4.01E-01
524	3.59E-01	3.59E-01	3.63E-01	3.66E-01	3.69E-01
536	3.67E-01	3.69E-01	3.71E-01	3.74E-01	3.79E-01
537	3.74E-01	3.75E-01	3.78E-01	3.81E-01	3.86E-01
538	3.74E-01	3.76E-01	3.78E-01	3.82E-01	3.87E-01
539	3.68E-01	3.69E-01	3.72E-01	3.75E-01	3.80E-01
542	3.70E-01	3.71E-01	3.74E-01	3.77E-01	3.82E-01
543	3.60E-01	3.58E-01	3.58E-01	3.57E-01	3.58E-01
544	3.43E-01	3.42E-01	3.42E-01	3.42E-01	3.43E-01
Biased Statistics					
Average Biased	3.68E-01	3.70E-01	3.75E-01	3.77E-01	3.81E-01
Std Dev Biased	1.22E-02	1.24E-02	1.39E-02	1.32E-02	1.46E-02
Ps90%/90% (+KTL) Biased	4.02E-01	4.04E-01	4.13E-01	4.14E-01	4.21E-01
Ps90%/90% (-KTL) Biased	3.35E-01	3.36E-01	3.36E-01	3.41E-01	3.42E-01
Un-Biased Statistics					
Average Un-Biased	3.71E-01	3.72E-01	3.74E-01	3.78E-01	3.83E-01
Std Dev Un-Biased	3.27E-03	3.26E-03	3.46E-03	3.70E-03	3.70E-03
Ps90%/90% (+KTL) Un-Biased	3.80E-01	3.81E-01	3.84E-01	3.88E-01	3.93E-01
Ps90%/90% (-KTL) Un-Biased	3.62E-01	3.63E-01	3.65E-01	3.68E-01	3.73E-01
Specification MAX	8.00E-01	8.00E-01	8.00E-01	8.00E-01	8.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.60. Plot of Output Voltage Swing High3 2 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.60. Raw data for Output Voltage Swing High3 2 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High3 2 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.74E-01	3.75E-01	3.82E-01	3.82E-01	3.87E-01
520	3.65E-01	3.68E-01	3.71E-01	3.73E-01	3.78E-01
521	3.55E-01	3.57E-01	3.60E-01	3.63E-01	3.66E-01
522	3.54E-01	3.55E-01	3.59E-01	3.61E-01	3.65E-01
524	3.55E-01	3.55E-01	3.59E-01	3.63E-01	3.66E-01
536	3.66E-01	3.67E-01	3.68E-01	3.71E-01	3.76E-01
537	3.70E-01	3.70E-01	3.73E-01	3.77E-01	3.81E-01
538	3.58E-01	3.58E-01	3.61E-01	3.64E-01	3.68E-01
539	3.72E-01	3.73E-01	3.75E-01	3.78E-01	3.84E-01
542	3.69E-01	3.70E-01	3.73E-01	3.77E-01	3.82E-01
543	3.67E-01	3.65E-01	3.65E-01	3.65E-01	3.65E-01
544	3.52E-01	3.51E-01	3.51E-01	3.51E-01	3.52E-01
Biased Statistics					
Average Biased	3.61E-01	3.62E-01	3.66E-01	3.68E-01	3.72E-01
Std Dev Biased	8.54E-03	8.74E-03	1.03E-02	8.89E-03	9.60E-03
Ps90%/90% (+KTL) Biased	3.84E-01	3.86E-01	3.94E-01	3.93E-01	3.99E-01
Ps90%/90% (-KTL) Biased	3.37E-01	3.38E-01	3.38E-01	3.44E-01	3.46E-01
Un-Biased Statistics					
Average Un-Biased	3.67E-01	3.68E-01	3.70E-01	3.73E-01	3.78E-01
Std Dev Un-Biased	5.62E-03	5.79E-03	5.80E-03	6.03E-03	6.44E-03
Ps90%/90% (+KTL) Un-Biased	3.82E-01	3.84E-01	3.86E-01	3.90E-01	3.96E-01
Ps90%/90% (-KTL) Un-Biased	3.52E-01	3.52E-01	3.54E-01	3.57E-01	3.60E-01
Specification MAX	8.00E-01	8.00E-01	8.00E-01	8.00E-01	8.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.61. Plot of Output Voltage Swing High3 3 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.61. Raw data for Output Voltage Swing High3 3 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High3 3 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.74E-01	3.75E-01	3.83E-01	3.83E-01	3.88E-01
520	3.69E-01	3.72E-01	3.76E-01	3.79E-01	3.83E-01
521	3.55E-01	3.57E-01	3.59E-01	3.63E-01	3.65E-01
522	3.55E-01	3.56E-01	3.59E-01	3.61E-01	3.65E-01
524	3.55E-01	3.55E-01	3.60E-01	3.63E-01	3.66E-01
536	3.66E-01	3.66E-01	3.69E-01	3.72E-01	3.77E-01
537	3.72E-01	3.73E-01	3.76E-01	3.79E-01	3.85E-01
538	3.58E-01	3.59E-01	3.61E-01	3.64E-01	3.68E-01
539	3.72E-01	3.73E-01	3.75E-01	3.78E-01	3.83E-01
542	3.69E-01	3.70E-01	3.73E-01	3.76E-01	3.81E-01
543	3.69E-01	3.67E-01	3.68E-01	3.67E-01	3.68E-01
544	3.54E-01	3.53E-01	3.53E-01	3.53E-01	3.54E-01
Biased Statistics					
Average Biased	3.62E-01	3.63E-01	3.67E-01	3.70E-01	3.74E-01
Std Dev Biased	9.38E-03	9.81E-03	1.13E-02	1.02E-02	1.10E-02
Ps90%/90% (+KTL) Biased	3.88E-01	3.90E-01	3.98E-01	3.98E-01	4.04E-01
Ps90%/90% (-KTL) Biased	3.36E-01	3.36E-01	3.36E-01	3.42E-01	3.44E-01
Un-Biased Statistics					
Average Un-Biased	3.67E-01	3.68E-01	3.71E-01	3.74E-01	3.79E-01
Std Dev Un-Biased	5.78E-03	5.97E-03	5.95E-03	6.32E-03	6.62E-03
Ps90%/90% (+KTL) Un-Biased	3.83E-01	3.84E-01	3.87E-01	3.91E-01	3.97E-01
Ps90%/90% (-KTL) Un-Biased	3.52E-01	3.52E-01	3.55E-01	3.57E-01	3.60E-01
Specification MAX	8.00E-01	8.00E-01	8.00E-01	8.00E-01	8.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.62. Plot of Output Voltage Swing High3 4 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.62. Raw data for Output Voltage Swing High3 4 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High3 4 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.82E-01	3.84E-01	3.91E-01	3.92E-01	3.97E-01
520	3.62E-01	3.65E-01	3.68E-01	3.71E-01	3.75E-01
521	3.60E-01	3.63E-01	3.65E-01	3.69E-01	3.72E-01
522	3.84E-01	3.87E-01	3.91E-01	3.95E-01	4.01E-01
524	3.57E-01	3.57E-01	3.61E-01	3.64E-01	3.67E-01
536	3.69E-01	3.70E-01	3.73E-01	3.75E-01	3.81E-01
537	3.73E-01	3.73E-01	3.76E-01	3.79E-01	3.84E-01
538	3.76E-01	3.77E-01	3.81E-01	3.84E-01	3.90E-01
539	3.70E-01	3.70E-01	3.74E-01	3.77E-01	3.82E-01
542	3.69E-01	3.70E-01	3.73E-01	3.76E-01	3.81E-01
543	3.58E-01	3.56E-01	3.56E-01	3.56E-01	3.57E-01
544	3.43E-01	3.42E-01	3.42E-01	3.42E-01	3.43E-01
Biased Statistics					
Average Biased	3.69E-01	3.71E-01	3.75E-01	3.78E-01	3.82E-01
Std Dev Biased	1.28E-02	1.33E-02	1.48E-02	1.43E-02	1.53E-02
Ps90%/90% (+KTL) Biased	4.04E-01	4.08E-01	4.16E-01	4.17E-01	4.24E-01
Ps90%/90% (-KTL) Biased	3.34E-01	3.35E-01	3.35E-01	3.39E-01	3.40E-01
Un-Biased Statistics					
Average Un-Biased	3.71E-01	3.72E-01	3.75E-01	3.78E-01	3.84E-01
Std Dev Un-Biased	3.02E-03	3.11E-03	3.36E-03	3.68E-03	3.66E-03
Ps90%/90% (+KTL) Un-Biased	3.80E-01	3.81E-01	3.84E-01	3.88E-01	3.94E-01
Ps90%/90% (-KTL) Un-Biased	3.63E-01	3.64E-01	3.66E-01	3.68E-01	3.74E-01
Specification MAX	8.00E-01	8.00E-01	8.00E-01	8.00E-01	8.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.63. Plot of Output Voltage Swing Low1 1 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.63. Raw data for Output Voltage Swing Low1 1 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low1 1 (V) @ VS=+/-15V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.87E-02	1.89E-02	1.96E-02	1.95E-02	1.98E-02
520	1.86E-02	1.89E-02	1.90E-02	1.93E-02	1.97E-02
521	1.79E-02	1.82E-02	1.82E-02	1.86E-02	1.88E-02
522	1.78E-02	1.80E-02	1.82E-02	1.84E-02	1.90E-02
524	1.85E-02	1.86E-02	1.91E-02	1.92E-02	1.97E-02
536	1.90E-02	1.91E-02	1.94E-02	1.96E-02	2.00E-02
537	1.92E-02	1.91E-02	1.93E-02	1.96E-02	1.99E-02
538	1.86E-02	1.87E-02	1.88E-02	1.92E-02	1.97E-02
539	1.90E-02	1.91E-02	1.94E-02	1.97E-02	2.01E-02
542	1.80E-02	1.79E-02	1.83E-02	1.88E-02	1.89E-02
543	1.83E-02	1.82E-02	1.82E-02	1.81E-02	1.81E-02
544	1.74E-02	1.72E-02	1.73E-02	1.73E-02	1.73E-02
Biased Statistics					
Average Biased	1.83E-02	1.85E-02	1.88E-02	1.90E-02	1.94E-02
Std Dev Biased	4.21E-04	3.95E-04	5.98E-04	4.62E-04	4.81E-04
Ps90%/90% (+KTL) Biased	1.95E-02	1.96E-02	2.04E-02	2.03E-02	2.07E-02
Ps90%/90% (-KTL) Biased	1.72E-02	1.74E-02	1.72E-02	1.77E-02	1.81E-02
Un-Biased Statistics					
Average Un-Biased	1.87E-02	1.88E-02	1.90E-02	1.94E-02	1.97E-02
Std Dev Un-Biased	4.73E-04	4.94E-04	4.94E-04	3.90E-04	4.97E-04
Ps90%/90% (+KTL) Un-Biased	2.00E-02	2.01E-02	2.04E-02	2.04E-02	2.11E-02
Ps90%/90% (-KTL) Un-Biased	1.74E-02	1.74E-02	1.77E-02	1.83E-02	1.83E-02
Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.64. Plot of Output Voltage Swing Low1 2 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.64. Raw data for Output Voltage Swing Low1 2 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low1 2 (V) @ VS=+/-15V IL=0mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.80E-02	1.83E-02	1.86E-02	1.87E-02	1.93E-02
	520	1.92E-02	1.95E-02	1.96E-02	1.99E-02	2.04E-02
	521	1.78E-02	1.82E-02	1.82E-02	1.84E-02	1.89E-02
	522	1.87E-02	1.89E-02	1.91E-02	1.94E-02	1.99E-02
	524	1.95E-02	1.97E-02	2.00E-02	2.06E-02	2.08E-02
	536	1.90E-02	1.91E-02	1.92E-02	1.97E-02	2.01E-02
	537	1.84E-02	1.85E-02	1.87E-02	1.90E-02	1.95E-02
	538	1.91E-02	1.93E-02	1.94E-02	1.97E-02	2.02E-02
	539	1.82E-02	1.85E-02	1.86E-02	1.88E-02	1.93E-02
	542	1.80E-02	1.82E-02	1.83E-02	1.86E-02	1.92E-02
	543	2.17E-02	2.15E-02	2.14E-02	2.15E-02	2.15E-02
	544	1.91E-02	1.91E-02	1.90E-02	1.91E-02	1.91E-02
Biased Statistics						
	Average Biased	1.86E-02	1.89E-02	1.91E-02	1.94E-02	1.98E-02
	Std Dev Biased	7.42E-04	6.75E-04	7.18E-04	8.86E-04	7.83E-04
	Ps90%/90% (+KTL) Biased	2.07E-02	2.08E-02	2.11E-02	2.18E-02	2.20E-02
	Ps90%/90% (-KTL) Biased	1.66E-02	1.71E-02	1.72E-02	1.70E-02	1.77E-02
Un-Biased Statistics						
	Average Un-Biased	1.86E-02	1.87E-02	1.88E-02	1.91E-02	1.96E-02
	Std Dev Un-Biased	4.78E-04	4.68E-04	4.49E-04	4.96E-04	4.69E-04
	Ps90%/90% (+KTL) Un-Biased	1.99E-02	2.00E-02	2.01E-02	2.05E-02	2.09E-02
	Ps90%/90% (-KTL) Un-Biased	1.72E-02	1.74E-02	1.76E-02	1.78E-02	1.84E-02
	Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
	Status	PASS	PASS	PASS	PASS	PASS




Figure 5.65. Plot of Output Voltage Swing Low1 3 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.65. Raw data for Output Voltage Swing Low1 3 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low1 3 (V) @ VS=+/-15V IL=0mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.81E-02	1.83E-02	1.88E-02	1.88E-02	1.93E-02
	520	1.90E-02	1.95E-02	1.96E-02	1.99E-02	2.04E-02
	521	1.72E-02	1.76E-02	1.77E-02	1.79E-02	1.82E-02
	522	1.84E-02	1.85E-02	1.89E-02	1.91E-02	1.95E-02
	524	1.94E-02	1.92E-02	1.99E-02	2.00E-02	2.06E-02
	536	1.88E-02	1.88E-02	1.91E-02	1.94E-02	1.98E-02
	537	1.82E-02	1.82E-02	1.85E-02	1.87E-02	1.91E-02
	538	1.89E-02	1.91E-02	1.93E-02	1.94E-02	1.98E-02
	539	1.78E-02	1.78E-02	1.81E-02	1.83E-02	1.88E-02
	542	1.77E-02	1.78E-02	1.81E-02	1.83E-02	1.86E-02
	543	2.12E-02	2.13E-02	2.12E-02	2.12E-02	2.13E-02
	544	1.82E-02	1.83E-02	1.81E-02	1.82E-02	1.83E-02
Biased Statistics						
Average Biased		1.84E-02	1.86E-02	1.90E-02	1.91E-02	1.96E-02
Std Dev Biased		8.45E-04	7.51E-04	8.45E-04	8.59E-04	9.45E-04
Ps90%/90% (+KTL) Biased		2.07E-02	2.07E-02	2.13E-02	2.15E-02	2.22E-02
Ps90%/90% (-KTL) Biased		1.61E-02	1.66E-02	1.67E-02	1.68E-02	1.70E-02
Un-Biased Statistics						
Average Un-Biased		1.83E-02	1.83E-02	1.86E-02	1.88E-02	1.92E-02
Std Dev Un-Biased		5.41E-04	5.86E-04	5.30E-04	5.46E-04	5.87E-04
Ps90%/90% (+KTL) Un-Biased		1.98E-02	1.99E-02	2.01E-02	2.03E-02	2.08E-02
Ps90%/90% (-KTL) Un-Biased		1.68E-02	1.67E-02	1.71E-02	1.73E-02	1.76E-02
Specification MAX		3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.66. Plot of Output Voltage Swing Low1 4 (V) @ VS=+-15V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.66. Raw data for Output Voltage Swing Low1 4 (V) @ VS=+/-15V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low1 4 (V) @ VS=+/-15V IL=0mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.87E-02	1.89E-02	1.94E-02	1.93E-02	1.97E-02
	520	1.91E-02	1.91E-02	1.94E-02	1.98E-02	2.02E-02
	521	1.85E-02	1.90E-02	1.91E-02	1.94E-02	1.98E-02
	522	1.81E-02	1.83E-02	1.85E-02	1.87E-02	1.92E-02
	524	1.81E-02	1.80E-02	1.84E-02	1.88E-02	1.92E-02
	536	1.92E-02	1.93E-02	1.95E-02	1.98E-02	2.04E-02
	537	1.93E-02	1.91E-02	1.94E-02	1.99E-02	2.01E-02
	538	1.85E-02	1.86E-02	1.88E-02	1.92E-02	1.96E-02
	539	1.95E-02	1.96E-02	1.99E-02	2.00E-02	2.05E-02
	542	1.81E-02	1.81E-02	1.83E-02	1.88E-02	1.92E-02
	543	1.86E-02	1.86E-02	1.84E-02	1.85E-02	1.84E-02
	544	1.74E-02	1.72E-02	1.72E-02	1.73E-02	1.74E-02
Biased Statistics						
Average Biased		1.85E-02	1.87E-02	1.90E-02	1.92E-02	1.96E-02
Std Dev Biased		4.10E-04	4.68E-04	4.71E-04	4.48E-04	4.67E-04
Ps90%/90% (+KTL) Biased		1.96E-02	1.99E-02	2.03E-02	2.04E-02	2.09E-02
Ps90%/90% (-KTL) Biased		1.74E-02	1.74E-02	1.77E-02	1.80E-02	1.83E-02
Un-Biased Statistics						
Average Un-Biased		1.89E-02	1.90E-02	1.92E-02	1.95E-02	2.00E-02
Std Dev Un-Biased		5.94E-04	6.00E-04	6.41E-04	5.25E-04	5.41E-04
Ps90%/90% (+KTL) Un-Biased		2.05E-02	2.06E-02	2.09E-02	2.10E-02	2.14E-02
Ps90%/90% (-KTL) Un-Biased		1.73E-02	1.73E-02	1.74E-02	1.81E-02	1.85E-02
Specification MAX		3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.67. Plot of Output Voltage Swing Low2 1 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.67. Raw data for Output Voltage Swing Low2 1 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low2 1 (V) @ VS=+/-15V IL=1mA		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	5.30E-02	5.30E-02	5.38E-02	5.38E-02	5.40E-02
	520	5.21E-02	5.23E-02	5.26E-02	5.29E-02	5.36E-02
	521	5.13E-02	5.16E-02	5.16E-02	5.23E-02	5.23E-02
	522	5.21E-02	5.20E-02	5.25E-02	5.28E-02	5.33E-02
	524	5.22E-02	5.20E-02	5.25E-02	5.28E-02	5.34E-02
	536	5.31E-02	5.32E-02	5.34E-02	5.34E-02	5.38E-02
	537	5.31E-02	5.29E-02	5.32E-02	5.34E-02	5.39E-02
	538	5.29E-02	5.30E-02	5.31E-02	5.35E-02	5.39E-02
	539	5.34E-02	5.33E-02	5.34E-02	5.38E-02	5.41E-02
	542	5.19E-02	5.19E-02	5.21E-02	5.24E-02	5.27E-02
	543	5.15E-02	5.13E-02	5.13E-02	5.13E-02	5.14E-02
	544	4.97E-02	4.96E-02	4.96E-02	4.95E-02	4.98E-02
Biased Statistics						
Average Biased		5.21E-02	5.22E-02	5.26E-02	5.29E-02	5.33E-02
Std Dev Biased		6.22E-04	5.41E-04	7.61E-04	5.45E-04	6.30E-04
Ps90%/90% (+KTL) Biased		5.39E-02	5.37E-02	5.47E-02	5.44E-02	5.51E-02
Ps90%/90% (-KTL) Biased		5.04E-02	5.07E-02	5.05E-02	5.14E-02	5.16E-02
Un-Biased Statistics						
Average Un-Biased		5.29E-02	5.28E-02	5.30E-02	5.33E-02	5.37E-02
Std Dev Un-Biased		5.67E-04	5.72E-04	5.19E-04	5.26E-04	5.73E-04
Ps90%/90% (+KTL) Un-Biased		5.44E-02	5.44E-02	5.45E-02	5.47E-02	5.52E-02
Ps90%/90% (-KTL) Un-Biased		5.13E-02	5.13E-02	5.16E-02	5.18E-02	5.21E-02
Specification MAX		1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.68. Plot of Output Voltage Swing Low2 2 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.68. Raw data for Output Voltage Swing Low2 2 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low2 2 (V) @ VS=+/-15V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.22E-02	5.24E-02	5.32E-02	5.27E-02	5.35E-02
520	5.33E-02	5.36E-02	5.39E-02	5.42E-02	5.48E-02
521	5.09E-02	5.09E-02	5.12E-02	5.16E-02	5.19E-02
522	5.23E-02	5.23E-02	5.27E-02	5.29E-02	5.34E-02
524	5.37E-02	5.35E-02	5.41E-02	5.44E-02	5.50E-02
536	5.32E-02	5.31E-02	5.30E-02	5.34E-02	5.38E-02
537	5.30E-02	5.28E-02	5.29E-02	5.34E-02	5.38E-02
538	5.30E-02	5.30E-02	5.29E-02	5.35E-02	5.36E-02
539	5.21E-02	5.23E-02	5.24E-02	5.27E-02	5.32E-02
542	5.23E-02	5.24E-02	5.23E-02	5.26E-02	5.31E-02
543	5.62E-02	5.57E-02	5.58E-02	5.57E-02	5.57E-02
544	5.28E-02	5.25E-02	5.25E-02	5.25E-02	5.27E-02
Biased Statistics					
Average Biased	5.25E-02	5.25E-02	5.30E-02	5.32E-02	5.37E-02
Std Dev Biased	1.12E-03	1.09E-03	1.17E-03	1.16E-03	1.26E-03
Ps90%/90% (+KTL) Biased	5.55E-02	5.55E-02	5.62E-02	5.64E-02	5.72E-02
Ps90%/90% (-KTL) Biased	4.94E-02	4.96E-02	4.98E-02	5.00E-02	5.03E-02
Un-Biased Statistics					
Average Un-Biased	5.27E-02	5.27E-02	5.27E-02	5.31E-02	5.35E-02
Std Dev Un-Biased	4.73E-04	3.67E-04	3.24E-04	4.29E-04	3.37E-04
Ps90%/90% (+KTL) Un-Biased	5.40E-02	5.37E-02	5.36E-02	5.43E-02	5.44E-02
Ps90%/90% (-KTL) Un-Biased	5.14E-02	5.17E-02	5.18E-02	5.19E-02	5.26E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.69. Plot of Output Voltage Swing Low2 3 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.69. Raw data for Output Voltage Swing Low2 3 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low2 3 (V) @ VS=+/-15V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.23E-02	5.21E-02	5.32E-02	5.30E-02	5.32E-02
520	5.34E-02	5.35E-02	5.40E-02	5.41E-02	5.48E-02
521	5.02E-02	5.04E-02	5.07E-02	5.10E-02	5.13E-02
522	5.17E-02	5.16E-02	5.18E-02	5.21E-02	5.25E-02
524	5.30E-02	5.29E-02	5.34E-02	5.38E-02	5.42E-02
536	5.29E-02	5.26E-02	5.28E-02	5.32E-02	5.34E-02
537	5.20E-02	5.21E-02	5.24E-02	5.27E-02	5.31E-02
538	5.25E-02	5.23E-02	5.25E-02	5.28E-02	5.32E-02
539	5.17E-02	5.16E-02	5.19E-02	5.20E-02	5.23E-02
542	5.17E-02	5.16E-02	5.19E-02	5.21E-02	5.26E-02
543	5.57E-02	5.56E-02	5.54E-02	5.53E-02	5.55E-02
544	5.18E-02	5.16E-02	5.15E-02	5.16E-02	5.15E-02
Biased Statistics					
Average Biased	5.21E-02	5.21E-02	5.26E-02	5.28E-02	5.32E-02
Std Dev Biased	1.23E-03	1.21E-03	1.32E-03	1.28E-03	1.38E-03
Ps90%/90% (+KTL) Biased	5.55E-02	5.54E-02	5.62E-02	5.63E-02	5.70E-02
Ps90%/90% (-KTL) Biased	4.87E-02	4.88E-02	4.90E-02	4.93E-02	4.94E-02
Un-Biased Statistics					
Average Un-Biased	5.21E-02	5.20E-02	5.23E-02	5.26E-02	5.29E-02
Std Dev Un-Biased	5.24E-04	4.44E-04	4.13E-04	4.93E-04	4.47E-04
Ps90%/90% (+KTL) Un-Biased	5.36E-02	5.33E-02	5.34E-02	5.39E-02	5.41E-02
Ps90%/90% (-KTL) Un-Biased	5.07E-02	5.08E-02	5.12E-02	5.12E-02	5.17E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.70. Plot of Output Voltage Swing Low2 4 (V) @ VS=+-15V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.70. Raw data for Output Voltage Swing Low2 4 (V) @ VS=+/-15V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low2 4 (V) @ VS=+/-15V IL=1mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	5.35E-02	5.35E-02	5.44E-02	5.41E-02	5.49E-02
520	5.29E-02	5.31E-02	5.33E-02	5.36E-02	5.41E-02
521	5.26E-02	5.28E-02	5.30E-02	5.33E-02	5.38E-02
522	5.23E-02	5.24E-02	5.28E-02	5.32E-02	5.37E-02
524	5.19E-02	5.16E-02	5.21E-02	5.23E-02	5.29E-02
536	5.37E-02	5.36E-02	5.37E-02	5.41E-02	5.44E-02
537	5.36E-02	5.34E-02	5.36E-02	5.39E-02	5.41E-02
538	5.34E-02	5.34E-02	5.34E-02	5.38E-02	5.42E-02
539	5.40E-02	5.40E-02	5.42E-02	5.46E-02	5.48E-02
542	5.24E-02	5.23E-02	5.24E-02	5.30E-02	5.33E-02
543	5.25E-02	5.20E-02	5.19E-02	5.20E-02	5.21E-02
544	5.03E-02	5.01E-02	5.03E-02	5.02E-02	5.03E-02
Biased Statistics					
Average Biased	5.26E-02	5.27E-02	5.31E-02	5.33E-02	5.39E-02
Std Dev Biased	5.96E-04	7.41E-04	8.40E-04	6.61E-04	7.21E-04
Ps90%/90% (+KTL) Biased	5.43E-02	5.47E-02	5.54E-02	5.51E-02	5.58E-02
Ps90%/90% (-KTL) Biased	5.10E-02	5.07E-02	5.08E-02	5.15E-02	5.19E-02
Un-Biased Statistics					
Average Un-Biased	5.34E-02	5.33E-02	5.35E-02	5.39E-02	5.42E-02
Std Dev Un-Biased	6.16E-04	6.31E-04	6.44E-04	5.89E-04	5.48E-04
Ps90%/90% (+KTL) Un-Biased	5.51E-02	5.51E-02	5.52E-02	5.55E-02	5.57E-02
Ps90%/90% (-KTL) Un-Biased	5.17E-02	5.16E-02	5.17E-02	5.23E-02	5.27E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.71. Plot of Output Voltage Swing Low3 1 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.71. Raw data for Output Voltage Swing Low3 1 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low3 1 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.19E-01	2.18E-01	2.21E-01	2.19E-01	2.20E-01
520	2.17E-01	2.16E-01	2.17E-01	2.17E-01	2.18E-01
521	2.14E-01	2.14E-01	2.14E-01	2.15E-01	2.15E-01
522	2.17E-01	2.16E-01	2.16E-01	2.17E-01	2.17E-01
524	2.18E-01	2.17E-01	2.17E-01	2.18E-01	2.19E-01
536	2.19E-01	2.19E-01	2.19E-01	2.19E-01	2.20E-01
537	2.18E-01	2.17E-01	2.17E-01	2.18E-01	2.18E-01
538	2.18E-01	2.18E-01	2.18E-01	2.19E-01	2.19E-01
539	2.20E-01	2.19E-01	2.20E-01	2.20E-01	2.21E-01
542	2.16E-01	2.15E-01	2.16E-01	2.16E-01	2.17E-01
543	2.14E-01	2.12E-01	2.12E-01	2.12E-01	2.12E-01
544	2.09E-01	2.09E-01	2.09E-01	2.09E-01	2.09E-01
Biased Statistics					
Average Biased	2.17E-01	2.16E-01	2.17E-01	2.17E-01	2.18E-01
Std Dev Biased	1.90E-03	1.40E-03	2.49E-03	1.57E-03	2.01E-03
Ps90%/90% (+KTL) Biased	2.22E-01	2.20E-01	2.24E-01	2.21E-01	2.23E-01
Ps90%/90% (-KTL) Biased	2.12E-01	2.12E-01	2.10E-01	2.13E-01	2.12E-01
Un-Biased Statistics					
Average Un-Biased	2.18E-01	2.17E-01	2.18E-01	2.18E-01	2.19E-01
Std Dev Un-Biased	1.59E-03	1.56E-03	1.53E-03	1.57E-03	1.58E-03
Ps90%/90% (+KTL) Un-Biased	2.23E-01	2.22E-01	2.22E-01	2.23E-01	2.23E-01
Ps90%/90% (-KTL) Un-Biased	2.14E-01	2.13E-01	2.14E-01	2.14E-01	2.15E-01
Specification MAX	5.00E-01	5.00E-01	5.00E-01	5.00E-01	5.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.72. Plot of Output Voltage Swing Low3 2 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.72. Raw data for Output Voltage Swing Low3 2 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low3 2 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.19E-01	2.18E-01	2.21E-01	2.19E-01	2.20E-01
520	2.21E-01	2.21E-01	2.21E-01	2.21E-01	2.23E-01
521	2.14E-01	2.13E-01	2.14E-01	2.14E-01	2.15E-01
522	2.15E-01	2.14E-01	2.14E-01	2.15E-01	2.16E-01
524	2.19E-01	2.18E-01	2.19E-01	2.20E-01	2.21E-01
536	2.20E-01	2.20E-01	2.20E-01	2.21E-01	2.21E-01
537	2.19E-01	2.18E-01	2.19E-01	2.19E-01	2.20E-01
538	2.17E-01	2.17E-01	2.17E-01	2.17E-01	2.18E-01
539	2.18E-01	2.18E-01	2.18E-01	2.18E-01	2.19E-01
542	2.18E-01	2.17E-01	2.18E-01	2.18E-01	2.19E-01
543	2.22E-01	2.21E-01	2.20E-01	2.21E-01	2.21E-01
544	2.14E-01	2.14E-01	2.14E-01	2.14E-01	2.15E-01
Biased Statistics					
Average Biased	2.18E-01	2.17E-01	2.18E-01	2.18E-01	2.19E-01
Std Dev Biased	3.11E-03	3.06E-03	3.35E-03	3.02E-03	3.33E-03
Ps90%/90% (+KTL) Biased	2.26E-01	2.25E-01	2.27E-01	2.26E-01	2.28E-01
Ps90%/90% (-KTL) Biased	2.09E-01	2.08E-01	2.08E-01	2.10E-01	2.10E-01
Un-Biased Statistics					
Average Un-Biased	2.19E-01	2.18E-01	2.18E-01	2.19E-01	2.19E-01
Std Dev Un-Biased	1.31E-03	1.36E-03	1.29E-03	1.31E-03	1.23E-03
Ps90%/90% (+KTL) Un-Biased	2.22E-01	2.22E-01	2.22E-01	2.22E-01	2.23E-01
Ps90%/90% (-KTL) Un-Biased	2.15E-01	2.14E-01	2.15E-01	2.15E-01	2.16E-01
Specification MAX	5.00E-01	5.00E-01	5.00E-01	5.00E-01	5.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.73. Plot of Output Voltage Swing Low3 3 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.73. Raw data for Output Voltage Swing Low3 3 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low3 3 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.17E-01	2.16E-01	2.19E-01	2.18E-01	2.19E-01
520	2.19E-01	2.19E-01	2.19E-01	2.20E-01	2.21E-01
521	2.12E-01	2.11E-01	2.11E-01	2.12E-01	2.13E-01
522	2.12E-01	2.11E-01	2.12E-01	2.12E-01	2.13E-01
524	2.17E-01	2.16E-01	2.16E-01	2.17E-01	2.18E-01
536	2.19E-01	2.19E-01	2.19E-01	2.19E-01	2.20E-01
537	2.16E-01	2.16E-01	2.16E-01	2.16E-01	2.17E-01
538	2.14E-01	2.14E-01	2.14E-01	2.15E-01	2.15E-01
539	2.16E-01	2.15E-01	2.16E-01	2.16E-01	2.17E-01
542	2.15E-01	2.15E-01	2.15E-01	2.15E-01	2.17E-01
543	2.20E-01	2.19E-01	2.19E-01	2.19E-01	2.19E-01
544	2.12E-01	2.11E-01	2.12E-01	2.12E-01	2.12E-01
Biased Statistics					
Average Biased	2.15E-01	2.15E-01	2.15E-01	2.16E-01	2.17E-01
Std Dev Biased	3.29E-03	3.29E-03	3.80E-03	3.57E-03	3.72E-03
Ps90%/90% (+KTL) Biased	2.24E-01	2.24E-01	2.26E-01	2.25E-01	2.27E-01
Ps90%/90% (-KTL) Biased	2.06E-01	2.06E-01	2.05E-01	2.06E-01	2.06E-01
Un-Biased Statistics					
Average Un-Biased	2.16E-01	2.16E-01	2.16E-01	2.16E-01	2.17E-01
Std Dev Un-Biased	1.82E-03	1.92E-03	1.62E-03	1.50E-03	1.63E-03
Ps90%/90% (+KTL) Un-Biased	2.21E-01	2.21E-01	2.20E-01	2.20E-01	2.22E-01
Ps90%/90% (-KTL) Un-Biased	2.11E-01	2.10E-01	2.11E-01	2.12E-01	2.13E-01
Specification MAX	5.00E-01	5.00E-01	5.00E-01	5.00E-01	5.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.74. Plot of Output Voltage Swing Low3 4 (V) @ VS=+-15V IL=10mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.74. Raw data for Output Voltage Swing Low3 4 (V) @ VS=+/-15V IL=10mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low3 4 (V) @ VS=+/-15V IL=10mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.21E-01	2.20E-01	2.23E-01	2.22E-01	2.23E-01
520	2.19E-01	2.19E-01	2.20E-01	2.20E-01	2.21E-01
521	2.18E-01	2.18E-01	2.17E-01	2.18E-01	2.19E-01
522	2.19E-01	2.18E-01	2.19E-01	2.19E-01	2.20E-01
524	2.19E-01	2.18E-01	2.18E-01	2.19E-01	2.20E-01
536	2.21E-01	2.21E-01	2.21E-01	2.21E-01	2.22E-01
537	2.20E-01	2.19E-01	2.20E-01	2.21E-01	2.21E-01
538	2.21E-01	2.21E-01	2.21E-01	2.21E-01	2.22E-01
539	2.22E-01	2.22E-01	2.22E-01	2.23E-01	2.23E-01
542	2.18E-01	2.18E-01	2.18E-01	2.18E-01	2.19E-01
543	2.16E-01	2.15E-01	2.15E-01	2.15E-01	2.15E-01
544	2.12E-01	2.12E-01	2.11E-01	2.12E-01	2.12E-01
Biased Statistics					
Average Biased	2.19E-01	2.19E-01	2.19E-01	2.20E-01	2.21E-01
Std Dev Biased	1.36E-03	1.20E-03	2.37E-03	1.38E-03	1.55E-03
Ps90%/90% (+KTL) Biased	2.23E-01	2.22E-01	2.26E-01	2.23E-01	2.25E-01
Ps90%/90% (-KTL) Biased	2.16E-01	2.15E-01	2.13E-01	2.16E-01	2.16E-01
Un-Biased Statistics					
Average Un-Biased	2.21E-01	2.20E-01	2.20E-01	2.21E-01	2.21E-01
Std Dev Un-Biased	1.71E-03	1.80E-03	1.60E-03	1.56E-03	1.64E-03
Ps90%/90% (+KTL) Un-Biased	2.25E-01	2.25E-01	2.25E-01	2.25E-01	2.26E-01
Ps90%/90% (-KTL) Un-Biased	2.16E-01	2.15E-01	2.16E-01	2.17E-01	2.17E-01
Specification MAX	5.00E-01	5.00E-01	5.00E-01	5.00E-01	5.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.75. Plot of Large Signal Voltage Gain1 1 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.75. Raw data for Large Signal Voltage Gain1 1 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain1 1 (V/mV) @ VO=+/-14.5V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.33E+03	3.80E+03	3.86E+03	3.78E+03	3.64E+03
520	4.89E+03	4.62E+03	4.54E+03	4.39E+03	4.03E+03
521	3.86E+03	4.52E+03	3.79E+03	4.18E+03	4.06E+03
522	6.05E+03	5.59E+03	5.33E+03	4.90E+03	4.63E+03
524	3.51E+03	3.42E+03	3.12E+03	3.18E+03	2.99E+03
536	3.52E+03	3.49E+03	3.25E+03	3.22E+03	3.15E+03
537	3.45E+03	3.37E+03	3.25E+03	2.94E+03	3.05E+03
538	5.22E+03	4.96E+03	4.71E+03	4.66E+03	4.31E+03
539	3.19E+03	3.26E+03	3.13E+03	3.15E+03	2.83E+03
542	4.13E+03	4.16E+03	4.11E+03	3.95E+03	3.52E+03
543	5.54E+03	5.65E+03	5.64E+03	5.64E+03	5.47E+03
544	4.52E+03	4.57E+03	4.56E+03	4.62E+03	4.51E+03
Biased Statistics					
Average Biased	4.53E+03	4.39E+03	4.13E+03	4.09E+03	3.87E+03
Std Dev Biased	9.98E+02	8.37E+02	8.40E+02	6.47E+02	6.06E+02
Ps90%/90% (+KTL) Biased	7.26E+03	6.68E+03	6.43E+03	5.86E+03	5.53E+03
Ps90%/90% (-KTL) Biased	1.79E+03	2.09E+03	1.83E+03	2.31E+03	2.21E+03
Un-Biased Statistics					
Average Un-Biased	3.90E+03	3.85E+03	3.69E+03	3.59E+03	3.37E+03
Std Dev Un-Biased	8.14E+02	7.15E+02	6.90E+02	7.13E+02	5.82E+02
Ps90%/90% (+KTL) Un-Biased	6.13E+03	5.81E+03	5.58E+03	5.54E+03	4.97E+03
Ps90%/90% (-KTL) Un-Biased	1.67E+03	1.89E+03	1.80E+03	1.63E+03	1.78E+03
Specification MIN	1.00E+03	5.00E+02	5.00E+02	5.00E+02	5.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.76. Plot of Large Signal Voltage Gain1 2 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.76. Raw data for Large Signal Voltage Gain1 2 (V/mV) @ VO= \pm 14.5V, RL=10k Ω versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain1 2 (V/mV) @ VO= \pm 14.5V, RL=10k Ω	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	6.56E+03	6.55E+03	6.23E+03	5.90E+03	5.41E+03
520	6.88E+03	6.51E+03	6.13E+03	5.91E+03	5.64E+03
521	4.92E+03	4.59E+03	4.77E+03	4.15E+03	4.03E+03
522	4.34E+03	4.16E+03	3.97E+03	3.84E+03	3.91E+03
524	8.63E+03	8.61E+03	8.09E+03	7.05E+03	6.73E+03
536	6.61E+03	6.42E+03	5.97E+03	5.49E+03	5.37E+03
537	4.69E+03	3.96E+03	3.97E+03	4.08E+03	4.34E+03
538	5.92E+03	5.93E+03	5.22E+03	5.00E+03	5.06E+03
539	6.98E+03	6.90E+03	5.95E+03	5.93E+03	5.27E+03
542	6.65E+03	6.91E+03	5.30E+03	5.82E+03	5.02E+03
543	6.24E+03	6.07E+03	6.24E+03	6.05E+03	6.28E+03
544	5.53E+03	6.40E+03	5.65E+03	5.61E+03	5.44E+03
Biased Statistics					
Average Biased	6.26E+03	6.08E+03	5.84E+03	5.37E+03	5.15E+03
Std Dev Biased	1.70E+03	1.78E+03	1.58E+03	1.35E+03	1.18E+03
Ps90%/90% (+KTL) Biased	1.09E+04	1.10E+04	1.02E+04	9.06E+03	8.38E+03
Ps90%/90% (-KTL) Biased	1.60E+03	1.19E+03	1.51E+03	1.68E+03	1.91E+03
Un-Biased Statistics					
Average Un-Biased	6.17E+03	6.02E+03	5.28E+03	5.27E+03	5.01E+03
Std Dev Un-Biased	9.15E+02	1.22E+03	8.11E+02	7.53E+02	4.04E+02
Ps90%/90% (+KTL) Un-Biased	8.68E+03	9.38E+03	7.51E+03	7.33E+03	6.12E+03
Ps90%/90% (-KTL) Un-Biased	3.66E+03	2.67E+03	3.06E+03	3.20E+03	3.91E+03
Specification MIN	1.00E+03	5.00E+02	5.00E+02	5.00E+02	5.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.77. Plot of Large Signal Voltage Gain1 3 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.77. Raw data for Large Signal Voltage Gain1 3 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain1 3 (V/mV) @ VO=+/-14.5V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.43E+03	4.16E+03	3.93E+03	3.94E+03	3.63E+03
520	4.08E+03	3.85E+03	3.73E+03	3.70E+03	3.55E+03
521	5.42E+03	5.16E+03	4.89E+03	4.83E+03	4.54E+03
522	4.16E+03	3.96E+03	3.78E+03	3.74E+03	3.46E+03
524	3.74E+03	3.80E+03	3.51E+03	3.43E+03	3.21E+03
536	5.30E+03	5.18E+03	5.10E+03	4.62E+03	4.97E+03
537	6.27E+03	6.38E+03	5.51E+03	5.44E+03	5.60E+03
538	5.90E+03	5.73E+03	5.87E+03	4.92E+03	4.92E+03
539	4.27E+03	4.12E+03	3.82E+03	4.04E+03	3.50E+03
542	6.43E+03	6.43E+03	5.23E+03	6.11E+03	5.30E+03
543	6.02E+03	6.16E+03	6.17E+03	6.32E+03	6.12E+03
544	5.29E+03	5.36E+03	5.07E+03	5.42E+03	5.27E+03
Biased Statistics					
Average Biased	4.37E+03	4.19E+03	3.97E+03	3.93E+03	3.68E+03
Std Dev Biased	6.38E+02	5.62E+02	5.38E+02	5.39E+02	5.09E+02
Ps90%/90% (+KTL) Biased	6.12E+03	5.73E+03	5.44E+03	5.40E+03	5.07E+03
Ps90%/90% (-KTL) Biased	2.62E+03	2.65E+03	2.49E+03	2.45E+03	2.28E+03
Un-Biased Statistics					
Average Un-Biased	5.63E+03	5.57E+03	5.10E+03	5.02E+03	4.86E+03
Std Dev Un-Biased	8.76E+02	9.61E+02	7.76E+02	7.92E+02	8.07E+02
Ps90%/90% (+KTL) Un-Biased	8.04E+03	8.20E+03	7.23E+03	7.20E+03	7.07E+03
Ps90%/90% (-KTL) Un-Biased	3.23E+03	2.93E+03	2.98E+03	2.85E+03	2.64E+03
Specification MIN	1.00E+03	5.00E+02	5.00E+02	5.00E+02	5.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.78. Plot of Large Signal Voltage Gain1 4 (V/mV) @ VO=+/-14.5V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.78. Raw data for Large Signal Voltage Gain1 4 (V/mV) @ VO= \pm 14.5V, RL=10k Ω versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain1 4 (V/mV) @ VO= \pm 14.5V, RL=10k Ω	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.89E+03	4.40E+03	4.26E+03	5.30E+03	4.12E+03
520	6.19E+03	5.76E+03	5.45E+03	5.74E+03	4.95E+03
521	5.48E+03	5.23E+03	5.60E+03	4.80E+03	4.66E+03
522	4.10E+03	6.35E+03	6.09E+03	5.91E+03	5.30E+03
524	3.96E+03	3.89E+03	3.60E+03	3.64E+03	3.36E+03
536	5.68E+03	5.50E+03	5.17E+03	5.53E+03	4.53E+03
537	4.24E+03	4.15E+03	4.25E+03	3.96E+03	3.54E+03
538	4.25E+03	4.21E+03	4.03E+03	3.79E+03	3.86E+03
539	8.12E+03	8.76E+03	8.19E+03	7.56E+03	6.82E+03
542	4.32E+03	4.26E+03	4.59E+03	3.89E+03	3.71E+03
543	6.58E+03	6.73E+03	6.76E+03	6.94E+03	6.73E+03
544	5.74E+03	5.93E+03	4.62E+03	5.27E+03	5.68E+03
Biased Statistics					
Average Biased	4.72E+03	5.13E+03	5.00E+03	5.08E+03	4.48E+03
Std Dev Biased	1.05E+03	9.94E+02	1.03E+03	9.14E+02	7.61E+02
Ps90%/90% (+KTL) Biased	7.59E+03	7.85E+03	7.83E+03	7.58E+03	6.56E+03
Ps90%/90% (-KTL) Biased	1.85E+03	2.40E+03	2.17E+03	2.57E+03	2.39E+03
Un-Biased Statistics					
Average Un-Biased	5.32E+03	5.37E+03	5.24E+03	4.95E+03	4.49E+03
Std Dev Un-Biased	1.68E+03	1.97E+03	1.70E+03	1.63E+03	1.36E+03
Ps90%/90% (+KTL) Un-Biased	9.93E+03	1.08E+04	9.90E+03	9.41E+03	8.21E+03
Ps90%/90% (-KTL) Un-Biased	7.17E+02	-3.93E+01	5.82E+02	4.79E+02	7.74E+02
Specification MIN	1.00E+03	5.00E+02	5.00E+02	5.00E+02	5.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.79. Plot of Large Signal Voltage Gain2 1 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.79. Raw data for Large Signal Voltage Gain2 1 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain2 1 (V/mV) @ VO=+/-10V, RL=2kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.15E+03	1.09E+03	1.04E+03	1.06E+03	1.02E+03
520	1.47E+03	1.41E+03	1.41E+03	1.33E+03	1.25E+03
521	1.49E+03	1.31E+03	1.32E+03	1.34E+03	1.27E+03
522	2.58E+03	2.30E+03	2.25E+03	2.16E+03	2.06E+03
524	1.03E+03	1.01E+03	9.65E+02	9.41E+02	9.16E+02
536	1.03E+03	1.03E+03	9.81E+02	9.70E+02	9.35E+02
537	1.02E+03	9.99E+02	9.79E+02	9.86E+02	9.20E+02
538	2.33E+03	2.29E+03	2.18E+03	2.10E+03	1.89E+03
539	9.87E+02	9.80E+02	9.43E+02	9.35E+02	9.06E+02
542	1.23E+03	1.20E+03	1.14E+03	1.14E+03	1.07E+03
543	2.23E+03	2.27E+03	2.26E+03	2.28E+03	2.27E+03
544	2.03E+03	2.03E+03	2.04E+03	2.07E+03	2.10E+03
Biased Statistics					
Average Biased	1.54E+03	1.43E+03	1.39E+03	1.37E+03	1.31E+03
Std Dev Biased	6.12E+02	5.15E+02	5.12E+02	4.76E+02	4.50E+02
Ps90%/90% (+KTL) Biased	3.22E+03	2.84E+03	2.80E+03	2.67E+03	2.54E+03
Ps90%/90% (-KTL) Biased	-1.37E+02	1.45E+01	-9.72E+00	5.96E+01	7.22E+01
Un-Biased Statistics					
Average Un-Biased	1.32E+03	1.30E+03	1.24E+03	1.23E+03	1.14E+03
Std Dev Un-Biased	5.73E+02	5.62E+02	5.28E+02	4.95E+02	4.22E+02
Ps90%/90% (+KTL) Un-Biased	2.89E+03	2.84E+03	2.69E+03	2.58E+03	2.30E+03
Ps90%/90% (-KTL) Un-Biased	-2.54E+02	-2.39E+02	-2.02E+02	-1.30E+02	-1.31E+01
Specification MIN	5.00E+02	2.50E+02	2.50E+02	2.50E+02	2.50E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.80. Plot of Large Signal Voltage Gain2 2 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.80. Raw data for Large Signal Voltage Gain2 2 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain2 2 (V/mV) @ VO=+/-10V, RL=2kΩ		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	2.56E+03	2.42E+03	2.25E+03	2.16E+03	2.02E+03
	520	2.55E+03	2.28E+03	2.23E+03	2.17E+03	1.96E+03
	521	1.76E+03	1.61E+03	1.60E+03	1.53E+03	1.47E+03
	522	1.42E+03	1.37E+03	1.33E+03	1.32E+03	1.27E+03
	524	3.28E+03	2.91E+03	2.81E+03	2.77E+03	2.33E+03
	536	2.45E+03	2.30E+03	2.32E+03	2.16E+03	2.00E+03
	537	1.50E+03	1.47E+03	1.37E+03	1.34E+03	1.28E+03
	538	2.06E+03	2.06E+03	2.00E+03	1.79E+03	1.84E+03
	539	2.34E+03	2.31E+03	2.16E+03	2.07E+03	1.88E+03
	542	2.37E+03	2.11E+03	2.32E+03	2.13E+03	1.94E+03
	543	2.31E+03	2.29E+03	2.32E+03	2.30E+03	2.31E+03
	544	2.00E+03	2.08E+03	2.12E+03	2.07E+03	2.09E+03
Biased Statistics						
Average Biased		2.31E+03	2.12E+03	2.05E+03	1.99E+03	1.81E+03
Std Dev Biased		7.38E+02	6.24E+02	5.86E+02	5.75E+02	4.32E+02
Ps90%/90% (+KTL) Biased		4.34E+03	3.83E+03	3.65E+03	3.56E+03	3.00E+03
Ps90%/90% (-KTL) Biased		2.92E+02	4.05E+02	4.37E+02	4.12E+02	6.24E+02
Un-Biased Statistics						
Average Un-Biased		2.14E+03	2.05E+03	2.03E+03	1.90E+03	1.79E+03
Std Dev Un-Biased		3.88E+02	3.44E+02	3.95E+02	3.44E+02	2.90E+02
Ps90%/90% (+KTL) Un-Biased		3.21E+03	2.99E+03	3.12E+03	2.84E+03	2.58E+03
Ps90%/90% (-KTL) Un-Biased		1.08E+03	1.11E+03	9.50E+02	9.55E+02	9.94E+02
Specification MIN		5.00E+02	2.50E+02	2.50E+02	2.50E+02	2.50E+02
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.81. Plot of Large Signal Voltage Gain2 3 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.81. Raw data for Large Signal Voltage Gain2 3 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain2 3 (V/mV) @ VO=+/-10V, RL=2kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.17E+03	1.11E+03	1.10E+03	1.12E+03	1.07E+03
520	1.09E+03	1.04E+03	1.01E+03	9.77E+02	9.49E+02
521	2.10E+03	2.00E+03	1.87E+03	1.84E+03	1.69E+03
522	1.12E+03	1.07E+03	1.04E+03	1.03E+03	9.99E+02
524	1.09E+03	1.08E+03	1.03E+03	9.90E+02	9.58E+02
536	1.98E+03	1.87E+03	1.92E+03	1.83E+03	1.71E+03
537	2.36E+03	2.31E+03	2.21E+03	2.23E+03	2.02E+03
538	2.31E+03	2.22E+03	2.24E+03	2.04E+03	1.90E+03
539	1.14E+03	1.13E+03	1.14E+03	1.06E+03	1.04E+03
542	2.45E+03	2.34E+03	2.27E+03	2.10E+03	2.03E+03
543	2.36E+03	2.41E+03	2.35E+03	2.38E+03	2.40E+03
544	1.60E+03	1.57E+03	1.51E+03	1.54E+03	1.51E+03
Biased Statistics					
Average Biased	1.31E+03	1.26E+03	1.21E+03	1.19E+03	1.13E+03
Std Dev Biased	4.38E+02	4.16E+02	3.73E+02	3.67E+02	3.17E+02
Ps90%/90% (+KTL) Biased	2.52E+03	2.40E+03	2.23E+03	2.19E+03	2.00E+03
Ps90%/90% (-KTL) Biased	1.11E+02	1.20E+02	1.87E+02	1.84E+02	2.64E+02
Un-Biased Statistics					
Average Un-Biased	2.05E+03	1.97E+03	1.96E+03	1.85E+03	1.74E+03
Std Dev Un-Biased	5.37E+02	5.07E+02	4.76E+02	4.63E+02	4.16E+02
Ps90%/90% (+KTL) Un-Biased	3.52E+03	3.36E+03	3.26E+03	3.12E+03	2.88E+03
Ps90%/90% (-KTL) Un-Biased	5.76E+02	5.82E+02	6.50E+02	5.81E+02	6.02E+02
Specification MIN	5.00E+02	2.50E+02	2.50E+02	2.50E+02	2.50E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.82. Plot of Large Signal Voltage Gain2 4 (V/mV) @ VO=+-10V, RL=2kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.82. Raw data for Large Signal Voltage Gain2 4 (V/mV) @ VO=+/-10V, RL=2kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain2 4 (V/mV) @ VO=+/-10V, RL=2kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.18E+03	1.13E+03	1.10E+03	1.08E+03	1.02E+03
520	2.41E+03	2.23E+03	2.06E+03	2.04E+03	1.95E+03
521	1.62E+03	1.50E+03	1.45E+03	1.45E+03	1.36E+03
522	2.34E+03	2.31E+03	2.24E+03	2.01E+03	1.93E+03
524	1.07E+03	1.05E+03	9.89E+02	9.63E+02	9.30E+02
536	2.12E+03	2.14E+03	2.09E+03	2.01E+03	1.79E+03
537	1.10E+03	1.08E+03	1.09E+03	1.05E+03	9.89E+02
538	1.12E+03	1.09E+03	1.05E+03	1.01E+03	9.63E+02
539	3.19E+03	3.13E+03	2.91E+03	2.72E+03	2.63E+03
542	1.20E+03	1.20E+03	1.16E+03	1.16E+03	1.07E+03
543	2.57E+03	2.46E+03	2.46E+03	2.52E+03	2.48E+03
544	2.21E+03	2.25E+03	2.32E+03	2.43E+03	2.41E+03
Biased Statistics					
Average Biased	1.72E+03	1.64E+03	1.57E+03	1.51E+03	1.44E+03
Std Dev Biased	6.29E+02	5.96E+02	5.62E+02	5.04E+02	4.86E+02
Ps90%/90% (+KTL) Biased	3.45E+03	3.28E+03	3.11E+03	2.89E+03	2.77E+03
Ps90%/90% (-KTL) Biased	-2.13E+00	9.60E+00	2.59E+01	1.25E+02	1.05E+02
Un-Biased Statistics					
Average Un-Biased	1.74E+03	1.73E+03	1.66E+03	1.59E+03	1.49E+03
Std Dev Un-Biased	9.15E+02	9.03E+02	8.22E+02	7.53E+02	7.23E+02
Ps90%/90% (+KTL) Un-Biased	4.25E+03	4.20E+03	3.91E+03	3.65E+03	3.47E+03
Ps90%/90% (-KTL) Un-Biased	-7.64E+02	-7.48E+02	-5.96E+02	-4.76E+02	-4.93E+02
Specification MIN	5.00E+02	2.50E+02	2.50E+02	2.50E+02	2.50E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.83. Plot of Common Mode Rejection Ratio 1 (dB) @ VS=+-15V, VCM=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.83. Raw data for Common Mode Rejection Ratio1 1 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio1 1 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
520	1.05E+02	1.05E+02	1.05E+02	1.05E+02	1.04E+02
521	1.01E+02	1.02E+02	1.02E+02	1.02E+02	1.01E+02
522	9.90E+01	9.88E+01	9.86E+01	9.84E+01	9.81E+01
524	9.83E+01	9.84E+01	9.85E+01	9.85E+01	9.82E+01
536	1.05E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
537	9.76E+01	9.76E+01	9.76E+01	9.75E+01	9.74E+01
538	1.08E+02	1.08E+02	1.07E+02	1.07E+02	1.06E+02
539	1.01E+02	1.01E+02	1.01E+02	1.00E+02	1.00E+02
542	1.05E+02	1.04E+02	1.04E+02	1.04E+02	1.03E+02
543	9.78E+01	9.78E+01	9.78E+01	9.78E+01	9.78E+01
544	9.67E+01	9.67E+01	9.67E+01	9.67E+01	9.67E+01
Biased Statistics					
Average Biased	1.01E+02	1.02E+02	1.01E+02	1.01E+02	1.01E+02
Std Dev Biased	2.88E+00	2.92E+00	2.89E+00	2.89E+00	2.79E+00
Ps90%/90% (+KTL) Biased	1.09E+02	1.10E+02	1.09E+02	1.09E+02	1.09E+02
Ps90%/90% (-KTL) Biased	9.36E+01	9.35E+01	9.36E+01	9.34E+01	9.34E+01
Un-Biased Statistics					
Average Un-Biased	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.02E+02
Std Dev Un-Biased	3.92E+00	4.02E+00	3.81E+00	3.71E+00	3.52E+00
Ps90%/90% (+KTL) Un-Biased	1.14E+02	1.14E+02	1.13E+02	1.13E+02	1.12E+02
Ps90%/90% (-KTL) Un-Biased	9.23E+01	9.20E+01	9.24E+01	9.24E+01	9.27E+01
Specification MIN	9.00E+01	8.60E+01	8.60E+01	8.60E+01	8.60E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.84. Plot of Common Mode Rejection Ratio 1 2 (dB) @ VS=+-15V, VCM=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.84. Raw data for Common Mode Rejection Ratio1 2 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio1 2 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.01E+02	1.00E+02	1.00E+02	1.00E+02	1.00E+02
520	1.13E+02	1.12E+02	1.11E+02	1.11E+02	1.10E+02
521	9.87E+01	9.89E+01	9.89E+01	9.89E+01	9.87E+01
522	9.80E+01	9.80E+01	9.79E+01	9.78E+01	9.77E+01
524	1.18E+02	1.14E+02	1.15E+02	1.17E+02	1.20E+02
536	1.25E+02	1.24E+02	1.22E+02	1.21E+02	1.19E+02
537	9.87E+01	9.83E+01	9.82E+01	9.81E+01	9.81E+01
538	9.84E+01	9.83E+01	9.83E+01	9.82E+01	9.80E+01
539	9.83E+01	9.84E+01	9.82E+01	9.80E+01	9.79E+01
542	9.99E+01	9.97E+01	9.96E+01	9.96E+01	9.95E+01
543	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
544	1.05E+02	1.05E+02	1.05E+02	1.05E+02	1.05E+02
Biased Statistics					
Average Biased	1.06E+02	1.05E+02	1.05E+02	1.05E+02	1.05E+02
Std Dev Biased	9.09E+00	7.77E+00	8.04E+00	8.60E+00	9.67E+00
Ps90%/90% (+KTL) Biased	1.31E+02	1.26E+02	1.27E+02	1.29E+02	1.32E+02
Ps90%/90% (-KTL) Biased	8.08E+01	8.34E+01	8.28E+01	8.15E+01	7.89E+01
Un-Biased Statistics					
Average Un-Biased	1.04E+02	1.04E+02	1.03E+02	1.03E+02	1.03E+02
Std Dev Un-Biased	1.16E+01	1.15E+01	1.05E+01	1.00E+01	9.34E+00
Ps90%/90% (+KTL) Un-Biased	1.36E+02	1.35E+02	1.32E+02	1.30E+02	1.28E+02
Ps90%/90% (-KTL) Un-Biased	7.22E+01	7.24E+01	7.46E+01	7.55E+01	7.69E+01
Specification MIN	9.00E+01	8.60E+01	8.60E+01	8.60E+01	8.60E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.85. Plot of Common Mode Rejection Ratio 1 3 (dB) @ VS=+-15V, VCM=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.85. Raw data for Common Mode Rejection Ratio1 3 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio1 3 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.02E+02	1.01E+02	1.01E+02	1.01E+02	1.01E+02
520	9.68E+01	9.68E+01	9.68E+01	9.67E+01	9.65E+01
521	9.80E+01	9.79E+01	9.79E+01	9.78E+01	9.77E+01
522	1.06E+02	1.07E+02	1.06E+02	1.06E+02	1.06E+02
524	1.24E+02	1.22E+02	1.19E+02	1.17E+02	1.15E+02
536	9.99E+01	1.00E+02	9.99E+01	9.98E+01	9.96E+01
537	1.07E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
538	9.95E+01	9.95E+01	9.94E+01	9.92E+01	9.91E+01
539	1.01E+02	1.00E+02	1.00E+02	1.00E+02	1.00E+02
542	1.24E+02	1.24E+02	1.29E+02	1.46E+02	1.32E+02
543	1.08E+02	1.07E+02	1.07E+02	1.07E+02	1.08E+02
544	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
Biased Statistics					
Average Biased	1.05E+02	1.05E+02	1.04E+02	1.04E+02	1.03E+02
Std Dev Biased	1.09E+01	1.02E+01	9.25E+00	8.29E+00	7.58E+00
Ps90%/90% (+KTL) Biased	1.35E+02	1.33E+02	1.30E+02	1.26E+02	1.24E+02
Ps90%/90% (-KTL) Biased	7.55E+01	7.68E+01	7.89E+01	8.10E+01	8.24E+01
Un-Biased Statistics					
Average Un-Biased	1.06E+02	1.06E+02	1.07E+02	1.10E+02	1.07E+02
Std Dev Un-Biased	1.02E+01	1.06E+01	1.27E+01	2.00E+01	1.39E+01
Ps90%/90% (+KTL) Un-Biased	1.34E+02	1.35E+02	1.42E+02	1.65E+02	1.45E+02
Ps90%/90% (-KTL) Un-Biased	7.81E+01	7.71E+01	7.22E+01	5.51E+01	6.91E+01
Specification MIN	9.00E+01	8.60E+01	8.60E+01	8.60E+01	8.60E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.86. Plot of Common Mode Rejection Ratio 1 4 (dB) @ VS=+-15V, VCM=+-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.86. Raw data for Common Mode Rejection Ratio1 4 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio1 4 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.01E+02	1.01E+02	1.01E+02	1.01E+02	1.01E+02
520	1.10E+02	1.09E+02	1.08E+02	1.08E+02	1.08E+02
521	1.11E+02	1.10E+02	1.10E+02	1.10E+02	1.09E+02
522	1.06E+02	1.05E+02	1.05E+02	1.05E+02	1.05E+02
524	1.05E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
536	1.15E+02	1.14E+02	1.14E+02	1.13E+02	1.12E+02
537	9.66E+01	9.66E+01	9.66E+01	9.66E+01	9.66E+01
538	1.10E+02	1.09E+02	1.09E+02	1.09E+02	1.08E+02
539	1.04E+02	1.04E+02	1.04E+02	1.03E+02	1.03E+02
542	1.07E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
543	1.11E+02	1.11E+02	1.12E+02	1.12E+02	1.11E+02
544	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
Biased Statistics					
Average Biased	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.05E+02
Std Dev Biased	3.90E+00	3.63E+00	3.54E+00	3.27E+00	3.20E+00
Ps90%/90% (+KTL) Biased	1.17E+02	1.16E+02	1.16E+02	1.15E+02	1.14E+02
Ps90%/90% (-KTL) Biased	9.57E+01	9.60E+01	9.62E+01	9.67E+01	9.65E+01
Un-Biased Statistics					
Average Un-Biased	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.05E+02
Std Dev Un-Biased	6.78E+00	6.47E+00	6.37E+00	6.12E+00	5.81E+00
Ps90%/90% (+KTL) Un-Biased	1.25E+02	1.24E+02	1.23E+02	1.22E+02	1.21E+02
Ps90%/90% (-KTL) Un-Biased	8.78E+01	8.82E+01	8.83E+01	8.88E+01	8.93E+01
Specification MIN	9.00E+01	8.60E+01	8.60E+01	8.60E+01	8.60E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.87. Plot of CMRR Match1 1 to 4 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.87. Raw data for CMRR Match1 1 to 4 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

CMRR Match1 1 to 4 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.13E+02	1.13E+02	1.13E+02	1.14E+02	1.13E+02
520	1.12E+02	1.14E+02	1.14E+02	1.14E+02	1.13E+02
521	1.05E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
522	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
524	1.04E+02	1.05E+02	1.05E+02	1.05E+02	1.05E+02
536	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
537	1.16E+02	1.15E+02	1.16E+02	1.17E+02	1.17E+02
538	1.20E+02	1.27E+02	1.23E+02	1.23E+02	1.22E+02
539	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
542	1.18E+02	1.18E+02	1.18E+02	1.16E+02	1.15E+02
543	9.61E+01	9.61E+01	9.62E+01	9.61E+01	9.61E+01
544	1.00E+02	1.00E+02	1.00E+02	1.00E+02	1.00E+02
Biased Statistics					
Average Biased	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
Std Dev Biased	4.56E+00	4.72E+00	4.82E+00	5.03E+00	4.70E+00
Ps90%/90% (+KTL) Biased	1.20E+02	1.21E+02	1.22E+02	1.22E+02	1.21E+02
Ps90%/90% (-KTL) Biased	9.53E+01	9.54E+01	9.51E+01	9.47E+01	9.53E+01
Un-Biased Statistics					
Average Un-Biased	1.15E+02	1.16E+02	1.15E+02	1.15E+02	1.15E+02
Std Dev Un-Biased	5.03E+00	7.16E+00	5.85E+00	5.91E+00	5.42E+00
Ps90%/90% (+KTL) Un-Biased	1.29E+02	1.36E+02	1.31E+02	1.31E+02	1.30E+02
Ps90%/90% (-KTL) Un-Biased	1.01E+02	9.63E+01	9.92E+01	9.89E+01	9.98E+01
Specification MIN	8.40E+01	8.30E+01	8.30E+01	8.30E+01	8.30E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.88. Plot of CMRR Match1 2 to 3 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.88. Raw data for CMRR Match1 2 to 3 (dB) @ VS=+/-15V, VCM=+/-15V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

CMRR Match1 2 to 3 (dB) @ VS=+/-15V, VCM=+/-15V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.17E+02	1.27E+02	1.25E+02	1.22E+02	1.20E+02
520	9.82E+01	9.85E+01	9.85E+01	9.85E+01	9.85E+01
521	1.20E+02	1.17E+02	1.17E+02	1.17E+02	1.17E+02
522	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
524	1.14E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
536	1.00E+02	1.01E+02	1.01E+02	1.01E+02	1.01E+02
537	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
538	1.16E+02	1.16E+02	1.17E+02	1.17E+02	1.17E+02
539	1.11E+02	1.12E+02	1.12E+02	1.11E+02	1.11E+02
542	9.93E+01	9.92E+01	9.93E+01	9.95E+01	9.97E+01
543	9.90E+01	9.90E+01	9.90E+01	9.90E+01	9.90E+01
544	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
Biased Statistics					
Average Biased	1.10E+02	1.11E+02	1.11E+02	1.10E+02	1.10E+02
Std Dev Biased	9.54E+00	1.15E+01	1.08E+01	9.78E+00	9.32E+00
Ps90%/90% (+KTL) Biased	1.36E+02	1.43E+02	1.40E+02	1.37E+02	1.35E+02
Ps90%/90% (-KTL) Biased	8.42E+01	7.96E+01	8.11E+01	8.33E+01	8.43E+01
Un-Biased Statistics					
Average Un-Biased	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
Std Dev Un-Biased	7.39E+00	7.60E+00	7.58E+00	7.71E+00	7.60E+00
Ps90%/90% (+KTL) Un-Biased	1.26E+02	1.27E+02	1.27E+02	1.27E+02	1.27E+02
Ps90%/90% (-KTL) Un-Biased	8.57E+01	8.53E+01	8.54E+01	8.51E+01	8.55E+01
Specification MIN	8.40E+01	8.30E+01	8.30E+01	8.30E+01	8.30E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.89. Plot of Power Supply Rejection Ratio1 1 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.89. Raw data for Power Supply Rejection Ratio1 1 (dB) @ VS=+/-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio1 1 (dB) @ VS=+/-2V to +/-16V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.17E+02	1.17E+02	1.17E+02	1.16E+02	1.16E+02
	520	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
	521	1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.17E+02
	522	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	524	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.10E+02
	536	1.13E+02	1.13E+02	1.12E+02	1.12E+02	1.12E+02
	537	1.30E+02	1.29E+02	1.28E+02	1.28E+02	1.26E+02
	538	1.05E+02	1.05E+02	1.06E+02	1.06E+02	1.06E+02
	539	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
	542	1.09E+02	1.09E+02	1.09E+02	1.10E+02	1.10E+02
	543	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
	544	1.26E+02	1.25E+02	1.25E+02	1.25E+02	1.25E+02
Biased Statistics						
Average Biased		1.10E+02	1.10E+02	1.11E+02	1.10E+02	1.11E+02
Std Dev Biased		5.82E+00	5.83E+00	5.86E+00	5.66E+00	5.65E+00
Ps90%/90% (+KTL) Biased		1.26E+02	1.26E+02	1.27E+02	1.26E+02	1.26E+02
Ps90%/90% (-KTL) Biased		9.44E+01	9.45E+01	9.45E+01	9.49E+01	9.51E+01
Un-Biased Statistics						
Average Un-Biased		1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
Std Dev Un-Biased		9.76E+00	9.28E+00	8.98E+00	8.79E+00	8.14E+00
Ps90%/90% (+KTL) Un-Biased		1.40E+02	1.38E+02	1.37E+02	1.37E+02	1.35E+02
Ps90%/90% (-KTL) Un-Biased		8.64E+01	8.75E+01	8.82E+01	8.87E+01	9.02E+01
Specification MIN		9.00E+01	9.00E+01	9.00E+01	9.00E+01	9.00E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.90. Plot of Power Supply Rejection Ratio1 2 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.90. Raw data for Power Supply Rejection Ratio1 2 (dB) @ VS=+/-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio1 2 (dB) @ VS=+/-2V to +/-16V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
	520	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	521	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.04E+02
	522	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.10E+02
	524	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
	536	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
	537	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
	538	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
	539	1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
	542	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
	543	1.01E+02	1.01E+02	1.01E+02	1.01E+02	1.01E+02
	544	1.24E+02	1.25E+02	1.25E+02	1.25E+02	1.25E+02
Biased Statistics						
Average Biased		1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
Std Dev Biased		4.20E+00	4.15E+00	4.19E+00	4.19E+00	4.25E+00
Ps90%/90% (+KTL) Biased		1.18E+02	1.18E+02	1.18E+02	1.18E+02	1.18E+02
Ps90%/90% (-KTL) Biased		9.52E+01	9.54E+01	9.53E+01	9.53E+01	9.52E+01
Un-Biased Statistics						
Average Un-Biased		1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
Std Dev Un-Biased		4.00E+00	4.00E+00	4.01E+00	4.00E+00	3.96E+00
Ps90%/90% (+KTL) Un-Biased		1.20E+02	1.20E+02	1.20E+02	1.20E+02	1.20E+02
Ps90%/90% (-KTL) Un-Biased		9.83E+01	9.84E+01	9.84E+01	9.84E+01	9.84E+01
Specification MIN		9.00E+01	9.00E+01	9.00E+01	9.00E+01	9.00E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.91. Plot of Power Supply Rejection Ratio 1 3 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.91. Raw data for Power Supply Rejection Ratio1 3 (dB) @ VS=+/-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio1 3 (dB) @ VS=+/-2V to +/-16V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.18E+02	1.18E+02	1.17E+02	1.17E+02	1.17E+02
	520	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
	521	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.13E+02
	522	1.20E+02	1.20E+02	1.21E+02	1.20E+02	1.21E+02
	524	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.10E+02
	536	1.37E+02	1.37E+02	1.37E+02	1.38E+02	1.38E+02
	537	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
	538	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.12E+02
	539	1.27E+02	1.27E+02	1.27E+02	1.27E+02	1.28E+02
	542	1.05E+02	1.05E+02	1.05E+02	1.06E+02	1.06E+02
	543	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
	544	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
Biased Statistics						
Average Biased		1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.13E+02
Std Dev Biased		7.01E+00	7.06E+00	7.05E+00	6.88E+00	6.89E+00
Ps90%/90% (+KTL) Biased		1.31E+02	1.32E+02	1.32E+02	1.31E+02	1.31E+02
Ps90%/90% (-KTL) Biased		9.30E+01	9.30E+01	9.31E+01	9.35E+01	9.36E+01
Un-Biased Statistics						
Average Un-Biased		1.18E+02	1.18E+02	1.18E+02	1.18E+02	1.18E+02
Std Dev Un-Biased		1.39E+01	1.38E+01	1.40E+01	1.42E+01	1.42E+01
Ps90%/90% (+KTL) Un-Biased		1.56E+02	1.55E+02	1.56E+02	1.57E+02	1.57E+02
Ps90%/90% (-KTL) Un-Biased		7.94E+01	7.98E+01	7.94E+01	7.90E+01	7.90E+01
Specification MIN		9.00E+01	9.00E+01	9.00E+01	9.00E+01	9.00E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.92. Plot of Power Supply Rejection Ratio1 4 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.92. Raw data for Power Supply Rejection Ratio1 4 (dB) @ VS=+-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio1 4 (dB) @ VS=+-2V to +/-16V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
	520	1.01E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
	521	1.01E+02	1.01E+02	1.01E+02	1.01E+02	1.01E+02
	522	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
	524	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	536	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
	537	1.23E+02	1.23E+02	1.24E+02	1.24E+02	1.25E+02
	538	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	539	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
	542	1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
	543	1.02E+02	1.02E+02	1.02E+02	1.02E+02	1.02E+02
	544	1.18E+02	1.18E+02	1.18E+02	1.18E+02	1.18E+02
Biased Statistics						
Average Biased		1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
Std Dev Biased		1.81E+00	1.83E+00	1.82E+00	1.81E+00	1.74E+00
Ps90%/90% (+KTL) Biased		1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
Ps90%/90% (-KTL) Biased		9.80E+01	9.81E+01	9.81E+01	9.81E+01	9.83E+01
Un-Biased Statistics						
Average Un-Biased		1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
Std Dev Un-Biased		7.99E+00	8.09E+00	8.30E+00	8.26E+00	8.68E+00
Ps90%/90% (+KTL) Un-Biased		1.33E+02	1.33E+02	1.34E+02	1.34E+02	1.35E+02
Ps90%/90% (-KTL) Un-Biased		8.89E+01	8.87E+01	8.82E+01	8.83E+01	8.73E+01
Specification MIN		9.00E+01	9.00E+01	9.00E+01	9.00E+01	9.00E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.93. Plot of PSRR Match1 1 to 4 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.93. Raw data for PSRR Match1 1 to 4 (dB) @ VS=+/-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

PSRR Match1 1 to 4 (dB) @ VS=+/-2V to +/-16V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
520	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.14E+02
521	1.03E+02	1.03E+02	1.03E+02	1.03E+02	1.03E+02
522	1.14E+02	1.14E+02	1.14E+02	1.14E+02	1.13E+02
524	1.14E+02	1.14E+02	1.14E+02	1.14E+02	1.14E+02
536	1.05E+02	1.05E+02	1.05E+02	1.05E+02	1.04E+02
537	1.29E+02	1.30E+02	1.32E+02	1.32E+02	1.41E+02
538	1.27E+02	1.27E+02	1.28E+02	1.27E+02	1.29E+02
539	1.09E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
542	1.18E+02	1.18E+02	1.18E+02	1.19E+02	1.20E+02
543	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
544	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.15E+02
Biased Statistics					
Average Biased	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.10E+02
Std Dev Biased	5.57E+00	5.53E+00	5.48E+00	5.41E+00	5.10E+00
Ps90%/90% (+KTL) Biased	1.26E+02	1.26E+02	1.25E+02	1.25E+02	1.24E+02
Ps90%/90% (-KTL) Biased	9.51E+01	9.52E+01	9.53E+01	9.54E+01	9.61E+01
Un-Biased Statistics					
Average Un-Biased	1.17E+02	1.18E+02	1.18E+02	1.18E+02	1.20E+02
Std Dev Un-Biased	1.06E+01	1.11E+01	1.20E+01	1.20E+01	1.49E+01
Ps90%/90% (+KTL) Un-Biased	1.46E+02	1.48E+02	1.51E+02	1.51E+02	1.61E+02
Ps90%/90% (-KTL) Un-Biased	8.82E+01	8.71E+01	8.55E+01	8.54E+01	7.94E+01
Specification MIN	8.30E+01	8.30E+01	8.30E+01	8.30E+01	8.30E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.94. Plot of PSRR Match1 2 to 3 (dB) @ VS=+-2V to +/-16V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.94. Raw data for PSRR Match1 2 to 3 (dB) @ VS=+/-2V to +/-16V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

PSRR Match1 2 to 3 (dB) @ VS=+/-2V to +/-16V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.18E+02	1.19E+02	1.19E+02	1.20E+02	1.20E+02
520	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
521	1.08E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
522	1.08E+02	1.08E+02	1.07E+02	1.07E+02	1.08E+02
524	1.08E+02	1.08E+02	1.07E+02	1.07E+02	1.07E+02
536	1.07E+02	1.07E+02	1.08E+02	1.08E+02	1.08E+02
537	1.14E+02	1.14E+02	1.14E+02	1.14E+02	1.15E+02
538	1.05E+02	1.05E+02	1.05E+02	1.05E+02	1.05E+02
539	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
542	1.18E+02	1.18E+02	1.17E+02	1.17E+02	1.17E+02
543	1.19E+02	1.19E+02	1.19E+02	1.19E+02	1.19E+02
544	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
Biased Statistics					
Average Biased	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
Std Dev Biased	4.77E+00	4.86E+00	5.21E+00	5.40E+00	5.70E+00
Ps90%/90% (+KTL) Biased	1.24E+02	1.24E+02	1.25E+02	1.26E+02	1.26E+02
Ps90%/90% (-KTL) Biased	9.76E+01	9.73E+01	9.64E+01	9.59E+01	9.52E+01
Un-Biased Statistics					
Average Un-Biased	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
Std Dev Un-Biased	5.04E+00	5.02E+00	4.91E+00	4.82E+00	4.89E+00
Ps90%/90% (+KTL) Un-Biased	1.25E+02	1.25E+02	1.25E+02	1.24E+02	1.25E+02
Ps90%/90% (-KTL) Un-Biased	9.73E+01	9.74E+01	9.77E+01	9.79E+01	9.78E+01
Specification MIN	8.30E+01	8.30E+01	8.30E+01	8.30E+01	8.30E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.95. Plot of +Short-Circuit Current1 1 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.95. Raw data for +Short-Circuit Current1 1 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current1 1 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.85E-02	-3.72E-02	-3.65E-02	-3.56E-02	-3.45E-02
520	-4.10E-02	-3.96E-02	-3.85E-02	-3.77E-02	-3.71E-02
521	-4.16E-02	-4.02E-02	-3.92E-02	-3.83E-02	-3.75E-02
522	-3.80E-02	-3.64E-02	-3.55E-02	-3.46E-02	-3.38E-02
524	-4.42E-02	-4.32E-02	-4.17E-02	-4.08E-02	-4.05E-02
536	-4.02E-02	-3.92E-02	-3.84E-02	-3.76E-02	-3.64E-02
537	-3.77E-02	-3.68E-02	-3.61E-02	-3.54E-02	-3.44E-02
538	-4.02E-02	-3.93E-02	-3.85E-02	-3.77E-02	-3.66E-02
539	-4.03E-02	-3.95E-02	-3.87E-02	-3.79E-02	-3.68E-02
542	-4.04E-02	-3.95E-02	-3.87E-02	-3.79E-02	-3.68E-02
543	-3.97E-02	-3.92E-02	-3.92E-02	-3.92E-02	-3.93E-02
544	-4.48E-02	-4.45E-02	-4.44E-02	-4.45E-02	-4.46E-02
Biased Statistics					
Average Biased	-4.07E-02	-3.93E-02	-3.83E-02	-3.74E-02	-3.67E-02
Std Dev Biased	2.53E-03	2.68E-03	2.43E-03	2.45E-03	2.65E-03
Ps90%/90% (+KTL) Biased	-3.37E-02	-3.20E-02	-3.16E-02	-3.07E-02	-2.94E-02
Ps90%/90% (-KTL) Biased	-4.76E-02	-4.66E-02	-4.49E-02	-4.41E-02	-4.40E-02
Un-Biased Statistics					
Average Un-Biased	-3.97E-02	-3.89E-02	-3.81E-02	-3.73E-02	-3.62E-02
Std Dev Un-Biased	1.16E-03	1.14E-03	1.10E-03	1.04E-03	9.94E-04
Ps90%/90% (+KTL) Un-Biased	-3.66E-02	-3.57E-02	-3.51E-02	-3.44E-02	-3.35E-02
Ps90%/90% (-KTL) Un-Biased	-4.29E-02	-4.20E-02	-4.11E-02	-4.01E-02	-3.89E-02
Specification MAX	-1.50E-02	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.96. Plot of +Short-Circuit Current1 2 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.96. Raw data for +Short-Circuit Current1 2 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current1 2 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-4.01E-02	-3.88E-02	-3.81E-02	-3.72E-02	-3.60E-02
520	-4.07E-02	-3.93E-02	-3.83E-02	-3.75E-02	-3.69E-02
521	-4.19E-02	-4.06E-02	-3.97E-02	-3.89E-02	-3.79E-02
522	-4.01E-02	-3.85E-02	-3.76E-02	-3.67E-02	-3.59E-02
524	-4.30E-02	-4.19E-02	-4.03E-02	-3.94E-02	-3.88E-02
536	-4.14E-02	-4.05E-02	-3.97E-02	-3.89E-02	-3.76E-02
537	-4.09E-02	-4.00E-02	-3.92E-02	-3.84E-02	-3.73E-02
538	-4.13E-02	-4.04E-02	-3.96E-02	-3.88E-02	-3.77E-02
539	-4.03E-02	-3.96E-02	-3.88E-02	-3.80E-02	-3.70E-02
542	-4.07E-02	-3.98E-02	-3.90E-02	-3.81E-02	-3.70E-02
543	-3.85E-02	-3.80E-02	-3.79E-02	-3.79E-02	-3.80E-02
544	-4.09E-02	-4.07E-02	-4.06E-02	-4.07E-02	-4.08E-02
Biased Statistics					
Average Biased	-4.12E-02	-3.98E-02	-3.88E-02	-3.79E-02	-3.71E-02
Std Dev Biased	1.29E-03	1.42E-03	1.16E-03	1.15E-03	1.27E-03
Ps90%/90% (+KTL) Biased	-3.76E-02	-3.60E-02	-3.56E-02	-3.48E-02	-3.36E-02
Ps90%/90% (-KTL) Biased	-4.47E-02	-4.37E-02	-4.20E-02	-4.11E-02	-4.06E-02
Un-Biased Statistics					
Average Un-Biased	-4.09E-02	-4.00E-02	-3.92E-02	-3.84E-02	-3.73E-02
Std Dev Un-Biased	4.39E-04	3.94E-04	3.88E-04	4.05E-04	3.48E-04
Ps90%/90% (+KTL) Un-Biased	-3.97E-02	-3.89E-02	-3.82E-02	-3.73E-02	-3.64E-02
Ps90%/90% (-KTL) Un-Biased	-4.21E-02	-4.11E-02	-4.03E-02	-3.95E-02	-3.83E-02
Specification MAX	-1.50E-02	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.97. Plot of +Short-Circuit Current1 3 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.97. Raw data for +Short-Circuit Current1 3 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current1 3 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-4.02E-02	-3.90E-02	-3.82E-02	-3.73E-02	-3.61E-02
520	-3.96E-02	-3.82E-02	-3.71E-02	-3.63E-02	-3.57E-02
521	-4.28E-02	-4.15E-02	-4.05E-02	-3.97E-02	-3.87E-02
522	-4.07E-02	-3.91E-02	-3.81E-02	-3.72E-02	-3.63E-02
524	-4.36E-02	-4.25E-02	-4.09E-02	-4.00E-02	-3.93E-02
536	-4.22E-02	-4.12E-02	-4.04E-02	-3.96E-02	-3.83E-02
537	-4.05E-02	-3.95E-02	-3.88E-02	-3.80E-02	-3.68E-02
538	-4.17E-02	-4.08E-02	-4.00E-02	-3.92E-02	-3.81E-02
539	-4.10E-02	-4.02E-02	-3.94E-02	-3.86E-02	-3.76E-02
542	-4.15E-02	-4.05E-02	-3.97E-02	-3.88E-02	-3.77E-02
543	-3.83E-02	-3.78E-02	-3.78E-02	-3.77E-02	-3.78E-02
544	-4.05E-02	-4.02E-02	-4.02E-02	-4.02E-02	-4.03E-02
Biased Statistics					
Average Biased	-4.14E-02	-4.00E-02	-3.90E-02	-3.81E-02	-3.72E-02
Std Dev Biased	1.74E-03	1.86E-03	1.65E-03	1.63E-03	1.66E-03
Ps90%/90% (+KTL) Biased	-3.66E-02	-3.50E-02	-3.45E-02	-3.36E-02	-3.27E-02
Ps90%/90% (-KTL) Biased	-4.61E-02	-4.51E-02	-4.35E-02	-4.26E-02	-4.18E-02
Un-Biased Statistics					
Average Un-Biased	-4.14E-02	-4.05E-02	-3.97E-02	-3.88E-02	-3.77E-02
Std Dev Un-Biased	6.66E-04	6.40E-04	6.29E-04	6.15E-04	5.76E-04
Ps90%/90% (+KTL) Un-Biased	-3.95E-02	-3.87E-02	-3.79E-02	-3.71E-02	-3.61E-02
Ps90%/90% (-KTL) Un-Biased	-4.32E-02	-4.22E-02	-4.14E-02	-4.05E-02	-3.93E-02
Specification MAX	-1.50E-02	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.98. Plot of +Short-Circuit Current1 4 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.98. Raw data for +Short-Circuit Current1 4 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current1 4 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.85E-02	-3.72E-02	-3.65E-02	-3.56E-02	-3.45E-02
520	-4.14E-02	-4.00E-02	-3.90E-02	-3.82E-02	-3.75E-02
521	-4.25E-02	-4.11E-02	-4.01E-02	-3.92E-02	-3.83E-02
522	-3.87E-02	-3.71E-02	-3.62E-02	-3.54E-02	-3.45E-02
524	-4.60E-02	-4.49E-02	-4.34E-02	-4.26E-02	-4.21E-02
536	-4.04E-02	-3.95E-02	-3.87E-02	-3.79E-02	-3.66E-02
537	-3.94E-02	-3.85E-02	-3.78E-02	-3.70E-02	-3.60E-02
538	-4.04E-02	-3.95E-02	-3.87E-02	-3.78E-02	-3.67E-02
539	-4.09E-02	-4.01E-02	-3.93E-02	-3.85E-02	-3.74E-02
542	-4.16E-02	-4.07E-02	-3.99E-02	-3.90E-02	-3.79E-02
543	-4.13E-02	-4.08E-02	-4.08E-02	-4.08E-02	-4.08E-02
544	-4.59E-02	-4.56E-02	-4.56E-02	-4.56E-02	-4.57E-02
Biased Statistics					
Average Biased	-4.14E-02	-4.01E-02	-3.90E-02	-3.82E-02	-3.74E-02
Std Dev Biased	3.06E-03	3.20E-03	2.95E-03	2.95E-03	3.13E-03
Ps90%/90% (+KTL) Biased	-3.30E-02	-3.13E-02	-3.09E-02	-3.01E-02	-2.88E-02
Ps90%/90% (-KTL) Biased	-4.98E-02	-4.89E-02	-4.71E-02	-4.63E-02	-4.60E-02
Un-Biased Statistics					
Average Un-Biased	-4.05E-02	-3.96E-02	-3.89E-02	-3.80E-02	-3.69E-02
Std Dev Un-Biased	8.11E-04	8.08E-04	7.83E-04	7.26E-04	7.29E-04
Ps90%/90% (+KTL) Un-Biased	-3.83E-02	-3.74E-02	-3.67E-02	-3.60E-02	-3.49E-02
Ps90%/90% (-KTL) Un-Biased	-4.28E-02	-4.19E-02	-4.10E-02	-4.00E-02	-3.89E-02
Specification MAX	-1.50E-02	-1.00E-02	-1.00E-02	-1.00E-02	-1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.99. Plot of -Short-Circuit Current1 1 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.99. Raw data for -Short-Circuit Current1 1 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current1 1 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.92E-02	5.91E-02	5.88E-02	5.88E-02	5.89E-02
520	5.94E-02	5.94E-02	5.94E-02	5.93E-02	5.90E-02
521	6.03E-02	6.03E-02	6.04E-02	6.01E-02	6.00E-02
522	5.99E-02	6.03E-02	6.02E-02	6.01E-02	5.98E-02
524	5.94E-02	6.00E-02	5.98E-02	5.96E-02	5.92E-02
536	5.83E-02	5.88E-02	5.88E-02	5.86E-02	5.84E-02
537	5.98E-02	6.02E-02	6.02E-02	6.00E-02	5.97E-02
538	5.99E-02	6.01E-02	6.01E-02	5.99E-02	5.96E-02
539	5.86E-02	5.88E-02	5.88E-02	5.86E-02	5.82E-02
542	6.04E-02	6.08E-02	6.07E-02	6.06E-02	6.02E-02
543	6.05E-02	6.13E-02	6.13E-02	6.14E-02	6.12E-02
544	6.17E-02	6.21E-02	6.22E-02	6.22E-02	6.21E-02
Biased Statistics					
Average Biased	5.96E-02	5.98E-02	5.97E-02	5.96E-02	5.94E-02
Std Dev Biased	4.36E-04	5.36E-04	6.49E-04	5.80E-04	4.84E-04
Ps90%/90% (+KTL) Biased	6.08E-02	6.13E-02	6.15E-02	6.12E-02	6.07E-02
Ps90%/90% (-KTL) Biased	5.84E-02	5.83E-02	5.79E-02	5.80E-02	5.81E-02
Un-Biased Statistics					
Average Un-Biased	5.94E-02	5.97E-02	5.97E-02	5.95E-02	5.92E-02
Std Dev Un-Biased	8.85E-04	9.08E-04	8.75E-04	9.05E-04	8.54E-04
Ps90%/90% (+KTL) Un-Biased	6.18E-02	6.22E-02	6.21E-02	6.20E-02	6.15E-02
Ps90%/90% (-KTL) Un-Biased	5.69E-02	5.73E-02	5.73E-02	5.70E-02	5.69E-02
Specification MIN	1.50E-02	1.00E-02	1.00E-02	1.00E-02	1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.100. Plot of -Short-Circuit Current1 2 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.100. Raw data for -Short-Circuit Current1 2 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current1 2 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.89E-02	5.87E-02	5.83E-02	5.84E-02	5.85E-02
520	5.77E-02	5.76E-02	5.77E-02	5.75E-02	5.72E-02
521	5.98E-02	5.98E-02	5.98E-02	5.96E-02	5.95E-02
522	5.92E-02	5.95E-02	5.94E-02	5.93E-02	5.89E-02
524	5.77E-02	5.82E-02	5.80E-02	5.78E-02	5.73E-02
536	5.74E-02	5.78E-02	5.79E-02	5.77E-02	5.75E-02
537	5.88E-02	5.93E-02	5.92E-02	5.89E-02	5.87E-02
538	5.91E-02	5.94E-02	5.94E-02	5.92E-02	5.88E-02
539	5.91E-02	5.93E-02	5.93E-02	5.91E-02	5.87E-02
542	5.91E-02	5.95E-02	5.95E-02	5.93E-02	5.89E-02
543	5.73E-02	5.80E-02	5.82E-02	5.82E-02	5.80E-02
544	5.94E-02	5.98E-02	5.99E-02	5.99E-02	5.97E-02
Biased Statistics					
Average Biased	5.86E-02	5.88E-02	5.86E-02	5.85E-02	5.83E-02
Std Dev Biased	9.31E-04	9.02E-04	9.29E-04	9.14E-04	9.90E-04
Ps90%/90% (+KTL) Biased	6.12E-02	6.12E-02	6.12E-02	6.10E-02	6.10E-02
Ps90%/90% (-KTL) Biased	5.61E-02	5.63E-02	5.61E-02	5.60E-02	5.56E-02
Un-Biased Statistics					
Average Un-Biased	5.87E-02	5.91E-02	5.90E-02	5.88E-02	5.85E-02
Std Dev Un-Biased	7.35E-04	7.00E-04	6.54E-04	6.74E-04	5.99E-04
Ps90%/90% (+KTL) Un-Biased	6.07E-02	6.10E-02	6.08E-02	6.07E-02	6.02E-02
Ps90%/90% (-KTL) Un-Biased	5.67E-02	5.71E-02	5.72E-02	5.70E-02	5.69E-02
Specification MIN	1.50E-02	1.00E-02	1.00E-02	1.00E-02	1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.101. Plot of -Short-Circuit Current1 3 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.101. Raw data for -Short-Circuit Current1 3 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current1 3 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.84E-02	5.82E-02	5.79E-02	5.79E-02	5.80E-02
520	5.73E-02	5.73E-02	5.73E-02	5.71E-02	5.69E-02
521	5.98E-02	5.98E-02	5.98E-02	5.96E-02	5.95E-02
522	5.92E-02	5.95E-02	5.95E-02	5.94E-02	5.89E-02
524	5.77E-02	5.83E-02	5.81E-02	5.79E-02	5.74E-02
536	5.75E-02	5.79E-02	5.79E-02	5.77E-02	5.75E-02
537	5.90E-02	5.94E-02	5.93E-02	5.91E-02	5.88E-02
538	5.90E-02	5.93E-02	5.93E-02	5.90E-02	5.88E-02
539	5.90E-02	5.92E-02	5.92E-02	5.90E-02	5.87E-02
542	5.91E-02	5.95E-02	5.94E-02	5.92E-02	5.88E-02
543	5.73E-02	5.79E-02	5.80E-02	5.80E-02	5.79E-02
544	5.92E-02	5.96E-02	5.97E-02	5.97E-02	5.96E-02
Biased Statistics					
Average Biased	5.85E-02	5.86E-02	5.85E-02	5.84E-02	5.81E-02
Std Dev Biased	1.02E-03	1.04E-03	1.08E-03	1.06E-03	1.05E-03
Ps90%/90% (+KTL) Biased	6.13E-02	6.15E-02	6.15E-02	6.13E-02	6.10E-02
Ps90%/90% (-KTL) Biased	5.57E-02	5.58E-02	5.55E-02	5.55E-02	5.53E-02
Un-Biased Statistics					
Average Un-Biased	5.87E-02	5.90E-02	5.90E-02	5.88E-02	5.85E-02
Std Dev Un-Biased	7.05E-04	6.64E-04	6.23E-04	6.31E-04	5.67E-04
Ps90%/90% (+KTL) Un-Biased	6.06E-02	6.09E-02	6.07E-02	6.05E-02	6.01E-02
Ps90%/90% (-KTL) Un-Biased	5.68E-02	5.72E-02	5.73E-02	5.71E-02	5.70E-02
Specification MIN	1.50E-02	1.00E-02	1.00E-02	1.00E-02	1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.102. Plot of -Short-Circuit Current1 4 (A) @ VS=+-15V, VOUT=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.102. Raw data for -Short-Circuit Current1 4 (A) @ VS=+/-15V, VOUT=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current1 4 (A) @ VS=+/-15V, VOUT=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.71E-02	5.69E-02	5.66E-02	5.66E-02	5.68E-02
520	5.71E-02	5.71E-02	5.71E-02	5.69E-02	5.66E-02
521	5.79E-02	5.79E-02	5.79E-02	5.77E-02	5.76E-02
522	5.75E-02	5.78E-02	5.77E-02	5.76E-02	5.72E-02
524	5.73E-02	5.78E-02	5.76E-02	5.74E-02	5.70E-02
536	5.60E-02	5.64E-02	5.64E-02	5.62E-02	5.60E-02
537	5.71E-02	5.75E-02	5.75E-02	5.72E-02	5.70E-02
538	5.75E-02	5.77E-02	5.76E-02	5.74E-02	5.71E-02
539	5.65E-02	5.67E-02	5.67E-02	5.65E-02	5.61E-02
542	5.80E-02	5.84E-02	5.83E-02	5.82E-02	5.78E-02
543	5.78E-02	5.85E-02	5.86E-02	5.86E-02	5.85E-02
544	5.93E-02	5.97E-02	5.97E-02	5.97E-02	5.96E-02
Biased Statistics					
Average Biased	5.74E-02	5.75E-02	5.74E-02	5.72E-02	5.70E-02
Std Dev Biased	3.36E-04	4.58E-04	5.37E-04	4.65E-04	3.83E-04
Ps90%/90% (+KTL) Biased	5.83E-02	5.87E-02	5.88E-02	5.85E-02	5.81E-02
Ps90%/90% (-KTL) Biased	5.64E-02	5.62E-02	5.59E-02	5.60E-02	5.60E-02
Un-Biased Statistics					
Average Un-Biased	5.70E-02	5.73E-02	5.73E-02	5.71E-02	5.68E-02
Std Dev Un-Biased	7.88E-04	8.13E-04	7.53E-04	7.89E-04	7.39E-04
Ps90%/90% (+KTL) Un-Biased	5.92E-02	5.96E-02	5.94E-02	5.93E-02	5.88E-02
Ps90%/90% (-KTL) Un-Biased	5.48E-02	5.51E-02	5.52E-02	5.50E-02	5.48E-02
Specification MIN	1.50E-02	1.00E-02	1.00E-02	1.00E-02	1.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.103. Plot of +Supply Current (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.103. Raw data for +Supply Current (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Supply Current (A) @ VS=+5V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	7.50E-03	7.38E-03	7.40E-03	7.31E-03	7.29E-03
520	7.52E-03	7.41E-03	7.36E-03	7.34E-03	7.37E-03
521	7.61E-03	7.52E-03	7.46E-03	7.43E-03	7.40E-03
522	7.44E-03	7.33E-03	7.28E-03	7.25E-03	7.23E-03
524	7.53E-03	7.47E-03	7.38E-03	7.35E-03	7.37E-03
536	7.48E-03	7.44E-03	7.40E-03	7.37E-03	7.31E-03
537	7.51E-03	7.46E-03	7.43E-03	7.40E-03	7.35E-03
538	7.33E-03	7.28E-03	7.25E-03	7.22E-03	7.17E-03
539	7.47E-03	7.42E-03	7.39E-03	7.36E-03	7.31E-03
542	7.45E-03	7.40E-03	7.37E-03	7.34E-03	7.28E-03
543	7.44E-03	7.40E-03	7.40E-03	7.40E-03	7.41E-03
544	7.49E-03	7.48E-03	7.47E-03	7.48E-03	7.49E-03
Biased Statistics					
Average Biased	7.52E-03	7.42E-03	7.37E-03	7.34E-03	7.33E-03
Std Dev Biased	6.05E-05	7.57E-05	6.46E-05	6.75E-05	7.18E-05
Ps90%/90% (+KTL) Biased	7.68E-03	7.63E-03	7.55E-03	7.52E-03	7.53E-03
Ps90%/90% (-KTL) Biased	7.35E-03	7.22E-03	7.20E-03	7.15E-03	7.14E-03
Un-Biased Statistics					
Average Un-Biased	7.45E-03	7.40E-03	7.37E-03	7.34E-03	7.29E-03
Std Dev Un-Biased	6.86E-05	6.97E-05	6.65E-05	6.87E-05	6.83E-05
Ps90%/90% (+KTL) Un-Biased	7.64E-03	7.59E-03	7.55E-03	7.53E-03	7.47E-03
Ps90%/90% (-KTL) Un-Biased	7.26E-03	7.21E-03	7.18E-03	7.15E-03	7.10E-03
Specification MAX	8.80E-03	8.80E-03	8.80E-03	8.80E-03	8.80E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.104. Plot of -Supply Current (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.104. Raw data for -Supply Current (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Supply Current (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-7.50E-03	-7.38E-03	-7.39E-03	-7.31E-03	-7.28E-03
520	-7.52E-03	-7.41E-03	-7.35E-03	-7.33E-03	-7.37E-03
521	-7.61E-03	-7.52E-03	-7.46E-03	-7.43E-03	-7.40E-03
522	-7.44E-03	-7.33E-03	-7.28E-03	-7.24E-03	-7.23E-03
524	-7.53E-03	-7.47E-03	-7.38E-03	-7.35E-03	-7.37E-03
536	-7.48E-03	-7.43E-03	-7.40E-03	-7.36E-03	-7.31E-03
537	-7.51E-03	-7.46E-03	-7.42E-03	-7.40E-03	-7.35E-03
538	-7.33E-03	-7.28E-03	-7.25E-03	-7.22E-03	-7.17E-03
539	-7.47E-03	-7.42E-03	-7.39E-03	-7.36E-03	-7.31E-03
542	-7.44E-03	-7.40E-03	-7.36E-03	-7.33E-03	-7.28E-03
543	-7.44E-03	-7.40E-03	-7.40E-03	-7.40E-03	-7.41E-03
544	-7.49E-03	-7.47E-03	-7.47E-03	-7.47E-03	-7.48E-03
Biased Statistics					
Average Biased	-7.52E-03	-7.42E-03	-7.37E-03	-7.33E-03	-7.33E-03
Std Dev Biased	6.01E-05	7.51E-05	6.39E-05	6.77E-05	7.31E-05
Ps90%/90% (+KTL) Biased	-7.35E-03	-7.22E-03	-7.20E-03	-7.15E-03	-7.13E-03
Ps90%/90% (-KTL) Biased	-7.68E-03	-7.63E-03	-7.55E-03	-7.52E-03	-7.53E-03
Un-Biased Statistics					
Average Un-Biased	-7.45E-03	-7.40E-03	-7.36E-03	-7.33E-03	-7.28E-03
Std Dev Un-Biased	6.89E-05	6.91E-05	6.67E-05	6.81E-05	6.83E-05
Ps90%/90% (+KTL) Un-Biased	-7.26E-03	-7.21E-03	-7.18E-03	-7.15E-03	-7.10E-03
Ps90%/90% (-KTL) Un-Biased	-7.64E-03	-7.59E-03	-7.55E-03	-7.52E-03	-7.47E-03
Specification MIN	-8.80E-03	-8.80E-03	-8.80E-03	-8.80E-03	-8.80E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.105. Plot of Input Offset Voltage4 1 (V) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.105. Raw data for Input Offset Voltage4 1 (V) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage4 1 (V) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	8.30E-05	5.99E-05	6.98E-05	6.08E-05	6.13E-05
520	3.82E-04	3.47E-04	3.45E-04	3.36E-04	3.22E-04
521	-5.21E-05	-6.61E-05	-7.44E-05	-8.04E-05	-8.95E-05
522	-1.16E-04	-1.42E-04	-1.39E-04	-1.48E-04	-1.56E-04
524	1.08E-05	-1.03E-05	-7.91E-06	2.11E-06	1.38E-06
536	2.44E-05	4.64E-06	-3.56E-06	-1.66E-05	-4.41E-05
537	-1.36E-04	-1.51E-04	-1.58E-04	-1.70E-04	-1.94E-04
538	6.81E-06	6.69E-06	-6.58E-06	-2.24E-05	-4.47E-05
539	-2.32E-04	-2.35E-04	-2.44E-04	-2.53E-04	-2.78E-04
542	1.05E-04	8.73E-05	7.54E-05	6.34E-05	4.21E-05
543	-2.60E-04	-2.62E-04	-2.63E-04	-2.62E-04	-2.63E-04
544	-2.02E-04	-2.02E-04	-2.03E-04	-2.02E-04	-2.02E-04
Biased Statistics					
Average Biased	6.16E-05	3.76E-05	3.86E-05	3.41E-05	2.79E-05
Std Dev Biased	1.94E-04	1.88E-04	1.88E-04	1.86E-04	1.84E-04
Ps90%/90% (+KTL) Biased	5.93E-04	5.53E-04	5.54E-04	5.45E-04	5.33E-04
Ps90%/90% (-KTL) Biased	-4.69E-04	-4.78E-04	-4.77E-04	-4.77E-04	-4.78E-04
Un-Biased Statistics					
Average Un-Biased	-4.64E-05	-5.74E-05	-6.72E-05	-7.98E-05	-1.04E-04
Std Dev Un-Biased	1.35E-04	1.31E-04	1.30E-04	1.29E-04	1.29E-04
Ps90%/90% (+KTL) Un-Biased	3.25E-04	3.03E-04	2.89E-04	2.73E-04	2.50E-04
Ps90%/90% (-KTL) Un-Biased	-4.18E-04	-4.18E-04	-4.23E-04	-4.32E-04	-4.57E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.106. Plot of Input Offset Voltage4 2 (V) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.106. Raw data for Input Offset Voltage4 2 (V) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage4 2 (V) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-1.62E-04	-2.06E-04	-1.97E-04	-2.02E-04	-2.09E-04
520	2.07E-04	1.96E-04	1.95E-04	1.93E-04	1.92E-04
521	-4.04E-04	-4.41E-04	-4.34E-04	-4.29E-04	-4.25E-04
522	-3.06E-04	-3.24E-04	-3.14E-04	-3.09E-04	-3.03E-04
524	2.91E-04	2.59E-04	2.46E-04	2.54E-04	2.54E-04
536	1.70E-04	1.49E-04	1.41E-04	1.33E-04	1.10E-04
537	-3.87E-04	-4.16E-04	-4.21E-04	-4.33E-04	-4.44E-04
538	-1.87E-04	-2.00E-04	-1.97E-04	-1.97E-04	-2.11E-04
539	-1.07E-04	-1.16E-04	-1.23E-04	-1.35E-04	-1.50E-04
542	-1.13E-04	-1.36E-04	-1.43E-04	-1.55E-04	-1.68E-04
543	6.84E-05	6.13E-05	6.07E-05	6.11E-05	6.21E-05
544	-6.10E-05	-6.03E-05	-6.18E-05	-6.01E-05	-5.92E-05
Biased Statistics					
Average Biased	-7.49E-05	-1.03E-04	-1.01E-04	-9.86E-05	-9.81E-05
Std Dev Biased	3.09E-04	3.14E-04	3.06E-04	3.05E-04	3.04E-04
Ps90%/90% (+KTL) Biased	7.72E-04	7.57E-04	7.37E-04	7.39E-04	7.34E-04
Ps90%/90% (-KTL) Biased	-9.22E-04	-9.64E-04	-9.39E-04	-9.36E-04	-9.31E-04
Un-Biased Statistics					
Average Un-Biased	-1.25E-04	-1.44E-04	-1.49E-04	-1.57E-04	-1.73E-04
Std Dev Un-Biased	2.00E-04	2.02E-04	2.01E-04	2.01E-04	1.97E-04
Ps90%/90% (+KTL) Un-Biased	4.23E-04	4.11E-04	4.02E-04	3.95E-04	3.68E-04
Ps90%/90% (-KTL) Un-Biased	-6.73E-04	-6.99E-04	-6.99E-04	-7.09E-04	-7.13E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.107. Plot of Input Offset Voltage4 3 (V) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



Table 5.107. Raw data for Input Offset Voltage_{4 3} (V) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage _{4 3} (V) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.33E-06	2.83E-06	6.70E-06	6.57E-06	1.06E-05
520	1.20E-04	8.56E-05	7.96E-05	7.38E-05	6.68E-05
521	-2.23E-04	-2.49E-04	-2.46E-04	-2.48E-04	-2.48E-04
522	5.70E-05	4.29E-05	4.05E-05	3.62E-05	2.96E-05
524	-1.47E-05	-4.62E-05	-7.09E-05	-8.12E-05	-9.50E-05
536	-5.24E-04	-5.40E-04	-5.46E-04	-5.56E-04	-5.86E-04
537	4.42E-05	9.71E-06	2.47E-06	-1.11E-05	-2.75E-05
538	-1.22E-04	-1.39E-04	-1.47E-04	-1.64E-04	-1.87E-04
539	-5.68E-05	-3.56E-05	-4.76E-05	-6.39E-05	-8.22E-05
542	1.61E-04	1.42E-04	1.27E-04	1.06E-04	7.99E-05
543	1.84E-04	1.79E-04	1.78E-04	1.79E-04	1.81E-04
544	4.85E-05	4.79E-05	4.76E-05	4.79E-05	4.94E-05
Biased Statistics					
Average Biased	-1.26E-05	-3.27E-05	-3.80E-05	-4.26E-05	-4.72E-05
Std Dev Biased	1.29E-04	1.30E-04	1.29E-04	1.28E-04	1.27E-04
Ps90%/90% (+KTL) Biased	3.42E-04	3.25E-04	3.15E-04	3.09E-04	3.02E-04
Ps90%/90% (-KTL) Biased	-3.67E-04	-3.90E-04	-3.91E-04	-3.95E-04	-3.96E-04
Un-Biased Statistics					
Average Un-Biased	-9.96E-05	-1.12E-04	-1.22E-04	-1.38E-04	-1.61E-04
Std Dev Un-Biased	2.61E-04	2.59E-04	2.57E-04	2.53E-04	2.57E-04
Ps90%/90% (+KTL) Un-Biased	6.15E-04	5.98E-04	5.82E-04	5.56E-04	5.43E-04
Ps90%/90% (-KTL) Un-Biased	-8.14E-04	-8.23E-04	-8.26E-04	-8.32E-04	-8.64E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.108. Plot of Input Offset Voltage4 4 (V) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.108. Raw data for Input Offset Voltage4 4 (V) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage4 4 (V) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.20E-05	-1.14E-05	-4.65E-06	-7.07E-06	-8.27E-06
520	9.13E-05	4.33E-05	4.42E-05	3.78E-05	3.76E-05
521	2.64E-04	2.21E-04	2.23E-04	2.18E-04	2.16E-04
522	7.04E-05	5.49E-05	6.40E-05	6.37E-05	6.61E-05
524	1.92E-04	1.65E-04	1.61E-04	1.71E-04	1.75E-04
536	-5.66E-05	-5.75E-05	-6.33E-05	-7.09E-05	-8.93E-05
537	-7.37E-05	-7.82E-05	-8.22E-05	-8.81E-05	-1.01E-04
538	2.55E-04	2.46E-04	2.44E-04	2.30E-04	2.13E-04
539	1.43E-05	1.21E-05	5.01E-06	-7.31E-06	-2.25E-05
542	3.93E-05	2.09E-05	1.36E-05	3.68E-06	-4.65E-06
543	4.74E-04	4.67E-04	4.64E-04	4.65E-04	4.68E-04
544	-1.15E-05	-1.12E-05	-1.15E-05	-9.84E-06	-9.84E-06
Biased Statistics					
Average Biased	1.26E-04	9.45E-05	9.76E-05	9.68E-05	9.72E-05
Std Dev Biased	1.01E-04	9.53E-05	9.24E-05	9.44E-05	9.46E-05
Ps90%/90% (+KTL) Biased	4.02E-04	3.56E-04	3.51E-04	3.55E-04	3.57E-04
Ps90%/90% (-KTL) Biased	-1.50E-04	-1.67E-04	-1.56E-04	-1.62E-04	-1.62E-04
Un-Biased Statistics					
Average Un-Biased	3.57E-05	2.87E-05	2.35E-05	1.34E-05	-1.08E-06
Std Dev Un-Biased	1.31E-04	1.29E-04	1.30E-04	1.27E-04	1.26E-04
Ps90%/90% (+KTL) Un-Biased	3.96E-04	3.82E-04	3.81E-04	3.62E-04	3.46E-04
Ps90%/90% (-KTL) Un-Biased	-3.25E-04	-3.25E-04	-3.34E-04	-3.35E-04	-3.48E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.109. Plot of Input Offset Current4 1 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.109. Raw data for Input Offset Current4 1 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current4 1 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.86E-09	5.21E-09	5.31E-09	6.56E-09	7.51E-09
520	3.15E-09	2.15E-09	2.35E-09	2.85E-09	1.26E-09
521	-6.50E-10	-1.02E-09	-1.14E-09	-5.60E-10	-2.60E-10
522	-2.82E-09	-3.26E-09	-1.70E-09	-2.67E-09	-3.49E-09
524	3.60E-10	2.00E-10	-3.20E-10	8.50E-10	1.10E-09
536	1.78E-09	1.85E-09	2.39E-09	3.10E-09	4.70E-09
537	8.40E-10	7.20E-10	1.52E-09	1.60E-09	9.00E-10
538	-2.70E-09	-2.77E-09	-3.01E-09	-2.94E-09	-2.70E-09
539	-6.85E-09	-6.83E-09	-7.95E-09	-7.61E-09	-1.04E-08
542	-4.40E-10	-1.14E-09	-1.41E-09	-1.23E-09	-1.37E-09
543	-7.90E-10	-7.90E-10	-7.70E-10	-8.00E-10	-7.50E-10
544	-6.22E-09	-6.23E-09	-6.26E-09	-6.29E-09	-6.24E-09
Biased Statistics					
Average Biased	9.80E-10	6.56E-10	9.00E-10	1.41E-09	1.22E-09
Std Dev Biased	3.05E-09	3.21E-09	2.91E-09	3.52E-09	4.00E-09
Ps90%/90% (+KTL) Biased	9.35E-09	9.47E-09	8.89E-09	1.10E-08	1.22E-08
Ps90%/90% (-KTL) Biased	-7.39E-09	-8.16E-09	-7.09E-09	-8.23E-09	-9.74E-09
Un-Biased Statistics					
Average Un-Biased	-1.47E-09	-1.63E-09	-1.69E-09	-1.42E-09	-1.76E-09
Std Dev Un-Biased	3.44E-09	3.40E-09	4.12E-09	4.19E-09	5.56E-09
Ps90%/90% (+KTL) Un-Biased	7.97E-09	7.69E-09	9.61E-09	1.01E-08	1.35E-08
Ps90%/90% (-KTL) Un-Biased	-1.09E-08	-1.10E-08	-1.30E-08	-1.29E-08	-1.70E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.110. Plot of Input Offset Current4 2 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.110. Raw data for Input Offset Current_{4 2} (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{4 2} (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	9.80E-10	9.00E-11	-5.00E-11	-2.10E-10	-2.20E-10
520	-1.58E-09	-1.93E-09	-2.36E-09	-1.80E-09	-2.23E-09
521	1.83E-09	8.60E-10	2.02E-09	1.14E-09	8.20E-10
522	-1.93E-09	-2.05E-09	-2.90E-09	-1.56E-09	-1.35E-09
524	9.00E-10	1.12E-09	6.30E-10	1.38E-09	2.46E-09
536	5.33E-09	5.70E-09	5.18E-09	6.29E-09	5.77E-09
537	-4.95E-09	-5.35E-09	-5.47E-09	-5.91E-09	-5.01E-09
538	-1.31E-09	-1.26E-09	-8.70E-10	-1.14E-09	-1.12E-09
539	2.72E-09	2.66E-09	2.88E-09	3.15E-09	2.34E-09
542	-5.49E-09	-5.35E-09	-5.14E-09	-4.78E-09	-4.52E-09
543	-1.54E-09	-1.51E-09	-1.52E-09	-1.48E-09	-1.53E-09
544	6.72E-09	6.80E-09	6.89E-09	6.88E-09	6.78E-09
Biased Statistics					
Average Biased	4.00E-11	-3.82E-10	-5.32E-10	-2.10E-10	-1.04E-10
Std Dev Biased	1.68E-09	1.52E-09	2.06E-09	1.47E-09	1.84E-09
Ps90%/90% (+KTL) Biased	4.66E-09	3.78E-09	5.13E-09	3.83E-09	4.94E-09
Ps90%/90% (-KTL) Biased	-4.58E-09	-4.54E-09	-6.19E-09	-4.25E-09	-5.14E-09
Un-Biased Statistics					
Average Un-Biased	-7.40E-10	-7.20E-10	-6.84E-10	-4.78E-10	-5.08E-10
Std Dev Un-Biased	4.73E-09	4.89E-09	4.74E-09	5.18E-09	4.59E-09
Ps90%/90% (+KTL) Un-Biased	1.22E-08	1.27E-08	1.23E-08	1.37E-08	1.21E-08
Ps90%/90% (-KTL) Un-Biased	-1.37E-08	-1.41E-08	-1.37E-08	-1.47E-08	-1.31E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.111. Plot of Input Offset Current4 3 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.111. Raw data for Input Offset Current4 3 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current4 3 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.59E-09	3.39E-09	3.76E-09	3.92E-09	4.45E-09
520	-3.20E-10	5.00E-10	1.30E-10	-2.10E-10	-4.00E-11
521	-1.62E-09	-1.17E-09	-1.00E-09	-1.38E-09	-9.80E-10
522	-1.10E-10	8.30E-10	2.60E-10	1.69E-09	3.96E-09
524	-4.29E-09	-4.10E-09	-4.52E-09	-5.41E-09	-5.33E-09
536	-3.10E-09	-3.36E-09	-3.74E-09	-3.19E-09	-3.37E-09
537	-1.89E-09	-2.06E-09	-1.55E-09	-8.60E-10	-7.60E-10
538	6.20E-10	4.50E-10	6.00E-10	5.10E-10	1.81E-09
539	4.48E-09	4.58E-09	4.77E-09	4.54E-09	4.46E-09
542	-2.79E-09	-2.76E-09	-2.94E-09	-4.58E-09	-5.66E-09
543	-1.35E-09	-1.36E-09	-1.44E-09	-1.35E-09	-1.36E-09
544	-8.40E-10	-8.60E-10	-9.00E-10	-9.10E-10	-9.10E-10
Biased Statistics					
Average Biased	-7.50E-10	-1.10E-10	-2.74E-10	-2.78E-10	4.12E-10
Std Dev Biased	2.50E-09	2.76E-09	2.97E-09	3.50E-09	4.00E-09
Ps90%/90% (+KTL) Biased	6.11E-09	7.47E-09	7.87E-09	9.32E-09	1.14E-08
Ps90%/90% (-KTL) Biased	-7.61E-09	-7.69E-09	-8.42E-09	-9.88E-09	-1.06E-08
Un-Biased Statistics					
Average Un-Biased	-5.36E-10	-6.30E-10	-5.72E-10	-7.16E-10	-7.04E-10
Std Dev Un-Biased	3.16E-09	3.25E-09	3.41E-09	3.54E-09	4.02E-09
Ps90%/90% (+KTL) Un-Biased	8.13E-09	8.29E-09	8.78E-09	9.00E-09	1.03E-08
Ps90%/90% (-KTL) Un-Biased	-9.21E-09	-9.55E-09	-9.92E-09	-1.04E-08	-1.17E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.112. Plot of Input Offset Current4 4 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.112. Raw data for Input Offset Current4 4 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current4 4 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.81E-09	1.83E-09	2.28E-09	1.81E-09	8.70E-10
520	7.10E-10	8.80E-10	1.12E-09	4.40E-10	4.10E-10
521	-3.56E-09	-4.02E-09	-2.94E-09	-3.19E-09	-2.19E-09
522	-4.20E-10	-3.50E-10	1.20E-10	-6.00E-11	4.90E-10
524	3.27E-09	3.83E-09	5.16E-09	6.99E-09	8.17E-09
536	-1.39E-09	-1.38E-09	-4.30E-10	3.30E-10	8.20E-10
537	3.03E-09	2.92E-09	3.04E-09	3.84E-09	2.81E-09
538	2.06E-09	1.32E-09	1.00E-09	1.28E-09	1.90E-10
539	3.11E-09	3.72E-09	4.66E-09	4.48E-09	4.49E-09
542	6.07E-09	6.14E-09	6.32E-09	6.29E-09	8.06E-09
543	-2.76E-09	-2.89E-09	-2.83E-09	-2.84E-09	-2.86E-09
544	-3.95E-09	-3.98E-09	-4.00E-09	-3.98E-09	-3.86E-09
Biased Statistics					
Average Biased	3.62E-10	4.34E-10	1.15E-09	1.20E-09	1.55E-09
Std Dev Biased	2.58E-09	2.92E-09	2.96E-09	3.72E-09	3.90E-09
Ps90%/90% (+KTL) Biased	7.44E-09	8.44E-09	9.28E-09	1.14E-08	1.22E-08
Ps90%/90% (-KTL) Biased	-6.72E-09	-7.58E-09	-6.98E-09	-9.00E-09	-9.13E-09
Un-Biased Statistics					
Average Un-Biased	2.58E-09	2.54E-09	2.92E-09	3.24E-09	3.27E-09
Std Dev Un-Biased	2.68E-09	2.80E-09	2.72E-09	2.42E-09	3.17E-09
Ps90%/90% (+KTL) Un-Biased	9.92E-09	1.02E-08	1.04E-08	9.89E-09	1.20E-08
Ps90%/90% (-KTL) Un-Biased	-4.77E-09	-5.13E-09	-4.53E-09	-3.40E-09	-5.41E-09
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.113. Plot of +Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.113. Raw data for +Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.03E-07	-3.16E-07	-3.24E-07	-3.41E-07	-3.69E-07
520	-3.14E-07	-3.28E-07	-3.45E-07	-3.59E-07	-3.89E-07
521	-3.17E-07	-3.30E-07	-3.47E-07	-3.63E-07	-3.92E-07
522	-3.10E-07	-3.24E-07	-3.37E-07	-3.55E-07	-3.82E-07
524	-2.97E-07	-3.11E-07	-3.25E-07	-3.45E-07	-3.72E-07
536	-2.93E-07	-3.05E-07	-3.21E-07	-3.47E-07	-3.78E-07
537	-3.12E-07	-3.25E-07	-3.46E-07	-3.67E-07	-4.00E-07
538	-2.89E-07	-3.02E-07	-3.17E-07	-3.38E-07	-3.76E-07
539	-2.93E-07	-3.05E-07	-3.22E-07	-3.48E-07	-3.81E-07
542	-3.07E-07	-3.20E-07	-3.37E-07	-3.62E-07	-3.95E-07
543	-3.09E-07	-3.12E-07	-3.12E-07	-3.12E-07	-3.11E-07
544	-3.13E-07	-3.14E-07	-3.14E-07	-3.14E-07	-3.13E-07
Biased Statistics					
Average Biased	-3.08E-07	-3.22E-07	-3.36E-07	-3.53E-07	-3.81E-07
Std Dev Biased	8.26E-09	8.13E-09	1.09E-08	9.51E-09	1.02E-08
Ps90%/90% (+KTL) Biased	-2.85E-07	-2.99E-07	-3.06E-07	-3.27E-07	-3.53E-07
Ps90%/90% (-KTL) Biased	-3.31E-07	-3.44E-07	-3.66E-07	-3.79E-07	-4.09E-07
Un-Biased Statistics					
Average Un-Biased	-2.99E-07	-3.12E-07	-3.29E-07	-3.52E-07	-3.86E-07
Std Dev Un-Biased	1.04E-08	1.06E-08	1.21E-08	1.19E-08	1.07E-08
Ps90%/90% (+KTL) Un-Biased	-2.70E-07	-2.82E-07	-2.95E-07	-3.20E-07	-3.56E-07
Ps90%/90% (-KTL) Un-Biased	-3.27E-07	-3.41E-07	-3.62E-07	-3.85E-07	-4.15E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.114. Plot of +Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.114. Raw data for +Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.12E-07	-3.24E-07	-3.31E-07	-3.49E-07	-3.71E-07
520	-2.98E-07	-3.09E-07	-3.21E-07	-3.32E-07	-3.62E-07
521	-3.34E-07	-3.49E-07	-3.60E-07	-3.72E-07	-3.95E-07
522	-3.13E-07	-3.26E-07	-3.37E-07	-3.51E-07	-3.74E-07
524	-2.84E-07	-2.96E-07	-3.05E-07	-3.17E-07	-3.38E-07
536	-2.95E-07	-3.06E-07	-3.20E-07	-3.38E-07	-3.69E-07
537	-3.07E-07	-3.20E-07	-3.34E-07	-3.58E-07	-3.83E-07
538	-2.92E-07	-3.04E-07	-3.16E-07	-3.34E-07	-3.64E-07
539	-3.15E-07	-3.27E-07	-3.46E-07	-3.66E-07	-3.94E-07
542	-3.12E-07	-3.23E-07	-3.37E-07	-3.60E-07	-3.91E-07
543	-2.85E-07	-2.87E-07	-2.88E-07	-2.87E-07	-2.87E-07
544	-3.11E-07	-3.12E-07	-3.12E-07	-3.12E-07	-3.11E-07
Biased Statistics					
Average Biased	-3.08E-07	-3.21E-07	-3.31E-07	-3.44E-07	-3.68E-07
Std Dev Biased	1.86E-08	1.97E-08	2.02E-08	2.08E-08	2.05E-08
Ps90%/90% (+KTL) Biased	-2.57E-07	-2.67E-07	-2.75E-07	-2.87E-07	-3.12E-07
Ps90%/90% (-KTL) Biased	-3.59E-07	-3.75E-07	-3.86E-07	-4.01E-07	-4.24E-07
Un-Biased Statistics					
Average Un-Biased	-3.04E-07	-3.16E-07	-3.31E-07	-3.51E-07	-3.80E-07
Std Dev Un-Biased	1.02E-08	1.05E-08	1.24E-08	1.40E-08	1.33E-08
Ps90%/90% (+KTL) Un-Biased	-2.76E-07	-2.87E-07	-2.97E-07	-3.13E-07	-3.44E-07
Ps90%/90% (-KTL) Un-Biased	-3.32E-07	-3.45E-07	-3.65E-07	-3.90E-07	-4.17E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.115. Plot of +Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.115. Raw data for +Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.09E-07	-3.22E-07	-3.30E-07	-3.48E-07	-3.72E-07
520	-2.93E-07	-3.06E-07	-3.19E-07	-3.33E-07	-3.64E-07
521	-3.35E-07	-3.52E-07	-3.64E-07	-3.77E-07	-4.01E-07
522	-3.10E-07	-3.23E-07	-3.35E-07	-3.52E-07	-3.75E-07
524	-2.88E-07	-3.01E-07	-3.12E-07	-3.28E-07	-3.56E-07
536	-2.97E-07	-3.10E-07	-3.26E-07	-3.51E-07	-3.81E-07
537	-3.07E-07	-3.20E-07	-3.36E-07	-3.63E-07	-3.95E-07
538	-2.97E-07	-3.10E-07	-3.25E-07	-3.50E-07	-3.78E-07
539	-3.13E-07	-3.25E-07	-3.41E-07	-3.66E-07	-3.97E-07
542	-3.10E-07	-3.23E-07	-3.40E-07	-3.68E-07	-4.03E-07
543	-2.86E-07	-2.88E-07	-2.88E-07	-2.88E-07	-2.87E-07
544	-3.12E-07	-3.13E-07	-3.13E-07	-3.13E-07	-3.12E-07
Biased Statistics					
Average Biased	-3.07E-07	-3.21E-07	-3.32E-07	-3.48E-07	-3.74E-07
Std Dev Biased	1.85E-08	2.00E-08	1.97E-08	1.94E-08	1.67E-08
Ps90%/90% (+KTL) Biased	-2.56E-07	-2.66E-07	-2.78E-07	-2.94E-07	-3.28E-07
Ps90%/90% (-KTL) Biased	-3.58E-07	-3.76E-07	-3.86E-07	-4.01E-07	-4.19E-07
Un-Biased Statistics					
Average Un-Biased	-3.05E-07	-3.18E-07	-3.34E-07	-3.60E-07	-3.91E-07
Std Dev Un-Biased	7.43E-09	7.27E-09	7.64E-09	8.64E-09	1.06E-08
Ps90%/90% (+KTL) Un-Biased	-2.84E-07	-2.98E-07	-3.13E-07	-3.36E-07	-3.62E-07
Ps90%/90% (-KTL) Un-Biased	-3.25E-07	-3.38E-07	-3.55E-07	-3.84E-07	-4.20E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.116. Plot of +Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.116. Raw data for +Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.05E-07	-3.17E-07	-3.24E-07	-3.40E-07	-3.64E-07
520	-3.18E-07	-3.29E-07	-3.40E-07	-3.55E-07	-3.82E-07
521	-3.19E-07	-3.30E-07	-3.47E-07	-3.61E-07	-3.83E-07
522	-3.11E-07	-3.24E-07	-3.35E-07	-3.53E-07	-3.76E-07
524	-2.96E-07	-3.08E-07	-3.18E-07	-3.32E-07	-3.61E-07
536	-2.92E-07	-3.03E-07	-3.17E-07	-3.34E-07	-3.63E-07
537	-3.10E-07	-3.22E-07	-3.35E-07	-3.57E-07	-3.86E-07
538	-2.87E-07	-2.99E-07	-3.12E-07	-3.30E-07	-3.63E-07
539	-2.90E-07	-3.00E-07	-3.13E-07	-3.31E-07	-3.64E-07
542	-3.10E-07	-3.21E-07	-3.36E-07	-3.59E-07	-3.88E-07
543	-3.13E-07	-3.16E-07	-3.16E-07	-3.16E-07	-3.16E-07
544	-3.16E-07	-3.17E-07	-3.17E-07	-3.17E-07	-3.16E-07
Biased Statistics					
Average Biased	-3.10E-07	-3.22E-07	-3.33E-07	-3.48E-07	-3.73E-07
Std Dev Biased	9.34E-09	9.09E-09	1.17E-08	1.19E-08	1.04E-08
Ps90%/90% (+KTL) Biased	-2.84E-07	-2.97E-07	-3.01E-07	-3.15E-07	-3.45E-07
Ps90%/90% (-KTL) Biased	-3.35E-07	-3.47E-07	-3.65E-07	-3.81E-07	-4.02E-07
Un-Biased Statistics					
Average Un-Biased	-2.98E-07	-3.09E-07	-3.22E-07	-3.42E-07	-3.73E-07
Std Dev Un-Biased	1.13E-08	1.14E-08	1.20E-08	1.47E-08	1.28E-08
Ps90%/90% (+KTL) Un-Biased	-2.67E-07	-2.78E-07	-2.90E-07	-3.02E-07	-3.38E-07
Ps90%/90% (-KTL) Un-Biased	-3.29E-07	-3.40E-07	-3.55E-07	-3.82E-07	-4.08E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.117. Plot of -Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.117. Raw data for -Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS4 1 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.09E-07	-3.23E-07	-3.31E-07	-3.51E-07	-3.78E-07
520	-3.19E-07	-3.32E-07	-3.48E-07	-3.63E-07	-3.93E-07
521	-3.17E-07	-3.31E-07	-3.49E-07	-3.65E-07	-3.92E-07
522	-3.08E-07	-3.23E-07	-3.37E-07	-3.53E-07	-3.80E-07
524	-2.98E-07	-3.12E-07	-3.26E-07	-3.48E-07	-3.75E-07
536	-2.96E-07	-3.08E-07	-3.25E-07	-3.51E-07	-3.83E-07
537	-3.15E-07	-3.28E-07	-3.47E-07	-3.70E-07	-4.00E-07
538	-2.87E-07	-3.00E-07	-3.16E-07	-3.37E-07	-3.74E-07
539	-2.87E-07	-3.00E-07	-3.16E-07	-3.37E-07	-3.71E-07
542	-3.08E-07	-3.21E-07	-3.36E-07	-3.62E-07	-3.93E-07
543	-3.10E-07	-3.13E-07	-3.13E-07	-3.13E-07	-3.12E-07
544	-3.08E-07	-3.09E-07	-3.09E-07	-3.09E-07	-3.08E-07
Biased Statistics					
Average Biased	-3.10E-07	-3.24E-07	-3.38E-07	-3.56E-07	-3.83E-07
Std Dev Biased	8.17E-09	7.78E-09	1.03E-08	7.62E-09	8.28E-09
Ps90%/90% (+KTL) Biased	-2.88E-07	-3.03E-07	-3.10E-07	-3.35E-07	-3.61E-07
Ps90%/90% (-KTL) Biased	-3.33E-07	-3.45E-07	-3.66E-07	-3.77E-07	-4.06E-07
Un-Biased Statistics					
Average Un-Biased	-2.99E-07	-3.11E-07	-3.28E-07	-3.51E-07	-3.84E-07
Std Dev Un-Biased	1.24E-08	1.26E-08	1.35E-08	1.48E-08	1.23E-08
Ps90%/90% (+KTL) Un-Biased	-2.65E-07	-2.77E-07	-2.91E-07	-3.11E-07	-3.50E-07
Ps90%/90% (-KTL) Un-Biased	-3.33E-07	-3.46E-07	-3.65E-07	-3.92E-07	-4.18E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.118. Plot of -Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.118. Raw data for -Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS4 2 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.14E-07	-3.26E-07	-3.33E-07	-3.49E-07	-3.72E-07
520	-2.98E-07	-3.09E-07	-3.20E-07	-3.32E-07	-3.60E-07
521	-3.37E-07	-3.52E-07	-3.62E-07	-3.76E-07	-3.97E-07
522	-3.13E-07	-3.26E-07	-3.36E-07	-3.52E-07	-3.73E-07
524	-2.86E-07	-2.98E-07	-3.07E-07	-3.20E-07	-3.45E-07
536	-3.02E-07	-3.13E-07	-3.27E-07	-3.51E-07	-3.76E-07
537	-3.04E-07	-3.16E-07	-3.30E-07	-3.52E-07	-3.81E-07
538	-2.92E-07	-3.04E-07	-3.17E-07	-3.34E-07	-3.63E-07
539	-3.20E-07	-3.31E-07	-3.50E-07	-3.69E-07	-3.96E-07
542	-3.08E-07	-3.19E-07	-3.33E-07	-3.56E-07	-3.88E-07
543	-2.85E-07	-2.87E-07	-2.87E-07	-2.87E-07	-2.87E-07
544	-3.19E-07	-3.21E-07	-3.21E-07	-3.20E-07	-3.20E-07
Biased Statistics					
Average Biased	-3.10E-07	-3.22E-07	-3.32E-07	-3.46E-07	-3.69E-07
Std Dev Biased	1.93E-08	2.04E-08	2.06E-08	2.11E-08	1.92E-08
Ps90%/90% (+KTL) Biased	-2.57E-07	-2.66E-07	-2.75E-07	-2.88E-07	-3.17E-07
Ps90%/90% (-KTL) Biased	-3.63E-07	-3.78E-07	-3.88E-07	-4.04E-07	-4.22E-07
Un-Biased Statistics					
Average Un-Biased	-3.05E-07	-3.17E-07	-3.31E-07	-3.53E-07	-3.81E-07
Std Dev Un-Biased	9.98E-09	1.00E-08	1.19E-08	1.24E-08	1.26E-08
Ps90%/90% (+KTL) Un-Biased	-2.78E-07	-2.89E-07	-2.99E-07	-3.18E-07	-3.46E-07
Ps90%/90% (-KTL) Un-Biased	-3.32E-07	-3.44E-07	-3.64E-07	-3.87E-07	-4.15E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.119. Plot of -Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.119. Raw data for -Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS4 3 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.13E-07	-3.27E-07	-3.35E-07	-3.53E-07	-3.79E-07
520	-2.94E-07	-3.08E-07	-3.21E-07	-3.35E-07	-3.66E-07
521	-3.35E-07	-3.52E-07	-3.64E-07	-3.78E-07	-4.01E-07
522	-3.11E-07	-3.26E-07	-3.37E-07	-3.53E-07	-3.80E-07
524	-2.85E-07	-2.98E-07	-3.09E-07	-3.24E-07	-3.52E-07
536	-2.95E-07	-3.08E-07	-3.24E-07	-3.50E-07	-3.80E-07
537	-3.07E-07	-3.20E-07	-3.37E-07	-3.63E-07	-3.94E-07
538	-2.99E-07	-3.12E-07	-3.27E-07	-3.53E-07	-3.81E-07
539	-3.19E-07	-3.31E-07	-3.52E-07	-3.72E-07	-4.03E-07
542	-3.09E-07	-3.22E-07	-3.39E-07	-3.63E-07	-3.97E-07
543	-2.85E-07	-2.88E-07	-2.88E-07	-2.88E-07	-2.88E-07
544	-3.12E-07	-3.13E-07	-3.13E-07	-3.13E-07	-3.12E-07
Biased Statistics					
Average Biased	-3.08E-07	-3.22E-07	-3.33E-07	-3.48E-07	-3.76E-07
Std Dev Biased	1.94E-08	2.09E-08	2.06E-08	2.05E-08	1.82E-08
Ps90%/90% (+KTL) Biased	-2.54E-07	-2.65E-07	-2.77E-07	-2.92E-07	-3.26E-07
Ps90%/90% (-KTL) Biased	-3.61E-07	-3.79E-07	-3.90E-07	-4.05E-07	-4.26E-07
Un-Biased Statistics					
Average Un-Biased	-3.06E-07	-3.18E-07	-3.36E-07	-3.60E-07	-3.91E-07
Std Dev Un-Biased	9.13E-09	9.10E-09	1.11E-08	8.75E-09	1.04E-08
Ps90%/90% (+KTL) Un-Biased	-2.81E-07	-2.94E-07	-3.05E-07	-3.36E-07	-3.62E-07
Ps90%/90% (-KTL) Un-Biased	-3.31E-07	-3.43E-07	-3.66E-07	-3.84E-07	-4.19E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.120. Plot of -Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.120. Raw data for -Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS4 4 (A) @ VS=+5V, VCM=0V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-3.08E-07	-3.20E-07	-3.28E-07	-3.45E-07	-3.69E-07
520	-3.20E-07	-3.31E-07	-3.47E-07	-3.57E-07	-3.82E-07
521	-3.16E-07	-3.28E-07	-3.40E-07	-3.58E-07	-3.82E-07
522	-3.12E-07	-3.25E-07	-3.37E-07	-3.52E-07	-3.79E-07
524	-3.01E-07	-3.13E-07	-3.25E-07	-3.40E-07	-3.69E-07
536	-2.92E-07	-3.03E-07	-3.17E-07	-3.35E-07	-3.65E-07
537	-3.14E-07	-3.26E-07	-3.40E-07	-3.61E-07	-3.87E-07
538	-2.90E-07	-3.01E-07	-3.14E-07	-3.32E-07	-3.62E-07
539	-2.94E-07	-3.05E-07	-3.20E-07	-3.37E-07	-3.68E-07
542	-3.17E-07	-3.29E-07	-3.47E-07	-3.67E-07	-3.96E-07
543	-3.12E-07	-3.14E-07	-3.15E-07	-3.15E-07	-3.14E-07
544	-3.13E-07	-3.15E-07	-3.15E-07	-3.15E-07	-3.14E-07
Biased Statistics					
Average Biased	-3.11E-07	-3.24E-07	-3.35E-07	-3.50E-07	-3.76E-07
Std Dev Biased	7.31E-09	7.05E-09	9.08E-09	7.57E-09	6.73E-09
Ps90%/90% (+KTL) Biased	-2.91E-07	-3.04E-07	-3.10E-07	-3.30E-07	-3.58E-07
Ps90%/90% (-KTL) Biased	-3.31E-07	-3.43E-07	-3.60E-07	-3.71E-07	-3.95E-07
Un-Biased Statistics					
Average Un-Biased	-3.02E-07	-3.13E-07	-3.28E-07	-3.46E-07	-3.75E-07
Std Dev Un-Biased	1.31E-08	1.33E-08	1.48E-08	1.62E-08	1.51E-08
Ps90%/90% (+KTL) Un-Biased	-2.66E-07	-2.76E-07	-2.87E-07	-3.02E-07	-3.34E-07
Ps90%/90% (-KTL) Un-Biased	-3.37E-07	-3.49E-07	-3.68E-07	-3.91E-07	-4.17E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.121. Plot of Input Offset Voltage5 1 (V) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.121. Raw data for Input Offset Voltage5 1 (V) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage5 1 (V) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.56E-04	2.34E-04	2.43E-04	2.35E-04	2.39E-04
520	5.22E-04	4.90E-04	4.90E-04	4.84E-04	4.85E-04
521	1.81E-04	1.52E-04	1.50E-04	1.44E-04	1.40E-04
522	1.69E-04	1.52E-04	1.61E-04	1.64E-04	1.70E-04
524	3.50E-04	3.28E-04	3.26E-04	3.35E-04	3.45E-04
536	1.89E-04	1.70E-04	1.66E-04	1.57E-04	1.37E-04
537	2.05E-04	1.89E-04	1.83E-04	1.75E-04	1.56E-04
538	8.43E-05	8.09E-05	7.62E-05	6.79E-05	5.76E-05
539	8.98E-06	1.24E-05	8.75E-06	2.95E-06	-1.30E-05
542	2.41E-04	2.26E-04	2.21E-04	2.16E-04	2.06E-04
543	1.00E-04	9.80E-05	9.75E-05	9.83E-05	9.77E-05
544	2.12E-04	2.11E-04	2.11E-04	2.11E-04	2.12E-04
Biased Statistics					
Average Biased	2.95E-04	2.71E-04	2.74E-04	2.72E-04	2.76E-04
Std Dev Biased	1.46E-04	1.42E-04	1.40E-04	1.40E-04	1.41E-04
Ps90%/90% (+KTL) Biased	6.95E-04	6.61E-04	6.58E-04	6.56E-04	6.62E-04
Ps90%/90% (-KTL) Biased	-1.04E-04	-1.19E-04	-1.10E-04	-1.11E-04	-1.10E-04
Un-Biased Statistics					
Average Un-Biased	1.46E-04	1.36E-04	1.31E-04	1.24E-04	1.09E-04
Std Dev Un-Biased	9.61E-05	8.72E-05	8.66E-05	8.65E-05	8.64E-05
Ps90%/90% (+KTL) Un-Biased	4.09E-04	3.75E-04	3.68E-04	3.61E-04	3.46E-04
Ps90%/90% (-KTL) Un-Biased	-1.18E-04	-1.03E-04	-1.06E-04	-1.13E-04	-1.28E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.122. Plot of Input Offset Voltage5 2 (V) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.122. Raw data for Input Offset Voltage5 2 (V) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage5 2 (V) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.71E-05	4.86E-05	5.60E-05	5.47E-05	5.54E-05
520	2.32E-04	2.30E-04	2.35E-04	2.36E-04	2.45E-04
521	-1.56E-04	-2.04E-04	-1.99E-04	-1.92E-04	-1.85E-04
522	4.01E-05	2.19E-05	3.77E-05	4.59E-05	5.92E-05
524	2.55E-04	2.04E-04	2.01E-04	2.17E-04	2.31E-04
536	1.53E-04	1.34E-04	1.31E-04	1.29E-04	1.14E-04
537	-7.98E-05	-9.07E-05	-9.58E-05	-1.01E-04	-1.08E-04
538	1.39E-04	1.29E-04	1.33E-04	1.38E-04	1.27E-04
539	2.20E-04	2.09E-04	2.08E-04	2.03E-04	1.96E-04
542	1.61E-04	1.44E-04	1.41E-04	1.33E-04	1.22E-04
543	-2.20E-04	-2.22E-04	-2.23E-04	-2.22E-04	-2.22E-04
544	6.56E-05	6.66E-05	6.56E-05	6.68E-05	6.77E-05
Biased Statistics					
Average Biased	8.97E-05	6.01E-05	6.63E-05	7.24E-05	8.09E-05
Std Dev Biased	1.66E-04	1.74E-04	1.72E-04	1.72E-04	1.74E-04
Ps90%/90% (+KTL) Biased	5.46E-04	5.37E-04	5.37E-04	5.45E-04	5.58E-04
Ps90%/90% (-KTL) Biased	-3.66E-04	-4.17E-04	-4.05E-04	-4.00E-04	-3.96E-04
Un-Biased Statistics					
Average Un-Biased	1.19E-04	1.05E-04	1.03E-04	1.00E-04	9.02E-05
Std Dev Un-Biased	1.15E-04	1.14E-04	1.16E-04	1.17E-04	1.16E-04
Ps90%/90% (+KTL) Un-Biased	4.35E-04	4.18E-04	4.21E-04	4.21E-04	4.07E-04
Ps90%/90% (-KTL) Un-Biased	-1.97E-04	-2.08E-04	-2.14E-04	-2.20E-04	-2.27E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.123. Plot of Input Offset Voltage5 3 (V) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.123. Raw data for Input Offset Voltage5 3 (V) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage5 3 (V) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.92E-04	2.41E-04	2.41E-04	2.35E-04	2.42E-04
520	5.29E-04	4.91E-04	4.89E-04	4.89E-04	4.93E-04
521	1.27E-04	1.01E-04	1.05E-04	1.04E-04	1.08E-04
522	1.69E-04	1.44E-04	1.50E-04	1.51E-04	1.53E-04
524	-4.78E-05	-7.32E-05	-8.99E-05	-9.01E-05	-9.30E-05
536	-2.50E-04	-2.66E-04	-2.69E-04	-2.74E-04	-2.95E-04
537	1.24E-04	1.02E-04	9.99E-05	9.18E-05	8.28E-05
538	1.66E-04	1.52E-04	1.50E-04	1.41E-04	1.24E-04
539	1.87E-04	2.14E-04	2.08E-04	1.97E-04	1.83E-04
542	9.24E-05	7.33E-05	6.67E-05	5.46E-05	4.38E-05
543	2.30E-04	2.29E-04	2.29E-04	2.29E-04	2.30E-04
544	2.56E-04	2.54E-04	2.55E-04	2.55E-04	2.56E-04
Biased Statistics					
Average Biased	1.94E-04	1.81E-04	1.79E-04	1.78E-04	1.80E-04
Std Dev Biased	2.09E-04	2.07E-04	2.12E-04	2.11E-04	2.13E-04
Ps90%/90% (+KTL) Biased	7.68E-04	7.50E-04	7.59E-04	7.56E-04	7.65E-04
Ps90%/90% (-KTL) Biased	-3.81E-04	-3.88E-04	-4.01E-04	-4.00E-04	-4.04E-04
Un-Biased Statistics					
Average Un-Biased	6.38E-05	5.50E-05	5.11E-05	4.21E-05	2.77E-05
Std Dev Un-Biased	1.79E-04	1.87E-04	1.87E-04	1.85E-04	1.88E-04
Ps90%/90% (+KTL) Un-Biased	5.56E-04	5.68E-04	5.63E-04	5.48E-04	5.42E-04
Ps90%/90% (-KTL) Un-Biased	-4.28E-04	-4.58E-04	-4.61E-04	-4.64E-04	-4.87E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.124. Plot of Input Offset Voltage5 4 (V) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.124. Raw data for Input Offset Voltage5 4 (V) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Voltage5 4 (V) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	Device	0	20	50	100
519	2.38E-04	2.16E-04	2.21E-04	2.18E-04	2.26E-04
520	1.40E-04	1.05E-04	1.09E-04	1.08E-04	1.17E-04
521	2.99E-04	2.63E-04	2.65E-04	2.63E-04	2.68E-04
522	1.92E-04	1.84E-04	1.94E-04	1.96E-04	2.06E-04
524	3.30E-04	3.09E-04	3.03E-04	3.16E-04	3.26E-04
536	-4.11E-05	-3.69E-05	-3.98E-05	-4.41E-05	-5.50E-05
537	3.73E-04	3.70E-04	3.64E-04	3.58E-04	3.46E-04
538	3.03E-04	3.07E-04	3.06E-04	2.97E-04	2.90E-04
539	2.71E-04	2.73E-04	2.71E-04	2.63E-04	2.54E-04
542	1.59E-04	1.44E-04	1.39E-04	1.34E-04	1.27E-04
543	3.16E-04	3.13E-04	3.13E-04	3.12E-04	3.15E-04
544	1.20E-04	1.22E-04	1.21E-04	1.22E-04	1.22E-04
Biased Statistics					
Average Biased	2.40E-04	2.15E-04	2.18E-04	2.20E-04	2.29E-04
Std Dev Biased	7.73E-05	7.78E-05	7.40E-05	7.79E-05	7.76E-05
Ps90%/90% (+KTL) Biased	4.52E-04	4.29E-04	4.21E-04	4.34E-04	4.42E-04
Ps90%/90% (-KTL) Biased	2.77E-05	2.25E-06	1.56E-05	6.76E-06	1.60E-05
Un-Biased Statistics					
Average Un-Biased	2.13E-04	2.11E-04	2.08E-04	2.02E-04	1.92E-04
Std Dev Un-Biased	1.62E-04	1.62E-04	1.61E-04	1.60E-04	1.60E-04
Ps90%/90% (+KTL) Un-Biased	6.57E-04	6.54E-04	6.51E-04	6.41E-04	6.31E-04
Ps90%/90% (-KTL) Un-Biased	-2.31E-04	-2.31E-04	-2.35E-04	-2.37E-04	-2.46E-04
Specification MIN	-8.00E-04	-9.50E-04	-9.50E-04	-9.50E-04	-9.50E-04
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	8.00E-04	9.50E-04	9.50E-04	9.50E-04	9.50E-04
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.125. Plot of Input Offset Current5 1 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.125. Raw data for Input Offset Current5 1 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current5 1 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	5.81E-09	4.08E-09	3.38E-09	2.25E-09	2.76E-09
520	2.87E-09	1.35E-09	1.02E-09	-1.40E-09	-1.08E-09
521	1.30E-09	1.21E-09	1.37E-09	1.13E-09	3.35E-09
522	6.44E-09	4.87E-09	4.59E-09	6.30E-09	6.29E-09
524	-7.60E-10	-5.80E-10	-2.58E-09	-4.96E-09	-3.13E-09
536	1.50E-10	-8.00E-11	-1.10E-10	-6.70E-10	1.15E-09
537	-9.00E-10	-3.20E-10	-5.50E-10	-6.40E-10	-2.80E-10
538	5.79E-09	4.12E-09	5.44E-09	5.04E-09	5.14E-09
539	-5.41E-09	-1.72E-09	-3.36E-09	-4.55E-09	-5.43E-09
542	3.30E-09	3.45E-09	1.59E-09	3.01E-09	2.35E-09
543	1.80E-10	2.10E-10	1.70E-10	2.00E-10	1.20E-10
544	2.60E-10	9.00E-11	1.30E-10	7.00E-11	1.10E-10
Biased Statistics					
Average Biased	3.13E-09	2.19E-09	1.56E-09	6.64E-10	1.64E-09
Std Dev Biased	3.03E-09	2.24E-09	2.74E-09	4.19E-09	3.74E-09
Ps90%/90% (+KTL) Biased	1.14E-08	8.33E-09	9.06E-09	1.22E-08	1.19E-08
Ps90%/90% (-KTL) Biased	-5.17E-09	-3.96E-09	-5.95E-09	-1.08E-08	-8.62E-09
Un-Biased Statistics					
Average Un-Biased	5.86E-10	1.09E-09	6.02E-10	4.38E-10	5.86E-10
Std Dev Un-Biased	4.27E-09	2.55E-09	3.24E-09	3.71E-09	3.91E-09
Ps90%/90% (+KTL) Un-Biased	1.23E-08	8.08E-09	9.48E-09	1.06E-08	1.13E-08
Ps90%/90% (-KTL) Un-Biased	-1.11E-08	-5.90E-09	-8.27E-09	-9.74E-09	-1.01E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.126. Plot of Input Offset Current5 2 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.126. Raw data for Input Offset Current5 2 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current5 2 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	9.80E-09	1.01E-08	8.95E-09	8.12E-09	9.33E-09
520	-1.04E-09	-1.11E-09	-1.82E-09	-3.88E-09	-3.06E-09
521	9.18E-09	1.11E-09	1.70E-09	4.79E-09	7.88E-09
522	4.17E-09	3.37E-09	5.05E-09	6.14E-09	5.41E-09
524	8.23E-09	-7.70E-10	-1.90E-09	5.20E-10	4.23E-09
536	3.68E-09	3.47E-09	3.79E-09	4.36E-09	3.57E-09
537	6.96E-09	6.60E-09	4.64E-09	6.10E-09	4.96E-09
538	1.04E-08	1.12E-08	1.15E-08	1.36E-08	1.14E-08
539	1.24E-08	1.18E-08	1.19E-08	1.19E-08	1.37E-08
542	1.70E-10	-3.10E-10	-4.10E-10	-1.67E-09	-1.30E-09
543	1.43E-09	1.64E-09	1.59E-09	1.60E-09	1.55E-09
544	8.78E-09	8.78E-09	9.10E-09	8.72E-09	8.99E-09
Biased Statistics					
Average Biased	6.07E-09	2.54E-09	2.40E-09	3.14E-09	4.76E-09
Std Dev Biased	4.54E-09	4.59E-09	4.66E-09	4.81E-09	4.81E-09
Ps90%/90% (+KTL) Biased	1.85E-08	1.51E-08	1.52E-08	1.63E-08	1.79E-08
Ps90%/90% (-KTL) Biased	-6.38E-09	-1.00E-08	-1.04E-08	-1.01E-08	-8.43E-09
Un-Biased Statistics					
Average Un-Biased	6.72E-09	6.55E-09	6.27E-09	6.85E-09	6.46E-09
Std Dev Un-Biased	4.95E-09	5.13E-09	5.28E-09	6.12E-09	6.07E-09
Ps90%/90% (+KTL) Un-Biased	2.03E-08	2.06E-08	2.08E-08	2.36E-08	2.31E-08
Ps90%/90% (-KTL) Un-Biased	-6.85E-09	-7.53E-09	-8.22E-09	-9.94E-09	-1.02E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.127. Plot of Input Offset Current5 3 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.127. Raw data for Input Offset Current5 3 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current5 3 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-7.20E-10	6.30E-09	6.27E-09	3.13E-09	5.02E-09
520	1.64E-09	1.56E-09	1.70E-09	8.80E-10	1.44E-09
521	1.26E-08	1.27E-08	1.21E-08	1.11E-08	1.40E-08
522	-1.42E-09	-2.99E-09	-1.17E-09	2.35E-09	3.68E-09
524	-5.10E-10	-2.73E-09	-4.31E-09	-4.61E-09	-4.33E-09
536	-6.36E-09	-7.53E-09	-7.75E-09	-7.98E-09	-9.28E-09
537	-5.31E-09	-7.03E-09	-6.73E-09	-5.49E-09	-5.02E-09
538	1.43E-08	1.46E-08	1.55E-08	1.64E-08	1.79E-08
539	-2.51E-09	-2.80E-09	-3.49E-09	-3.07E-09	-1.79E-09
542	4.60E-09	-1.90E-10	-2.10E-10	-2.30E-10	9.60E-10
543	-2.82E-09	-1.57E-09	-1.48E-09	-1.52E-09	-1.48E-09
544	-2.07E-09	-2.39E-09	-2.45E-09	-2.38E-09	-2.27E-09
Biased Statistics					
Average Biased	2.31E-09	2.98E-09	2.92E-09	2.57E-09	3.96E-09
Std Dev Biased	5.85E-09	6.64E-09	6.44E-09	5.65E-09	6.66E-09
Ps90%/90% (+KTL) Biased	1.83E-08	2.12E-08	2.06E-08	1.81E-08	2.22E-08
Ps90%/90% (-KTL) Biased	-1.37E-08	-1.52E-08	-1.47E-08	-1.29E-08	-1.43E-08
Un-Biased Statistics					
Average Un-Biased	9.42E-10	-5.94E-10	-5.32E-10	-7.00E-11	5.52E-10
Std Dev Un-Biased	8.60E-09	9.01E-09	9.45E-09	9.66E-09	1.04E-08
Ps90%/90% (+KTL) Un-Biased	2.45E-08	2.41E-08	2.54E-08	2.64E-08	2.91E-08
Ps90%/90% (-KTL) Un-Biased	-2.26E-08	-2.53E-08	-2.64E-08	-2.65E-08	-2.80E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.128. Plot of Input Offset Current5 4 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.128. Raw data for Input Offset Current_{5 4} (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Input Offset Current _{5 4} (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.27E-09	6.92E-09	4.70E-09	1.65E-09	3.26E-09
520	-5.44E-09	-5.86E-09	-6.81E-09	-7.33E-09	-5.36E-09
521	-1.36E-08	-1.23E-08	-1.45E-08	-1.58E-08	-1.50E-08
522	1.18E-08	1.17E-08	1.09E-08	1.08E-08	1.14E-08
524	2.89E-09	2.89E-09	-1.90E-10	-1.80E-09	-1.43E-09
536	1.23E-09	7.40E-10	3.20E-10	-1.07E-09	1.10E-10
537	-5.30E-10	-1.22E-09	-2.34E-09	-2.56E-09	-3.53E-09
538	-9.65E-09	-8.02E-09	-8.83E-09	-7.87E-09	-7.51E-09
539	8.16E-09	9.12E-09	9.98E-09	9.64E-09	9.55E-09
542	-5.60E-10	-3.00E-10	-1.14E-09	1.70E-10	-1.27E-09
543	8.00E-11	-1.00E-10	-1.00E-10	-1.00E-10	-1.20E-10
544	4.35E-09	4.43E-09	4.53E-09	4.41E-09	4.46E-09
Biased Statistics					
Average Biased	5.84E-10	6.74E-10	-1.18E-09	-2.49E-09	-1.44E-09
Std Dev Biased	1.02E-08	9.70E-09	9.90E-09	9.96E-09	9.82E-09
Ps90%/90% (+KTL) Biased	2.84E-08	2.73E-08	2.60E-08	2.48E-08	2.55E-08
Ps90%/90% (-KTL) Biased	-2.73E-08	-2.59E-08	-2.83E-08	-2.98E-08	-2.84E-08
Un-Biased Statistics					
Average Un-Biased	-2.70E-10	6.40E-11	-4.02E-10	-3.38E-10	-5.30E-10
Std Dev Un-Biased	6.35E-09	6.12E-09	6.78E-09	6.36E-09	6.33E-09
Ps90%/90% (+KTL) Un-Biased	1.72E-08	1.68E-08	1.82E-08	1.71E-08	1.68E-08
Ps90%/90% (-KTL) Un-Biased	-1.77E-08	-1.67E-08	-1.90E-08	-1.78E-08	-1.79E-08
Specification MIN	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08	-6.50E-08
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-08	6.50E-08	6.50E-08	6.50E-08	6.50E-08
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.129. Plot of +Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.129. Raw data for +Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.02E-07	3.38E-07	3.79E-07	4.30E-07	5.03E-07
520	3.24E-07	3.58E-07	4.05E-07	4.57E-07	5.31E-07
521	3.07E-07	3.48E-07	3.98E-07	4.51E-07	5.22E-07
522	3.06E-07	3.40E-07	3.86E-07	4.34E-07	5.14E-07
524	3.03E-07	3.38E-07	3.75E-07	4.30E-07	5.05E-07
536	2.98E-07	3.35E-07	3.80E-07	4.37E-07	5.18E-07
537	3.08E-07	3.39E-07	3.88E-07	4.43E-07	5.19E-07
538	2.87E-07	3.30E-07	3.74E-07	4.32E-07	5.02E-07
539	2.91E-07	3.31E-07	3.74E-07	4.30E-07	5.00E-07
542	3.06E-07	3.40E-07	3.92E-07	4.53E-07	5.29E-07
543	3.01E-07	3.02E-07	3.03E-07	3.03E-07	3.02E-07
544	2.99E-07	3.00E-07	3.00E-07	3.00E-07	2.99E-07
Biased Statistics					
Average Biased	3.08E-07	3.45E-07	3.89E-07	4.40E-07	5.15E-07
Std Dev Biased	8.94E-09	8.87E-09	1.24E-08	1.28E-08	1.18E-08
Ps90%/90% (+KTL) Biased	3.33E-07	3.69E-07	4.23E-07	4.75E-07	5.47E-07
Ps90%/90% (-KTL) Biased	2.84E-07	3.20E-07	3.55E-07	4.05E-07	4.83E-07
Un-Biased Statistics					
Average Un-Biased	2.98E-07	3.35E-07	3.82E-07	4.39E-07	5.13E-07
Std Dev Un-Biased	9.06E-09	4.38E-09	8.03E-09	9.20E-09	1.23E-08
Ps90%/90% (+KTL) Un-Biased	3.23E-07	3.47E-07	4.04E-07	4.64E-07	5.47E-07
Ps90%/90% (-KTL) Un-Biased	2.73E-07	3.23E-07	3.60E-07	4.14E-07	4.80E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.130. Plot of +Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.130. Raw data for +Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.17E-07	3.54E-07	3.96E-07	4.49E-07	5.21E-07
520	2.98E-07	3.35E-07	3.77E-07	4.25E-07	5.01E-07
521	3.21E-07	3.51E-07	3.99E-07	4.52E-07	5.21E-07
522	3.13E-07	3.45E-07	3.93E-07	4.40E-07	5.18E-07
524	2.95E-07	3.27E-07	3.61E-07	4.11E-07	4.80E-07
536	3.08E-07	3.41E-07	3.95E-07	4.51E-07	5.31E-07
537	3.10E-07	3.42E-07	3.92E-07	4.47E-07	5.23E-07
538	3.03E-07	3.41E-07	3.81E-07	4.36E-07	5.01E-07
539	3.30E-07	3.65E-07	4.18E-07	4.74E-07	5.47E-07
542	3.07E-07	3.39E-07	3.92E-07	4.51E-07	5.26E-07
543	2.99E-07	3.01E-07	3.01E-07	3.01E-07	3.00E-07
544	3.17E-07	3.17E-07	3.18E-07	3.17E-07	3.17E-07
Biased Statistics					
Average Biased	3.09E-07	3.43E-07	3.85E-07	4.35E-07	5.08E-07
Std Dev Biased	1.17E-08	1.14E-08	1.59E-08	1.72E-08	1.81E-08
Ps90%/90% (+KTL) Biased	3.41E-07	3.74E-07	4.29E-07	4.82E-07	5.58E-07
Ps90%/90% (-KTL) Biased	2.77E-07	3.11E-07	3.42E-07	3.88E-07	4.59E-07
Un-Biased Statistics					
Average Un-Biased	3.11E-07	3.45E-07	3.96E-07	4.52E-07	5.26E-07
Std Dev Un-Biased	1.05E-08	1.10E-08	1.37E-08	1.39E-08	1.65E-08
Ps90%/90% (+KTL) Un-Biased	3.40E-07	3.75E-07	4.33E-07	4.90E-07	5.71E-07
Ps90%/90% (-KTL) Un-Biased	2.83E-07	3.15E-07	3.58E-07	4.14E-07	4.81E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.131. Plot of +Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.131. Raw data for +Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.03E-07	3.45E-07	3.87E-07	4.38E-07	5.10E-07
520	2.95E-07	3.30E-07	3.71E-07	4.21E-07	4.93E-07
521	3.25E-07	3.57E-07	4.05E-07	4.60E-07	5.33E-07
522	3.05E-07	3.43E-07	3.91E-07	4.38E-07	5.20E-07
524	2.87E-07	3.24E-07	3.59E-07	4.10E-07	4.80E-07
536	2.98E-07	3.36E-07	3.80E-07	4.38E-07	5.17E-07
537	3.02E-07	3.39E-07	3.87E-07	4.45E-07	5.22E-07
538	3.13E-07	3.48E-07	3.97E-07	4.53E-07	5.24E-07
539	3.22E-07	3.54E-07	4.05E-07	4.62E-07	5.36E-07
542	3.02E-07	3.36E-07	3.89E-07	4.49E-07	5.24E-07
543	2.96E-07	2.98E-07	2.98E-07	2.98E-07	2.98E-07
544	3.02E-07	3.03E-07	3.03E-07	3.03E-07	3.02E-07
Biased Statistics					
Average Biased	3.03E-07	3.40E-07	3.83E-07	4.33E-07	5.07E-07
Std Dev Biased	1.44E-08	1.31E-08	1.78E-08	1.90E-08	2.08E-08
Ps90%/90% (+KTL) Biased	3.43E-07	3.76E-07	4.31E-07	4.86E-07	5.64E-07
Ps90%/90% (-KTL) Biased	2.64E-07	3.04E-07	3.34E-07	3.81E-07	4.50E-07
Un-Biased Statistics					
Average Un-Biased	3.07E-07	3.43E-07	3.92E-07	4.49E-07	5.25E-07
Std Dev Un-Biased	1.02E-08	7.98E-09	9.41E-09	8.84E-09	7.05E-09
Ps90%/90% (+KTL) Un-Biased	3.35E-07	3.65E-07	4.17E-07	4.74E-07	5.44E-07
Ps90%/90% (-KTL) Un-Biased	2.79E-07	3.21E-07	3.66E-07	4.25E-07	5.05E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.132. Plot of +Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.132. Raw data for +Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.04E-07	3.38E-07	3.78E-07	4.25E-07	4.99E-07
520	3.11E-07	3.44E-07	3.90E-07	4.42E-07	5.19E-07
521	3.08E-07	3.39E-07	3.86E-07	4.37E-07	5.06E-07
522	3.16E-07	3.49E-07	3.95E-07	4.40E-07	5.16E-07
524	3.09E-07	3.36E-07	3.78E-07	4.30E-07	5.03E-07
536	2.92E-07	3.34E-07	3.76E-07	4.32E-07	5.11E-07
537	3.05E-07	3.41E-07	3.88E-07	4.41E-07	5.15E-07
538	2.96E-07	3.36E-07	3.79E-07	4.36E-07	5.07E-07
539	2.98E-07	3.35E-07	3.77E-07	4.31E-07	5.01E-07
542	3.05E-07	3.41E-07	3.91E-07	4.50E-07	5.26E-07
543	3.05E-07	3.07E-07	3.07E-07	3.07E-07	3.06E-07
544	3.09E-07	3.10E-07	3.10E-07	3.10E-07	3.10E-07
Biased Statistics					
Average Biased	3.10E-07	3.41E-07	3.85E-07	4.35E-07	5.09E-07
Std Dev Biased	4.42E-09	5.06E-09	7.37E-09	7.13E-09	8.51E-09
Ps90%/90% (+KTL) Biased	3.22E-07	3.55E-07	4.06E-07	4.54E-07	5.32E-07
Ps90%/90% (-KTL) Biased	2.98E-07	3.27E-07	3.65E-07	4.15E-07	4.85E-07
Un-Biased Statistics					
Average Un-Biased	2.99E-07	3.37E-07	3.82E-07	4.38E-07	5.12E-07
Std Dev Un-Biased	5.65E-09	3.49E-09	6.73E-09	7.68E-09	9.35E-09
Ps90%/90% (+KTL) Un-Biased	3.15E-07	3.47E-07	4.01E-07	4.59E-07	5.38E-07
Ps90%/90% (-KTL) Un-Biased	2.84E-07	3.28E-07	3.64E-07	4.17E-07	4.86E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.133. Plot of -Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.133. Raw data for -Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.98E-07	3.35E-07	3.75E-07	4.28E-07	4.99E-07
520	3.22E-07	3.58E-07	4.05E-07	4.59E-07	5.35E-07
521	3.07E-07	3.46E-07	3.98E-07	4.50E-07	5.19E-07
522	3.00E-07	3.36E-07	3.83E-07	4.29E-07	5.07E-07
524	3.05E-07	3.40E-07	3.80E-07	4.36E-07	5.12E-07
536	2.99E-07	3.37E-07	3.80E-07	4.38E-07	5.17E-07
537	3.10E-07	3.40E-07	3.89E-07	4.43E-07	5.20E-07
538	2.82E-07	3.27E-07	3.70E-07	4.26E-07	4.96E-07
539	2.98E-07	3.34E-07	3.78E-07	4.35E-07	5.06E-07
542	3.04E-07	3.37E-07	3.92E-07	4.52E-07	5.26E-07
543	3.02E-07	3.03E-07	3.04E-07	3.03E-07	3.03E-07
544	3.00E-07	3.01E-07	3.01E-07	3.01E-07	3.00E-07
Biased Statistics					
Average Biased	3.06E-07	3.43E-07	3.88E-07	4.40E-07	5.14E-07
Std Dev Biased	9.46E-09	9.68E-09	1.26E-08	1.36E-08	1.36E-08
Ps90%/90% (+KTL) Biased	3.32E-07	3.69E-07	4.23E-07	4.78E-07	5.52E-07
Ps90%/90% (-KTL) Biased	2.81E-07	3.16E-07	3.54E-07	4.03E-07	4.77E-07
Un-Biased Statistics					
Average Un-Biased	2.99E-07	3.35E-07	3.82E-07	4.39E-07	5.13E-07
Std Dev Un-Biased	1.03E-08	4.79E-09	8.91E-09	9.58E-09	1.20E-08
Ps90%/90% (+KTL) Un-Biased	3.27E-07	3.48E-07	4.06E-07	4.65E-07	5.46E-07
Ps90%/90% (-KTL) Un-Biased	2.71E-07	3.22E-07	3.57E-07	4.12E-07	4.80E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.134. Plot of -Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.134. Raw data for -Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.08E-07	3.42E-07	3.87E-07	4.41E-07	5.13E-07
520	3.00E-07	3.37E-07	3.78E-07	4.31E-07	5.03E-07
521	3.13E-07	3.51E-07	3.97E-07	4.47E-07	5.14E-07
522	3.10E-07	3.42E-07	3.87E-07	4.33E-07	5.14E-07
524	2.88E-07	3.28E-07	3.64E-07	4.11E-07	4.78E-07
536	3.05E-07	3.40E-07	3.89E-07	4.47E-07	5.27E-07
537	3.04E-07	3.37E-07	3.87E-07	4.43E-07	5.19E-07
538	2.93E-07	3.31E-07	3.71E-07	4.23E-07	4.91E-07
539	3.18E-07	3.55E-07	4.05E-07	4.63E-07	5.34E-07
542	3.08E-07	3.40E-07	3.95E-07	4.53E-07	5.28E-07
543	2.99E-07	3.00E-07	3.00E-07	3.00E-07	3.00E-07
544	3.09E-07	3.10E-07	3.10E-07	3.10E-07	3.09E-07
Biased Statistics					
Average Biased	3.04E-07	3.40E-07	3.83E-07	4.32E-07	5.04E-07
Std Dev Biased	1.02E-08	8.31E-09	1.25E-08	1.34E-08	1.55E-08
Ps90%/90% (+KTL) Biased	3.32E-07	3.63E-07	4.17E-07	4.69E-07	5.47E-07
Ps90%/90% (-KTL) Biased	2.76E-07	3.17E-07	3.49E-07	3.96E-07	4.62E-07
Un-Biased Statistics					
Average Un-Biased	3.06E-07	3.41E-07	3.89E-07	4.46E-07	5.20E-07
Std Dev Un-Biased	8.93E-09	8.88E-09	1.24E-08	1.51E-08	1.71E-08
Ps90%/90% (+KTL) Un-Biased	3.30E-07	3.65E-07	4.23E-07	4.87E-07	5.67E-07
Ps90%/90% (-KTL) Un-Biased	2.81E-07	3.16E-07	3.55E-07	4.04E-07	4.73E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.135. Plot of -Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.135. Raw data for -Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.05E-07	3.41E-07	3.81E-07	4.34E-07	5.05E-07
520	2.95E-07	3.30E-07	3.69E-07	4.21E-07	4.92E-07
521	3.14E-07	3.46E-07	3.94E-07	4.49E-07	5.21E-07
522	3.07E-07	3.46E-07	3.92E-07	4.36E-07	5.17E-07
524	2.88E-07	3.28E-07	3.63E-07	4.16E-07	4.86E-07
536	3.05E-07	3.39E-07	3.89E-07	4.46E-07	5.25E-07
537	3.08E-07	3.46E-07	3.97E-07	4.52E-07	5.27E-07
538	3.00E-07	3.40E-07	3.82E-07	4.38E-07	5.07E-07
539	3.26E-07	3.59E-07	4.10E-07	4.67E-07	5.40E-07
542	2.98E-07	3.37E-07	3.91E-07	4.50E-07	5.24E-07
543	3.00E-07	3.01E-07	3.01E-07	3.00E-07	3.00E-07
544	3.05E-07	3.06E-07	3.06E-07	3.06E-07	3.06E-07
Biased Statistics					
Average Biased	3.02E-07	3.38E-07	3.80E-07	4.31E-07	5.04E-07
Std Dev Biased	1.04E-08	8.53E-09	1.37E-08	1.30E-08	1.51E-08
Ps90%/90% (+KTL) Biased	3.30E-07	3.61E-07	4.17E-07	4.67E-07	5.46E-07
Ps90%/90% (-KTL) Biased	2.73E-07	3.15E-07	3.42E-07	3.96E-07	4.63E-07
Un-Biased Statistics					
Average Un-Biased	3.07E-07	3.44E-07	3.94E-07	4.50E-07	5.25E-07
Std Dev Un-Biased	1.11E-08	8.88E-09	1.06E-08	1.05E-08	1.17E-08
Ps90%/90% (+KTL) Un-Biased	3.38E-07	3.68E-07	4.23E-07	4.79E-07	5.57E-07
Ps90%/90% (-KTL) Un-Biased	2.77E-07	3.20E-07	3.65E-07	4.22E-07	4.92E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.136. Plot of -Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.136. Raw data for -Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.98E-07	3.33E-07	3.73E-07	4.27E-07	4.96E-07
520	3.18E-07	3.50E-07	3.98E-07	4.51E-07	5.25E-07
521	3.23E-07	3.53E-07	4.01E-07	4.54E-07	5.24E-07
522	3.05E-07	3.38E-07	3.83E-07	4.30E-07	5.07E-07
524	3.07E-07	3.41E-07	3.79E-07	4.34E-07	5.06E-07
536	2.92E-07	3.34E-07	3.77E-07	4.34E-07	5.11E-07
537	3.07E-07	3.43E-07	3.92E-07	4.45E-07	5.19E-07
538	3.07E-07	3.39E-07	3.88E-07	4.44E-07	5.15E-07
539	2.91E-07	3.27E-07	3.69E-07	4.23E-07	4.93E-07
542	3.07E-07	3.39E-07	3.93E-07	4.50E-07	5.26E-07
543	3.07E-07	3.08E-07	3.08E-07	3.08E-07	3.08E-07
544	3.06E-07	3.07E-07	3.07E-07	3.07E-07	3.06E-07
Biased Statistics					
Average Biased	3.10E-07	3.43E-07	3.87E-07	4.39E-07	5.12E-07
Std Dev Biased	1.00E-08	8.42E-09	1.21E-08	1.25E-08	1.26E-08
Ps90%/90% (+KTL) Biased	3.38E-07	3.66E-07	4.20E-07	4.73E-07	5.46E-07
Ps90%/90% (-KTL) Biased	2.83E-07	3.20E-07	3.54E-07	4.05E-07	4.77E-07
Un-Biased Statistics					
Average Un-Biased	3.01E-07	3.36E-07	3.84E-07	4.39E-07	5.13E-07
Std Dev Un-Biased	8.31E-09	6.44E-09	1.04E-08	1.07E-08	1.25E-08
Ps90%/90% (+KTL) Un-Biased	3.23E-07	3.54E-07	4.12E-07	4.69E-07	5.47E-07
Ps90%/90% (-KTL) Un-Biased	2.78E-07	3.19E-07	3.55E-07	4.10E-07	4.78E-07
Specification MIN	-6.50E-07	-7.50E-07	-8.00E-07	-8.50E-07	-9.50E-07
Status	PASS	PASS	PASS	PASS	PASS
Specification MAX	6.50E-07	7.50E-07	8.00E-07	8.50E-07	9.50E-07
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.137. Plot of Output Voltage Swing High4 1 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.137. Raw data for Output Voltage Swing High4 1 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High4 1 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.43E-03	4.54E-03	4.85E-03	4.78E-03	5.03E-03
520	4.61E-03	4.59E-03	4.60E-03	4.76E-03	5.05E-03
521	4.49E-03	4.57E-03	4.73E-03	4.88E-03	4.97E-03
522	4.73E-03	4.74E-03	4.73E-03	4.91E-03	5.13E-03
524	4.56E-03	4.54E-03	4.72E-03	4.76E-03	4.97E-03
536	4.64E-03	4.62E-03	4.82E-03	4.96E-03	5.25E-03
537	4.64E-03	4.65E-03	4.87E-03	4.96E-03	5.29E-03
538	4.34E-03	4.47E-03	4.60E-03	4.83E-03	5.10E-03
539	4.49E-03	4.59E-03	4.73E-03	4.88E-03	5.17E-03
542	4.64E-03	4.65E-03	4.97E-03	5.03E-03	5.30E-03
543	4.46E-03	4.52E-03	4.43E-03	4.51E-03	4.58E-03
544	4.38E-03	4.47E-03	4.60E-03	4.49E-03	4.63E-03
Biased Statistics					
Average Biased	4.56E-03	4.60E-03	4.73E-03	4.82E-03	5.03E-03
Std Dev Biased	1.15E-04	8.32E-05	8.85E-05	7.16E-05	6.63E-05
Ps90%/90% (+KTL) Biased	4.88E-03	4.82E-03	4.97E-03	5.01E-03	5.21E-03
Ps90%/90% (-KTL) Biased	4.25E-03	4.37E-03	4.48E-03	4.62E-03	4.85E-03
Un-Biased Statistics					
Average Un-Biased	4.55E-03	4.60E-03	4.80E-03	4.93E-03	5.22E-03
Std Dev Un-Biased	1.34E-04	7.47E-05	1.41E-04	7.79E-05	8.53E-05
Ps90%/90% (+KTL) Un-Biased	4.92E-03	4.80E-03	5.18E-03	5.15E-03	5.46E-03
Ps90%/90% (-KTL) Un-Biased	4.18E-03	4.39E-03	4.41E-03	4.72E-03	4.99E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.138. Plot of Output Voltage Swing High4 2 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.138. Raw data for Output Voltage Swing High4 2 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High4 2 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.85E-03	4.65E-03	4.97E-03	4.98E-03	5.18E-03
520	4.63E-03	4.69E-03	4.63E-03	4.93E-03	4.95E-03
521	4.64E-03	4.67E-03	4.82E-03	4.83E-03	5.05E-03
522	4.54E-03	4.52E-03	4.70E-03	4.69E-03	4.93E-03
524	4.61E-03	4.42E-03	4.68E-03	4.80E-03	4.90E-03
536	4.71E-03	4.86E-03	4.89E-03	5.05E-03	5.37E-03
537	4.75E-03	4.70E-03	4.97E-03	5.17E-03	5.22E-03
538	4.49E-03	4.57E-03	4.92E-03	4.90E-03	5.08E-03
539	4.64E-03	4.67E-03	5.05E-03	5.15E-03	5.37E-03
542	4.63E-03	4.52E-03	4.89E-03	5.01E-03	5.30E-03
543	4.51E-03	4.37E-03	4.52E-03	4.46E-03	4.49E-03
544	4.48E-03	4.64E-03	4.72E-03	4.80E-03	4.63E-03
Biased Statistics					
Average Biased	4.65E-03	4.59E-03	4.76E-03	4.85E-03	5.00E-03
Std Dev Biased	1.16E-04	1.16E-04	1.37E-04	1.14E-04	1.14E-04
Ps90%/90% (+KTL) Biased	4.97E-03	4.91E-03	5.13E-03	5.16E-03	5.32E-03
Ps90%/90% (-KTL) Biased	4.34E-03	4.27E-03	4.39E-03	4.53E-03	4.69E-03
Un-Biased Statistics					
Average Un-Biased	4.64E-03	4.66E-03	4.94E-03	5.06E-03	5.27E-03
Std Dev Un-Biased	9.94E-05	1.32E-04	6.77E-05	1.10E-04	1.22E-04
Ps90%/90% (+KTL) Un-Biased	4.92E-03	5.02E-03	5.13E-03	5.36E-03	5.60E-03
Ps90%/90% (-KTL) Un-Biased	4.37E-03	4.30E-03	4.76E-03	4.75E-03	4.93E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.139. Plot of Output Voltage Swing High4 3 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.139. Raw data for Output Voltage Swing High4 3 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High4 3 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.83E-03	4.89E-03	5.02E-03	5.03E-03	5.22E-03
520	4.59E-03	4.82E-03	4.73E-03	4.98E-03	5.07E-03
521	4.64E-03	4.64E-03	4.77E-03	5.01E-03	5.03E-03
522	4.46E-03	4.50E-03	4.72E-03	4.85E-03	4.85E-03
524	4.56E-03	4.54E-03	4.68E-03	4.83E-03	4.97E-03
536	4.58E-03	4.82E-03	4.90E-03	5.10E-03	5.45E-03
537	4.80E-03	4.82E-03	4.94E-03	5.10E-03	5.27E-03
538	4.41E-03	4.59E-03	4.78E-03	4.96E-03	5.13E-03
539	4.85E-03	4.86E-03	4.99E-03	5.20E-03	5.45E-03
542	4.63E-03	4.76E-03	5.02E-03	4.88E-03	5.27E-03
543	4.41E-03	4.38E-03	4.58E-03	4.49E-03	4.48E-03
544	4.49E-03	4.52E-03	4.68E-03	4.63E-03	4.70E-03
Biased Statistics					
Average Biased	4.62E-03	4.68E-03	4.78E-03	4.94E-03	5.03E-03
Std Dev Biased	1.36E-04	1.71E-04	1.36E-04	9.33E-05	1.36E-04
Ps90%/90% (+KTL) Biased	4.99E-03	5.15E-03	5.16E-03	5.20E-03	5.40E-03
Ps90%/90% (-KTL) Biased	4.24E-03	4.21E-03	4.41E-03	4.68E-03	4.66E-03
Un-Biased Statistics					
Average Un-Biased	4.65E-03	4.77E-03	4.93E-03	5.05E-03	5.31E-03
Std Dev Un-Biased	1.77E-04	1.07E-04	9.37E-05	1.27E-04	1.37E-04
Ps90%/90% (+KTL) Un-Biased	5.14E-03	5.06E-03	5.18E-03	5.40E-03	5.69E-03
Ps90%/90% (-KTL) Un-Biased	4.17E-03	4.48E-03	4.67E-03	4.70E-03	4.94E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.140. Plot of Output Voltage Swing High4 4 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.140. Raw data for Output Voltage Swing High4 4 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High4 4 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.70E-03	4.86E-03	4.85E-03	4.95E-03	5.02E-03
520	4.73E-03	4.72E-03	4.89E-03	5.10E-03	4.98E-03
521	4.70E-03	4.74E-03	4.75E-03	4.93E-03	5.02E-03
522	4.78E-03	4.74E-03	4.99E-03	4.98E-03	5.18E-03
524	4.66E-03	4.77E-03	4.80E-03	4.78E-03	5.05E-03
536	4.64E-03	4.77E-03	4.94E-03	4.98E-03	5.32E-03
537	4.58E-03	4.81E-03	4.94E-03	5.03E-03	5.40E-03
538	4.63E-03	4.70E-03	4.72E-03	4.95E-03	5.15E-03
539	4.61E-03	4.65E-03	4.84E-03	4.98E-03	5.20E-03
542	4.68E-03	4.76E-03	4.87E-03	5.15E-03	5.30E-03
543	4.51E-03	4.57E-03	4.57E-03	4.56E-03	4.68E-03
544	4.56E-03	4.67E-03	4.63E-03	4.66E-03	4.59E-03
Biased Statistics					
Average Biased	4.71E-03	4.77E-03	4.86E-03	4.95E-03	5.05E-03
Std Dev Biased	4.45E-05	5.55E-05	9.15E-05	1.15E-04	7.68E-05
Ps90%/90% (+KTL) Biased	4.84E-03	4.92E-03	5.11E-03	5.26E-03	5.26E-03
Ps90%/90% (-KTL) Biased	4.59E-03	4.61E-03	4.60E-03	4.63E-03	4.84E-03
Un-Biased Statistics					
Average Un-Biased	4.63E-03	4.74E-03	4.86E-03	5.02E-03	5.27E-03
Std Dev Un-Biased	3.70E-05	6.30E-05	9.07E-05	7.92E-05	9.94E-05
Ps90%/90% (+KTL) Un-Biased	4.73E-03	4.91E-03	5.11E-03	5.24E-03	5.55E-03
Ps90%/90% (-KTL) Un-Biased	4.53E-03	4.57E-03	4.61E-03	4.80E-03	5.00E-03
Specification MAX	1.00E-02	2.00E-02	2.00E-02	2.00E-02	2.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.141. Plot of Output Voltage Swing High5 1 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.141. Raw data for Output Voltage Swing High5 1 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High5 1 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	6.98E-02	7.10E-02	7.22E-02	7.25E-02	7.32E-02
520	6.63E-02	6.75E-02	6.85E-02	6.93E-02	6.99E-02
521	6.62E-02	6.75E-02	6.81E-02	6.88E-02	6.95E-02
522	7.12E-02	7.23E-02	7.31E-02	7.38E-02	7.47E-02
524	6.60E-02	6.61E-02	6.76E-02	6.84E-02	6.90E-02
536	6.76E-02	6.77E-02	6.81E-02	6.87E-02	6.95E-02
537	6.85E-02	6.85E-02	6.90E-02	6.97E-02	7.03E-02
538	6.86E-02	6.90E-02	6.95E-02	7.01E-02	7.09E-02
539	6.76E-02	6.81E-02	6.84E-02	6.91E-02	6.98E-02
542	6.86E-02	6.89E-02	6.94E-02	7.00E-02	7.08E-02
543	6.67E-02	6.63E-02	6.62E-02	6.62E-02	6.64E-02
544	6.47E-02	6.46E-02	6.44E-02	6.47E-02	6.46E-02
Biased Statistics					
Average Biased	6.79E-02	6.89E-02	6.99E-02	7.06E-02	7.12E-02
Std Dev Biased	2.43E-03	2.62E-03	2.54E-03	2.41E-03	2.52E-03
Ps90%/90% (+KTL) Biased	7.45E-02	7.60E-02	7.69E-02	7.72E-02	7.82E-02
Ps90%/90% (-KTL) Biased	6.12E-02	6.17E-02	6.29E-02	6.39E-02	6.43E-02
Un-Biased Statistics					
Average Un-Biased	6.82E-02	6.84E-02	6.89E-02	6.95E-02	7.03E-02
Std Dev Un-Biased	5.23E-04	5.34E-04	6.20E-04	6.02E-04	6.23E-04
Ps90%/90% (+KTL) Un-Biased	6.96E-02	6.99E-02	7.06E-02	7.12E-02	7.20E-02
Ps90%/90% (-KTL) Un-Biased	6.67E-02	6.70E-02	6.72E-02	6.79E-02	6.85E-02
Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.142. Plot of Output Voltage Swing High5 2 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.142. Raw data for Output Voltage Swing High5 2 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High5 2 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	6.90E-02	7.00E-02	7.13E-02	7.14E-02	7.23E-02
520	6.77E-02	6.90E-02	6.97E-02	7.06E-02	7.12E-02
521	6.68E-02	6.79E-02	6.86E-02	6.93E-02	7.00E-02
522	6.57E-02	6.67E-02	6.74E-02	6.79E-02	6.87E-02
524	6.48E-02	6.51E-02	6.65E-02	6.74E-02	6.81E-02
536	6.71E-02	6.76E-02	6.76E-02	6.84E-02	6.92E-02
537	6.85E-02	6.86E-02	6.89E-02	6.96E-02	7.04E-02
538	6.55E-02	6.60E-02	6.65E-02	6.69E-02	6.78E-02
539	6.89E-02	6.90E-02	6.95E-02	7.02E-02	7.10E-02
542	6.84E-02	6.88E-02	6.92E-02	6.99E-02	7.06E-02
543	6.44E-02	6.41E-02	6.41E-02	6.40E-02	6.41E-02
544	6.52E-02	6.50E-02	6.49E-02	6.49E-02	6.49E-02
Biased Statistics					
Average Biased	6.68E-02	6.77E-02	6.87E-02	6.93E-02	7.01E-02
Std Dev Biased	1.65E-03	1.92E-03	1.89E-03	1.71E-03	1.72E-03
Ps90%/90% (+KTL) Biased	7.13E-02	7.30E-02	7.39E-02	7.40E-02	7.48E-02
Ps90%/90% (-KTL) Biased	6.23E-02	6.25E-02	6.35E-02	6.47E-02	6.53E-02
Un-Biased Statistics					
Average Un-Biased	6.77E-02	6.80E-02	6.83E-02	6.90E-02	6.98E-02
Std Dev Un-Biased	1.39E-03	1.23E-03	1.25E-03	1.34E-03	1.31E-03
Ps90%/90% (+KTL) Un-Biased	7.15E-02	7.14E-02	7.18E-02	7.27E-02	7.34E-02
Ps90%/90% (-KTL) Un-Biased	6.39E-02	6.46E-02	6.49E-02	6.53E-02	6.62E-02
Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.143. Plot of Output Voltage Swing High5 3 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.143. Raw data for Output Voltage Swing High5 3 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High5 3 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	6.89E-02	7.02E-02	7.15E-02	7.18E-02	7.23E-02
520	6.79E-02	6.91E-02	6.98E-02	7.10E-02	7.16E-02
521	6.68E-02	6.81E-02	6.89E-02	6.94E-02	7.02E-02
522	6.56E-02	6.65E-02	6.74E-02	6.80E-02	6.86E-02
524	6.51E-02	6.52E-02	6.67E-02	6.74E-02	6.82E-02
536	6.73E-02	6.73E-02	6.78E-02	6.84E-02	6.90E-02
537	6.88E-02	6.91E-02	6.94E-02	7.01E-02	7.09E-02
538	6.56E-02	6.60E-02	6.62E-02	6.69E-02	6.77E-02
539	6.88E-02	6.91E-02	6.95E-02	7.02E-02	7.10E-02
542	6.81E-02	6.83E-02	6.90E-02	6.95E-02	7.02E-02
543	6.50E-02	6.47E-02	6.47E-02	6.46E-02	6.47E-02
544	6.56E-02	6.53E-02	6.54E-02	6.55E-02	6.56E-02
Biased Statistics					
Average Biased	6.69E-02	6.78E-02	6.88E-02	6.95E-02	7.02E-02
Std Dev Biased	1.59E-03	2.00E-03	1.92E-03	1.87E-03	1.79E-03
Ps90%/90% (+KTL) Biased	7.12E-02	7.33E-02	7.41E-02	7.46E-02	7.51E-02
Ps90%/90% (-KTL) Biased	6.25E-02	6.23E-02	6.36E-02	6.44E-02	6.53E-02
Un-Biased Statistics					
Average Un-Biased	6.77E-02	6.80E-02	6.84E-02	6.90E-02	6.98E-02
Std Dev Un-Biased	1.33E-03	1.31E-03	1.38E-03	1.40E-03	1.40E-03
Ps90%/90% (+KTL) Un-Biased	7.14E-02	7.15E-02	7.22E-02	7.28E-02	7.36E-02
Ps90%/90% (-KTL) Un-Biased	6.41E-02	6.44E-02	6.46E-02	6.52E-02	6.59E-02
Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.144. Plot of Output Voltage Swing High5 4 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.144. Raw data for Output Voltage Swing High5 4 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High5 4 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.04E-02	7.14E-02	7.28E-02	7.31E-02	7.36E-02
520	6.66E-02	6.81E-02	6.86E-02	6.92E-02	6.98E-02
521	6.62E-02	6.76E-02	6.83E-02	6.93E-02	6.98E-02
522	7.11E-02	7.24E-02	7.32E-02	7.39E-02	7.46E-02
524	6.61E-02	6.63E-02	6.76E-02	6.85E-02	6.92E-02
536	6.78E-02	6.79E-02	6.84E-02	6.91E-02	6.99E-02
537	6.79E-02	6.78E-02	6.84E-02	6.91E-02	6.98E-02
538	6.90E-02	6.92E-02	6.98E-02	7.03E-02	7.13E-02
539	6.77E-02	6.81E-02	6.87E-02	6.91E-02	6.98E-02
542	6.82E-02	6.85E-02	6.90E-02	6.98E-02	7.04E-02
543	6.63E-02	6.58E-02	6.59E-02	6.59E-02	6.60E-02
544	6.47E-02	6.43E-02	6.43E-02	6.43E-02	6.45E-02
Biased Statistics					
Average Biased	6.81E-02	6.92E-02	7.01E-02	7.08E-02	7.14E-02
Std Dev Biased	2.44E-03	2.62E-03	2.67E-03	2.50E-03	2.51E-03
Ps90%/90% (+KTL) Biased	7.48E-02	7.63E-02	7.74E-02	7.76E-02	7.83E-02
Ps90%/90% (-KTL) Biased	6.14E-02	6.20E-02	6.28E-02	6.39E-02	6.45E-02
Un-Biased Statistics					
Average Un-Biased	6.81E-02	6.83E-02	6.89E-02	6.95E-02	7.03E-02
Std Dev Un-Biased	5.38E-04	5.73E-04	5.66E-04	5.67E-04	6.39E-04
Ps90%/90% (+KTL) Un-Biased	6.96E-02	6.99E-02	7.04E-02	7.10E-02	7.20E-02
Ps90%/90% (-KTL) Un-Biased	6.66E-02	6.67E-02	6.73E-02	6.79E-02	6.85E-02
Specification MAX	1.50E-01	1.50E-01	1.50E-01	1.50E-01	1.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.145. Plot of Output Voltage Swing High6 1 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.145. Raw data for Output Voltage Swing High6 1 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High6 1 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.27E-01	1.28E-01	1.30E-01	1.30E-01	1.31E-01
520	1.22E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
521	1.22E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
522	1.29E-01	1.30E-01	1.30E-01	1.31E-01	1.33E-01
524	1.22E-01	1.22E-01	1.23E-01	1.24E-01	1.26E-01
536	1.24E-01	1.24E-01	1.24E-01	1.25E-01	1.26E-01
537	1.25E-01	1.25E-01	1.25E-01	1.26E-01	1.27E-01
538	1.26E-01	1.26E-01	1.26E-01	1.27E-01	1.28E-01
539	1.24E-01	1.24E-01	1.25E-01	1.25E-01	1.26E-01
542	1.25E-01	1.25E-01	1.26E-01	1.27E-01	1.28E-01
543	1.22E-01	1.21E-01	1.21E-01	1.21E-01	1.22E-01
544	1.20E-01	1.19E-01	1.19E-01	1.19E-01	1.19E-01
Biased Statistics					
Average Biased	1.24E-01	1.25E-01	1.26E-01	1.27E-01	1.28E-01
Std Dev Biased	3.43E-03	3.38E-03	3.47E-03	3.23E-03	3.35E-03
Ps90%/90% (+KTL) Biased	1.34E-01	1.34E-01	1.36E-01	1.36E-01	1.37E-01
Ps90%/90% (-KTL) Biased	1.15E-01	1.16E-01	1.17E-01	1.18E-01	1.19E-01
Un-Biased Statistics					
Average Un-Biased	1.25E-01	1.25E-01	1.25E-01	1.26E-01	1.27E-01
Std Dev Un-Biased	8.31E-04	7.02E-04	8.57E-04	9.15E-04	8.81E-04
Ps90%/90% (+KTL) Un-Biased	1.27E-01	1.27E-01	1.28E-01	1.29E-01	1.30E-01
Ps90%/90% (-KTL) Un-Biased	1.22E-01	1.23E-01	1.23E-01	1.24E-01	1.25E-01
Specification MAX	2.50E-01	2.50E-01	2.50E-01	2.50E-01	2.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.146. Plot of Output Voltage Swing High6 2 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.146. Raw data for Output Voltage Swing High6 2 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High6 2 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.26E-01	1.27E-01	1.29E-01	1.29E-01	1.29E-01
520	1.24E-01	1.25E-01	1.26E-01	1.27E-01	1.28E-01
521	1.22E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
522	1.21E-01	1.21E-01	1.22E-01	1.23E-01	1.24E-01
524	1.20E-01	1.20E-01	1.22E-01	1.23E-01	1.24E-01
536	1.24E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
537	1.25E-01	1.25E-01	1.26E-01	1.26E-01	1.27E-01
538	1.21E-01	1.21E-01	1.22E-01	1.22E-01	1.23E-01
539	1.25E-01	1.26E-01	1.26E-01	1.27E-01	1.28E-01
542	1.25E-01	1.25E-01	1.26E-01	1.26E-01	1.28E-01
543	1.19E-01	1.19E-01	1.19E-01	1.19E-01	1.19E-01
544	1.20E-01	1.20E-01	1.19E-01	1.19E-01	1.20E-01
Biased Statistics					
Average Biased	1.22E-01	1.23E-01	1.25E-01	1.25E-01	1.26E-01
Std Dev Biased	2.38E-03	2.75E-03	2.86E-03	2.62E-03	2.46E-03
Ps90%/90% (+KTL) Biased	1.29E-01	1.31E-01	1.32E-01	1.32E-01	1.33E-01
Ps90%/90% (-KTL) Biased	1.16E-01	1.16E-01	1.17E-01	1.18E-01	1.20E-01
Un-Biased Statistics					
Average Un-Biased	1.24E-01	1.24E-01	1.25E-01	1.25E-01	1.26E-01
Std Dev Un-Biased	1.79E-03	1.86E-03	1.98E-03	1.85E-03	1.88E-03
Ps90%/90% (+KTL) Un-Biased	1.29E-01	1.29E-01	1.30E-01	1.30E-01	1.31E-01
Ps90%/90% (-KTL) Un-Biased	1.19E-01	1.19E-01	1.19E-01	1.20E-01	1.21E-01
Specification MAX	2.50E-01	2.50E-01	2.50E-01	2.50E-01	2.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.147. Plot of Output Voltage Swing High6 3 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.147. Raw data for Output Voltage Swing High6 3 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High6 3 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	1.26E-01	1.27E-01	1.29E-01	1.29E-01	1.30E-01
520	1.24E-01	1.25E-01	1.26E-01	1.27E-01	1.28E-01
521	1.22E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
522	1.21E-01	1.21E-01	1.22E-01	1.23E-01	1.24E-01
524	1.20E-01	1.20E-01	1.22E-01	1.23E-01	1.24E-01
536	1.23E-01	1.24E-01	1.24E-01	1.25E-01	1.26E-01
537	1.25E-01	1.25E-01	1.26E-01	1.27E-01	1.28E-01
538	1.21E-01	1.21E-01	1.22E-01	1.22E-01	1.24E-01
539	1.26E-01	1.26E-01	1.26E-01	1.27E-01	1.28E-01
542	1.25E-01	1.24E-01	1.25E-01	1.26E-01	1.27E-01
543	1.20E-01	1.19E-01	1.19E-01	1.19E-01	1.19E-01
544	1.21E-01	1.20E-01	1.20E-01	1.20E-01	1.20E-01
Biased Statistics					
Average Biased	1.23E-01	1.23E-01	1.25E-01	1.25E-01	1.27E-01
Std Dev Biased	2.30E-03	2.75E-03	2.80E-03	2.60E-03	2.43E-03
Ps90%/90% (+KTL) Biased	1.29E-01	1.31E-01	1.32E-01	1.33E-01	1.33E-01
Ps90%/90% (-KTL) Biased	1.16E-01	1.16E-01	1.17E-01	1.18E-01	1.20E-01
Un-Biased Statistics					
Average Un-Biased	1.24E-01	1.24E-01	1.25E-01	1.25E-01	1.26E-01
Std Dev Un-Biased	1.88E-03	1.82E-03	1.87E-03	1.93E-03	1.90E-03
Ps90%/90% (+KTL) Un-Biased	1.29E-01	1.29E-01	1.30E-01	1.31E-01	1.32E-01
Ps90%/90% (-KTL) Un-Biased	1.19E-01	1.19E-01	1.19E-01	1.20E-01	1.21E-01
Specification MAX	2.50E-01	2.50E-01	2.50E-01	2.50E-01	2.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.148. Plot of Output Voltage Swing High6 4 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.148. Raw data for Output Voltage Swing High6 4 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing High6 4 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.28E-01	1.29E-01	1.31E-01	1.31E-01	1.32E-01
520	1.22E-01	1.24E-01	1.25E-01	1.26E-01	1.26E-01
521	1.22E-01	1.23E-01	1.24E-01	1.25E-01	1.26E-01
522	1.29E-01	1.30E-01	1.31E-01	1.31E-01	1.33E-01
524	1.22E-01	1.22E-01	1.23E-01	1.24E-01	1.26E-01
536	1.24E-01	1.24E-01	1.25E-01	1.25E-01	1.26E-01
537	1.24E-01	1.24E-01	1.25E-01	1.26E-01	1.27E-01
538	1.26E-01	1.26E-01	1.27E-01	1.28E-01	1.29E-01
539	1.24E-01	1.24E-01	1.25E-01	1.26E-01	1.27E-01
542	1.25E-01	1.25E-01	1.25E-01	1.26E-01	1.27E-01
543	1.22E-01	1.21E-01	1.21E-01	1.21E-01	1.21E-01
544	1.19E-01	1.19E-01	1.19E-01	1.19E-01	1.19E-01
Biased Statistics					
Average Biased	1.25E-01	1.25E-01	1.27E-01	1.27E-01	1.28E-01
Std Dev Biased	3.37E-03	3.49E-03	3.69E-03	3.33E-03	3.45E-03
Ps90%/90% (+KTL) Biased	1.34E-01	1.35E-01	1.37E-01	1.37E-01	1.38E-01
Ps90%/90% (-KTL) Biased	1.15E-01	1.16E-01	1.16E-01	1.18E-01	1.19E-01
Un-Biased Statistics					
Average Un-Biased	1.25E-01	1.25E-01	1.25E-01	1.26E-01	1.27E-01
Std Dev Un-Biased	8.19E-04	8.19E-04	8.19E-04	8.67E-04	8.53E-04
Ps90%/90% (+KTL) Un-Biased	1.27E-01	1.27E-01	1.28E-01	1.28E-01	1.30E-01
Ps90%/90% (-KTL) Un-Biased	1.22E-01	1.23E-01	1.23E-01	1.24E-01	1.25E-01
Specification MAX	2.50E-01	2.50E-01	2.50E-01	2.50E-01	2.50E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.149. Plot of Output Voltage Swing Low4 1 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.149. Raw data for Output Voltage Swing Low4 1 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low4 1 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.46E-02	1.46E-02	1.50E-02	1.48E-02	1.50E-02
520	1.45E-02	1.48E-02	1.48E-02	1.48E-02	1.51E-02
521	1.41E-02	1.42E-02	1.44E-02	1.43E-02	1.44E-02
522	1.43E-02	1.44E-02	1.45E-02	1.45E-02	1.48E-02
524	1.46E-02	1.46E-02	1.47E-02	1.48E-02	1.51E-02
536	1.47E-02	1.45E-02	1.48E-02	1.51E-02	1.56E-02
537	1.47E-02	1.47E-02	1.49E-02	1.52E-02	1.55E-02
538	1.43E-02	1.45E-02	1.47E-02	1.49E-02	1.53E-02
539	1.46E-02	1.46E-02	1.49E-02	1.51E-02	1.56E-02
542	1.41E-02	1.43E-02	1.45E-02	1.48E-02	1.52E-02
543	1.43E-02	1.41E-02	1.41E-02	1.43E-02	1.43E-02
544	1.43E-02	1.42E-02	1.41E-02	1.41E-02	1.42E-02
Biased Statistics					
Average Biased	1.44E-02	1.45E-02	1.47E-02	1.46E-02	1.49E-02
Std Dev Biased	2.13E-04	2.09E-04	2.34E-04	2.02E-04	2.88E-04
Ps90%/90% (+KTL) Biased	1.50E-02	1.51E-02	1.53E-02	1.52E-02	1.57E-02
Ps90%/90% (-KTL) Biased	1.38E-02	1.39E-02	1.40E-02	1.41E-02	1.41E-02
Un-Biased Statistics					
Average Un-Biased	1.45E-02	1.45E-02	1.48E-02	1.50E-02	1.54E-02
Std Dev Un-Biased	2.69E-04	1.68E-04	1.73E-04	1.68E-04	1.67E-04
Ps90%/90% (+KTL) Un-Biased	1.52E-02	1.50E-02	1.52E-02	1.55E-02	1.59E-02
Ps90%/90% (-KTL) Un-Biased	1.37E-02	1.41E-02	1.43E-02	1.45E-02	1.50E-02
Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.150. Plot of Output Voltage Swing Low4 2 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.150. Raw data for Output Voltage Swing Low4 2 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low4 2 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.46E-02	1.46E-02	1.49E-02	1.47E-02	1.49E-02
520	1.51E-02	1.52E-02	1.53E-02	1.51E-02	1.56E-02
521	1.46E-02	1.47E-02	1.49E-02	1.49E-02	1.52E-02
522	1.45E-02	1.47E-02	1.48E-02	1.49E-02	1.52E-02
524	1.46E-02	1.46E-02	1.48E-02	1.50E-02	1.51E-02
536	1.48E-02	1.48E-02	1.50E-02	1.53E-02	1.58E-02
537	1.45E-02	1.44E-02	1.48E-02	1.50E-02	1.54E-02
538	1.46E-02	1.47E-02	1.49E-02	1.51E-02	1.53E-02
539	1.46E-02	1.48E-02	1.48E-02	1.51E-02	1.54E-02
542	1.43E-02	1.43E-02	1.47E-02	1.48E-02	1.53E-02
543	1.45E-02	1.45E-02	1.45E-02	1.45E-02	1.46E-02
544	1.46E-02	1.47E-02	1.47E-02	1.48E-02	1.49E-02
Biased Statistics					
Average Biased	1.47E-02	1.48E-02	1.49E-02	1.49E-02	1.52E-02
Std Dev Biased	2.18E-04	2.65E-04	2.09E-04	1.24E-04	2.43E-04
Ps90%/90% (+KTL) Biased	1.53E-02	1.55E-02	1.55E-02	1.52E-02	1.59E-02
Ps90%/90% (-KTL) Biased	1.41E-02	1.40E-02	1.44E-02	1.46E-02	1.45E-02
Un-Biased Statistics					
Average Un-Biased	1.45E-02	1.46E-02	1.48E-02	1.51E-02	1.54E-02
Std Dev Un-Biased	1.82E-04	2.46E-04	1.20E-04	1.77E-04	1.75E-04
Ps90%/90% (+KTL) Un-Biased	1.50E-02	1.53E-02	1.51E-02	1.55E-02	1.59E-02
Ps90%/90% (-KTL) Un-Biased	1.40E-02	1.39E-02	1.45E-02	1.46E-02	1.50E-02
Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.151. Plot of Output Voltage Swing Low4 3 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.151. Raw data for Output Voltage Swing Low4 3 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low4 3 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.44E-02	1.44E-02	1.48E-02	1.47E-02	1.48E-02
520	1.47E-02	1.47E-02	1.49E-02	1.48E-02	1.51E-02
521	1.42E-02	1.45E-02	1.45E-02	1.47E-02	1.47E-02
522	1.43E-02	1.44E-02	1.46E-02	1.46E-02	1.48E-02
524	1.44E-02	1.45E-02	1.47E-02	1.47E-02	1.49E-02
536	1.46E-02	1.46E-02	1.47E-02	1.51E-02	1.54E-02
537	1.42E-02	1.41E-02	1.46E-02	1.48E-02	1.51E-02
538	1.42E-02	1.42E-02	1.45E-02	1.47E-02	1.53E-02
539	1.41E-02	1.43E-02	1.46E-02	1.47E-02	1.51E-02
542	1.41E-02	1.40E-02	1.43E-02	1.47E-02	1.50E-02
543	1.43E-02	1.44E-02	1.43E-02	1.43E-02	1.44E-02
544	1.42E-02	1.41E-02	1.41E-02	1.41E-02	1.42E-02
Biased Statistics					
Average Biased	1.44E-02	1.45E-02	1.47E-02	1.47E-02	1.48E-02
Std Dev Biased	1.72E-04	1.28E-04	1.56E-04	7.71E-05	1.43E-04
Ps90%/90% (+KTL) Biased	1.49E-02	1.48E-02	1.51E-02	1.49E-02	1.52E-02
Ps90%/90% (-KTL) Biased	1.39E-02	1.41E-02	1.42E-02	1.45E-02	1.45E-02
Un-Biased Statistics					
Average Un-Biased	1.42E-02	1.42E-02	1.45E-02	1.48E-02	1.52E-02
Std Dev Un-Biased	2.19E-04	2.15E-04	1.68E-04	1.58E-04	1.67E-04
Ps90%/90% (+KTL) Un-Biased	1.48E-02	1.48E-02	1.50E-02	1.52E-02	1.56E-02
Ps90%/90% (-KTL) Un-Biased	1.36E-02	1.37E-02	1.41E-02	1.44E-02	1.47E-02
Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.152. Plot of Output Voltage Swing Low4 4 (V) @ VS=+5V IL=0mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.152. Raw data for Output Voltage Swing Low4 4 (V) @ VS=+5V IL=0mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low4 4 (V) @ VS=+5V IL=0mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.47E-02	1.49E-02	1.51E-02	1.51E-02	1.52E-02
520	1.49E-02	1.50E-02	1.52E-02	1.51E-02	1.54E-02
521	1.45E-02	1.47E-02	1.48E-02	1.48E-02	1.49E-02
522	1.46E-02	1.46E-02	1.48E-02	1.46E-02	1.52E-02
524	1.47E-02	1.44E-02	1.49E-02	1.48E-02	1.49E-02
536	1.48E-02	1.48E-02	1.51E-02	1.53E-02	1.58E-02
537	1.48E-02	1.49E-02	1.49E-02	1.53E-02	1.58E-02
538	1.45E-02	1.45E-02	1.46E-02	1.49E-02	1.54E-02
539	1.50E-02	1.50E-02	1.53E-02	1.56E-02	1.59E-02
542	1.44E-02	1.44E-02	1.47E-02	1.51E-02	1.54E-02
543	1.47E-02	1.44E-02	1.44E-02	1.44E-02	1.45E-02
544	1.44E-02	1.43E-02	1.41E-02	1.42E-02	1.43E-02
Biased Statistics					
Average Biased	1.47E-02	1.47E-02	1.50E-02	1.49E-02	1.51E-02
Std Dev Biased	1.53E-04	2.52E-04	1.90E-04	2.07E-04	2.11E-04
Ps90%/90% (+KTL) Biased	1.51E-02	1.54E-02	1.55E-02	1.54E-02	1.57E-02
Ps90%/90% (-KTL) Biased	1.43E-02	1.40E-02	1.44E-02	1.43E-02	1.45E-02
Un-Biased Statistics					
Average Un-Biased	1.47E-02	1.47E-02	1.49E-02	1.52E-02	1.57E-02
Std Dev Un-Biased	2.53E-04	2.50E-04	2.63E-04	2.63E-04	2.40E-04
Ps90%/90% (+KTL) Un-Biased	1.54E-02	1.54E-02	1.56E-02	1.60E-02	1.63E-02
Ps90%/90% (-KTL) Un-Biased	1.40E-02	1.40E-02	1.42E-02	1.45E-02	1.50E-02
Specification MAX	3.00E-02	6.00E-02	6.00E-02	6.00E-02	6.00E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.153. Plot of Output Voltage Swing Low5 1 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.153. Raw data for Output Voltage Swing Low5 1 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low5 1 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.35E-02	3.37E-02	3.40E-02	3.38E-02	3.44E-02
520	3.32E-02	3.33E-02	3.35E-02	3.35E-02	3.41E-02
521	3.27E-02	3.28E-02	3.28E-02	3.31E-02	3.32E-02
522	3.32E-02	3.31E-02	3.36E-02	3.36E-02	3.40E-02
524	3.32E-02	3.31E-02	3.35E-02	3.35E-02	3.41E-02
536	3.37E-02	3.36E-02	3.37E-02	3.40E-02	3.44E-02
537	3.33E-02	3.33E-02	3.34E-02	3.38E-02	3.41E-02
538	3.35E-02	3.35E-02	3.36E-02	3.41E-02	3.45E-02
539	3.37E-02	3.36E-02	3.39E-02	3.42E-02	3.47E-02
542	3.30E-02	3.32E-02	3.34E-02	3.35E-02	3.41E-02
543	3.29E-02	3.27E-02	3.27E-02	3.25E-02	3.28E-02
544	3.27E-02	3.28E-02	3.27E-02	3.28E-02	3.27E-02
Biased Statistics					
Average Biased	3.31E-02	3.32E-02	3.35E-02	3.35E-02	3.39E-02
Std Dev Biased	3.01E-04	3.22E-04	4.35E-04	2.35E-04	4.55E-04
Ps90%/90% (+KTL) Biased	3.40E-02	3.41E-02	3.47E-02	3.41E-02	3.52E-02
Ps90%/90% (-KTL) Biased	3.23E-02	3.23E-02	3.23E-02	3.29E-02	3.27E-02
Un-Biased Statistics					
Average Un-Biased	3.34E-02	3.35E-02	3.36E-02	3.39E-02	3.43E-02
Std Dev Un-Biased	2.85E-04	1.92E-04	2.04E-04	2.62E-04	2.64E-04
Ps90%/90% (+KTL) Un-Biased	3.42E-02	3.40E-02	3.41E-02	3.46E-02	3.51E-02
Ps90%/90% (-KTL) Un-Biased	3.27E-02	3.29E-02	3.30E-02	3.32E-02	3.36E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.154. Plot of Output Voltage Swing Low5 2 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.154. Raw data for Output Voltage Swing Low5 2 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low5 2 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.35E-02	3.35E-02	3.40E-02	3.40E-02	3.42E-02
520	3.44E-02	3.46E-02	3.47E-02	3.46E-02	3.52E-02
521	3.32E-02	3.32E-02	3.35E-02	3.36E-02	3.39E-02
522	3.33E-02	3.35E-02	3.37E-02	3.37E-02	3.41E-02
524	3.38E-02	3.36E-02	3.41E-02	3.44E-02	3.46E-02
536	3.37E-02	3.36E-02	3.39E-02	3.39E-02	3.44E-02
537	3.37E-02	3.38E-02	3.38E-02	3.42E-02	3.47E-02
538	3.37E-02	3.36E-02	3.38E-02	3.40E-02	3.44E-02
539	3.35E-02	3.36E-02	3.37E-02	3.38E-02	3.44E-02
542	3.33E-02	3.33E-02	3.36E-02	3.40E-02	3.43E-02
543	3.37E-02	3.34E-02	3.35E-02	3.35E-02	3.34E-02
544	3.37E-02	3.35E-02	3.36E-02	3.36E-02	3.36E-02
Biased Statistics					
Average Biased	3.36E-02	3.37E-02	3.40E-02	3.41E-02	3.44E-02
Std Dev Biased	4.99E-04	5.22E-04	4.54E-04	4.47E-04	5.18E-04
Ps90%/90% (+KTL) Biased	3.50E-02	3.51E-02	3.52E-02	3.53E-02	3.58E-02
Ps90%/90% (-KTL) Biased	3.23E-02	3.22E-02	3.28E-02	3.28E-02	3.30E-02
Un-Biased Statistics					
Average Un-Biased	3.36E-02	3.36E-02	3.38E-02	3.40E-02	3.44E-02
Std Dev Un-Biased	1.69E-04	1.55E-04	1.09E-04	1.38E-04	1.45E-04
Ps90%/90% (+KTL) Un-Biased	3.40E-02	3.40E-02	3.41E-02	3.44E-02	3.48E-02
Ps90%/90% (-KTL) Un-Biased	3.31E-02	3.32E-02	3.35E-02	3.36E-02	3.40E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.155. Plot of Output Voltage Swing Low5 3 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.155. Raw data for Output Voltage Swing Low5 3 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low5 3 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.33E-02	3.34E-02	3.40E-02	3.38E-02	3.41E-02
520	3.39E-02	3.39E-02	3.43E-02	3.41E-02	3.45E-02
521	3.28E-02	3.28E-02	3.32E-02	3.34E-02	3.36E-02
522	3.29E-02	3.30E-02	3.32E-02	3.34E-02	3.37E-02
524	3.33E-02	3.34E-02	3.36E-02	3.37E-02	3.41E-02
536	3.34E-02	3.33E-02	3.36E-02	3.38E-02	3.41E-02
537	3.33E-02	3.32E-02	3.34E-02	3.36E-02	3.39E-02
538	3.32E-02	3.32E-02	3.32E-02	3.34E-02	3.37E-02
539	3.30E-02	3.31E-02	3.33E-02	3.35E-02	3.39E-02
542	3.31E-02	3.31E-02	3.32E-02	3.34E-02	3.39E-02
543	3.34E-02	3.34E-02	3.32E-02	3.32E-02	3.31E-02
544	3.29E-02	3.28E-02	3.27E-02	3.29E-02	3.28E-02
Biased Statistics					
Average Biased	3.32E-02	3.33E-02	3.37E-02	3.37E-02	3.40E-02
Std Dev Biased	4.42E-04	4.26E-04	4.70E-04	3.04E-04	3.78E-04
Ps90%/90% (+KTL) Biased	3.45E-02	3.45E-02	3.50E-02	3.45E-02	3.50E-02
Ps90%/90% (-KTL) Biased	3.20E-02	3.22E-02	3.24E-02	3.29E-02	3.29E-02
Un-Biased Statistics					
Average Un-Biased	3.32E-02	3.32E-02	3.33E-02	3.35E-02	3.39E-02
Std Dev Un-Biased	1.73E-04	8.07E-05	1.54E-04	1.68E-04	1.28E-04
Ps90%/90% (+KTL) Un-Biased	3.36E-02	3.34E-02	3.37E-02	3.40E-02	3.43E-02
Ps90%/90% (-KTL) Un-Biased	3.27E-02	3.29E-02	3.29E-02	3.31E-02	3.35E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.156. Plot of Output Voltage Swing Low5 4 (V) @ VS=+5V IL=1mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.156. Raw data for Output Voltage Swing Low5 4 (V) @ VS=+5V IL=1mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low5 4 (V) @ VS=+5V IL=1mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	3.41E-02	3.41E-02	3.47E-02	3.46E-02	3.49E-02
520	3.38E-02	3.39E-02	3.40E-02	3.41E-02	3.46E-02
521	3.35E-02	3.35E-02	3.38E-02	3.39E-02	3.42E-02
522	3.36E-02	3.36E-02	3.38E-02	3.40E-02	3.46E-02
524	3.34E-02	3.33E-02	3.37E-02	3.38E-02	3.40E-02
536	3.40E-02	3.41E-02	3.42E-02	3.44E-02	3.48E-02
537	3.38E-02	3.37E-02	3.39E-02	3.41E-02	3.45E-02
538	3.39E-02	3.38E-02	3.40E-02	3.42E-02	3.47E-02
539	3.43E-02	3.43E-02	3.45E-02	3.47E-02	3.51E-02
542	3.34E-02	3.34E-02	3.36E-02	3.39E-02	3.42E-02
543	3.34E-02	3.34E-02	3.31E-02	3.33E-02	3.33E-02
544	3.32E-02	3.31E-02	3.29E-02	3.31E-02	3.31E-02
Biased Statistics					
Average Biased	3.37E-02	3.37E-02	3.40E-02	3.41E-02	3.44E-02
Std Dev Biased	3.02E-04	3.33E-04	4.03E-04	2.94E-04	3.73E-04
Ps90%/90% (+KTL) Biased	3.45E-02	3.46E-02	3.51E-02	3.49E-02	3.55E-02
Ps90%/90% (-KTL) Biased	3.28E-02	3.27E-02	3.29E-02	3.33E-02	3.34E-02
Un-Biased Statistics					
Average Un-Biased	3.39E-02	3.39E-02	3.40E-02	3.42E-02	3.46E-02
Std Dev Un-Biased	3.11E-04	3.38E-04	3.47E-04	3.18E-04	3.43E-04
Ps90%/90% (+KTL) Un-Biased	3.47E-02	3.48E-02	3.50E-02	3.51E-02	3.56E-02
Ps90%/90% (-KTL) Un-Biased	3.30E-02	3.29E-02	3.31E-02	3.34E-02	3.37E-02
Specification MAX	1.00E-01	1.00E-01	1.00E-01	1.00E-01	1.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.157. Plot of Output Voltage Swing Low6 1 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.157. Raw data for Output Voltage Swing Low6 1 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low6 1 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	7.36E-02	7.37E-02	7.44E-02	7.42E-02	7.44E-02
520	7.28E-02	7.29E-02	7.31E-02	7.34E-02	7.39E-02
521	7.19E-02	7.21E-02	7.20E-02	7.23E-02	7.27E-02
522	7.32E-02	7.30E-02	7.33E-02	7.35E-02	7.41E-02
524	7.31E-02	7.28E-02	7.31E-02	7.34E-02	7.43E-02
536	7.37E-02	7.35E-02	7.37E-02	7.41E-02	7.45E-02
537	7.30E-02	7.28E-02	7.30E-02	7.34E-02	7.36E-02
538	7.36E-02	7.37E-02	7.37E-02	7.43E-02	7.45E-02
539	7.41E-02	7.39E-02	7.41E-02	7.44E-02	7.48E-02
542	7.28E-02	7.27E-02	7.29E-02	7.32E-02	7.37E-02
543	7.22E-02	7.17E-02	7.17E-02	7.17E-02	7.17E-02
544	7.18E-02	7.16E-02	7.15E-02	7.17E-02	7.18E-02
Biased Statistics					
Average Biased	7.29E-02	7.29E-02	7.32E-02	7.33E-02	7.39E-02
Std Dev Biased	6.14E-04	5.55E-04	8.43E-04	6.76E-04	6.83E-04
Ps90%/90% (+KTL) Biased	7.46E-02	7.44E-02	7.55E-02	7.52E-02	7.57E-02
Ps90%/90% (-KTL) Biased	7.12E-02	7.14E-02	7.09E-02	7.15E-02	7.20E-02
Un-Biased Statistics					
Average Un-Biased	7.35E-02	7.33E-02	7.34E-02	7.39E-02	7.42E-02
Std Dev Un-Biased	5.36E-04	5.40E-04	5.07E-04	5.66E-04	5.50E-04
Ps90%/90% (+KTL) Un-Biased	7.49E-02	7.48E-02	7.48E-02	7.54E-02	7.57E-02
Ps90%/90% (-KTL) Un-Biased	7.20E-02	7.18E-02	7.21E-02	7.23E-02	7.27E-02
Specification MAX	2.00E-01	2.00E-01	2.00E-01	2.00E-01	2.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.158. Plot of Output Voltage Swing Low6 2 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.158. Raw data for Output Voltage Swing Low6 2 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low6 2 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	7.33E-02	7.33E-02	7.41E-02	7.38E-02	7.42E-02
520	7.48E-02	7.48E-02	7.50E-02	7.51E-02	7.59E-02
521	7.24E-02	7.25E-02	7.25E-02	7.30E-02	7.33E-02
522	7.28E-02	7.28E-02	7.29E-02	7.30E-02	7.37E-02
524	7.39E-02	7.37E-02	7.43E-02	7.44E-02	7.50E-02
536	7.38E-02	7.36E-02	7.36E-02	7.39E-02	7.44E-02
537	7.40E-02	7.37E-02	7.40E-02	7.42E-02	7.45E-02
538	7.35E-02	7.32E-02	7.35E-02	7.36E-02	7.42E-02
539	7.34E-02	7.33E-02	7.33E-02	7.37E-02	7.42E-02
542	7.33E-02	7.32E-02	7.34E-02	7.36E-02	7.41E-02
543	7.36E-02	7.32E-02	7.32E-02	7.32E-02	7.34E-02
544	7.31E-02	7.28E-02	7.28E-02	7.29E-02	7.28E-02
Biased Statistics					
Average Biased	7.34E-02	7.34E-02	7.38E-02	7.39E-02	7.44E-02
Std Dev Biased	9.64E-04	9.14E-04	1.02E-03	9.13E-04	1.04E-03
Ps90%/90% (+KTL) Biased	7.61E-02	7.59E-02	7.66E-02	7.64E-02	7.73E-02
Ps90%/90% (-KTL) Biased	7.08E-02	7.09E-02	7.10E-02	7.13E-02	7.16E-02
Un-Biased Statistics					
Average Un-Biased	7.36E-02	7.34E-02	7.35E-02	7.38E-02	7.43E-02
Std Dev Un-Biased	3.13E-04	2.33E-04	2.58E-04	2.75E-04	1.79E-04
Ps90%/90% (+KTL) Un-Biased	7.44E-02	7.40E-02	7.43E-02	7.46E-02	7.48E-02
Ps90%/90% (-KTL) Un-Biased	7.27E-02	7.28E-02	7.28E-02	7.30E-02	7.38E-02
Specification MAX	2.00E-01	2.00E-01	2.00E-01	2.00E-01	2.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.159. Plot of Output Voltage Swing Low6 3 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.159. Raw data for Output Voltage Swing Low6 3 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low6 3 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	Device	0	20	50	100
519	7.30E-02	7.30E-02	7.38E-02	7.35E-02	7.39E-02
520	7.39E-02	7.41E-02	7.44E-02	7.43E-02	7.51E-02
521	7.19E-02	7.19E-02	7.22E-02	7.25E-02	7.26E-02
522	7.19E-02	7.17E-02	7.20E-02	7.24E-02	7.26E-02
524	7.30E-02	7.29E-02	7.34E-02	7.36E-02	7.41E-02
536	7.33E-02	7.31E-02	7.31E-02	7.35E-02	7.39E-02
537	7.28E-02	7.26E-02	7.29E-02	7.32E-02	7.36E-02
538	7.23E-02	7.23E-02	7.24E-02	7.28E-02	7.31E-02
539	7.25E-02	7.25E-02	7.28E-02	7.29E-02	7.36E-02
542	7.25E-02	7.26E-02	7.27E-02	7.30E-02	7.35E-02
543	7.31E-02	7.26E-02	7.26E-02	7.28E-02	7.28E-02
544	7.21E-02	7.18E-02	7.18E-02	7.18E-02	7.18E-02
Biased Statistics					
Average Biased	7.28E-02	7.27E-02	7.31E-02	7.33E-02	7.36E-02
Std Dev Biased	8.54E-04	9.61E-04	1.03E-03	8.18E-04	1.08E-03
Ps90%/90% (+KTL) Biased	7.51E-02	7.53E-02	7.60E-02	7.55E-02	7.66E-02
Ps90%/90% (-KTL) Biased	7.04E-02	7.01E-02	7.03E-02	7.10E-02	7.07E-02
Un-Biased Statistics					
Average Un-Biased	7.27E-02	7.26E-02	7.28E-02	7.31E-02	7.35E-02
Std Dev Un-Biased	3.92E-04	2.87E-04	2.75E-04	2.83E-04	3.03E-04
Ps90%/90% (+KTL) Un-Biased	7.37E-02	7.34E-02	7.35E-02	7.39E-02	7.44E-02
Ps90%/90% (-KTL) Un-Biased	7.16E-02	7.18E-02	7.20E-02	7.23E-02	7.27E-02
Specification MAX	2.00E-01	2.00E-01	2.00E-01	2.00E-01	2.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.160. Plot of Output Voltage Swing Low6 4 (V) @ VS=+5V IL=2.5mA versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.160. Raw data for Output Voltage Swing Low6 4 (V) @ VS=+5V IL=2.5mA versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Output Voltage Swing Low6 4 (V) @ VS=+5V IL=2.5mA	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.45E-02	7.46E-02	7.52E-02	7.51E-02	7.55E-02
520	7.35E-02	7.37E-02	7.40E-02	7.40E-02	7.47E-02
521	7.31E-02	7.33E-02	7.34E-02	7.37E-02	7.40E-02
522	7.36E-02	7.36E-02	7.38E-02	7.40E-02	7.47E-02
524	7.35E-02	7.32E-02	7.35E-02	7.37E-02	7.43E-02
536	7.43E-02	7.43E-02	7.42E-02	7.46E-02	7.50E-02
537	7.37E-02	7.36E-02	7.37E-02	7.39E-02	7.44E-02
538	7.42E-02	7.41E-02	7.43E-02	7.47E-02	7.50E-02
539	7.49E-02	7.45E-02	7.48E-02	7.51E-02	7.56E-02
542	7.34E-02	7.31E-02	7.35E-02	7.37E-02	7.42E-02
543	7.30E-02	7.25E-02	7.25E-02	7.25E-02	7.26E-02
544	7.25E-02	7.23E-02	7.23E-02	7.23E-02	7.24E-02
Biased Statistics					
Average Biased	7.36E-02	7.37E-02	7.40E-02	7.41E-02	7.47E-02
Std Dev Biased	5.08E-04	5.33E-04	7.39E-04	5.58E-04	5.71E-04
Ps90%/90% (+KTL) Biased	7.50E-02	7.51E-02	7.60E-02	7.56E-02	7.62E-02
Ps90%/90% (-KTL) Biased	7.22E-02	7.22E-02	7.19E-02	7.26E-02	7.31E-02
Un-Biased Statistics					
Average Un-Biased	7.41E-02	7.39E-02	7.41E-02	7.44E-02	7.48E-02
Std Dev Un-Biased	5.70E-04	5.72E-04	5.34E-04	5.95E-04	5.72E-04
Ps90%/90% (+KTL) Un-Biased	7.57E-02	7.55E-02	7.56E-02	7.60E-02	7.64E-02
Ps90%/90% (-KTL) Un-Biased	7.25E-02	7.23E-02	7.26E-02	7.27E-02	7.32E-02
Specification MAX	2.00E-01	2.00E-01	2.00E-01	2.00E-01	2.00E-01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.161. Plot of Large Signal Voltage Gain3 1 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.161. Raw data for Large Signal Voltage Gain3 1 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain3 1 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	7.40E+03	4.33E+03	3.53E+03	3.54E+03	2.99E+03
520	4.47E+03	5.70E+03	3.54E+03	6.41E+03	2.90E+03
521	4.92E+03	3.17E+03	5.10E+03	4.63E+03	4.22E+03
522	2.20E+04	4.56E+04	5.13E+04	1.25E+04	8.78E+03
524	1.67E+04	3.75E+04	1.23E+04	8.27E+03	1.03E+04
536	1.15E+04	1.10E+04	6.57E+03	5.70E+04	6.61E+03
537	9.15E+04	9.01E+03	9.05E+03	1.67E+04	4.90E+03
538	1.49E+04	3.12E+04	1.15E+04	1.04E+04	4.26E+03
539	1.21E+04	2.05E+04	1.37E+04	1.76E+05	2.06E+04
542	4.24E+03	3.26E+03	3.22E+03	2.94E+03	2.48E+03
543	2.70E+04	2.68E+06	4.07E+04	7.30E+04	3.33E+04
544	9.94E+03	7.40E+03	8.41E+03	7.58E+03	7.39E+03
Biased Statistics					
Average Biased	1.11E+04	1.93E+04	1.51E+04	7.08E+03	5.83E+03
Std Dev Biased	7.86E+03	2.06E+04	2.05E+04	3.54E+03	3.45E+03
Ps90%/90% (+KTL) Biased	3.27E+04	7.56E+04	7.14E+04	1.68E+04	1.53E+04
Ps90%/90% (-KTL) Biased	-1.04E+04	-3.71E+04	-4.11E+04	-2.62E+03	-3.63E+03
Un-Biased Statistics					
Average Un-Biased	2.68E+04	1.50E+04	8.81E+03	5.26E+04	7.77E+03
Std Dev Un-Biased	3.63E+04	1.10E+04	4.11E+03	7.20E+04	7.31E+03
Ps90%/90% (+KTL) Un-Biased	1.26E+05	4.51E+04	2.01E+04	2.50E+05	2.78E+04
Ps90%/90% (-KTL) Un-Biased	-7.28E+04	-1.51E+04	-2.46E+03	-1.45E+05	-1.23E+04
Specification MIN	6.00E+02	3.00E+02	3.00E+02	3.00E+02	3.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.162. Plot of Large Signal Voltage Gain3 2 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.162. Raw data for Large Signal Voltage Gain3 2 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain3 2 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.47E+03	4.67E+03	5.69E+03	5.04E+03	4.14E+03
520	2.69E+03	2.53E+03	2.72E+03	2.48E+03	2.80E+03
521	4.07E+03	5.55E+03	4.30E+03	9.14E+03	3.74E+03
522	3.75E+03	4.07E+03	3.22E+03	4.20E+03	2.83E+03
524	2.68E+03	3.19E+03	2.23E+03	2.53E+03	3.28E+03
536	3.66E+03	3.60E+03	2.53E+03	3.90E+03	2.16E+03
537	2.34E+03	5.60E+03	3.43E+03	4.80E+03	3.94E+03
538	2.86E+03	2.99E+03	2.64E+03	3.33E+03	2.05E+03
539	3.04E+03	3.39E+03	3.08E+03	1.88E+03	2.64E+03
542	4.01E+03	4.38E+03	3.61E+03	5.68E+03	3.27E+03
543	2.92E+03	2.59E+03	2.76E+03	3.05E+03	2.56E+03
544	3.04E+03	3.27E+03	3.13E+03	3.31E+03	3.15E+03
Biased Statistics					
Average Biased	3.53E+03	4.00E+03	3.63E+03	4.68E+03	3.36E+03
Std Dev Biased	8.12E+02	1.19E+03	1.38E+03	2.73E+03	5.81E+02
Ps90%/90% (+KTL) Biased	5.75E+03	7.26E+03	7.42E+03	1.22E+04	4.95E+03
Ps90%/90% (-KTL) Biased	1.30E+03	7.39E+02	-1.60E+02	-2.80E+03	1.76E+03
Un-Biased Statistics					
Average Un-Biased	3.18E+03	3.99E+03	3.06E+03	3.92E+03	2.81E+03
Std Dev Un-Biased	6.63E+02	1.03E+03	4.74E+02	1.45E+03	7.96E+02
Ps90%/90% (+KTL) Un-Biased	5.00E+03	6.83E+03	4.36E+03	7.88E+03	4.99E+03
Ps90%/90% (-KTL) Un-Biased	1.36E+03	1.16E+03	1.76E+03	-5.22E+01	6.26E+02
Specification MIN	6.00E+02	3.00E+02	3.00E+02	3.00E+02	3.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.163. Plot of Large Signal Voltage Gain3 3 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.163. Raw data for Large Signal Voltage Gain3 3 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain3 3 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	2.40E+03	2.56E+03	2.92E+03	2.77E+03	1.95E+03
520	2.36E+03	2.36E+03	1.98E+03	2.60E+03	2.05E+03
521	5.01E+03	3.64E+03	4.09E+03	3.56E+03	2.75E+03
522	2.26E+03	2.31E+03	2.46E+03	2.10E+03	2.22E+03
524	2.31E+03	1.95E+03	2.33E+03	1.71E+03	1.97E+03
536	4.46E+03	4.45E+03	3.77E+03	3.59E+03	3.36E+03
537	3.70E+03	4.56E+03	3.25E+03	2.62E+03	4.90E+03
538	4.85E+03	4.04E+03	3.98E+03	2.89E+03	2.09E+03
539	1.78E+03	1.93E+03	3.59E+03	1.68E+03	2.10E+03
542	2.88E+03	2.89E+03	3.15E+03	3.79E+03	3.23E+03
543	2.52E+03	2.94E+03	3.17E+03	3.34E+03	3.80E+03
544	1.93E+03	3.30E+03	2.85E+03	3.48E+03	2.10E+03
Biased Statistics					
Average Biased	2.87E+03	2.56E+03	2.75E+03	2.55E+03	2.19E+03
Std Dev Biased	1.20E+03	6.40E+02	8.17E+02	7.04E+02	3.31E+02
Ps90%/90% (+KTL) Biased	6.16E+03	4.32E+03	4.99E+03	4.48E+03	3.09E+03
Ps90%/90% (-KTL) Biased	-4.20E+02	8.10E+02	5.11E+02	6.18E+02	1.28E+03
Un-Biased Statistics					
Average Un-Biased	3.53E+03	3.57E+03	3.55E+03	2.91E+03	3.14E+03
Std Dev Un-Biased	1.24E+03	1.13E+03	3.46E+02	8.40E+02	1.16E+03
Ps90%/90% (+KTL) Un-Biased	6.93E+03	6.68E+03	4.50E+03	5.22E+03	6.31E+03
Ps90%/90% (-KTL) Un-Biased	1.37E+02	4.65E+02	2.60E+03	6.09E+02	-3.46E+01
Specification MIN	6.00E+02	3.00E+02	3.00E+02	3.00E+02	3.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.164. Plot of Large Signal Voltage Gain3 4 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.164. Raw data for Large Signal Voltage Gain3 4 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Large Signal Voltage Gain3 4 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.66E+03	3.80E+04	1.45E+03	1.50E+03	2.74E+03
520	3.79E+03	3.44E+03	3.94E+03	2.67E+03	2.78E+03
521	1.84E+03	2.14E+03	1.85E+03	2.56E+03	1.68E+03
522	3.48E+03	3.13E+03	3.17E+03	6.90E+03	2.82E+03
524	2.23E+03	2.22E+03	2.32E+03	2.36E+03	1.75E+03
536	1.29E+03	3.54E+03	5.66E+03	3.14E+03	3.71E+03
537	2.30E+03	2.35E+03	2.39E+03	2.16E+03	1.89E+03
538	1.76E+03	2.32E+03	2.28E+03	2.30E+03	1.83E+03
539	2.71E+03	2.74E+03	3.22E+03	2.52E+03	2.42E+03
542	2.72E+03	2.84E+03	2.06E+03	2.39E+03	3.23E+03
543	2.80E+03	2.95E+03	2.66E+03	3.02E+03	2.69E+03
544	2.77E+03	2.12E+03	1.21E+04	2.91E+03	2.89E+03
Biased Statistics					
Average Biased	2.60E+03	9.78E+03	2.55E+03	3.20E+03	2.35E+03
Std Dev Biased	9.73E+02	1.58E+04	1.01E+03	2.12E+03	5.83E+02
Ps90%/90% (+KTL) Biased	5.27E+03	5.30E+04	5.31E+03	9.01E+03	3.95E+03
Ps90%/90% (-KTL) Biased	-6.76E+01	-3.34E+04	-2.21E+02	-2.61E+03	7.54E+02
Un-Biased Statistics					
Average Un-Biased	2.16E+03	2.76E+03	3.12E+03	2.50E+03	2.62E+03
Std Dev Un-Biased	6.23E+02	4.94E+02	1.49E+03	3.81E+02	8.29E+02
Ps90%/90% (+KTL) Un-Biased	3.87E+03	4.11E+03	7.20E+03	3.55E+03	4.89E+03
Ps90%/90% (-KTL) Un-Biased	4.48E+02	1.40E+03	-9.53E+02	1.46E+03	3.41E+02
Specification MIN	6.00E+02	3.00E+02	3.00E+02	3.00E+02	3.00E+02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.165. Plot of Common Mode Rejection Ratio2 1 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.165. Raw data for Common Mode Rejection Ratio2 1 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio2 1 (dB) @ VS=+5V, VCM=0 to +5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	8.85E+01	8.85E+01	8.85E+01	8.84E+01	8.82E+01
520	9.02E+01	9.01E+01	8.99E+01	8.97E+01	8.90E+01
521	8.61E+01	8.67E+01	8.65E+01	8.65E+01	8.62E+01
522	8.45E+01	8.43E+01	8.41E+01	8.38E+01	8.34E+01
524	8.31E+01	8.31E+01	8.32E+01	8.32E+01	8.30E+01
536	8.90E+01	8.89E+01	8.88E+01	8.86E+01	8.83E+01
537	8.30E+01	8.31E+01	8.30E+01	8.29E+01	8.28E+01
538	9.52E+01	9.55E+01	9.45E+01	9.39E+01	9.31E+01
539	8.60E+01	8.58E+01	8.57E+01	8.55E+01	8.53E+01
542	9.04E+01	9.02E+01	8.98E+01	8.94E+01	8.90E+01
543	8.26E+01	8.26E+01	8.26E+01	8.26E+01	8.26E+01
544	8.14E+01	8.15E+01	8.14E+01	8.14E+01	8.14E+01
Biased Statistics					
Average Biased	8.65E+01	8.65E+01	8.64E+01	8.63E+01	8.60E+01
Std Dev Biased	2.90E+00	2.89E+00	2.83E+00	2.82E+00	2.72E+00
Ps90%/90% (+KTL) Biased	9.44E+01	9.44E+01	9.42E+01	9.41E+01	9.34E+01
Ps90%/90% (-KTL) Biased	7.85E+01	7.86E+01	7.87E+01	7.86E+01	7.85E+01
Un-Biased Statistics					
Average Un-Biased	8.87E+01	8.87E+01	8.84E+01	8.81E+01	8.77E+01
Std Dev Un-Biased	4.61E+00	4.72E+00	4.34E+00	4.15E+00	3.90E+00
Ps90%/90% (+KTL) Un-Biased	1.01E+02	1.02E+02	1.00E+02	9.95E+01	9.84E+01
Ps90%/90% (-KTL) Un-Biased	7.61E+01	7.58E+01	7.65E+01	7.67E+01	7.70E+01
Specification MIN	7.60E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.166. Plot of Common Mode Rejection Ratio2 2 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.166. Raw data for Common Mode Rejection Ratio2 2 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio2 2 (dB) @ VS=+5V, VCM=0 to +5V Device	Total Dose (krad(Si))				
	0	20	50	100	200
519	8.61E+01	8.57E+01	8.57E+01	8.56E+01	8.52E+01
520	1.03E+02	1.01E+02	9.97E+01	9.91E+01	9.77E+01
521	8.60E+01	8.64E+01	8.65E+01	8.65E+01	8.63E+01
522	8.31E+01	8.31E+01	8.29E+01	8.29E+01	8.27E+01
524	1.05E+02	1.01E+02	1.03E+02	1.06E+02	1.12E+02
536	1.14E+02	1.15E+02	1.29E+02	1.38E+02	1.14E+02
537	8.41E+01	8.36E+01	8.35E+01	8.34E+01	8.33E+01
538	8.35E+01	8.35E+01	8.34E+01	8.33E+01	8.32E+01
539	8.34E+01	8.35E+01	8.33E+01	8.31E+01	8.30E+01
542	8.50E+01	8.48E+01	8.47E+01	8.46E+01	8.45E+01
543	8.50E+01	8.51E+01	8.51E+01	8.51E+01	8.51E+01
544	9.16E+01	9.16E+01	9.15E+01	9.16E+01	9.16E+01
Biased Statistics					
Average Biased	9.28E+01	9.14E+01	9.15E+01	9.20E+01	9.27E+01
Std Dev Biased	1.06E+01	8.73E+00	9.06E+00	1.00E+01	1.20E+01
Ps90%/90% (+KTL) Biased	1.22E+02	1.15E+02	1.16E+02	1.19E+02	1.26E+02
Ps90%/90% (-KTL) Biased	6.37E+01	6.74E+01	6.67E+01	6.45E+01	5.98E+01
Un-Biased Statistics					
Average Un-Biased	9.00E+01	9.02E+01	9.28E+01	9.45E+01	8.95E+01
Std Dev Un-Biased	1.34E+01	1.42E+01	2.02E+01	2.43E+01	1.35E+01
Ps90%/90% (+KTL) Un-Biased	1.27E+02	1.29E+02	1.48E+02	1.61E+02	1.27E+02
Ps90%/90% (-KTL) Un-Biased	5.32E+01	5.13E+01	3.75E+01	2.78E+01	5.24E+01
Specification MIN	7.60E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.167. Plot of Common Mode Rejection Ratio2 3 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.167. Raw data for Common Mode Rejection Ratio2 3 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio2 3 (dB) @ VS=+5V, VCM=0 to +5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	8.79E+01	8.63E+01	8.64E+01	8.66E+01	8.65E+01
520	8.16E+01	8.17E+01	8.16E+01	8.14E+01	8.13E+01
521	8.31E+01	8.31E+01	8.31E+01	8.30E+01	8.29E+01
522	9.25E+01	9.34E+01	9.28E+01	9.23E+01	9.17E+01
524	1.06E+02	1.09E+02	1.15E+02	1.40E+02	1.14E+02
536	8.53E+01	8.53E+01	8.51E+01	8.50E+01	8.49E+01
537	9.57E+01	9.44E+01	9.41E+01	9.35E+01	9.29E+01
538	8.47E+01	8.46E+01	8.45E+01	8.43E+01	8.41E+01
539	8.60E+01	8.58E+01	8.56E+01	8.55E+01	8.53E+01
542	9.80E+01	9.84E+01	9.96E+01	1.02E+02	1.04E+02
543	9.94E+01	9.89E+01	9.88E+01	9.89E+01	9.89E+01
544	8.74E+01	8.74E+01	8.73E+01	8.73E+01	8.73E+01
Biased Statistics					
Average Biased	9.02E+01	9.06E+01	9.17E+01	9.66E+01	9.13E+01
Std Dev Biased	9.78E+00	1.11E+01	1.35E+01	2.44E+01	1.33E+01
Ps90%/90% (+KTL) Biased	1.17E+02	1.21E+02	1.29E+02	1.63E+02	1.28E+02
Ps90%/90% (-KTL) Biased	6.34E+01	6.01E+01	5.46E+01	2.97E+01	5.49E+01
Un-Biased Statistics					
Average Un-Biased	8.99E+01	8.97E+01	8.98E+01	9.00E+01	9.03E+01
Std Dev Un-Biased	6.38E+00	6.30E+00	6.76E+00	7.52E+00	8.61E+00
Ps90%/90% (+KTL) Un-Biased	1.07E+02	1.07E+02	1.08E+02	1.11E+02	1.14E+02
Ps90%/90% (-KTL) Un-Biased	7.24E+01	7.24E+01	7.13E+01	6.94E+01	6.67E+01
Specification MIN	7.60E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.168. Plot of Common Mode Rejection Ratio2 4 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.168. Raw data for Common Mode Rejection Ratio2 4 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Common Mode Rejection Ratio2 4 (dB) @ VS=+5V, VCM=0 to +5V Device	Total Dose (krad(Si))				
	0	20	50	100	200
519	8.67E+01	8.67E+01	8.66E+01	8.67E+01	8.65E+01
520	9.94E+01	9.74E+01	9.70E+01	9.62E+01	9.53E+01
521	1.00E+02	9.95E+01	9.91E+01	9.84E+01	9.74E+01
522	9.19E+01	9.14E+01	9.13E+01	9.10E+01	9.06E+01
524	9.07E+01	9.03E+01	9.03E+01	9.02E+01	8.98E+01
536	1.10E+02	1.07E+02	1.06E+02	1.05E+02	1.03E+02
537	8.09E+01	8.08E+01	8.09E+01	8.09E+01	8.09E+01
538	9.92E+01	9.74E+01	9.72E+01	9.62E+01	9.56E+01
539	8.56E+01	8.55E+01	8.53E+01	8.52E+01	8.50E+01
542	9.20E+01	9.18E+01	9.16E+01	9.15E+01	9.13E+01
543	9.06E+01	9.08E+01	9.09E+01	9.09E+01	9.08E+01
544	9.13E+01	9.12E+01	9.11E+01	9.12E+01	9.12E+01
Biased Statistics					
Average Biased	9.38E+01	9.30E+01	9.29E+01	9.25E+01	9.19E+01
Std Dev Biased	5.89E+00	5.28E+00	5.13E+00	4.72E+00	4.40E+00
Ps90%/90% (+KTL) Biased	1.10E+02	1.08E+02	1.07E+02	1.05E+02	1.04E+02
Ps90%/90% (-KTL) Biased	7.77E+01	7.86E+01	7.88E+01	7.96E+01	7.98E+01
Un-Biased Statistics					
Average Un-Biased	9.34E+01	9.26E+01	9.22E+01	9.17E+01	9.11E+01
Std Dev Un-Biased	1.13E+01	1.03E+01	9.94E+00	9.30E+00	8.62E+00
Ps90%/90% (+KTL) Un-Biased	1.24E+02	1.21E+02	1.19E+02	1.17E+02	1.15E+02
Ps90%/90% (-KTL) Un-Biased	6.24E+01	6.43E+01	6.50E+01	6.62E+01	6.75E+01
Specification MIN	7.60E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.169. Plot of CMRR Match2 1 to 4 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.169. Raw data for CMRR Match2 1 to 4 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

CMRR Match2 1 to 4 (dB) @ VS=+5V, VCM=0 to +5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.01E+02	1.01E+02	1.01E+02	1.02E+02	1.01E+02
520	9.39E+01	9.50E+01	9.49E+01	9.52E+01	9.47E+01
521	8.80E+01	8.89E+01	8.88E+01	8.90E+01	8.90E+01
522	8.94E+01	8.93E+01	8.91E+01	8.87E+01	8.85E+01
524	8.77E+01	8.81E+01	8.83E+01	8.84E+01	8.83E+01
536	8.99E+01	9.01E+01	9.00E+01	9.01E+01	9.01E+01
537	9.39E+01	9.38E+01	9.41E+01	9.44E+01	9.47E+01
538	1.04E+02	1.10E+02	1.06E+02	1.06E+02	1.05E+02
539	1.13E+02	1.14E+02	1.13E+02	1.14E+02	1.15E+02
542	1.06E+02	1.05E+02	1.05E+02	1.03E+02	1.01E+02
543	7.97E+01	7.98E+01	7.98E+01	7.98E+01	7.98E+01
544	8.48E+01	8.49E+01	8.49E+01	8.49E+01	8.48E+01
Biased Statistics					
Average Biased	9.21E+01	9.25E+01	9.23E+01	9.26E+01	9.24E+01
Std Dev Biased	5.80E+00	5.49E+00	5.33E+00	5.86E+00	5.66E+00
Ps90%/90% (+KTL) Biased	1.08E+02	1.08E+02	1.07E+02	1.09E+02	1.08E+02
Ps90%/90% (-KTL) Biased	7.62E+01	7.74E+01	7.77E+01	7.65E+01	7.68E+01
Un-Biased Statistics					
Average Un-Biased	1.01E+02	1.03E+02	1.02E+02	1.02E+02	1.01E+02
Std Dev Un-Biased	9.55E+00	1.04E+01	9.34E+00	9.45E+00	9.55E+00
Ps90%/90% (+KTL) Un-Biased	1.28E+02	1.31E+02	1.27E+02	1.27E+02	1.27E+02
Ps90%/90% (-KTL) Un-Biased	7.53E+01	7.42E+01	7.59E+01	7.56E+01	7.51E+01
Specification MIN	7.50E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.170. Plot of CMRR Match2 2 to 3 (dB) @ VS=+5V, VCM=0 to +5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.170. Raw data for CMRR Match2 2 to 3 (dB) @ VS=+5V, VCM=0 to +5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

CMRR Match2 2 to 3 (dB) @ VS=+5V, VCM=0 to +5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.01E+02	1.09E+02	1.08E+02	1.05E+02	1.03E+02
520	8.24E+01	8.27E+01	8.27E+01	8.27E+01	8.27E+01
521	9.40E+01	9.29E+01	9.28E+01	9.26E+01	9.26E+01
522	8.67E+01	8.62E+01	8.63E+01	8.64E+01	8.65E+01
524	1.28E+02	1.05E+02	1.05E+02	1.06E+02	1.07E+02
536	8.49E+01	8.50E+01	8.51E+01	8.50E+01	8.52E+01
537	8.67E+01	8.65E+01	8.66E+01	8.66E+01	8.67E+01
538	1.01E+02	1.01E+02	1.02E+02	1.02E+02	1.03E+02
539	9.53E+01	9.63E+01	9.60E+01	9.55E+01	9.54E+01
542	8.33E+01	8.32E+01	8.33E+01	8.35E+01	8.36E+01
543	8.35E+01	8.35E+01	8.35E+01	8.35E+01	8.35E+01
544	9.57E+01	9.59E+01	9.55E+01	9.56E+01	9.56E+01
Biased Statistics					
Average Biased	9.84E+01	9.52E+01	9.50E+01	9.45E+01	9.42E+01
Std Dev Biased	1.82E+01	1.16E+01	1.12E+01	1.06E+01	1.02E+01
Ps90%/90% (+KTL) Biased	1.48E+02	1.27E+02	1.26E+02	1.23E+02	1.22E+02
Ps90%/90% (-KTL) Biased	4.86E+01	6.35E+01	6.42E+01	6.56E+01	6.61E+01
Un-Biased Statistics					
Average Un-Biased	9.03E+01	9.05E+01	9.06E+01	9.06E+01	9.08E+01
Std Dev Un-Biased	7.64E+00	7.95E+00	8.04E+00	8.08E+00	8.18E+00
Ps90%/90% (+KTL) Un-Biased	1.11E+02	1.12E+02	1.13E+02	1.13E+02	1.13E+02
Ps90%/90% (-KTL) Un-Biased	6.93E+01	6.87E+01	6.85E+01	6.85E+01	6.83E+01
Specification MIN	7.50E+01	7.00E+01	7.00E+01	7.00E+01	7.00E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.171. Plot of Power Supply Rejection Ratio2 1 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.171. Raw data for Power Supply Rejection Ratio2 1 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio2 1 (dB) @ VS=+4.5V to +12V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
	520	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	521	1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
	522	1.25E+02	1.26E+02	1.28E+02	1.28E+02	1.29E+02
	524	1.09E+02	1.09E+02	1.10E+02	1.09E+02	1.09E+02
	536	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
	537	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
	538	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.16E+02
	539	1.18E+02	1.18E+02	1.18E+02	1.18E+02	1.19E+02
	542	1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.17E+02
	543	1.15E+02	1.15E+02	1.14E+02	1.15E+02	1.15E+02
	544	1.25E+02	1.26E+02	1.26E+02	1.25E+02	1.25E+02
Biased Statistics						
Average Biased		1.13E+02	1.13E+02	1.14E+02	1.14E+02	1.14E+02
Std Dev Biased		7.17E+00	7.68E+00	8.09E+00	8.44E+00	8.86E+00
Ps90%/90% (+KTL) Biased		1.33E+02	1.35E+02	1.36E+02	1.37E+02	1.38E+02
Ps90%/90% (-KTL) Biased		9.35E+01	9.24E+01	9.17E+01	9.07E+01	8.96E+01
Un-Biased Statistics						
Average Un-Biased		1.12E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
Std Dev Un-Biased		5.31E+00	5.41E+00	5.40E+00	5.52E+00	5.80E+00
Ps90%/90% (+KTL) Un-Biased		1.27E+02	1.27E+02	1.27E+02	1.28E+02	1.29E+02
Ps90%/90% (-KTL) Un-Biased		9.78E+01	9.77E+01	9.78E+01	9.76E+01	9.72E+01
Specification MIN		8.80E+01	8.80E+01	8.80E+01	8.80E+01	8.80E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.172. Plot of Power Supply Rejection Ratio2 2 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.172. Raw data for Power Supply Rejection Ratio2 2 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio2 2 (dB) @ VS=+4.5V to +12V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.10E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
	520	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
	521	1.30E+02	1.31E+02	1.31E+02	1.29E+02	1.27E+02
	522	1.17E+02	1.17E+02	1.17E+02	1.17E+02	1.16E+02
	524	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
	536	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
	537	1.46E+02	1.43E+02	1.49E+02	1.43E+02	1.35E+02
	538	1.17E+02	1.17E+02	1.17E+02	1.17E+02	1.17E+02
	539	1.14E+02	1.14E+02	1.14E+02	1.14E+02	1.14E+02
	542	1.07E+02	1.07E+02	1.07E+02	1.08E+02	1.07E+02
	543	1.07E+02	1.08E+02	1.07E+02	1.08E+02	1.08E+02
	544	1.36E+02	1.39E+02	1.39E+02	1.38E+02	1.37E+02
Biased Statistics						
Average Biased		1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.15E+02
Std Dev Biased		8.36E+00	8.56E+00	8.53E+00	7.87E+00	7.08E+00
Ps90%/90% (+KTL) Biased		1.39E+02	1.40E+02	1.40E+02	1.37E+02	1.35E+02
Ps90%/90% (-KTL) Biased		9.30E+01	9.28E+01	9.30E+01	9.43E+01	9.60E+01
Un-Biased Statistics						
Average Un-Biased		1.18E+02	1.18E+02	1.19E+02	1.18E+02	1.16E+02
Std Dev Un-Biased		1.60E+01	1.47E+01	1.74E+01	1.47E+01	1.10E+01
Ps90%/90% (+KTL) Un-Biased		1.62E+02	1.58E+02	1.67E+02	1.58E+02	1.46E+02
Ps90%/90% (-KTL) Un-Biased		7.45E+01	7.76E+01	7.14E+01	7.76E+01	8.60E+01
Specification MIN		8.80E+01	8.80E+01	8.80E+01	8.80E+01	8.80E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.173. Plot of Power Supply Rejection Ratio 2 3 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.173. Raw data for Power Supply Rejection Ratio2 3 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio2 3 (dB) @ VS=+4.5V to +12V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.16E+02	1.16E+02	1.16E+02	1.15E+02	1.15E+02
	520	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
	521	1.24E+02	1.24E+02	1.24E+02	1.24E+02	1.25E+02
	522	1.18E+02	1.18E+02	1.18E+02	1.18E+02	1.18E+02
	524	1.39E+02	1.34E+02	1.30E+02	1.29E+02	1.27E+02
	536	1.66E+02	1.65E+02	1.55E+02	1.50E+02	1.44E+02
	537	1.21E+02	1.20E+02	1.21E+02	1.21E+02	1.22E+02
	538	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.11E+02
	539	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.15E+02
	542	1.14E+02	1.15E+02	1.15E+02	1.15E+02	1.15E+02
	543	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
	544	1.08E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
Biased Statistics						
Average Biased		1.20E+02	1.19E+02	1.18E+02	1.18E+02	1.18E+02
Std Dev Biased		1.27E+01	1.13E+01	9.76E+00	9.61E+00	9.42E+00
Ps90%/90% (+KTL) Biased		1.55E+02	1.50E+02	1.45E+02	1.44E+02	1.44E+02
Ps90%/90% (-KTL) Biased		8.51E+01	8.83E+01	9.16E+01	9.16E+01	9.20E+01
Un-Biased Statistics						
Average Un-Biased		1.25E+02	1.25E+02	1.23E+02	1.22E+02	1.21E+02
Std Dev Un-Biased		2.30E+01	2.29E+01	1.82E+01	1.61E+01	1.33E+01
Ps90%/90% (+KTL) Un-Biased		1.88E+02	1.88E+02	1.73E+02	1.66E+02	1.58E+02
Ps90%/90% (-KTL) Un-Biased		6.20E+01	6.22E+01	7.33E+01	7.80E+01	8.49E+01
Specification MIN		8.80E+01	8.80E+01	8.80E+01	8.80E+01	8.80E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.174. Plot of Power Supply Rejection Ratio2 4 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.174. Raw data for Power Supply Rejection Ratio2 4 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

Power Supply Rejection Ratio2 4 (dB) @ VS=+4.5V to +12V		Total Dose (krad(Si))				
		0	20	50	100	200
Device						
	519	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	520	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
	521	1.07E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
	522	1.06E+02	1.06E+02	1.06E+02	1.06E+02	1.06E+02
	524	1.10E+02	1.11E+02	1.11E+02	1.11E+02	1.10E+02
	536	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.15E+02
	537	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.10E+02
	538	1.11E+02	1.12E+02	1.12E+02	1.11E+02	1.11E+02
	539	1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
	542	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
	543	1.15E+02	1.15E+02	1.15E+02	1.15E+02	1.15E+02
	544	1.38E+02	1.42E+02	1.39E+02	1.38E+02	1.38E+02
Biased Statistics						
Average Biased		1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
Std Dev Biased		1.88E+00	1.87E+00	2.00E+00	1.94E+00	1.85E+00
Ps90%/90% (+KTL) Biased		1.13E+02	1.13E+02	1.13E+02	1.13E+02	1.13E+02
Ps90%/90% (-KTL) Biased		1.03E+02	1.03E+02	1.02E+02	1.03E+02	1.03E+02
Un-Biased Statistics						
Average Un-Biased		1.11E+02	1.12E+02	1.12E+02	1.11E+02	1.11E+02
Std Dev Un-Biased		2.62E+00	2.69E+00	2.81E+00	2.76E+00	2.91E+00
Ps90%/90% (+KTL) Un-Biased		1.19E+02	1.19E+02	1.19E+02	1.19E+02	1.19E+02
Ps90%/90% (-KTL) Un-Biased		1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.03E+02
Specification MIN		8.80E+01	8.80E+01	8.80E+01	8.80E+01	8.80E+01
Status		PASS	PASS	PASS	PASS	PASS




Figure 5.175. Plot of PSRR Match2 1 to 4 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.175. Raw data for PSRR Match2 1 to 4 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

PSRR Match2 1 to 4 (dB) @ VS=+4.5V to +12V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.12E+02	1.12E+02	1.11E+02	1.12E+02	1.13E+02
520	1.17E+02	1.17E+02	1.17E+02	1.17E+02	1.17E+02
521	1.14E+02	1.14E+02	1.14E+02	1.14E+02	1.14E+02
522	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
524	1.29E+02	1.27E+02	1.30E+02	1.27E+02	1.28E+02
536	1.11E+02	1.11E+02	1.11E+02	1.11E+02	1.11E+02
537	1.17E+02	1.17E+02	1.18E+02	1.17E+02	1.18E+02
538	1.20E+02	1.21E+02	1.21E+02	1.20E+02	1.19E+02
539	1.20E+02	1.20E+02	1.21E+02	1.20E+02	1.20E+02
542	1.13E+02	1.13E+02	1.12E+02	1.12E+02	1.11E+02
543	1.52E+02	1.43E+02	1.39E+02	1.47E+02	1.53E+02
544	1.27E+02	1.27E+02	1.28E+02	1.28E+02	1.27E+02
Biased Statistics					
Average Biased	1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.16E+02
Std Dev Biased	8.00E+00	7.22E+00	8.68E+00	7.50E+00	7.64E+00
Ps90%/90% (+KTL) Biased	1.38E+02	1.35E+02	1.40E+02	1.36E+02	1.37E+02
Ps90%/90% (-KTL) Biased	9.37E+01	9.59E+01	9.21E+01	9.51E+01	9.48E+01
Un-Biased Statistics					
Average Un-Biased	1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.16E+02
Std Dev Un-Biased	4.39E+00	4.58E+00	4.65E+00	4.31E+00	4.28E+00
Ps90%/90% (+KTL) Un-Biased	1.28E+02	1.29E+02	1.29E+02	1.28E+02	1.28E+02
Ps90%/90% (-KTL) Un-Biased	1.04E+02	1.04E+02	1.04E+02	1.04E+02	1.04E+02
Specification MIN	8.20E+01	8.20E+01	8.20E+01	8.20E+01	8.20E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.176. Plot of PSRR Match2 2 to 3 (dB) @ VS=+4.5V to +12V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.176. Raw data for PSRR Match2 2 to 3 (dB) @ VS=+4.5V to +12V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

PSRR Match2 2 to 3 (dB) @ VS=+4.5V to +12V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	1.17E+02	1.17E+02	1.17E+02	1.18E+02	1.18E+02
520	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
521	1.20E+02	1.21E+02	1.21E+02	1.20E+02	1.20E+02
522	1.37E+02	1.35E+02	1.37E+02	1.34E+02	1.32E+02
524	1.10E+02	1.10E+02	1.10E+02	1.10E+02	1.10E+02
536	1.08E+02	1.08E+02	1.08E+02	1.08E+02	1.08E+02
537	1.21E+02	1.21E+02	1.21E+02	1.22E+02	1.24E+02
538	1.07E+02	1.07E+02	1.07E+02	1.07E+02	1.07E+02
539	1.32E+02	1.33E+02	1.32E+02	1.32E+02	1.29E+02
542	1.12E+02	1.12E+02	1.12E+02	1.12E+02	1.12E+02
543	1.25E+02	1.25E+02	1.24E+02	1.24E+02	1.24E+02
544	1.09E+02	1.09E+02	1.09E+02	1.09E+02	1.09E+02
Biased Statistics					
Average Biased	1.19E+02	1.18E+02	1.19E+02	1.18E+02	1.18E+02
Std Dev Biased	1.16E+01	1.08E+01	1.14E+01	1.04E+01	9.58E+00
Ps90%/90% (+KTL) Biased	1.50E+02	1.48E+02	1.50E+02	1.47E+02	1.44E+02
Ps90%/90% (-KTL) Biased	8.68E+01	8.87E+01	8.74E+01	8.95E+01	9.13E+01
Un-Biased Statistics					
Average Un-Biased	1.16E+02	1.16E+02	1.16E+02	1.16E+02	1.16E+02
Std Dev Un-Biased	1.05E+01	1.08E+01	1.07E+01	1.06E+01	1.00E+01
Ps90%/90% (+KTL) Un-Biased	1.45E+02	1.46E+02	1.45E+02	1.45E+02	1.44E+02
Ps90%/90% (-KTL) Un-Biased	8.72E+01	8.66E+01	8.70E+01	8.72E+01	8.88E+01
Specification MIN	8.20E+01	8.20E+01	8.20E+01	8.20E+01	8.20E+01
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.177. Plot of +Short-Circuit Current2 1 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.177. Raw data for +Short-Circuit Current2 1 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current2 1 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.49E-02	-2.45E-02	-2.42E-02	-2.37E-02	-2.33E-02
520	-2.68E-02	-2.63E-02	-2.60E-02	-2.54E-02	-2.50E-02
521	-2.69E-02	-2.65E-02	-2.62E-02	-2.56E-02	-2.51E-02
522	-2.42E-02	-2.38E-02	-2.36E-02	-2.32E-02	-2.28E-02
524	-2.70E-02	-2.68E-02	-2.63E-02	-2.59E-02	-2.55E-02
536	-2.63E-02	-2.61E-02	-2.58E-02	-2.55E-02	-2.51E-02
537	-2.57E-02	-2.55E-02	-2.53E-02	-2.50E-02	-2.46E-02
538	-2.54E-02	-2.52E-02	-2.50E-02	-2.47E-02	-2.43E-02
539	-2.61E-02	-2.59E-02	-2.56E-02	-2.54E-02	-2.50E-02
542	-2.56E-02	-2.54E-02	-2.52E-02	-2.49E-02	-2.45E-02
543	-2.67E-02	-2.67E-02	-2.67E-02	-2.67E-02	-2.67E-02
544	-2.80E-02	-2.80E-02	-2.80E-02	-2.80E-02	-2.80E-02
Biased Statistics					
Average Biased	-2.60E-02	-2.56E-02	-2.53E-02	-2.47E-02	-2.43E-02
Std Dev Biased	1.30E-03	1.33E-03	1.29E-03	1.22E-03	1.23E-03
Ps90%/90% (+KTL) Biased	-2.24E-02	-2.19E-02	-2.17E-02	-2.14E-02	-2.10E-02
Ps90%/90% (-KTL) Biased	-2.95E-02	-2.93E-02	-2.88E-02	-2.81E-02	-2.77E-02
Un-Biased Statistics					
Average Un-Biased	-2.58E-02	-2.56E-02	-2.54E-02	-2.51E-02	-2.47E-02
Std Dev Un-Biased	3.59E-04	3.58E-04	3.54E-04	3.57E-04	3.31E-04
Ps90%/90% (+KTL) Un-Biased	-2.48E-02	-2.46E-02	-2.44E-02	-2.41E-02	-2.38E-02
Ps90%/90% (-KTL) Un-Biased	-2.68E-02	-2.66E-02	-2.63E-02	-2.61E-02	-2.56E-02
Specification MAX	-1.25E-02	-8.00E-03	-8.00E-03	-8.00E-03	-8.00E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.178. Plot of +Short-Circuit Current2 2 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.178. Raw data for +Short-Circuit Current2 2 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current2 2 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.54E-02	-2.50E-02	-2.47E-02	-2.43E-02	-2.38E-02
520	-2.60E-02	-2.56E-02	-2.52E-02	-2.46E-02	-2.42E-02
521	-2.66E-02	-2.62E-02	-2.58E-02	-2.54E-02	-2.49E-02
522	-2.74E-02	-2.70E-02	-2.66E-02	-2.60E-02	-2.54E-02
524	-2.79E-02	-2.76E-02	-2.71E-02	-2.66E-02	-2.58E-02
536	-2.65E-02	-2.63E-02	-2.60E-02	-2.57E-02	-2.53E-02
537	-2.57E-02	-2.55E-02	-2.53E-02	-2.50E-02	-2.46E-02
538	-2.73E-02	-2.71E-02	-2.68E-02	-2.65E-02	-2.61E-02
539	-2.53E-02	-2.52E-02	-2.49E-02	-2.47E-02	-2.43E-02
542	-2.56E-02	-2.54E-02	-2.52E-02	-2.49E-02	-2.44E-02
543	-2.81E-02	-2.81E-02	-2.80E-02	-2.80E-02	-2.80E-02
544	-2.78E-02	-2.78E-02	-2.78E-02	-2.78E-02	-2.77E-02
Biased Statistics					
Average Biased	-2.66E-02	-2.63E-02	-2.59E-02	-2.53E-02	-2.48E-02
Std Dev Biased	1.02E-03	1.06E-03	9.75E-04	9.60E-04	8.48E-04
Ps90%/90% (+KTL) Biased	-2.39E-02	-2.34E-02	-2.32E-02	-2.27E-02	-2.25E-02
Ps90%/90% (-KTL) Biased	-2.94E-02	-2.92E-02	-2.86E-02	-2.80E-02	-2.71E-02
Un-Biased Statistics					
Average Un-Biased	-2.61E-02	-2.59E-02	-2.56E-02	-2.53E-02	-2.49E-02
Std Dev Un-Biased	7.90E-04	7.75E-04	7.65E-04	7.59E-04	7.39E-04
Ps90%/90% (+KTL) Un-Biased	-2.39E-02	-2.38E-02	-2.35E-02	-2.33E-02	-2.29E-02
Ps90%/90% (-KTL) Un-Biased	-2.82E-02	-2.80E-02	-2.77E-02	-2.74E-02	-2.70E-02
Specification MAX	-1.25E-02	-8.00E-03	-8.00E-03	-8.00E-03	-8.00E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.179. Plot of +Short-Circuit Current2 3 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.179. Raw data for +Short-Circuit Current2 3 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current2 3 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.53E-02	-2.49E-02	-2.46E-02	-2.42E-02	-2.37E-02
520	-2.59E-02	-2.55E-02	-2.51E-02	-2.44E-02	-2.40E-02
521	-2.66E-02	-2.62E-02	-2.58E-02	-2.54E-02	-2.49E-02
522	-2.74E-02	-2.69E-02	-2.65E-02	-2.60E-02	-2.54E-02
524	-2.77E-02	-2.75E-02	-2.70E-02	-2.65E-02	-2.58E-02
536	-2.65E-02	-2.63E-02	-2.61E-02	-2.58E-02	-2.53E-02
537	-2.54E-02	-2.52E-02	-2.50E-02	-2.47E-02	-2.43E-02
538	-2.73E-02	-2.70E-02	-2.68E-02	-2.65E-02	-2.61E-02
539	-2.54E-02	-2.52E-02	-2.50E-02	-2.47E-02	-2.43E-02
542	-2.57E-02	-2.55E-02	-2.53E-02	-2.50E-02	-2.46E-02
543	-2.78E-02	-2.78E-02	-2.78E-02	-2.78E-02	-2.78E-02
544	-2.74E-02	-2.74E-02	-2.74E-02	-2.74E-02	-2.74E-02
Biased Statistics					
Average Biased	-2.66E-02	-2.62E-02	-2.58E-02	-2.53E-02	-2.48E-02
Std Dev Biased	1.02E-03	1.06E-03	9.88E-04	9.94E-04	8.98E-04
Ps90%/90% (+KTL) Biased	-2.38E-02	-2.33E-02	-2.31E-02	-2.25E-02	-2.23E-02
Ps90%/90% (-KTL) Biased	-2.94E-02	-2.91E-02	-2.85E-02	-2.80E-02	-2.72E-02
Un-Biased Statistics					
Average Un-Biased	-2.61E-02	-2.59E-02	-2.56E-02	-2.53E-02	-2.49E-02
Std Dev Un-Biased	8.10E-04	7.94E-04	7.85E-04	7.74E-04	7.59E-04
Ps90%/90% (+KTL) Un-Biased	-2.38E-02	-2.37E-02	-2.35E-02	-2.32E-02	-2.28E-02
Ps90%/90% (-KTL) Un-Biased	-2.83E-02	-2.80E-02	-2.78E-02	-2.74E-02	-2.70E-02
Specification MAX	-1.25E-02	-8.00E-03	-8.00E-03	-8.00E-03	-8.00E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.180. Plot of +Short-Circuit Current2 4 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.180. Raw data for +Short-Circuit Current2 4 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

+Short-Circuit Current2 4 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	-2.46E-02	-2.43E-02	-2.39E-02	-2.35E-02	-2.30E-02
520	-2.66E-02	-2.62E-02	-2.58E-02	-2.53E-02	-2.49E-02
521	-2.69E-02	-2.64E-02	-2.61E-02	-2.55E-02	-2.50E-02
522	-2.42E-02	-2.38E-02	-2.35E-02	-2.31E-02	-2.27E-02
524	-2.70E-02	-2.68E-02	-2.64E-02	-2.58E-02	-2.54E-02
536	-2.61E-02	-2.59E-02	-2.56E-02	-2.53E-02	-2.48E-02
537	-2.60E-02	-2.58E-02	-2.55E-02	-2.53E-02	-2.49E-02
538	-2.53E-02	-2.51E-02	-2.48E-02	-2.45E-02	-2.41E-02
539	-2.60E-02	-2.58E-02	-2.56E-02	-2.53E-02	-2.49E-02
542	-2.58E-02	-2.56E-02	-2.53E-02	-2.50E-02	-2.46E-02
543	-2.69E-02	-2.69E-02	-2.69E-02	-2.69E-02	-2.69E-02
544	-2.80E-02	-2.80E-02	-2.80E-02	-2.80E-02	-2.80E-02
Biased Statistics					
Average Biased	-2.59E-02	-2.55E-02	-2.51E-02	-2.47E-02	-2.42E-02
Std Dev Biased	1.33E-03	1.37E-03	1.33E-03	1.26E-03	1.26E-03
Ps90%/90% (+KTL) Biased	-2.22E-02	-2.18E-02	-2.15E-02	-2.12E-02	-2.07E-02
Ps90%/90% (-KTL) Biased	-2.95E-02	-2.93E-02	-2.88E-02	-2.81E-02	-2.77E-02
Un-Biased Statistics					
Average Un-Biased	-2.58E-02	-2.56E-02	-2.54E-02	-2.51E-02	-2.47E-02
Std Dev Un-Biased	3.26E-04	3.32E-04	3.28E-04	3.33E-04	3.22E-04
Ps90%/90% (+KTL) Un-Biased	-2.49E-02	-2.47E-02	-2.45E-02	-2.42E-02	-2.38E-02
Ps90%/90% (-KTL) Un-Biased	-2.67E-02	-2.65E-02	-2.63E-02	-2.60E-02	-2.55E-02
Specification MAX	-1.25E-02	-8.00E-03	-8.00E-03	-8.00E-03	-8.00E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.181. Plot of -Short-Circuit Current2 1 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.181. Raw data for -Short-Circuit Current2 1 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current2 1 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.76E-02	4.74E-02	4.72E-02	4.73E-02	4.74E-02
520	4.92E-02	4.91E-02	4.91E-02	4.91E-02	4.89E-02
521	4.96E-02	4.96E-02	4.96E-02	4.96E-02	4.95E-02
522	4.74E-02	4.76E-02	4.75E-02	4.75E-02	4.72E-02
524	4.88E-02	4.91E-02	4.90E-02	4.89E-02	4.87E-02
536	4.82E-02	4.85E-02	4.85E-02	4.83E-02	4.82E-02
537	4.89E-02	4.91E-02	4.91E-02	4.89E-02	4.87E-02
538	4.82E-02	4.83E-02	4.82E-02	4.81E-02	4.78E-02
539	4.79E-02	4.82E-02	4.81E-02	4.79E-02	4.77E-02
542	4.85E-02	4.88E-02	4.88E-02	4.87E-02	4.83E-02
543	5.02E-02	5.08E-02	5.08E-02	5.08E-02	5.08E-02
544	5.16E-02	5.19E-02	5.19E-02	5.19E-02	5.18E-02
Biased Statistics					
Average Biased	4.85E-02	4.86E-02	4.85E-02	4.85E-02	4.83E-02
Std Dev Biased	9.96E-04	1.00E-03	1.08E-03	1.04E-03	1.02E-03
Ps90%/90% (+KTL) Biased	5.12E-02	5.13E-02	5.15E-02	5.13E-02	5.11E-02
Ps90%/90% (-KTL) Biased	4.58E-02	4.58E-02	4.55E-02	4.56E-02	4.55E-02
Un-Biased Statistics					
Average Un-Biased	4.83E-02	4.86E-02	4.85E-02	4.84E-02	4.81E-02
Std Dev Un-Biased	3.78E-04	3.90E-04	4.36E-04	4.07E-04	3.91E-04
Ps90%/90% (+KTL) Un-Biased	4.94E-02	4.97E-02	4.97E-02	4.95E-02	4.92E-02
Ps90%/90% (-KTL) Un-Biased	4.73E-02	4.75E-02	4.74E-02	4.73E-02	4.70E-02
Specification MIN	1.25E-02	8.00E-03	8.00E-03	8.00E-03	8.00E-03
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.182. Plot of -Short-Circuit Current2 2 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.182. Raw data for -Short-Circuit Current2 2 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current2 2 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.77E-02	4.76E-02	4.73E-02	4.74E-02	4.74E-02
520	4.81E-02	4.80E-02	4.79E-02	4.79E-02	4.77E-02
521	4.95E-02	4.95E-02	4.95E-02	4.94E-02	4.93E-02
522	5.04E-02	5.07E-02	5.06E-02	5.06E-02	5.03E-02
524	4.93E-02	4.96E-02	4.95E-02	4.94E-02	4.91E-02
536	4.78E-02	4.82E-02	4.82E-02	4.79E-02	4.78E-02
537	4.79E-02	4.82E-02	4.81E-02	4.79E-02	4.77E-02
538	5.00E-02	5.02E-02	5.01E-02	5.00E-02	4.98E-02
539	4.78E-02	4.80E-02	4.79E-02	4.78E-02	4.75E-02
542	4.82E-02	4.84E-02	4.84E-02	4.83E-02	4.79E-02
543	4.99E-02	5.04E-02	5.05E-02	5.05E-02	5.04E-02
544	5.07E-02	5.10E-02	5.11E-02	5.11E-02	5.10E-02
Biased Statistics					
Average Biased	4.90E-02	4.91E-02	4.90E-02	4.89E-02	4.88E-02
Std Dev Biased	1.09E-03	1.29E-03	1.32E-03	1.29E-03	1.17E-03
Ps90%/90% (+KTL) Biased	5.20E-02	5.26E-02	5.26E-02	5.25E-02	5.20E-02
Ps90%/90% (-KTL) Biased	4.60E-02	4.56E-02	4.53E-02	4.54E-02	4.55E-02
Un-Biased Statistics					
Average Un-Biased	4.83E-02	4.86E-02	4.85E-02	4.84E-02	4.82E-02
Std Dev Un-Biased	9.38E-04	9.19E-04	8.92E-04	9.12E-04	9.06E-04
Ps90%/90% (+KTL) Un-Biased	5.09E-02	5.11E-02	5.10E-02	5.09E-02	5.06E-02
Ps90%/90% (-KTL) Un-Biased	4.58E-02	4.61E-02	4.61E-02	4.59E-02	4.57E-02
Specification MIN	1.25E-02	8.00E-03	1.25E-02	1.25E-02	1.25E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.183. Plot of -Short-Circuit Current2 3 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

Table 5.183. Raw data for -Short-Circuit Current2 3 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current2 3 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.82E-02	4.81E-02	4.78E-02	4.78E-02	4.79E-02
520	4.87E-02	4.87E-02	4.87E-02	4.87E-02	4.84E-02
521	5.02E-02	5.03E-02	5.02E-02	5.01E-02	5.00E-02
522	5.13E-02	5.16E-02	5.15E-02	5.15E-02	5.11E-02
524	5.00E-02	5.05E-02	5.03E-02	5.02E-02	4.99E-02
536	4.85E-02	4.88E-02	4.88E-02	4.87E-02	4.85E-02
537	4.88E-02	4.90E-02	4.90E-02	4.88E-02	4.85E-02
538	5.07E-02	5.10E-02	5.09E-02	5.07E-02	5.05E-02
539	4.84E-02	4.87E-02	4.85E-02	4.84E-02	4.82E-02
542	4.89E-02	4.91E-02	4.91E-02	4.90E-02	4.87E-02
543	5.05E-02	5.11E-02	5.11E-02	5.12E-02	5.11E-02
544	5.13E-02	5.17E-02	5.17E-02	5.17E-02	5.16E-02
Biased Statistics					
Average Biased	4.97E-02	4.98E-02	4.97E-02	4.96E-02	4.94E-02
Std Dev Biased	1.27E-03	1.43E-03	1.44E-03	1.43E-03	1.29E-03
Ps90%/90% (+KTL) Biased	5.32E-02	5.38E-02	5.36E-02	5.36E-02	5.30E-02
Ps90%/90% (-KTL) Biased	4.62E-02	4.59E-02	4.57E-02	4.57E-02	4.59E-02
Un-Biased Statistics					
Average Un-Biased	4.91E-02	4.93E-02	4.93E-02	4.91E-02	4.89E-02
Std Dev Un-Biased	9.35E-04	9.41E-04	9.25E-04	9.25E-04	9.14E-04
Ps90%/90% (+KTL) Un-Biased	5.16E-02	5.19E-02	5.18E-02	5.17E-02	5.14E-02
Ps90%/90% (-KTL) Un-Biased	4.65E-02	4.67E-02	4.67E-02	4.66E-02	4.64E-02
Specification MIN	1.25E-02	8.00E-03	1.25E-02	1.25E-02	1.25E-02
Status	PASS	PASS	PASS	PASS	PASS




Figure 5.184. Plot of -Short-Circuit Current2 4 (A) @ VS=+5V versus total dose. The solid diamonds are the average of the measured data points for the samples irradiated under electrical bias while the shaded diamonds are the average of the measured data points for the samples irradiated with all pins tied to ground. The black lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated under electrical bias while the gray lines (solid and/or dashed) are the average of the data points after application of the KTL statistics on the samples irradiated in the unbiased condition. The red dotted line(s) are the pre- and/or post-irradiation minimum and/or maximum specification value as defined in the datasheet and/or test plan.



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table 5.184. Raw data for -Short-Circuit Current2 4 (A) @ VS=+5V versus total dose, including the statistical analysis, specification and the status of the testing (pass/fail).

-Short-Circuit Current2 4 (A) @ VS=+5V	Total Dose (krad(Si))				
	0	20	50	100	200
Device					
519	4.71E-02	4.70E-02	4.67E-02	4.68E-02	4.69E-02
520	4.88E-02	4.87E-02	4.87E-02	4.87E-02	4.84E-02
521	4.92E-02	4.91E-02	4.91E-02	4.90E-02	4.90E-02
522	4.67E-02	4.69E-02	4.68E-02	4.68E-02	4.65E-02
524	4.82E-02	4.86E-02	4.84E-02	4.84E-02	4.81E-02
536	4.77E-02	4.79E-02	4.79E-02	4.78E-02	4.76E-02
537	4.81E-02	4.84E-02	4.84E-02	4.82E-02	4.79E-02
538	4.76E-02	4.77E-02	4.77E-02	4.75E-02	4.73E-02
539	4.77E-02	4.78E-02	4.78E-02	4.77E-02	4.74E-02
542	4.82E-02	4.84E-02	4.84E-02	4.82E-02	4.79E-02
543	4.95E-02	5.00E-02	5.01E-02	5.01E-02	5.00E-02
544	5.11E-02	5.13E-02	5.14E-02	5.13E-02	5.13E-02
Biased Statistics					
Average Biased	4.80E-02	4.81E-02	4.80E-02	4.79E-02	4.78E-02
Std Dev Biased	1.06E-03	1.04E-03	1.11E-03	1.06E-03	1.05E-03
Ps90%/90% (+KTL) Biased	5.09E-02	5.09E-02	5.10E-02	5.08E-02	5.07E-02
Ps90%/90% (-KTL) Biased	4.51E-02	4.52E-02	4.49E-02	4.50E-02	4.49E-02
Un-Biased Statistics					
Average Un-Biased	4.78E-02	4.81E-02	4.80E-02	4.79E-02	4.76E-02
Std Dev Un-Biased	2.56E-04	3.35E-04	3.16E-04	3.01E-04	2.96E-04
Ps90%/90% (+KTL) Un-Biased	4.85E-02	4.90E-02	4.89E-02	4.87E-02	4.84E-02
Ps90%/90% (-KTL) Un-Biased	4.71E-02	4.71E-02	4.72E-02	4.71E-02	4.68E-02
Specification MIN	1.25E-02	8.00E-03	1.25E-02	1.25E-02	1.25E-02
Status	PASS	PASS	PASS	PASS	PASS



6.0. Summary / Conclusions


The total ionizing dose testing described in this final report was performed using the facilities at Aeroflex RAD's Longmire Laboratories in Colorado Springs, CO. The high dose rate total ionizing dose (TID) source is a JLSA 81-24 irradiator modified to provide a panoramic exposure. The Co-60 rods are held in the base of the irradiator heavily shielded by lead, during the radiation exposures the rod is raised by an electronic timer/controller and the exposure is performed in air. The dose rate for this irradiator in this configuration ranges from <math><1\text{rad(Si)/s}</math> to a maximum of approximately

The parametric data was obtained as "read and record" and all the raw data plus an attributes summary are contained in this report as well as in a separate Excel file. The attributes data contains the average, standard deviation and the average with the KTL values applied. The KTL value used in this work is 2.742 per MIL-HDBK-814 using one sided tolerance limits of 90/90 and a 5-piece sample size. The 90/90 KTL values were selected to match the statistical levels specified in the MIL-PRF-38535 sampling plan for the qualification of a radiation hardness assured (RHA) component. Note that the following criteria must be met for a device to pass the total ionizing dose test: following the radiation exposure each of the 5 pieces irradiated under electrical bias shall pass the specification value. The units irradiated without electrical bias and the KTL statistics are included in this report for reference only. If any of the 5 pieces irradiated under electrical bias exceed the device post radiation data sheet specification limits, then the lot could be logged as a failure.

Based on this criterion the RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp (from the lot date code identified on the first page of this test report) PASSED the total ionizing dose test to the maximum tested dose level of



Appendix A: Photograph of a Sample Unit-Under-Test to Show Part Traceability



Appendix B: Radiation Bias Connections and Absolute Maximum Ratings

TID Radiation Biased Conditions: Extracted from Linear Technology RH1499M datasheet, ID No 66-10-1499.

Pin	Function	Connection / Bias
1	OUT A	To Pin 2 via 5kΩ & 40pF, in Parallel
2	-INPUT A	To Pin 1 via 5kΩ & 40pF, in Parallel
3	+INPUT A	To 8V via 5kΩ Resistor
4	V+	To +15V using 0.1μF Decoupling
5	+INPUT B	To 8V via 5kΩ Resistor
6	-INPUT B	To Pin 7 via 5kΩ & 40pF, in Parallel
7	OUT B	To Pin 6 via 5kΩ & 40pF, in Parallel
8	OUT C	To Pin 9 via 5kΩ & 40pF, in Parallel
9	-INPUT C	To Pin 8 via 5kΩ & 40pF, in Parallel
10	+INPUT C	To 8V via 5kΩ Resistor
11	V-	To -15V using 0.1μF Decoupling
12	+INPUT D	To 8V via 10kΩ Resistor
13	-INPUT D	To Pin 14 via 5kΩ & 40pF, in Parallel
14	OUT D	To Pin 13 via 5kΩ & 40pF, in Parallel




Figure B.1. Irradiation bias circuit. This figure was extracted from Linear Technology RH1499M datasheet, ID No 66-10-1499.



TID Radiation Unbiased Conditions:

Pin	Function	Connection / Bias
1	OUT A	GND
2	-INPUT A	GND
3	+INPUT A	GND
4	V+	GND
5	+INPUT B	GND
6	-INPUT B	GND
7	OUT B	GND
8	OUT C	GND
9	-INPUT C	GND
10	+INPUT C	GND
11	V-	GND
12	+INPUT D	GND
13	-INPUT D	GND
14	OUT D	GND




Figure B.2. W package drawing (for reference only). This figure was extracted from Linear Technology RH1499M datasheet, ID No 66-10-1499.

Absolute Maximum Ratings:

Parameter	Max Rating
Total Supply Voltage (V+ to V-)	36V
Input Current	±10mA
Output Short-Circuit Duration	Continuous

An ISO 9001:2008 and DSCC Certified Company



Appendix C: Electrical Test Parameters and Conditions

The expected ranges of values as well as the measurement conditions are taken from Linear Technology RH1499M datasheet. All electrical tests for this device are performed on one of Aeroflex RAD's LTS2020 Test Systems. The LTS2020 Test System is a programmable parametric tester that provides parameter measurements for a variety of digital, analog and mixed signal products including voltage regulators, voltage comparators, D to A and A to D converters. The LTS2020 Test System achieves accuracy and sensitivity through the use of software self-calibration and an internal relay matrix with separate family boards and custom personality adapter boards. The tester uses this relay matrix to connect the required test circuits, select the appropriate voltage / current sources and establish the needed measurement loops for all the tests performed. The measured parameters and test conditions are shown in Table C.1.

A listing of the measurement precision/resolution for each parameter is shown in Table C.2. The precision/resolution values were obtained from test data or from the DAC resolution of the LTS-2020 for the particular test shown, whichever is greater. To generate the precision/resolution shown in Table C.2, one of the units-under-test was tested repetitively (a total of 10-times with re-insertion between tests) to obtain the average test value and standard deviation. Using this test data MIL-HDBK-814 90/90 KTL statistics were applied to the measured standard deviation to generate the final measurement range. This value encompasses the precision/resolution of all aspects of the test system, including the LTS2020 mainframe, family board, socket assembly and DUT board as well as insertion error. In some cases, the measurement resolution is limited by the internal DACs, which results in a measured standard deviation of zero. In these instances the precision/resolution will be reported back as the LSB of the DAC.

Note that the testing and statistics used in this document are based on an “analysis of variables” technique, which relies on small sample sizes to qualify much larger lot sizes (see MIL-HDBK-814, p. 91 for a discussion of statistical treatments). Not all measured parameters are well suited to this approach due to inherent large variations. If necessary, larger samples sizes could be used to qualify these parameters using an “attributes” approach.



Table C.1. Measured parameters and test conditions for the RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp.

Parameter	Symbol	Test Conditions
+Supply Current (A)	+ICC15	VS=+/-15V
-Supply Current (A)	-IEE15	VS=+/-15V
Input Offset Voltage1 (V)	VOS1_1→4	VS=+/-15V, VCM=0V
Input Offset Current1 (A)	IOS1_1→4	VS=+/-15V, VCM=0V
+Input Bias Current BIAS1 (A)	+IBIAS1_1→4	VS=+/-15V, VCM=0V
-Input Bias Current BIAS1 (A)	-IBIAS1_1→4	VS=+/-15V, VCM=0V
Input Offset Voltage2 (V)	VOS2_1→4	VS=+/-15V, VCM=15V
Input Offset Current2 (A)	IOS2_1→4	VS=+/-15V, VCM=15V
+Input Bias Current BIAS2 (A)	+IBIAS2_1→4	VS=+/-15V, VCM=15V
-Input Bias Current BIAS2 (A)	-IBIAS2_1→4	VS=+/-15V, VCM=15V
Input Offset Voltage3 (V)	VOS3_1→4	VS=+/-15V, VCM=-15V
Input Offset Current3 (A)	IOS3_1→4	VS=+/-15V, VCM=-15V
+Input Bias Current BIAS3 (A)	+IBIAS3_1→4	VS=+/-15V, VCM=-15V
-Input Bias Current BIAS3 (A)	-IBIAS3_1→4	VS=+/-15V, VCM=-15V
Output Voltage Swing High1 (V)	+VOUT1_1→4	VS=+/-15V IL=0mA
Output Voltage Swing High2 (V)	+VOUT2_1→4	VS=+/-15V IL=1mA
Output Voltage Swing High3 (V)	+VOUT3_1→4	VS=+/-15V IL=10mA
Output Voltage Swing Low1 (V)	-VOUT1_1→4	VS=+/-15V IL=0mA
Output Voltage Swing Low2 (V)	-VOUT2_1→4	VS=+/-15V IL=1mA
Output Voltage Swing Low3 (V)	-VOUT3_1→4	VS=+/-15V IL=10mA
Large Signal Voltage Gain1 (V/mV)	AVOL1_1→4	VO=+/-14.5V, RL=10kΩ
Large Signal Voltage Gain2 (V/mV)	AVOL2_1→4	VO=+/-10V, RL=2kΩ
Common Mode Rejection Ratio1 (dB)	CMRR1_1→4	VS=+/-15V, VCM=+/-15V
CMRR Match1 1 to 4 (dB)	CMRR1 MATCH 1 to 4	VS=+/-15V, VCM=+/-15V
CMRR Match1 2 to 3 (dB)	CMRR1 MATCH 2 to 3	VS=+/-15V, VCM=+/-15V
Power Supply Rejection Ratio1 (dB)	PSRR1_1→4	VS=+/-2V to +/-16V
PSRR Match1 1 to 4 (dB)	PSRR1 MATCH 1 to 4	VS=+/-2V to +/-16V
PSRR Match1 2 to 3 (dB)	PSRR1 MATCH 2 to 3	VS=+/-2V to +/-16V



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

+Short-Circuit Current1 (A)	+ISC1_1→4	VS=+/-15V, VOUT=0V
-Short-Circuit Current1 (A)	-ISC1_1→4	VS=+/-15V, VOUT=0V
+Supply Current (A)	+ICC5	VS=+5V
-Supply Current (A)	-IEE5	VS=+5V
Input Offset Voltage4 (V)	VOS4_1→4	VS=+5V, VCM=0V
Input Offset Current4 (A)	IOS4_1→4	VS=+5V, VCM=0V
+Input Bias Current BIAS4 (A)	+IBIAS4_1→4	VS=+5V, VCM=0V
-Input Bias Current BIAS4 (A)	-IBIAS4_1→4	VS=+5V, VCM=0V
Input Offset Voltage5 (V)	VOS5_1→4	VS=+5V, VCM=5V
Input Offset Current5 (A)	IOS5_1→4	VS=+5V, VCM=5V
+Input Bias Current BIAS5 (A)	+IBIAS5_1→4	VS=+5V, VCM=5V
-Input Bias Current BIAS5 (A)	-IBIAS5_1→4	VS=+5V, VCM=5V
Output Voltage Swing High4 (V)	+VOUT4_1→4	VS=+5V IL=0mA
Output Voltage Swing High5 (V)	+VOUT5_1→4	VS=+5V IL=1mA
Output Voltage Swing High6 (V)	+VOUT6_1→4	VS=+5V IL=2.5mA
Output Voltage Swing Low4 (V)	-VOUT4_1→4	VS=+5V IL=0mA
Output Voltage Swing Low5 (V)	-VOUT5_1→4	VS=+5V IL=1mA
Output Voltage Swing Low6 (V)	-VOUT6_1→4	VS=+5V IL=2.5mA
Large Signal Voltage Gain3 (V/mV)	AVOL3_1→4	VO=75mV to 4.8V, RL=10kΩ
Common Mode Rejection Ratio2 (dB)	CMRR2_1→4	VS=+5V, VCM=0 to +5V
CMRR Match2 1 to 4 (dB)	CMRR2 MATCH 1 to 4	VS=+5V, VCM=0 to +5V
CMRR Match2 2 to 3 (dB)	CMRR2 MATCH 2 to 3	VS=+5V, VCM=0 to +5V
Power Supply Rejection Ratio2 (dB)	PSRR2_1→4	VS=+4.5V to +12V
PSRR Match2 1 to 4 (dB)	PSRR2 MATCH 1 to 4	VS=+4.5V to +12V
PSRR Match2 2 to 3 (dB)	PSRR2 MATCH 2 to 3	VS=+4.5V to +12V
+Short-Circuit Current2 (A)	+ISC2_1→4	VS=+5V
-Short-Circuit Current2 (A)	-ISC2_1→4	VS=+5V



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

Table C.2. Measured parameters, pre-irradiation specifications and measurement precision for the RH1499MW Quad Rail-to-Rail Input and Output Precision C-Load Op Amp.

Parameter	Pre-Irradiation Specification		Measurement Precision/Resolution
	MIN	MAX	
+Supply Current (A)		1.00E-02	±1.64E-04
-Supply Current (A)	-1.00E-02		±1.61E-04
Input Offset Voltage1 (V)	-8.00E-04	8.00E-04	±2.51E-05
Input Offset Current1 (A)	-7.00E-08	7.00E-08	±9.10E-10
+Input Bias Current BIAS1 (A)	-7.15E-07	7.15E-07	±1.22E-08
-Input Bias Current BIAS1 (A)	-7.15E-07	7.15E-07	±1.13E-08
Input Offset Voltage2 (V)	-8.00E-04	8.00E-04	±1.28E-05
Input Offset Current2 (A)	-7.00E-08	7.00E-08	±9.67E-10
+Input Bias Current BIAS2 (A)	-7.15E-07	7.15E-07	±7.21E-09
-Input Bias Current BIAS2 (A)	-7.15E-07	7.15E-07	±6.44E-09
Input Offset Voltage3 (V)	-8.00E-04	8.00E-04	±1.65E-05
Input Offset Current3 (A)	-7.00E-08	7.00E-08	±7.00E-10
+Input Bias Current BIAS3 (A)	-7.15E-07	7.15E-07	±1.01E-08
-Input Bias Current BIAS3 (A)	-7.15E-07	7.15E-07	±8.88E-09
Output Voltage Swing High1 (V)		1.00E-02	±2.81E-04
Output Voltage Swing High2 (V)		1.50E-01	±1.19E-03
Output Voltage Swing High3 (V)		8.00E-01	±6.15E-03
Output Voltage Swing Low1 (V)		3.00E-02	±5.56E-04
Output Voltage Swing Low2 (V)		1.00E-01	±1.03E-03
Output Voltage Swing Low3 (V)		5.00E-01	±3.44E-03
Large Signal Voltage Gain1 (V/mV)	1.00E+03		±7.02E+02
Large Signal Voltage Gain2 (V/mV)	5.00E+01		±1.02E+02
Common Mode Rejection Ratio1 (dB)	9.00E+01	3.00E+02	±9.45E-02
CMRR Match1 1 to 4 (dB)	8.40E+01	3.00E+02	±6.79E-02
CMRR Match1 2 to 3 (dB)	8.40E+01	3.00E+02	±1.71E-01
Power Supply Rejection Ratio1 (dB)	9.00E+01		±3.82E-01
PSRR Match1 1 to 4 (dB)	8.30E+01		±1.35E-01

An ISO 9001:2008 and DSCC Certified Company



TID Report
12-275 120517 R1.0

Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800

PSRR Match1 2 to 3 (dB)	8.30E+01		±8.96E-02
+Short-Circuit Current1 (A)		-1.50E-02	±4.01E-04
-Short-Circuit Current1 (A)	1.50E-02		±6.44E-04
+Supply Current (A)		8.80E-03	±8.67E-05
-Supply Current (A)	-8.80E-03		±8.59E-05
Input Offset Voltage4 (V)	-8.00E-04	8.00E-04	±1.49E-05
Input Offset Current4 (A)	-6.50E-08	6.50E-08	±5.28E-10
+Input Bias Current BIAS4 (A)	-6.50E-07	6.50E-07	±6.11E-09
-Input Bias Current BIAS4 (A)	-6.50E-07	6.50E-07	±6.24E-09
Input Offset Voltage5 (V)	-8.00E-04	8.00E-04	±8.65E-06
Input Offset Current5 (A)	-6.50E-08	6.50E-08	±5.15E-10
+Input Bias Current BIAS5 (A)	-6.50E-07	6.50E-07	±3.27E-09
-Input Bias Current BIAS5 (A)	-6.50E-07	6.50E-07	±2.91E-09
Output Voltage Swing High4 (V)		1.00E-02	±2.53E-04
Output Voltage Swing High5 (V)		1.50E-01	±8.19E-04
Output Voltage Swing High6 (V)		2.50E-01	±1.46E-03
Output Voltage Swing Low4 (V)		3.00E-02	±3.86E-04
Output Voltage Swing Low5 (V)		1.00E-01	±4.14E-04
Output Voltage Swing Low6 (V)		2.00E-01	±7.42E-04
Large Signal Voltage Gain3 (V/mV)	6.00E+02		±5.72E+02
Common Mode Rejection Ratio2 (dB)	7.60E+01		±1.49E-01
CMRR Match2 1 to 4 (dB)	7.50E+01		±5.95E-02
CMRR Match2 2 to 3 (dB)	7.50E+01		±3.80E-01
Power Supply Rejection Ratio2 (dB)	8.80E+01		±4.26E+00
PSRR Match2 1 to 4 (dB)	8.20E+01		±1.05E+00
PSRR Match2 2 to 3 (dB)	8.20E+01		±6.39E-01
+Short-Circuit Current2 (A)		-1.25E-02	±4.02E-05
-Short-Circuit Current2 (A)	1.25E-02		±4.63E-04



Appendix D: List of Figures Used in the Results Section (Section 5)

- 5.1. +Supply Current (A) @ $V_S = \pm 15V$
- 5.2. -Supply Current (A) @ $V_S = \pm 15V$
- 5.3. Input Offset Voltage1 1 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.4. Input Offset Voltage1 2 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.5. Input Offset Voltage1 3 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.6. Input Offset Voltage1 4 (V) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.7. Input Offset Current1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.8. Input Offset Current1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.9. Input Offset Current1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.10. Input Offset Current1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.11. +Input Bias Current BIAS1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.12. +Input Bias Current BIAS1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.13. +Input Bias Current BIAS1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.14. +Input Bias Current BIAS1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.15. -Input Bias Current BIAS1 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.16. -Input Bias Current BIAS1 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.17. -Input Bias Current BIAS1 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.18. -Input Bias Current BIAS1 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 0V$
- 5.19. Input Offset Voltage2 1 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.20. Input Offset Voltage2 2 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.21. Input Offset Voltage2 3 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.22. Input Offset Voltage2 4 (V) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.23. Input Offset Current2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.24. Input Offset Current2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.25. Input Offset Current2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.26. Input Offset Current2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.27. +Input Bias Current BIAS2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.28. +Input Bias Current BIAS2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.29. +Input Bias Current BIAS2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.30. +Input Bias Current BIAS2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.31. -Input Bias Current BIAS2 1 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.32. -Input Bias Current BIAS2 2 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.33. -Input Bias Current BIAS2 3 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.34. -Input Bias Current BIAS2 4 (A) @ $V_S = \pm 15V$, $V_{CM} = 15V$
- 5.35. Input Offset Voltage3 1 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
- 5.36. Input Offset Voltage3 2 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
- 5.37. Input Offset Voltage3 3 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
- 5.38. Input Offset Voltage3 4 (V) @ $V_S = \pm 15V$, $V_{CM} = -15V$
- 5.39. Input Offset Current3 1 (A) @ $V_S = \pm 15V$, $V_{CM} = -15V$
- 5.40. Input Offset Current3 2 (A) @ $V_S = \pm 15V$, $V_{CM} = -15V$



- 5.41. Input Offset Current3 3 (A) @ VS= \pm 15V, VCM=-15V
- 5.42. Input Offset Current3 4 (A) @ VS= \pm 15V, VCM=-15V
- 5.43. +Input Bias Current BIAS3 1 (A) @ VS= \pm 15V, VCM=-15V
- 5.44. +Input Bias Current BIAS3 2 (A) @ VS= \pm 15V, VCM=-15V
- 5.45. +Input Bias Current BIAS3 3 (A) @ VS= \pm 15V, VCM=-15V
- 5.46. +Input Bias Current BIAS3 4 (A) @ VS= \pm 15V, VCM=-15V
- 5.47. -Input Bias Current BIAS3 1 (A) @ VS= \pm 15V, VCM=-15V
- 5.48. -Input Bias Current BIAS3 2 (A) @ VS= \pm 15V, VCM=-15V
- 5.49. -Input Bias Current BIAS3 3 (A) @ VS= \pm 15V, VCM=-15V
- 5.50. -Input Bias Current BIAS3 4 (A) @ VS= \pm 15V, VCM=-15V
- 5.51. Output Voltage Swing High1 1 (V) @ VS= \pm 15V IL=0mA
- 5.52. Output Voltage Swing High1 2 (V) @ VS= \pm 15V IL=0mA
- 5.53. Output Voltage Swing High1 3 (V) @ VS= \pm 15V IL=0mA
- 5.54. Output Voltage Swing High1 4 (V) @ VS= \pm 15V IL=0mA
- 5.55. Output Voltage Swing High2 1 (V) @ VS= \pm 15V IL=1mA
- 5.56. Output Voltage Swing High2 2 (V) @ VS= \pm 15V IL=1mA
- 5.57. Output Voltage Swing High2 3 (V) @ VS= \pm 15V IL=1mA
- 5.58. Output Voltage Swing High2 4 (V) @ VS= \pm 15V IL=1mA
- 5.59. Output Voltage Swing High3 1 (V) @ VS= \pm 15V IL=10mA
- 5.60. Output Voltage Swing High3 2 (V) @ VS= \pm 15V IL=10mA
- 5.61. Output Voltage Swing High3 3 (V) @ VS= \pm 15V IL=10mA
- 5.62. Output Voltage Swing High3 4 (V) @ VS= \pm 15V IL=10mA
- 5.63. Output Voltage Swing Low1 1 (V) @ VS= \pm 15V IL=0mA
- 5.64. Output Voltage Swing Low1 2 (V) @ VS= \pm 15V IL=0mA
- 5.65. Output Voltage Swing Low1 3 (V) @ VS= \pm 15V IL=0mA
- 5.66. Output Voltage Swing Low1 4 (V) @ VS= \pm 15V IL=0mA
- 5.67. Output Voltage Swing Low2 1 (V) @ VS= \pm 15V IL=1mA
- 5.68. Output Voltage Swing Low2 2 (V) @ VS= \pm 15V IL=1mA
- 5.69. Output Voltage Swing Low2 3 (V) @ VS= \pm 15V IL=1mA
- 5.70. Output Voltage Swing Low2 4 (V) @ VS= \pm 15V IL=1mA
- 5.71. Output Voltage Swing Low3 1 (V) @ VS= \pm 15V IL=10mA
- 5.72. Output Voltage Swing Low3 2 (V) @ VS= \pm 15V IL=10mA
- 5.73. Output Voltage Swing Low3 3 (V) @ VS= \pm 15V IL=10mA
- 5.74. Output Voltage Swing Low3 4 (V) @ VS= \pm 15V IL=10mA
- 5.75. Large Signal Voltage Gain1 1 (V/mV) @ VO= \pm 14.5V, RL=10k Ω
- 5.76. Large Signal Voltage Gain1 2 (V/mV) @ VO= \pm 14.5V, RL=10k Ω
- 5.77. Large Signal Voltage Gain1 3 (V/mV) @ VO= \pm 14.5V, RL=10k Ω
- 5.78. Large Signal Voltage Gain1 4 (V/mV) @ VO= \pm 14.5V, RL=10k Ω
- 5.79. Large Signal Voltage Gain2 1 (V/mV) @ VO= \pm 10V, RL=2k Ω
- 5.80. Large Signal Voltage Gain2 2 (V/mV) @ VO= \pm 10V, RL=2k Ω
- 5.81. Large Signal Voltage Gain2 3 (V/mV) @ VO= \pm 10V, RL=2k Ω
- 5.82. Large Signal Voltage Gain2 4 (V/mV) @ VO= \pm 10V, RL=2k Ω



- 5.83. Common Mode Rejection Ratio1 1 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.84. Common Mode Rejection Ratio1 2 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.85. Common Mode Rejection Ratio1 3 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.86. Common Mode Rejection Ratio1 4 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.87. CMRR Match1 1 to 4 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.88. CMRR Match1 2 to 3 (dB) @ $V_S=+/-15V$, $V_{CM}=+/-15V$
- 5.89. Power Supply Rejection Ratio1 1 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.90. Power Supply Rejection Ratio1 2 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.91. Power Supply Rejection Ratio1 3 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.92. Power Supply Rejection Ratio1 4 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.93. PSRR Match1 1 to 4 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.94. PSRR Match1 2 to 3 (dB) @ $V_S=+/-2V$ to $+/-16V$
- 5.95. +Short-Circuit Current1 1 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.96. +Short-Circuit Current1 2 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.97. +Short-Circuit Current1 3 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.98. +Short-Circuit Current1 4 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.99. -Short-Circuit Current1 1 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.100. -Short-Circuit Current1 2 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.101. -Short-Circuit Current1 3 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.102. -Short-Circuit Current1 4 (A) @ $V_S=+/-15V$, $V_{OUT}=0V$
- 5.103. +Supply Current (A) @ $V_S=+5V$
- 5.104. -Supply Current (A) @ $V_S=+5V$
- 5.105. Input Offset Voltage4 1 (V) @ $V_S=+5V$, $V_{CM}=0V$
- 5.106. Input Offset Voltage4 2 (V) @ $V_S=+5V$, $V_{CM}=0V$
- 5.107. Input Offset Voltage4 3 (V) @ $V_S=+5V$, $V_{CM}=0V$
- 5.108. Input Offset Voltage4 4 (V) @ $V_S=+5V$, $V_{CM}=0V$
- 5.109. Input Offset Current4 1 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.110. Input Offset Current4 2 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.111. Input Offset Current4 3 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.112. Input Offset Current4 4 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.113. +Input Bias Current BIAS4 1 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.114. +Input Bias Current BIAS4 2 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.115. +Input Bias Current BIAS4 3 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.116. +Input Bias Current BIAS4 4 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.117. -Input Bias Current BIAS4 1 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.118. -Input Bias Current BIAS4 2 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.119. -Input Bias Current BIAS4 3 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.120. -Input Bias Current BIAS4 4 (A) @ $V_S=+5V$, $V_{CM}=0V$
- 5.121. Input Offset Voltage5 1 (V) @ $V_S=+5V$, $V_{CM}=5V$
- 5.122. Input Offset Voltage5 2 (V) @ $V_S=+5V$, $V_{CM}=5V$
- 5.123. Input Offset Voltage5 3 (V) @ $V_S=+5V$, $V_{CM}=5V$
- 5.124. Input Offset Voltage5 4 (V) @ $V_S=+5V$, $V_{CM}=5V$



- 5.125. Input Offset Current5 1 (A) @ VS=+5V, VCM=5V
- 5.126. Input Offset Current5 2 (A) @ VS=+5V, VCM=5V
- 5.127. Input Offset Current5 3 (A) @ VS=+5V, VCM=5V
- 5.128. Input Offset Current5 4 (A) @ VS=+5V, VCM=5V
- 5.129. +Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V
- 5.130. +Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V
- 5.131. +Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V
- 5.132. +Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V
- 5.133. -Input Bias Current BIAS5 1 (A) @ VS=+5V, VCM=5V
- 5.134. -Input Bias Current BIAS5 2 (A) @ VS=+5V, VCM=5V
- 5.135. -Input Bias Current BIAS5 3 (A) @ VS=+5V, VCM=5V
- 5.136. -Input Bias Current BIAS5 4 (A) @ VS=+5V, VCM=5V
- 5.137. Output Voltage Swing High4 1 (V) @ VS=+5V IL=0mA
- 5.138. Output Voltage Swing High4 2 (V) @ VS=+5V IL=0mA
- 5.139. Output Voltage Swing High4 3 (V) @ VS=+5V IL=0mA
- 5.140. Output Voltage Swing High4 4 (V) @ VS=+5V IL=0mA
- 5.141. Output Voltage Swing High5 1 (V) @ VS=+5V IL=1mA
- 5.142. Output Voltage Swing High5 2 (V) @ VS=+5V IL=1mA
- 5.143. Output Voltage Swing High5 3 (V) @ VS=+5V IL=1mA
- 5.144. Output Voltage Swing High5 4 (V) @ VS=+5V IL=1mA
- 5.145. Output Voltage Swing High6 1 (V) @ VS=+5V IL=2.5mA
- 5.146. Output Voltage Swing High6 2 (V) @ VS=+5V IL=2.5mA
- 5.147. Output Voltage Swing High6 3 (V) @ VS=+5V IL=2.5mA
- 5.148. Output Voltage Swing High6 4 (V) @ VS=+5V IL=2.5mA
- 5.149. Output Voltage Swing Low4 1 (V) @ VS=+5V IL=0mA
- 5.150. Output Voltage Swing Low4 2 (V) @ VS=+5V IL=0mA
- 5.151. Output Voltage Swing Low4 3 (V) @ VS=+5V IL=0mA
- 5.152. Output Voltage Swing Low4 4 (V) @ VS=+5V IL=0mA
- 5.153. Output Voltage Swing Low5 1 (V) @ VS=+5V IL=1mA
- 5.154. Output Voltage Swing Low5 2 (V) @ VS=+5V IL=1mA
- 5.155. Output Voltage Swing Low5 3 (V) @ VS=+5V IL=1mA
- 5.156. Output Voltage Swing Low5 4 (V) @ VS=+5V IL=1mA
- 5.157. Output Voltage Swing Low6 1 (V) @ VS=+5V IL=2.5mA
- 5.158. Output Voltage Swing Low6 2 (V) @ VS=+5V IL=2.5mA
- 5.159. Output Voltage Swing Low6 3 (V) @ VS=+5V IL=2.5mA
- 5.160. Output Voltage Swing Low6 4 (V) @ VS=+5V IL=2.5mA
- 5.161. Large Signal Voltage Gain3 1 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 5.162. Large Signal Voltage Gain3 2 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 5.163. Large Signal Voltage Gain3 3 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 5.164. Large Signal Voltage Gain3 4 (V/mV) @ VO=75mV to 4.8V, RL=10kΩ
- 5.165. Common Mode Rejection Ratio2 1 (dB) @ VS=+5V, VCM=0 to +5V
- 5.166. Common Mode Rejection Ratio2 2 (dB) @ VS=+5V, VCM=0 to +5V



**TID Report
12-275 120517 R1.0**

**Aeroflex RAD
5017 N. 30th Street
Colorado Springs, CO 80919
(719) 531-0800**

- 5.167. Common Mode Rejection Ratio2 3 (dB) @ VS=+5V, VCM=0 to +5V
- 5.168. Common Mode Rejection Ratio2 4 (dB) @ VS=+5V, VCM=0 to +5V
- 5.169. CMRR Match2 1 to 4 (dB) @ VS=+5V, VCM=0 to +5V
- 5.170. CMRR Match2 2 to 3 (dB) @ VS=+5V, VCM=0 to +5V
- 5.171. Power Supply Rejection Ratio2 1 (dB) @ VS=+4.5V to +12V
- 5.172. Power Supply Rejection Ratio2 2 (dB) @ VS=+4.5V to +12V
- 5.173. Power Supply Rejection Ratio2 3 (dB) @ VS=+4.5V to +12V
- 5.174. Power Supply Rejection Ratio2 4 (dB) @ VS=+4.5V to +12V
- 5.175. PSRR Match2 1 to 4 (dB) @ VS=+4.5V to +12V
- 5.176. PSRR Match2 2 to 3 (dB) @ VS=+4.5V to +12V
- 5.177. +Short-Circuit Current2 1 (A) @ VS=+5V
- 5.178. +Short-Circuit Current2 2 (A) @ VS=+5V
- 5.179. +Short-Circuit Current2 3 (A) @ VS=+5V
- 5.180. +Short-Circuit Current2 4 (A) @ VS=+5V
- 5.181. -Short-Circuit Current2 1 (A) @ VS=+5V
- 5.182. -Short-Circuit Current2 2 (A) @ VS=+5V
- 5.183. -Short-Circuit Current2 3 (A) @ VS=+5V
- 5.184. -Short-Circuit Current2 4 (A) @ VS=+5V