



Product Information

PSF-20cSt Silicone Heat Transfer Fluid

Operating Temperature Range: -50°C to 220°C (closed system)



PSF-20cSt Silicone Heat Transfer Fluid is 100% PDMS Silicone Oil that offers a wide service temperature range.

PSF-20cSt Silicone Heat Transfer Fluid is a clear, colorless and odorless low-viscosity linear Polydimethylsiloxane (CAS No. 63148-62-9) with a viscosity of 20cSt @ 25°C. It is formulated as a cold and heat transfer medium with an operating service temperature range of -50°C to 220°C (closed system*).

PSF-20cSt Silicone Heat Transfer Fluid is characterized by its low pour points, low temperature stability, wide service temperature range, low viscosity change at temperature (low V.T.C.), low surface tension, high dielectric strength, long service life, and hydrophobic nature (insoluble in water).

PSF-20cSt Silicone Heat Transfer Fluid has a Thermal Conductivity value of 0.00034 g cal/cm•sec• °C. Its specific heat value is 1.6 (J/g °C)

PSF-20cSt Silicone Heat Transfer Fluid has a low viscosity-temperature coefficient or V.T.C. (viscosity @99°C ÷viscosity @ 38°C). Thus, its viscosity will not significantly increase even at extremely low temperatures. For example, at -40°C, its viscosity increases to only 125cSt. This is critical for baths that have pumping systems that cannot operate with higher viscosity fluids.

Applications include: calibration bath fluids for low temperature, low temperature closed system baths, low temperature constant temperature baths, low temperature circulating baths, low temperature circulator baths, low temperature refrigerated baths, low temperature closed loop baths,

**Closed system baths are systems from which air has been excluded*

Specifications

Chemical Name	Polydimethylsiloxane / PDMS Silicone Oil
CAS #	63148-62-9
Appearance	Clear, colorless & odorless liquid
Viscosity Class	Low
Non-Flammable	Yes
Thermally Stable	Yes
Minimum Order	1-gallon (3.785 liters)

Features

- 100% PDMS Silicone Fluid
- Low Pour Point: -65°C
- Flash Point: 232°C
- Hydrophobic: insoluble with water
- Compatible with virtually all o-rings, gaskets, hoses, valves and seals*
- Chemically Inert
- Low V.T.C...viscosity remains low even at very low temps
- High Dielectric Strength

**Not recommended for silicone O-rings...may cause swelling.*

Typical Properties

Viscosity @ 25°C	Specific Gravity	Refractive Index	Pour Point	Flash Point	Boiling Point	Viscosity-temp coefficient	Surface Tension
20cSt	0.949	1.4009	-65°C	232°C	>200 °C	0.59	20.6

Thermal Properties

Thermal Conductivity @ 25°C g cal/cm•sec• °C	Thermal Expansion cc/cc °C	Specific Heat @ 25°C J/g °C
0.00034	0.00107	1.6

Dielectric Properties

Dielectric strength volts/mil	Volume Resistivity	Dielectric constant 50Hz
375	1.0 x 10 ¹⁵	2.72

Packaging

1-gallon (3.78 liters)3.6kg net wt.
 5-gallon pail (18.9 liters)18kg net wt.
 55-gallon drum (208 liters)190kg net wt.

F.O.B. Phila, PA U.S.A.

Viscosity @ temperature

Viscosity-Temperature-coefficient.....	0.59
Viscosity @ 25°C.....	20cSt (centistokes)
Viscosity @ 0°C.....	35cSt
Viscosity @ -20°C.....	60cSt
Viscosity @ -40°C.....	125cSt

For More Info, Contact: Clearco Products Co., Inc.

15 York Road
Willow Grove, PA 19090
U.S.A.

Tel: (215) 366-7860
Fax: (215) 366-7862
Email: info@clearcoproducts.com
Web: www.clearcoproducts.com