

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier Nexperia B.V.		User Part Number						
		BC817DS						
Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		Part Description						
		Nexperia DHAM Small Signal Bipolar Transistor						
		SMD package						
		Test Conditions	Duration	# Lots	# Quantity	# Rejects		
	TEST							
# E1	Pre- and Post-Stress Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
# L1		IESD22-A113	IV/A	See below	an parts	See below		
		Bake Tamb = 125 °C	24 hours					
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	849	61170	0		
		MIL-STD-750-1						
	HTRB	M1039 Method A						
		Tj = Tjmax, Vr = 100% of max. datasheet				_		
# B1	Bias	reverse voltage	1000 hours	202	16160	0		
	тс	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Timax, not to exceed 150°C	1000 cycles	171	13680	0		
# 74	. ,	IESD22-A102	1000 Cycles	1/1	13000	0		
	AC	Tamb = 121 °C, RH = 100 %						
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)	96 hours	173	13840	0		
	H3TRB	JESD22-A101						
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of						
# A2 alt	Temperature Reverse Bias		1000 hours	173	13840	0		
	701	MIL-STD-750 Method 1037						
# AF	IOL Intermittent Operating Life	ton = toff, devices powered to insure ΔTj =	1000	107	15760	0		
# A5	Intermittent Operating Life	100 C 101 13000 Cycles	1000 hours	197	15760	0		
	RSH	JESD22-A111						
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	135	4050	0		
	SD							
# C10	Solderability	J-STD-002		342	3420	0		

^[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1)
Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia	Small Signal Bipolar				
DHAM	Transistor	16160	0	0.26	3.81E+09

© 2022 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com