

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory		User Part Number PDZ3.9BGW Part Description												
										Nexperia DHAM	Zener			
								Assembly reliability labs		SMD package				
Based on AEC-Q101 Test		Test Conditions	Duration	# Lots	# Quantity	# Rejects								
	TEST													
	Pre- and Post-Stress													
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below								
		JESD22-A113 Bake Tamb = 125 °C	24 hours											
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours											
# A1	Preconditioning	Reflow soldering	3 cycles	810	58300	0								
	HTRB	MIL-STD-750-1 M1038 Method A												
	High Temperature Reverse	Tj = Tjmax, Vr = 100% of max. datasheet												
# B1	Bias	reverse voltage	1000 hours	138	11040	0								
		MIL-STD-750-1 M1038 Method B												
	SSOP	Tj = Tjmax, Iz = 100% of max. datasheet												
# B1b	Steady State Operational	reverse current	1000 hours	20	1600	0								
	тс	JESD22-A104												
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	170	13600	0								
		JESD22-A102												
# A2 ala	AC Autoclave	Tamb = 121 °C, RH = 100 % Pressure = 205 kPa (29.7 psia)	OC have	170	12600	0								
# A3 alt	Autociave	riessule – 203 kra (23.7 psia)	96 hours	170	13600	0								
	H3TRB	JESD22-A101												
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of												
# A2 alt		rated reverse voltage ^[1]	1000 hours	170	13600	0								
		MIL-STD-750 Method 1037												
	IOL	ton = toff, devices powered to insure ΔTj =												
# A5	Intermittent Operating Life	100 °C for 15000 cycles	1000 hours	170	13600	0								
	RSH	JESD22-A111 260 °C ± 5 °C				_								
# C8	Resistance to Solder Heat	200 -C = 5 -C	10 s	130	3900	0								
	SD Solderability	J-STD-002												

^[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Zener	11040	0	0.38	2.60E+09

^{© 2022} Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com