

## **Quarterly Reliability Monitoring Results**

## Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs		User Part Number						
		PESD16VV1BSF						
		Part Description						
		Nexperia DHAM Protection INDI BD package						
								Test
	TEST							
	Pre- and Post-Stress							
# 1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
		MIL-STD-750-1						
	HTRB	M1038 Method A						
		Tj = Tjmax, Vr = 100% of max. datasheet						
# 5	Bias	reverse voltage	1000 hours	15	1200	0		
	тс	JESD22-A104						
# 7	Temperature Cycling	-40 °C to 125°C	1000 cycles	67	5360	0		
# /	remperature eyemig	IESD22-A102	1000 Cycles	07	3300	0		
	AC	Tamb = 121 °C, RH = 100 %						
# 8	Autoclave	Pressure = 205 kPa (29.7 psia)	96 hours	n.a.	n.a.	n.a.		
<i>"</i> 0			30 110013	11.0.	mu.	ii.u.		
	HAST	JESD22-A110						
	Highly Accelerated Stress	Tamb = 130 °C, RH = 85%, VR = 80 % of						
# 9	Test	rated reverse voltage <sup>[1]</sup>	1000 hours	67	5360	0		
		MIL-STD-750 Method 1037						
	IOL	ton = toff, devices powered to insure $\Delta Tj$ =						
# 10	Intermittent Operating Life	100 °C for 15000 cycles	1000 hours	n.a.	n.a.	n.a.		
	<b>501</b>	150000 4444						
	RSH Resistance to Solder Heat	JESD22-A111 260 °C ± 5 °C						
# 20		200 °C ± 5 °C	10 s	n.a.	n.a.	n.a.		
# 21	SD Solderability	J-STD-002		10	120	0		
# 21	Soluerability	J-31D-00Z		12	120	0		

<sup>[1]</sup> The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

## Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test # 5) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Protection INDI	1200	0	3.5	2.83E+08

© 2022 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com