nexperia

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier		User Part Number						
Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		PESD30VF1BL Part Description						
								Nexperia DHAM
		MCD package						
		Test Conditions	Duration	# Lots	# Quantity	# Rejects		
			TEST					
	Pre- and Post-Stress							
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
		JESD22-A113						
		Bake Tamb = 125 °C	24 hours					
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	142	11435	0		
		MIL-STD-750-1						
	HTRB	M1038 Method A						
		Tj = Tjmax, Vr = 100% of max. datasheet						
# B1	Bias	reverse voltage	1000 hours	117	9360	0		
	тс	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	53	4225	0		
		JESD22-A102	1000 cycles	55	1225	0		
	AC	Tamb = $121 ^{\circ}C$, RH = $100 ^{\circ}M$						
# A3 alt	Autoclave	Pressure = $205 \text{ kPa} (29.7 \text{ psia})$	96 hours	39	3165	0		
# A5 dit	7.000.070		90 110013	39	5105	0		
	H3TRB	JESD22-A101						
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of						
# A2 alt	Temperature Reverse Bias		1000 hours	51	4045	0		
# AZ dit		MIL-STD-750 Method 1037	1000 10013	51	5-01	0		
	IOL	mil-SID-750 Method 1037 ton = toff, devices powered to insure ΔT_j =						
# A5	INTERMITTER Operating Life		1000 hours					
# A3	Intermittent Operating Life	100 C 101 15000 Cycles	1000 hours	n.a.	n.a.	n.a.		
	RSH	JESD22-A111						
# 69	Resistance to Solder Heat		10 .					
# C8		200 C ± J C	10 s	n.a.	n.a.	n.a.		
	SD Soldorability	J-STD-002		70	700			
# C10	Solderability	J-51D-002		78	780	0		

[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia DHAM	Protection	9360	0	0.45	2.20E+09

© 2022 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any nexperia.com representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.