

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs		User Part Number					
		PESD5V0V1BSF					
		Part Description					
		Nexperia DHAM Protection I					
		BD package					
Test		Test Conditions	Duration	# Lots	# Quantity	# Rejects	
	TEST						
	Pre- and Post-Stress						
# 1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below	
		MIL-STD-750-1					
	HTRB	M1038 Method A					
		Tj = Tjmax, Vr = 100% of max. datasheet					
# 5	Bias	reverse voltage	1000 hours	19	1520	0	
	тс	JESD22-A104					
# 7	Temperature Cycling	-40 °C to 125°C	1000 cycles	67	5360	0	
# /	remperature cycling	IESD22-A102	1000 cycles	67	5360	U	
	AC	Tamb = 121 °C, RH = 100 %					
# 8	Autoclave	Pressure = 205 kPa (29.7 psia)	96 hours	n.a.	n.a.	n.a.	
# 8	Autociave	11c33d1c = 203 Kt d (23.7 p3id)	90 110015	II.a.	II.a.	11.a.	
	HAST	JESD22-A110					
	Highly Accelerated Stress	Tamb = 130 °C, RH = 85%, VR = 80 % of					
# 9	Test	rated reverse voltage ^[1]	1000 hours	67	5360	0	
··· -		MIL-STD-750 Method 1037					
	IOL	ton = toff, devices powered to insure ΔT_j =					
# 10	Intermittent Operating Life	100 °C for 15000 cycles	1000 hours	n.a.	n.a.	n.a.	
	RSH	JESD22-A111					
# 20	Resistance to Solder Heat	260 °C ± 5 °C	10 s	n.a.	n.a.	n.a.	
	SD						
# 21	Solderability	J-STD-002		12	120	0	

^[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test # 5) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Protection I	1520	0	2.79	3.58E+08

© 2022 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com