

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		User Part Number PZU6.2B3 Part Description										
								Nexperia DHAM Zener				
								SMD package				
		Test Conditions	Duration	# Lots	# Quantity	# Rejects						
			TEST									
			Pre- and Post-Stress									
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below						
		JESD22-A113 Bake Tamb = 125 °C	24 hours									
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours									
# A1	Preconditioning	Reflow soldering	3 cycles	810	58300	0						
		MIL-STD-750-1										
	HTRB	M1038 Method A										
		Tj = Tjmax, Vr = 100% of max. datasheet										
# B1	Bias	reverse voltage	1000 hours	138	11040	0						
		MIL-STD-750-1 M1038 Method B										
	SSOP	Tj = Tjmax, Iz = 100% of max. datasheet										
# B1b	Steady State Operational	reverse current	1000 hours	20	1600	0						
	тс	JESD22-A104										
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	170	13600	0						
		JESD22-A102										
	AC	Tamb = 121 °C, RH = 100 %										
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)	96 hours	170	13600	0						
	HOTER	JESD22-A101										
	H3TRB High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of										
# A2 alt	Temperature Reverse Bias		1000 hours	170	13600	0						
,, ,,,, aic	p	MIL-STD-750 Method 1037		-, 0	_5000	-						
	IOL	ton = toff, devices powered to insure ΔTj =										
# A5	Intermittent Operating Life	100 °C for 15000 cycles	1000 hours	170	13600	0						
	RSH	JESD22-A111										
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	130	3900	0						
# C10	SD Solderability	J-STD-002		363	3630	0						
# CIU	Solderability	3 315 002		202	2020	U						

^[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Zener	11040	0	0.38	2.60E+09

^{© 2022} Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com