

Quarterly Reliability Monitoring Results

Quarters: Q1/2021 to Q4/2021

Based on structural similarity

| Supplier | User Part Number | | | | |
|---------------------------|---|-----------------------------------|-----------|------------|-----------|
| Nexperia B.V. | TL431AIDBZR | | | | |
| Name of Laboratory | Part Description | | | | |
| Assembly reliability labs | Nexperia DHAM Bipolar Analog Power SMD package | | | | |
| Based on AEC-Q100 Test | Test Conditions | Duration | # Lots | # Quantity | # Rejects |
| # E1 | TEST Pre- and Post-Stress Electrical Test Tamb = 25 °C | N/A | see below | all parts | see below |
| # A1 | PC Preconditioning JESD22-A113 Bake Tamb = 125 °C Soak Tamb = 85 °C, RH = 85% Reflow soldering | 24 hours 168 hours 3 cycles | 71 | 3840 | 0 |
| # A2 | THB Temperature Humidity Bias JESD22-A101 Tamb = 85 °C, RH = 85%, Vref = 0 V, VKA = 36 V | 1000 hours | 12 | 960 | 0 |
| # A3 | AC Autoclave JESD22-A102 Tamb = 121 °C, RH = 100 % Pressure = 205 kPa (29.7 psia) | 96 hours | 12 | 960 | 0 |
| # A4 | TC Temperature Cycling JESD22-A104 -65 °C to +150 °C | 1000 cycles | 12 | 960 | 0 |
| # A5 | IOL Intermittent Operating Life MIL-STD-750 Method 1037 ton = toff = 2 minutes, Ptot = 250 mW to insure ΔTj = 100 °C for 15000 cycles | 1000 hours | 12 | 960 | 0 |
| # B1 | HTOL High Temperature Operating Life Tamb = 150 °C, Vref = 0 V, VKA = 36 V | 1000 hours | 23 | 1840 | 0 |
| # C3 | RSH Resistance to Solder Heat JESD22-A111 / JESD22-B106 260 °C ± 5 °C | 10 s | 12 | 360 | 0 |
| | SD Solderability JESD22-B102 245 °C ± 5 °C | | 705 | 7050 | 0 |

Calculation of FIT and MTF

Test considered for FIT calculation: High Temperature Operating Life (HTOL, Test #B1)

Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

| Wafer Fab | Technology | Quantity | Rejects | Failure Rate (FIT) | MTTF (hrs) |
|------------------|----------------------|----------|---------|--------------------|------------|
| Nexperia DHAM | Bipolar Analog Power | 1840 | 0 | 2.31 | 4.33E+08 |

© 2022 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com